



**SLOVENSKI STANDARD**  
**SIST ISO 12301:2002/TC1:2002**  
**01-marec-2002**

---

8 fgb]`YÿU]!`H\ b]\_Y`\_cbffc`Y`\_U`cj cgh]`]b`\_cbffc`U[ Yca Yff]`g\_]\ `]b`a UHf]Ub]\  
nbU ]bcgh]!`H\ b] b]`dcdfUj Y`\_%

Plain bearings - Quality characteristics - Statistical process control (SPC)

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

**Ta slovenski standard je istoveten z: ISO 12301:1992/Cor 1:1995**

<https://standards.iteh.ai/catalog/standards/sist/31470130-2f30-4963-819a-987cec9f50e5/sist-iso-12301-2002-tc1-2002>

**ICS:**

21.100.10      Drsni ležaji      Plain bearings

**SIST ISO 12301:2002/TC1:2002**      en

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 12301:2002/TC1:2002

<https://standards.iteh.ai/catalog/standards/sist/31470130-2f30-4963-819a-987cec9f50e5/sist-iso-12301-2002-tc1-2002>



INTERNATIONAL STANDARD ISO 12301:1992  
TECHNICAL CORRIGENDUM 1

Published 1995-03-01

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

# Plain bearings — Quality control techniques and inspection of geometrical and material quality characteristics

## TECHNICAL CORRIGENDUM 1

*Paliers lisses — Techniques de contrôle de la qualité et vérifications des caractéristiques de qualité géométriques et des matériaux*

*RECTIFICATIF TECHNIQUE 1*

Technical corrigendum 1 to International Standard ISO 12301:1992 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 5, *Quality analysis and assurance*.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 12301:2002/TC1:2002](https://standards.iteh.ai/catalog/standards/sist/31470130-2f30-4963-819a-987cec9f50e5/sist-iso-12301-2002-tc1-2002)

<https://standards.iteh.ai/catalog/standards/sist/31470130-2f30-4963-819a-987cec9f50e5/sist-iso-12301-2002-tc1-2002>

Page 3

### Table 1 (concluded)

$\varepsilon_{\max}$  is now: Maximum diametral deformation in compression

$\varepsilon_{\min}$  is now: Minimum diametral deformation in compression

Page 31

### A.1.5

Should read as follows:

#### A.1.5 Crush height, $a$

According to the drawing specification,  $a = 0,040$  mm to  $0,070$  mm ( $a_{\min} = 0,040$  mm;  $a_{\max} = 0,070$  mm).

Tolerance on crush height,  $T_a = 0,030$  mm.

## ISO 12301:1992/Cor.1:1995(E)

## A.1.6

Should read as follows:

A.1.6 Diametral deformation in compression,  $\varepsilon$ 

NOTE — If the diameter of the checking block bore is larger than the upper limit of the housing diameter,  $\varepsilon$  is increased by that difference.

The minimum diametral deformation in compression,  $\varepsilon_{\min}$ , is calculated using the following formula:

$$\varepsilon_{\min} = \frac{2}{\pi} (E_{\text{red}} + a_{\min}) = \frac{2}{\pi} (0,039 + 0,040) = 0,050 \text{ mm}$$

The maximum diametral deformation in compression,  $\varepsilon_{\max}$ , is calculated using the following formula:

$$\varepsilon_{\max} = \frac{2}{\pi} \times T_a + (T_{d_H} + \varepsilon_{\min}) = \frac{2}{\pi} \times 0,030 + (0,019 + 0,050) = 0,088 \text{ mm}$$

where  $T_{d_H}$  is the tolerance on the housing diameter  $d_H$ .

## A.1.7

Should read as follows:

A.1.7 Tangential load,  $F_{\text{tan}}$ 

$$\frac{s_{\text{tot, eff}}}{d_H} = \frac{1,75}{64} = 0,027$$

SIST ISO 12301:2002/TC1:2002  
<https://standards.iteh.ai/catalog/standards/sist/31470130-2f30-4963-819a-987cec9f50e5/sist-iso-12301-2002-tc1-2002>

(See figure A.1.)

The stress,  $\Phi$ , is derived from figure A.1.

$$\Phi = 1,93 \times 10^5 \text{ N/mm}^2$$

Using this value derived for  $\Phi$ , the minimum and maximum tangential strengths can be calculated as follows:

$$\sigma_{\text{tan, min}} = \frac{\Phi}{d_H} \times \varepsilon_{\min} = \frac{1,93 \times 10^5}{64} \times 0,050 = 151 \text{ N/mm}^2$$

$$\sigma_{\text{tan, max}} = \frac{\Phi}{d_H} \times \varepsilon_{\max} = \frac{1,93 \times 10^5}{64} \times 0,088 = 265 \text{ N/mm}^2$$

Thus the median tangential load,  $\bar{F}_{\text{tan}}$ , to be applied in this example can be calculated as follows:

$$\bar{F}_{\text{tan}} = \frac{\sigma_{\text{tan, min}} + \sigma_{\text{tan, max}}}{2} \times A_{\text{eff}} = \frac{151 + 265}{2} \times 43,75 = 9\,100 \text{ N}$$

Page 33

### A.2.5

Should read as follows:

#### A.2.5 Crush height, $a$

According to the drawing specification,  $a = 0,050$  mm to  $0,080$  mm ( $a_{\min} = 0,050$  mm;  $a_{\max} = 0,080$  mm).

Tolerance on crush height,  $T_a = 0,030$  mm.

### A.2.6

Should read as follows:

#### A.2.6 Diametral deformation in compression, $\varepsilon$

NOTE — If the diameter of the checking block bore is larger than the upper limit of the housing diameter,  $\varepsilon$  is increased by that difference.

The minimum diametral deformation in compression,  $\varepsilon_{\min}$ , is calculated using the following formula:

$$\varepsilon_{\min} = \frac{2}{\pi} (E_{\text{red}} + a_{\min}) = \frac{2}{\pi} (0,065 + 0,050) = 0,073 \text{ mm}$$

The maximum diametral deformation in compression,  $\varepsilon_{\max}$ , is calculated using the following formula:

$$\varepsilon_{\max} = \frac{2}{\pi} \times T_a + (T_{d_H} + \varepsilon_{\min}) = \frac{2}{\pi} \times 0,030 + (0,022 + 0,073) = 0,114 \text{ mm}$$

where  $T_{d_H}$  is the tolerance on the housing diameter  $d_H$ .

SIST ISO 12301:2002/TC1:2002

### A.2.7

<https://standards.iteh.ai/catalog/standards/sist/31470130-2f30-4963-819a-987cec9f50e5/sist-iso-12301-2002-tc1-2002>

Should read as follows:

#### A.2.7 Tangential load, $F_{\text{tan}}$

$$\frac{s_{\text{tot. eff}}}{d_H} = \frac{5,56}{110} = 0,05$$

(See figure A.1.)

The stress,  $\Phi$ , is derived from figure A.1.

$$\Phi = 1,75 \times 10^5 \text{ N/mm}^2$$

Using this derived value for  $\Phi$ , the minimum and maximum tangential strengths can be calculated as follows:

$$\sigma_{\text{tan, min}} = \frac{\Phi}{d_H} \times \varepsilon_{\min} = \frac{1,75 \times 10^5}{110} \times 0,073 = 116 \text{ N/mm}^2$$

$$\sigma_{\text{tan, max}} = \frac{\Phi}{d_H} \times \varepsilon_{\max} = \frac{1,75 \times 10^5}{110} \times 0,114 = 181 \text{ N/mm}^2$$

Thus the median tangential load,  $\bar{F}_{\text{tan}}$ , to be applied in this example can be calculated as follows:

$$\bar{F}_{\text{tan}} = \frac{\sigma_{\text{tan, min}} + \sigma_{\text{tan, max}}}{2} \times A_{\text{eff}} = \frac{116 + 181}{2} \times 183,4 = 27\,235 \text{ N}$$