



# SLOVENSKI STANDARD

## SIST EN 634-2:2007

01-julij-2007

Nadomešča:  
SIST EN 634-2:1998

---

**Cementno-iverne plošče - Specifikacije - 2. del: Zahteve za iverne plošče, vezane z OPC, za uporabo v suhih, vlažnih in zunanjih pogojih**

Cement-bonded particleboards - Specifications - Part 2: Requirements for OPC bonded particleboards for use in dry, humid and external conditions

Zementgebundene Spanplatten - Anforderungen - Teil 2: Anforderungen an Portlandzement (PZ) gebundene Spanplatten zur Verwendung im Trocken-, Feucht- und Außenbereich

Panneaux de particules liées au ciment - Exigences - Partie 2: Exigences pour les panneaux de particules liées au ciment Portland ordinaire utilisés en milieux sec, humide et extérieur

**Ta slovenski standard je istoveten z: EN 634-2:2007**

---

**ICS:**

79.060.20      Vlakenne in iverne plošče      Fibre and particle boards

**SIST EN 634-2:2007**                      en,fr,de

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 634-2:2007

<https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007>

English Version

Cement-bonded particleboards - Specifications - Part 2:  
Requirements for OPC bonded particleboards for use in dry,  
humid and external conditions

Panneaux de particules liées au ciment - Exigences - Partie  
2 : Exigences pour les panneaux de particules liées au  
ciment Portland ordinaire utilisés en milieu sec, humide et  
extérieur

Zementgebundene Spanplatten - Anforderungen - Teil 2:  
Anforderungen an Portlandzement (PZ) gebundene  
Spanplatten zur Verwendung im Trocken-, Feucht- und  
Außenbereich

This European Standard was approved by CEN on 13 January 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

<b>Contents</b>		Page
Foreword.....		3
1 <b>Scope</b> .....		4
2 <b>Normative references</b> .....		4
3 <b>Requirements</b> .....		5
4 <b>Verification of compliance</b> .....		6
5 <b>Marking</b> .....		7
<b>Bibliography</b> .....		9

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 634-2:2007](https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007)

<https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007>

## Foreword

This document (EN 634-2:2007) has been prepared by Technical Committee CEN/TC 112 "Wood-based panels", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2007, and conflicting national standards shall be withdrawn at the latest by August 2007.

This document supersedes EN 634-2:1996.

The principal modifications introduced by this standard consist of a revision of the product marking requirements, clarification that external control in the factory is carried out according to EN 326-2, and clarification that inspection of an isolated lot of panels may be carried out according to EN 326-3.

This standard is one of a series specifying requirements for cement-bonded particleboards:

- EN 634-1, *Cement-bonded particleboards — Specification — Part 1: General requirements*;
- EN 634-2, *Cement-bonded particleboards — Specifications — Part 2: Requirements for OPC bonded particleboards for use in dry, humid and external conditions*.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

SIST EN 634-2:2007

<https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007>

## 1 Scope

This European Standard for cement-bonded particleboards specifies the requirements for particleboards bonded with Ordinary Portland Cement (OPC) for use in dry, humid<sup>1)</sup> and external<sup>2)</sup> conditions. Additional information on supplementary properties for certain applications is also given.

NOTE 1 Boards made with cement other than OPC may comply with this Standard if test values are declared according to EN 13986. However, further parts of EN 634 may be developed in the future to cover other types of cement or other materials.

NOTE 2 Cement-bonded particleboard does not contain any asbestos fibre.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 310, *Wood-based panels — Determination of modulus of elasticity in bending and of bending strength*

EN 317, *Particleboards and fibreboards — Determination of swelling in thickness after immersion in water*

EN 318, *Wood based panels — Determination of dimensional changes associated with changes in relative humidity*

EN 319, *Particleboards and fibreboards — Determination of tensile strength perpendicular to the plane of the board*

EN 320, *Fibreboards — Determination of resistance to axial withdrawal of screws*

EN 321, *Wood-based panels - Determination of moisture resistance under cyclic test conditions*

EN 323, *Wood-based panels — Determination of density*

EN 326-1, *Wood-based panels — Sampling, cutting and inspection — Part 1 Sampling and cutting of test pieces and expression of test results*

EN 326-2, *Wood-based panels — Sampling, cutting and inspection — Part 2: Quality control in the factory*

EN 634-1, *Cement-bonded particleboards — Specification — Part 1: General requirements*

EN 789, *Timber structures — Test methods — Determination of mechanical properties of wood based panels*

EN 1058, *Wood-based panels — Determination of characteristic values of mechanical properties and density*

EN 1128, *Cement-bonded particleboards — Determination of hard body impact resistance*

ENV 1156, *Wood-based panels — Determination of duration of load and creep factors*

- 
- 1) Humid conditions are defined in terms of service class 2 of EN 1995-1-1 which is characterized by moisture content in the material corresponding to a temperature of 20 °C and a relative humidity of the surrounding air exceeding 85 % for only a few weeks per year. Boards of this type are suitable for use in biological hazard classes 1 and 2 of EN 335-3.
  - 2) External conditions are defined in terms of service class 3 of EN 1995-1-1. Boards of this type are suitable for use in biological hazard classes 1, 2, 3 and 4 of EN 335-3.

EN 1328, *Cement bonded particleboards — Determination of frost resistance*

EN 13986:2004, *Wood-based panels for use in construction — Characteristics, evaluation of conformity and marking*

### 3 Requirements

#### 3.1 General requirements

OPC bonded particleboards shall comply with the general requirements listed in EN 634-1 and the requirements set out in Table 1 of this standard.

#### 3.2 Specified properties

The requirements in Table 1 shall be met by five percentile values (95 percentile values in the case of thickness swelling) based on the mean values for individual boards and calculated in accordance with EN 326-1. In the case of thickness swelling they shall be equal to or less than the values in Table 1 and in the case of all other properties they shall be equal to or greater than the values in Table 1.

**Table 1 — Requirements for specified properties**

Property	Test method	Unit	Requirement (all thicknesses)
Density	EN 323	Kg/m <sup>3</sup>	1 000
Bending strength	EN 310	N/mm <sup>2</sup>	9
Modulus of elasticity in bending	EN 310	N/mm <sup>2</sup>	Class 1 4 500 Class 2 4 000
Internal bond	EN 319	N/mm <sup>2</sup>	0,5
Swelling in thickness 24 h	EN 317	%	1,5
Internal bond after cyclic test	EN 319 and EN 321	N/mm <sup>2</sup>	0,3
Swelling in thickness after cyclic test	EN 317 and EN 321	%	1,5
<p>If it is made known by the purchaser that the boards are intended for specific use in flooring, walls or roofing, the relevant performance standard EN 12871 has to be consulted. This can result in having to comply with additional requirements.</p> <p>NOTE 1 The values in this table for both bending strength and modulus of elasticity shall apply to test results obtained in any direction in the plane of the panel.</p> <p>NOTE 2 With the exception of thickness swelling and the cyclic test, the values given in this table are characterized by moisture content in the material corresponding to a relative humidity of 65 % and a temperature of 20 °C.</p>			

#### 3.3 Supplementary properties

For certain applications, information on some of the properties listed in Table 2 can be required and where appropriate, shall be supplied by the board manufacturer. In this case all shall have been derived using the test methods listed in Table 2.

Table 2 — Supplementary properties and test methods

Property	Test method
Dimensional changes	EN 318
Impact resistance	EN 1128
Resistance to withdrawal of screws	EN 320
Frost resistance	EN 1328
Creep and duration of load	ENV 1156
Structural properties (strength and stiffness)	EN 789 and EN 1058
<p>NOTE For certain applications, information on additional properties not specified in Table 2 can be required. For example, for determining of thermal conductivity, water vapour transmission, and classification for reaction to fire, see EN 13986.</p>	

**4 Verification of compliance**

**4.1 General**

Verification of compliance with this EN shall be carried out using the test methods listed in Table 1, Table 2 (where required), EN 634-1, and shall comply with the requirements of EN 13986 for panels used for construction purposes.

**4.2 External control**

External control in the factory, if required by EN 13986, shall be carried out according to EN 326-2.

Inspection of consignments shall be carried out according to statistical basis.

NOTE Inspection of isolated lots of panels can be carried out according to EN 326-3.

iTech STANDARD PREVIEW  
(standards.iteh.ai)  
SIST EN 634-2:2007  
<https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007>

**4.3 Factory production control**

Factory production control shall be carried out according to EN 326-2.

The properties listed in Table 3 shall be controlled using intervals between tests not exceeding the intervals given. Sampling shall be carried out at random. Alternative test methods and/or unconditioned test pieces may be used if a valid correlation can be proven (see EN 326-2) with the specified test method.



Table 3 — Maximum intervals between tests for each production line

Property	Maximum interval between tests
General properties:	
Thickness (unsanded)	8 h per thickness
Thickness (sanded)	2 h per thickness
Length	2 h per thickness
Width	2 h per thickness
Squareness	2 h per thickness
Edge straightness	2 h per thickness
Moisture content	8 h per thickness
Density	
Bending strength	8 h per thickness range <sup>a</sup>
Modulus of elasticity (bending)	
Internal bond	
Swelling in thickness, 24 h	24 h
Internal bond after cyclic test	
Swelling in thickness after cyclic test	One week
<sup>a</sup> A thickness range is defined as any range of thicknesses extending to $\pm 6$ mm from the preceding manufactured thickness.	

## 5 Marking

SIST EN 634-2:2007

[https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-](https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007)

[57b252cbc43f/sist-en-634-2-2007](https://standards.iteh.ai/catalog/standards/sist/84e690e9-857d-44d7-899d-57b252cbc43f/sist-en-634-2-2007)

### 5.1 Marking boards placed on the internal market of the European Economic Area for construction purposes

Boards marketed in one or more market territories of the European Union or other territories of the wider European Economic Area shall be marked in accordance with the requirements of EN 13986, to signify compliance with that standard and denote the claim (by affixing a CE mark), that the boards are legally placed on the market in accordance with the Construction Products Directive provisions and corresponding national regulations.

NOTE For full details of the above requirements for marking, either by reference to the appropriate technical class (board type) for OPC bonded particleboards or on the basis of declared property values, see clause 7 (Marking) and ZA.3 (CE Marking) of EN 13986:2004.

### 5.2 Positioning of the marking applied according to 5.1

The marking and the accompanying information shall be placed according to the provisions of EN 13986.

### 5.3 Marking of other boards

Boards not marketed as mentioned in clause 5.1 shall be marked either (a) according to the requirements of clause 5.1 if acceptable to the buyer, or (b) according to the relevant properties for the intended application using the elements in Table 4.