



SLOVENSKI STANDARD

SIST EN 2632:2006

01-julij-2006

Aeronavtika – Aluminijeva zlitina AL-P7075 - T73511 – Iztiskane palice in profili - a ali D ≤ 150 mm s kontrolo debelozrnatega obrobja

Aerospace series - Aluminium alloy AL-P7075 - T73511 - Extruded bar and section - a or D ≤ 150 mm with peripheral coarse grain control

Luft- und Raumfahrt - Aluminiumlegierung AL-P7075 - T73511 - Stranggepresste Stange und Profile - a oder D ≤ 150 mm mit Kontrolle der Grobkornrandzone

iTeh STANDARD PREVIEW

Série aérospatiale - Alliage d'aluminium AL-P7075 - T73511 - Barres et profilés filés - a ou D ≤ 150 mm avec contrôle de la zone périphérique à gros grains

[SIST EN 2632:2006](https://standards.iteh.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-6105a18f889/sist-en-2632-2006)

Ta slovenski standard je istoveten z: EN 2632:2005

ICS:

49.025.20

SIST EN 2632:2006

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2632:2006

<https://standards.iteh.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-bf63aff8f889/sist-en-2632-2006>

English Version

Aerospace series - Aluminium alloy AL-P7075 - T73511 -
Extruded bar and section - a or $D \leq 150$ mm with peripheral
coarse grain control

Série aérospatiale - Alliage d'aluminium AL-P7075 -
T73511 - Barres et profilés filés - a ou $D \leq 150$ mm avec
contrôle de la zone périphérique à gros grains

Luft- und Raumfahrt - Aluminiumlegierung AL-P7075 -
T73511 - Stranggeprägte Stange und Profile - a oder $D \leq$
150 mm mit Kontrolle der Grobkornrandzone

This European Standard was approved by CEN on 26 September 2005.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

<https://standards.iteh.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-bf63aff8f889/sist-en-2632-2006>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

| Contents | | Page |
|-------------------------------------|--|-------------|
| Foreword | | 3 |
| Introduction | | 4 |
| 1 Scope | | 4 |
| 2 Normative references | | 4 |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2632:2006

<https://standards.iteh.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-bf63aff8f889/sist-en-2632-2006>

Foreword

This European Standard (EN 2632:2005) has been prepared by the European Association of Aerospace Manufacturers - Standardization (AECMA-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of AECMA, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2006, and conflicting national standards shall be withdrawn at the latest by April 2006.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This European Standard supersedes EN 2632:1993.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

(standards.iteh.ai)

SIST EN 2632:2006

<https://standards.iteh.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-bf63aff8f889/sist-en-2632-2006>

Introduction

This standard is part of the series of EN metallic material standards for aerospace applications. The general organization of this series is described in EN 4258.

This standard has been prepared in accordance with EN 4500-2.

1 Scope

This standard specifies the requirements relating to:

Aluminium alloy AL-P7075-
T73511
Extruded bar and section
a or $D \leq 150$ mm
with peripheral coarse grain control

for aerospace applications.

This standard may also be used to supply material in the T73510 condition if specified by the purchaser on the order and the product is marked accordingly.

STANDARD PREVIEW
(standards.iteh.ai)

2 Normative references

SIST EN 2632:2006

<https://standards.iteh.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-0105a0d0687/sist-en-2632-2006>

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 4258, *Aerospace series — Metallic materials — General organization of standardization — Links between types of EN standards and their use.*

EN 4400-3, *Aerospace series — Aluminium and aluminium alloy wrought products — Technical specification — Part 3: Bar and section.* ¹⁾

EN 4500-2, *Aerospace series — Metallic materials — Rules for drafting and presentation of material standards — Part 2: Specific rules for aluminium, aluminium alloys and magnesium alloys.* ¹⁾

1) Published as AECMA Prestandard at the date of publication of this standard.

| | | | | | | | | | | | | | | |
|------|-------------------------|---------|---------------------------|------|-----|------|-----|------|------|------|----------------------|--------|-------|------|
| 1 | Material designation | | Aluminium alloy AL-P7075- | | | | | | | | | | | |
| 2 | Chemical composition % | Element | Si | Fe | Cu | Mn | Mg | Cr | Zn | Ti | Zr + Ti ^a | Others | | Al |
| | | | | | | | | | | | | Each | Total | |
| | | min. | – | – | 1,2 | – | 2,1 | 0,18 | 5,1 | – | – | – | – | Base |
| max. | 0,40 | 0,50 | 2,0 | 0,30 | 2,9 | 0,28 | 6,1 | 0,2 | 0,25 | 0,05 | 0,15 | | | |
| 3 | Method of melting | | – | | | | | | | | | | | |
| 4.1 | Form | | Bar and section | | | | | | | | | | | |
| 4.2 | Method of production | | Extruded | | | | | | | | | | | |
| 4.3 | Limit dimension(s) | mm | a or D ≤ 150 | | | | | | | | | | | |
| 5 | Technical specification | | EN 4400-3 | | | | | | | | | | | |

| | | | | | | | | | |
|-----|-------------------------|---|--|--|--|---|--|--|--|
| 6.1 | Delivery condition | T6511 ^b | | | | T73511 | | | |
| | Heat treatment | 460 °C ≤ θ ≤ 470 °C / WQ θ ≤ 40 °C + 1 % ≤ controlled stretched ≤ 3 % + 105 °C ≤ θ ≤ 125 °C / 20 h ≤ t ≤ 30 h | | | | 460 °C ≤ θ ≤ 470 °C / WQ θ ≤ 40 °C + 1 % ≤ controlled stretched ≤ 3 % + 105 °C ≤ θ ≤ 125 °C / 20 h ≤ t ≤ 30 h + 172 °C ≤ θ ≤ 182 °C / 5 h ≤ t ≤ 12 h | | | |
| 6.2 | Delivery condition code | P | | | | U | | | |
| 7 | Use condition | T73511 | | | | T73511 | | | |
| | Heat treatment | Delivery condition + 172 °C ≤ θ ≤ 182 °C / 5 h ≤ t ≤ 12 h | | | | Delivery condition | | | |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Characteristics

| | | | | | | | | | |
|-----|------------------------------------|-----------------------|---------------------------------|------------------|------------------|------------------|-------------------|--------------------|--|
| 8.1 | Test sample(s) | | See EN 4400-3. | | | | | | |
| 8.2 | Test piece(s) | | See EN 4400-3. | | | | | | |
| 8.3 | Heat treatment | | Use condition | | | | | | |
| 9 | Dimensions concerned | mm | a or D ≤ 10 | 10 < a or D ≤ 20 | 20 < a or D ≤ 50 | 50 < a or D ≤ 75 | 75 < a or D ≤ 100 | 100 < a or D ≤ 150 | |
| 10 | Thickness of cladding on each face | % | – | – | – | – | – | – | |
| 11 | Direction of test piece | | L | L | L | L | L | L | |
| 12 | Temperature | θ °C | Ambient | Ambient | Ambient | Ambient | Ambient | Ambient | |
| 13 | Proof stress | R _{p0.2} MPa | ≥ 400 | ≥ 420 | ≥ 415 | ≥ 410 | ≥ 390 | ≥ 370 | |
| 14 | T Strength | R _m MPa | ≥ 470 | ≥ 485 | ≥ 485 | ≥ 475 | ≥ 470 | ≥ 450 | |
| 15 | Elongation | A % | A ≥ 8 or A _{50 mm} ≥ 7 | ≥ 8 | ≥ 8 | ≥ 8 | ≥ 7 | ≥ 7 | |
| 16 | Reduction of area | Z % | – | | | | | | |
| 17 | Hardness | | – | | | | | | |
| 18 | Shear strength | R _c MPa | – | | | | | | |
| 19 | Bending | k – | – | | | | | | |
| 20 | Impact strength | | – | | | | | | |
| 21 | Temperature | θ °C | – | | | | | | |
| 22 | Time | | h | | | | | | |
| 23 | Stress | σ _a MPa | – | | | | | | |
| 24 | C Elongation | a % | – | | | | | | |
| 25 | Rupture stress | σ _R MPa | – | | | | | | |
| 26 | Elongation at rupture | A % | – | | | | | | |
| 27 | Notes (see line 98) | | a,b | | | | | | |

EN 2632:2005 (E)

| | | | | | | | |
|--|---------------------------|---------------------|---|----------|--|-----------------------|-----------------------|
| 32 | Electrical conductivity | – | See EN 4400-3. | | | | |
| | | 7 | $\gamma \geq 23,0$ MS/m | | Acceptable | | |
| | | | $22,0$ MS/m $\leq \gamma < 23,0$ MS/m | | Acceptable if $R_{p0,2} L \leq R_{p0,2} \text{ min. } L + 85$ MPa (see line 13) or if stress corrosion results are acceptable (see line 39). | | |
| | | | $\gamma < 22,0$ MS/m | | Not acceptable | | |
| 39 | Stress corrosion | – | See EN 4400-3. | | | | |
| | | 6 | $\sigma = 75 \% R_{p0,2} \text{ min. } L$ (see line 13) | | | | |
| | | 7 | $t \geq 20 d$ | | | | |
| 44 | External defects | – | See EN 4400-3. | | | | |
| 61 | Internal defects | – | See EN 4400-3. | | | | |
| 82 | Batch uniformity | – | See EN 4400-3. | | | | |
| | | 5 | | | T6511 ^b | T73511 | |
| | | 7 | Electrical conductivity | γ | MS/m | 19,0 (Typical value) | 23,2(Typical value) |
| | | | or | | | | |
| | | | Hardness | – | HB | 150 (typical value) | 140 (typical value) |
| | | | | δ | | ≤ 20 per product | ≤ 20 per product |
| Δ | ≤ 30 per batch | ≤ 30 per batch | | | | | |
| 87 | Extrusion back-end defect | – | See EN 4400-3. | | | | |
| 88 | Peripheral coarse grain | – | See EN 4400-3. | | | | |
| | | 7 | Peripheral coarse grain : Level A | | | | |
| <p>SIST EN 2632:2006 https://standards.itech.ai/catalog/standards/sist/6c7d9be8-e515-4f48-8ba8-bf63aff8f889/sist-en-2632-2006</p> | | | | | | | |
| 95 | Marking inspection | – | See EN 4400-3. | | | | |
| 96 | Dimensional inspection | – | See EN 4400-3. | | | | |
| 98 | Notes | – | ^a A (Zr + Ti) addition may only be made subject to agreement with the purchaser. ^b T6510 if the use condition is T73510. | | | | |
| 99 | Typical use | – | – | | | | |