



SLOVENSKI STANDARD
oSIST prEN 13381-3:2008
01-december-2008

DfYg_i gbY'a YfcXY'nU'i [cHj `Ub`Ydf]gdYj _U_ `dcÿUfb]`cXdcfbcgh]`_cbglfi _W'g_]`
Y'Ya Yblcj `!' "XY.`NUý]HUVYfcbg_]`Y'Ya Yblcj

Test methods for determining the contribution to the fire resistance of structural members
- Part 3: Applied protection to concrete members

Prüfverfahren zur Bestimmung des Beitrages zum Feuerwiderstand von tragenden
Bauteilen - Teil 3: Brandschutzmaßnahmen für Betonbauteile

Méthode d'essai pour déterminer la contribution à la résistance au feu des éléments de
construction - Partie 3: Protection appliquée aux éléments en béton

<https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d->

Ta slovenski standard je istoveten z: prEN 13381-3

ICS:

13.220.50	Požarna odpornost gradbenih materialov in elementov	Fire-resistance of building materials and elements
-----------	---	---

oSIST prEN 13381-3:2008

en,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[oSIST prEN 13381-3:2008](https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d-d9ba41af9980/osist-pren-13381-3-2008)

<https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d-d9ba41af9980/osist-pren-13381-3-2008>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

DRAFT
prEN 13381-3

October 2008

ICS

Will supersede ENV 13381-3:2002

English Version

Test methods for determining the contribution to the fire resistance of structural members - Part 3: Applied protection to concrete members

Méthode d'essai pour déterminer la contribution à la résistance au feu des éléments de construction - Partie 3: Protection appliquée aux éléments en béton

Prüfverfahren zur Bestimmung des Beitrages zum Feuerwiderstand von tragenden Bauteilen - Teil 3: Brandschutzmaßnahmen für Betonbauteile

This draft European Standard is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 127.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword	4
1 Scope.....	5
2 Normative references	5
3 Terms and definitions, symbols and units	6
3.1 Terms and definitions.....	6
3.2 Symbols and units	7
4 Test equipment.....	8
4.1 General	8
4.2 Furnace	8
4.3 Loading equipment	8
5 Test conditions.....	8
5.1 General.....	8
5.2 Support and restraint conditions	9
5.2.1 Standard support and restraint conditions	9
5.2.2 Other support and restraint conditions	9
5.3 Loading conditions	9
6 Test specimens	10
6.1 Type and number of test specimens.....	10
6.1.1 Type of test specimens	10
6.1.2 Number of test specimens	10
6.2 Size of test specimens.....	10
6.2.1 Concrete slabs	10
6.2.2 Concrete beams	11
6.3 Construction of concrete test specimens	11
6.3.1 Concrete slab test members	11
6.3.2 Concrete beam test members.....	12
6.3.3 Fabrication of concrete test members.....	12
6.3.4 Application of fire protection material to concrete test member.....	12
6.4 Composition of test specimen component materials	13
6.4.1 Concrete.....	13
6.4.2 Steel reinforcement.....	13
6.4.3 Fire protection system.....	13
6.5 Properties of test materials.....	13
6.5.1 Concrete.....	13
6.5.2 Steel reinforcement.....	14
6.5.3 Fire protection materials	14
6.6 Verification of the test specimen.....	14
7 Installation of the test construction	15
7.1 Concrete slab test specimens	15
7.2 Concrete beam test specimens	15
8 Conditioning	15
9 Application of instrumentation	15
9.1 General	15
9.2 Instrumentation for measurement of furnace temperature	15
9.2.1 Slab specimens	15
9.2.2 Beam specimens.....	16
9.3 Instrumentation for the measurement of test specimen temperature.....	16

9.3.1	General	16
9.3.2	Large and small concrete slab test specimens	16
9.3.3	Beams.....	17
9.4	Instrumentation for the measurement of pressure	18
9.5	Instrumentation for the measurement of deformation	18
9.6	Instrumentation for the measurement of applied load.....	18
10	Test procedure	18
10.1	General.....	18
10.2	Furnace temperature and pressure.....	18
10.3	Application and control of load	18
10.4	Temperature of test specimen	19
10.5	Deformation	19
10.6	Observations	19
10.7	Termination of test.....	19
11	Test results	19
11.1	Acceptability of test results	19
11.2	Presentation of test results.....	19
12	Test report	21
13	Assessment	21
13.1	General.....	21
13.2	Concrete slabs	21
13.3	Concrete beams	22
13.4	Insulation	22
13.5	Stickability	22
13.6	Equivalent thickness of concrete.....	23
14	Report of the assessment.....	23
15	Limits of applicability of the results of the assessment.....	24
Annex A	(normative) Test method to the smouldering fire or slow heating curve	33
A.1	Introduction	33
A.2	Evaluation of the results	33
Annex B	(normative) Measurement of properties of fire protection materials	35
B.1	General.....	35
B.2	Thickness of fire protection materials	35
B.3	Density of applied fire protection materials	36
B.3.1	General.....	36
B.4	Moisture content of applied fire protection materials.....	37
Annex C	(normative) Equivalent thickness of concrete.....	38
C.1	General.....	38
C.1.1	Equivalent thickness of concrete slabs - preliminary data collection	38
C.1.2	Equivalent thickness of concrete beams - preliminary data collection	39
C.2	Equivalent thickness of concrete slabs and beams - assessment methodology.....	39
Bibliography	42

Foreword

This document (prEN 13381-3:2008) has been prepared by Technical Committee CEN/TC 127 “Fire safety in buildings”, the secretariat of which is held by BSI.

This document is currently submitted to the CEN Enquiry.

This document will supersede ENV 13381-3:2002.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of 89/106/EEC.

This European Standard is one of a series of standards for evaluating the contribution to the fire resistance of structural members by applied fire protection materials. Other parts of this standard are:

Part 1: Horizontal protective membranes.

Part 2: Vertical protective membranes.

Part 4: Applied protection to steel members.

Part 5: Applied protection to concrete/profiled sheet steel composite members.

Part 6: Applied protection to concrete filled hollow steel columns.

Part 7: Applied protection to timber members.

Annexes A, B and C are normative.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
oSIST prEN 13381-3:2008
<https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d-49ba41af9980/osist-pren-13381-3-2008>

Caution

The attention of all persons concerned with managing and carrying out this fire resistance test, is drawn to the fact that fire testing can be hazardous and that there is a possibility that toxic and/or harmful smoke and gases can be evolved during the test. Mechanical and operational hazards can also arise during the construction of test elements or structures, their testing and the disposal of test residues.

An assessment of all potential hazards and risks to health shall be made and safety precautions shall be identified and provided. Written safety instructions shall be issued. Appropriate training shall be given to relevant personnel. Laboratory personnel shall ensure that they follow written safety instructions at all times.

The specific health and safety instructions contained within this Standard shall be followed.

1 Scope

This part of this European Standard specifies a test method for determining the contribution of fire protection systems to the fire resistance of structural concrete members, for instance slabs, floors, roofs and walls and which can include integral beams and columns. The concrete can be lightweight, normalweight or heavyweight concrete and of strength classes 20/25 (LC/C/HC) to 50/60 (LC/C/HC). The member can contain steel reinforcing bars.

The test method is applicable to all fire protection materials used for the protection of concrete members and includes sprayed materials, coatings, cladding protection systems and multi-layer or composite fire protection materials, when the gap between the fire protection material and the concrete member is less than 5 mm. Otherwise the test methods in prEN 13381-1 or prEN 13381-2, as appropriate, apply.

This European Standard contains the fire test which specifies the tests which shall be carried out to determine the ability of the fire protection material to remain coherent and fixed to the concrete and to provide data on the temperature distribution throughout the protected concrete member, when exposed to the standard temperature time curve.

In special circumstances, where specified in national building regulations, there can be a need to subject the protection material to a smouldering curve. The test for this and the special circumstances for its use are detailed in Annex A.

The fire test methodology makes provision for the collection and presentation of data which can be used as direct input to the calculation of fire resistance of concrete members in accordance with the procedures given in EN 1992-1-2.

This European Standard also contains the assessment which prescribes how the analysis of the test data shall be made and gives guidance to the procedures by which interpolation shall be undertaken.

The limits of applicability of the results of the assessment arising from the fire test are defined together with permitted direct application of the results to different concrete structures, densities, strengths, thicknesses and production techniques over the range of thicknesses of the applied fire protection system tested.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 1363-1, *Fire resistance tests – Part 1: General requirements*

EN 1363-2, *Fire resistance tests – Part 2: Alternative and additional procedures*

EN 10080, *Steel for the reinforcement of concrete – Weldable ribbed reinforcing steel B 500 – Technical delivery conditions for bars, coils and welded fabric*

EN 206-1, *Concrete – Part 1: Specification, performance, production and conformity*

EN 1992-1-1, *Eurocode 2: Design of concrete structures – Part 1-1: General rules and rules for buildings*

prEN 13381-3:2008 (E)

EN 1992-1-2, *Eurocode 2: Design of concrete structures – Part 1-2: General rules - Structural fire design*

ISO 8421-2, *Fire protection – Vocabulary – Part 2: Structural fire protection*

EN ISO 13943, *Fire safety – Vocabulary (ISO 13943:1999)*

3 Terms and definitions, symbols and units**3.1 Terms and definitions**

For the purposes of this European Standard, the terms and definitions given in EN 1363-1, EN ISO 13943, ISO 8421-2 and EN 206-1, and the following apply:

3.1.1**concrete member**

element of building construction which is loadbearing and is fabricated from concrete, defined according to EN 206-1. It may contain steel reinforcing bars

3.1.2**fire protection material**

material or combination of materials applied to the surface of a concrete member for the purpose of increasing its fire resistance

3.1.3**passive fire protection materials**

materials which do not change their physical form upon heating and which provide fire protection by virtue of their physical or thermal properties. They may include materials containing water which, on heating, evaporates to produce cooling effects.

<https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d-d9ba41af9980/osist-pren-13381-3-2008>

3.1.4**reactive fire protection materials**

materials which are specifically formulated to provide a chemical reaction upon heating such that their physical form changes and in so doing provide fire protection by thermal insulative and cooling effects

3.1.5**fire protection system**

fire protection material together with a prescribed method of attachment to the concrete member

3.1.6**fire protection**

protection afforded to the concrete member by the fire protection system such that the temperature throughout the depth of the structural member and upon any steel reinforcing bars within it is limited throughout the period of exposure to fire

3.1.7**test specimen**

concrete slab or beam test member plus the fire protection system under test

3.1.8**fire protection thickness**

thickness of a single layer fire protection system or the combined thickness of all layers of a multilayer fire protection system

3.1.9**stickability**

ability of a fire protection material to remain sufficiently coherent and in position for a well defined range of deformations, furnace and test specimen surface temperatures, such that its ability to provide fire protection is not significantly impaired

3.1.10**critical temperature**

temperature at which failure is expected to occur in steel reinforcement within the concrete at a given load level

3.1.11**lathing**

mechanical fixing aids comprising non-combustible wires or similar constructions fixed to the concrete before sprayed fire protection material is applied

3.1.12**adhesive bond promoter**

material applied to the surface of the concrete, prior to application of the fire protection material, for promotion of increased bonding

3.1.13**equivalent thickness of concrete**

theoretical thickness of concrete which provides the same thermal insulation for a given period of test as does the given thickness of the applied fire protection system

NOTE Care shall be taken to ensure when using "equivalent thickness" that in the practical situation the concrete thickness will not be reduced by spalling etc.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

3.2 Symbols and units

Symbol	Unit	Designation
L_{exp}	mm	Length of the test specimen exposed to the furnace
L_{sup}	mm	Centre to centre distance between the test specimen supports
L_{spec}	mm	Total length of the test specimen
W_{exp}	mm	Width of the test specimen exposed to the furnace
h	mm	Thickness of concrete slab or height of concrete beam specimen
l_{sup}	mm	Distance of loading points from the specimen support points
P	kN	Loading applied to the slab or beam test specimen
θ_{crit}	°C	Critical temperature as specified in EN 1992-1-2
d_{θ}	mm	Depth in concrete at which chosen θ_{crit} is noted
d_p	mm	Thickness of fire protection material: $d_{p(min)}$ is minimum thickness and $d_{p(max)}$ is maximum applied thickness of fire protection material
$\Delta\theta_{CL}$	°C	Temperature rise, as a function of time
d_{cc}	mm	Depth in unprotected concrete slab at which $\Delta\theta_{CL}$ is noted [used in annex C]

prEN 13381-3:2008 (E)

d_{cp}	mm	Depth in protected concrete at which temperature rise $\Delta\theta(d_{cp},t)$ is measured at time t
$\Delta\theta(d_{cp},t)$	°C	Temperature rise measured in protected concrete at measured depth d_{cp}
f_y	N/mm ²	Yield strength of steel as defined in EN 10080
ε	mm	Equivalent concrete thickness

4 Test equipment**4.1 General**

The furnace and test equipment shall be as specified in EN 1363-1.

4.2 Furnace

The furnace shall be designed to permit the dimensions of the test specimen to be exposed to heating to be as specified in 6.2 and its installation to be as specified in Clause 7.

4.3 Loading equipment

Loading shall be applied according to EN 1363-1. The loading system shall permit loading, of the magnitude defined in 5.3, to be applied along the length and width of the test specimen.

The loading equipment shall not inhibit the free movement of air above the test specimen and no part of the loading equipment, other than at the loading points, shall be closer than 60 mm to the unexposed surface of the test specimen.

<https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d-d9ba41af9980/osist-pren-13381-3-2008>

5 Test conditions**5.1 General**

Test specimens, subjected to predefined loading, are heated upon a furnace in horizontal orientation to provide information on each of the following:

- the temperature distribution within the concrete test member;
- the behaviour of the fire protection system and its stickability;
- the behaviour of the test specimen with respect to specified performance criteria.

It is recommended that the test be continued until the mean temperature upon the main reinforcing bars within the concrete reaches 700 °C, or any single maximum value of 750 °C is recorded, to give the necessary information on the stickability of the fire protection system. However, these temperatures may be modified if requested by the sponsor.

If the recommended termination temperatures are not reached after 6 hours test duration, the test shall normally be terminated.

The procedures given in EN 1363-1 and, if applicable, EN 1363-2, shall be followed in the performance of this test method unless specific contrary instruction is given herein.

5.2 Support and restraint conditions

5.2.1 Standard support and restraint conditions

Concrete slab test specimens shall be tested as a simply supported one way structure with two free edges and an exposed surface and span as defined in 6.2.

Concrete beam test specimens shall be tested simply supported. The test arrangement shall provide lateral stability.

The concrete slab or beam test member shall be installed onto the furnace to allow freedom for longitudinal movement and deformation using at one side rolling support(s) and at the other hinge support(s).

The surface of the bearings shall be smooth concrete or steel plates. The width of the bearings shall be the minimum representative of practice.

5.2.2 Other support and restraint conditions

If the support and restraint conditions differ from the standard conditions specified in 5.2.1, these conditions shall be described in the test report and the validity of the test results shall be restricted to those tested.

5.3 Loading conditions

The load (P) applied to the test specimen shall be calculated, taking account of the dead-weight of the specimen (measured or derived by calculation from samples of the components, see 6.5.1) and the weight of load distribution beams or plates, such that the following bending moments are produced and that the same stresses exist within the steel reinforcement:

small slabs	5 kN.m/m width
large slabs	14 kN.m/m width
beams	25 kN.m

For concrete slab test specimens the load shall be symmetrically applied to the test specimen along two transverse loading lines, each one at a distance (L_{sup}) from each of the supports. The proportion of the total load applied at each loading position shall be as specified in Figure 1 (small slab test specimen) and Figure 2 (large slab test specimen). The load shall produce stresses approximating to a uniformly distributed load.

For concrete beam test specimens the load shall be symmetrically applied to the test specimen by a two point loading system, each one at a distance (L_{sup}) from each of the supports. The proportion of the total load applied at each loading position shall be as specified in Figure 3. The load shall produce stresses approximating to a uniformly distributed load.

Point loads shall be transferred to the test specimen through load distribution beams or plates (Figures 1, 2 and 3).

The total contact area between these and the concrete surface of the test specimen shall be as specified in EN 1363-1, provided that the load distribution beam or plate chosen has a flexural rigidity large enough to give the required distribution of the load.

Load distribution beams, for safety reasons, shall have a height to width ratio of < 1 .

If the load distribution beams or plates are of steel or other high conductivity material, they shall be insulated from the surface of the concrete test specimen by a suitable thermal insulation material.

prEN 13381-3:2008 (E)

Unexposed surface thermocouples shall not be closer than 100 mm to any part of the load distribution system as shown in Figures 1, 2 and 3.

6 Test specimens**6.1 Type and number of test specimens****6.1.1 Type of test specimens**

The type of concrete test member used is determined by the type and practical situation to which the fire protection system is to be used, i.e.:

- a) fire protection systems to be used on flat, two dimensional concrete members only, such as slabs and walls, are evaluated by carrying out the test on large concrete slabs;
- b) fire protection systems to be used on beams and columns only, and subject to three and four sided exposure, are evaluated by carrying out the test on concrete beams;
- c) fire protection systems to be used on slabs, walls, beams and columns are evaluated by carrying out the test on both concrete slabs and beams according to a) and b) above;
- d) tests may be carried out, in addition to the large scale tests, on small concrete test slabs to provide additional test results for the fire protection system when:
 - it is to be applied to a concrete member of concrete thickness less than that specified in this test method;
 - it is to be applied at intermediate fire protection thickness between maximum and minimum thickness;
 - the test is carried out to the smouldering curve (Annex A).

iTeh STANDARD PREVIEW
(standards.iteh.ai)

oSIST prEN 13381-3:2008
<https://standards.iteh.ai/catalog/standards/sist/0584d03b-2f78-486e-919d-d9ba41af9980/osist-pr-en-13381-3-2008>

6.1.2 Number of test specimens

Two full size loaded concrete members (either slabs or beams depending upon the end use as specified in 6.1.1a) and 6.1.1b) shall be tested.

To one the minimum thickness of the fire protection system shall be applied and to the other the maximum thickness. If the fire protection system is only available in a single thickness, then one test on one type of member only shall be carried out at that thickness, and the applicability of the result restricted.

In addition to the mandatory full size tests, small size tests may be carried out to obtain further data, as defined in 6.1.1d). One such test shall be carried out for each and every variable of concrete thickness or intermediate fire protection thickness to be considered. The use of the small slab in the smouldering fire is given in Annex A.

6.2 Size of test specimens**6.2.1 Concrete slabs**

The concrete test slabs shall be of the sizes specified in Table 1 and exemplified in Figure 1 (small specimen) and Figure 2 (large specimen).

Table 1 — Sizes of concrete test slabs

	small specimen	large specimen
Exposed length (mm) L_{exp}	$\geq 1\ 300$ and $< 2\ 300$	4 000 mm minimum
Span (mm) L_{sup}	$\geq 1\ 500$ and $< 2\ 700$ ($L_{exp}+200$) > L_{sup} < ($L_{exp}+400$) [note]	4 200 minimum ($L_{exp}+200$) > L_{sup} < ($L_{exp}+400$) [note]
Specimen length (mm) L_{spec}	$\geq 1\ 700$ and $< 3\ 000$ ($L_{exp}+400$) > L_{spec} < ($L_{exp}+700$)	4 400 mm minimum ($L_{exp}+400$) > L_{spec} < ($L_{exp}+700$)
Exposed width (mm) W_{exp}	$\geq 1\ 000$ and $< 2\ 000$	$\geq 3\ 000$
Thickness (mm) h	(90 ± 10)	(120 ± 10)
Position of loading points from support points (mm)	(600 ± 10)	(1000 ± 10)
NOTE The distance between the exposed part of the test specimen and the supports shall be kept as small as possible. For tests of short duration (less than 240 minutes) a distance of 100 mm at either end is recommended. For tests of longer duration this could be increased to 200 mm at either end, to protect the test equipment from heat damage.		

oSIST prEN 13381-3:2008

6.2.2 Concrete beams

The concrete test beams shall be of a size such that an overall exposed length (L_{exp}) not less than 4 000 mm is obtained.

The span (L_{sup}) shall not be greater than the exposed length by more than 200 mm at each end.

The total specimen length (L_{spec}) shall be not greater than the exposed length by more than 350 mm at each end.

The beam shall be of height (450 ± 10) mm and width (150 ± 10) mm.

The position of the loading points from the support points (L_{sup}) shall be (1 000 ± 10) mm.

The beam construction is shown in Figure 3.

6.3 Construction of concrete test specimens

6.3.1 Concrete slab test members

Concrete slab test members shall contain a reinforcing mesh, which may comprise single reinforcement bars tied together with lashing wire or a prefabricated "welded fabric" mesh.

The mesh (placed towards the exposed surface and protected by the fire protection material) shall comprise 10,0 mm diameter ribbed bars for the large slab and 8,0 mm diameter ribbed bars for the small slab. The permitted tolerances on dimensions of reinforcing bars are given in EN 10080.