
**Metallic and other inorganic coatings —
Electropolishing as a means of smoothing
and passivating stainless steel**

*Revêtements métalliques et autres revêtements inorganiques — Polissage
électrolytique: procédé de brillantage (ou nivellement) et de passivation des
aciers inoxydables*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15730:2000

<https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15730:2000

<https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Information to be supplied by the purchaser to the finisher	2
5 Requirements	2
6 Sampling	4
7 Test methods	4
8 Test report	5
 Annex	
A Typical electropolishing solution and operating conditions	7
Bibliography	8

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15730:2000

<https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 15730 was prepared by Technical Committee ISO/TC 107, *Metallic and other inorganic coatings*, Subcommittee SC 8, *Chemical conversion coatings*.

Annex A of this International Standard is for information only.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

ISO 15730:2000

<https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000>

Introduction

Electropolishing removes a small but finite amount of metal from the surface that, in addition to smoothing and brightening, produces a hygienically clean surface desirable for use by manufacturers of food processing and medical equipment.

In addition to improved passivation, electropolishing provides many other benefits. Some examples are surface stress relief, removal of surface carbon and oxides and reduction of friction. Hydrogen embrittlement of articles is not produced during the electropolishing process, which takes minutes to perform.

The quality of passivation depends on the type of stainless steel, the formulation of the electropolishing solution and the conditions of operation. Free iron on the surface of the stainless steel is removed resulting in improved corrosion resistance. No further chemical treatment is necessary in order to passivate the stainless steel surface. Surface smoothing obtained by electropolishing also improves passivation.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 15730:2000](https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000)

<https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15730:2000

<https://standards.iteh.ai/catalog/standards/sist/71490aa4-0997-4811-b497-35fae38084ef/iso-15730-2000>

Metallic and other inorganic coatings — Electropolishing as a means of smoothing and passivating stainless steel

WARNING — The use of this International Standard may involve hazardous materials, operations and equipment. This International Standard does not purport to address all the safety problems associated with its use. It is the responsibility of the user of this International Standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

Large quantities of hydrogen and oxygen gases are evolved at the electrodes during the electropolishing process. Proper ventilation procedures should be used to ensure their removal. Ignition of hydrogen gas can result in dangerous explosions.

1 Scope

This International Standard specifies the information to be supplied by the purchaser to the finisher, requirements and test methods for electropolishing as a means of smoothing and passivating stainless steel alloys in the S2XXXX, S3XXXX and S4XXXX series, and the precipitation hardened alloys (see ISO/TR 15510 for information on composition).

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 2064:1996, *Metallic and other inorganic coatings — Definitions and conventions concerning the measurement of thickness*.

ISO 2080:1981, *Electroplating and related processes — Vocabulary*.

ISO 4519:1980, *Electrodeposited metallic coatings and related finishes — Sampling procedures for inspection by attributes*.

ISO 9227, *Corrosion tests in artificial atmospheres — Salt spray tests*.

ISO/TR 15510, *Stainless steels — Chemical composition*.

ISO 16348:—¹⁾, *Metallic and other inorganic coatings — Definitions and conventions concerning appearance*.

3 Terms and definitions

For the purposes of this International Standard, the definitions given in ISO 2064, ISO 2080 and ISO 4519 (some of which are repeated below for convenience) and the following apply.

1) To be published.

3.1

passivation

rendering of a stainless steel surface into a lower state of chemical reactivity

NOTE Passivated surfaces are characterized by the absence of free iron and the formation of a thin coherent oxide film.

3.2

electropolishing

smoothing and brightening of a metal surface by making it anodic in an appropriate solution

[ISO 2080:1981]

3.3

inspection lot

collection of treated items that are of the same kind, that have been produced to the same specifications, that have been treated by a single supplier at one time, or at approximately the same time, under essentially identical conditions and that are submitted for acceptance or rejection as a group

[Based on ISO 4519:1980, definition 3.7]

3.4

significant surface

part of the article covered or to be covered by the coating and for which the coating is essential for serviceability and/or appearance and where the coating has to meet all of the specified requirements

[ISO 2064:1996]

iTeh STANDARD PREVIEW
(standards.iteh.ai)

4 Information to be supplied by the purchaser to the finisher

When ordering articles smoothed and passivated in accordance with this International Standard, the purchaser shall provide the following information:

- a) the number of this International Standard, i.e. ISO 15730, the alloy designation number and the test method(s) to be used to evaluate the article (see clause 7);
- b) the appearance required. Alternatively, a sample showing the required finish shall be supplied or approved by the purchaser in accordance with ISO 16348 (see note 1);
- c) those areas on the article where electrical contact is acceptable;
- d) the dimensional tolerances, if any, to be stated in the ordering document (see note 2);
- e) any requirements for passivation testing (see 5.3 and clause 7);
- f) any requirement for the provision of a test report (see 5.4 and clause 8).

NOTE 1 When required, the basis material may be subjected, prior to electropolishing, to such mechanical polishing as may be required to yield the desired final surface characteristics.

NOTE 2 Typically, 5 µm to 10 µm of metal are removed from the surface during electropolishing; however, up to 50 µm may be removed for additional smoothing. Greater amounts will be removed from corners and edges, i.e. areas of high current density, unless shields and/or auxiliary cathodes are used.

5 Requirements

5.1 Visual defects

Where specified the significant surfaces of the article to be smoothed and passivated by electropolishing shall be free of clearly visible defects such as pits, roughness, striations or discoloration when examined with 20/20 eyesight at a distance of approximately 0,5 m.

NOTE Defects in the surface of the basis material such as scratches, porosity and inclusions can adversely affect the appearance and performance of the article.

5.2 Process

5.2.1 General

The basis material may have to be subjected to preparatory operations, e.g. polishing and cleaning in order to remove surface soil such as polishing compounds, oils, etc.

5.2.2 Electropolishing

Following any preparatory operations, the article(s) shall be introduced into the electropolishing solution for a period of time at the current density and temperature required to produce the surface finish specified by the purchaser [see b) of clause 4].

NOTE 1 Annex A describes a typical electropolishing solution and operating conditions suitable for many stainless steel alloys.

NOTE 2 Proprietary electropolishing solutions are available offering special features such as low sludging, better bright throwing power, longer life or better performance with specific stainless steel alloys.

NOTE 3 Intricately shaped articles may not receive the same degree of passivation in recessed areas due to low current densities. By increasing the time and/or overall current density, or by using auxiliary cathodes, the electropolishing may be improved in such areas and subsequent passivation tests may be passed.

5.2.3 Post treatment and rinsing

The electropolishing process produces a residual surface film when withdrawn from the electropolishing solution that can adversely affect appearance or performance.

The film shall be removed either by:

- immersing the article in nitric acid solution of 10 % volume fraction to 30 % volume fraction (relative density 1,42; 70 % mass fraction) at room temperature; or
- using several rinse stages.

Neutralization procedures such as immersion in alkaline solutions shall not be used as they have a tendency to “set” the residual surface film and detract from appearance and performance.

The article shall be rinsed subsequently to remove all traces of acidified water that can affect the appearance and performance of the passive part.

NOTE De-ionized or distilled water may be used to avoid water spots.

5.3 Passivation testing

5.3.1 When tested in accordance with 7.1, there shall be no evidence on the article of red rust or other visible products resulting from the test.

5.3.2 When tested in accordance with 7.2, there shall be no evidence on the article of red rust or other visible products resulting from the test.

5.3.3 When tested in accordance with 7.3, there shall be no evidence on the article of red rust or other visible products resulting from the test.