

INTERNATIONAL STANDARD

**ISO
6221**

Third edition
1996-12-15

Photography — Films and papers — Determination of dimensional change

*Photographie — Films et papiers — Détermination des variations
dimensionnelles*

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

[ISO 6221:1996](https://standards.iteh.ai/catalog/standards/sist/73274368-0c9c-4bac-9b6e-47a10ad4398e/iso-6221-1996)

<https://standards.iteh.ai/catalog/standards/sist/73274368-0c9c-4bac-9b6e-47a10ad4398e/iso-6221-1996>



Reference number
ISO 6221:1996(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 6221 was prepared by Technical Committee ISO/TC 42, *Photography*.

This third edition cancels and replaces the second edition (ISO 6221:1991), which has been technically revised.

Annexes A, B and C of this International Standard are for information only.

Introduction

Photographic films and papers exhibit temporary or reversible dimensional changes as well as permanent dimensional changes. This International Standard is designed to provide uniform methods for treating the samples and for expressing the dimensional changes which occur with changes in atmospheric conditions and those which occur in processing and ageing.

Temporary or reversible dimensional changes are the result of changes in equilibrium moisture content (which is determined by the relative humidity of the surrounding atmosphere) or changes in temperature. Permanent dimensional changes occur as the result of processing and ageing. The rate of permanent shrinkage of film generally increases with temperature but decreases with time. The rate of shrinkage may also be greatest at either high or low relative humidity, depending on the type of film. Some materials, particularly photographic film on polyester base, can show a swelling after a high humidity exposure.

The increasing use of photographic films in recent years, in applications where dimensional stability is critical, has emphasized the importance of an accurate measure of dimensional properties. For example, in photo-mechanical reproductions a dimensional change of as little as 0,01 % may be of practical importance. In the case of aerial mapping, uniform shrinkage is not serious since it can be easily corrected by a change in magnification, but any difference in shrinkage in the two principal directions is a source of error. Any localized or non-uniform changes in dimension are of practical concern.

The dimensional change properties of any film or paper depend not only on their composition and method of manufacture but also on their thermal and moisture content history. Accurate evaluation of such properties requires some control over the sample history as well as very precise control over the conditioning and measuring procedures. Film and paper dimensions are also subject to hysteresis effects. These are relatively more important with the more stable materials such as polyester photographic base films.

Additional information on the dimensional characteristics of photographic films and papers and on methods of measurement may be found in the bibliography (see annex C).

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

ISO 6221:1996

<https://standards.iteh.ai/catalog/standards/sist/73274368-0c9c-4bac-9b6e-47a10ad4398e/iso-6221-1996>

Photography — Films and papers — Determination of dimensional change

1 Scope

This International Standard gives a method for determining the dimensional change of photographic films and papers caused by

- a) variations in equilibrium moisture content due to change in the relative humidity of the atmosphere (humidity coefficient of expansion);
- b) change in temperature (thermal coefficient of expansion);
- c) processing;
- d) ageing.

This International Standard deals with the moisture content and thermal history of the samples before measurement, the atmospheric conditions during measurement, and the treatment of the data. It does not describe the various experimental techniques used to make the measurements.

This International Standard is not suitable for determining the dimensional change of instant photographic film.

2 Definitions

For the purposes of this International Standard, the following definitions apply.

2.1 humidity expansion (or contraction): Dimensional change caused by the gain (or loss) of moisture following changes in the relative humidity of the ambient air at constant temperature.

2.2 humidity coefficient of expansion: Change in dimension per unit length per 1 % change in relative humidity at constant temperature.

2.3 thermal expansion (or contraction): Dimensional change caused by a rise (or fall) of temperature at constant relative humidity.

NOTE — This is an apparent thermal expansion since the moisture content of film varies slightly with temperature at constant relative humidity. However, the primary effect is thermal expansion. Thermal expansion is less important for paper because of the small changes involved, particularly compared to humidity effects.

2.4 thermal coefficient of expansion: Change in dimension per unit length per 1 °C change in temperature at constant relative humidity.

2.5 dimensional change due to processing: Permanent dimensional change caused by photographic processing. This may be the conventional wet chemical processing, vapour processing or heat processing. It is

measured after conditioning at the same relative humidity and temperature as used for the original measurement and is expressed as a percentage.

2.6 dimensional change due to processing plus ageing: Permanent dimensional change which occurs as a result of processing plus ageing of the processed material. It is measured after conditioning of the processed, aged film or paper at the same relative humidity and temperature as used for the original measurement and is expressed as a percentage.

2.7 length direction: Direction of the film or paper parallel to its forward movement in the film- or paper-making machine. This is also termed "grain" or "machine direction" in the case of papers.

2.8 width direction: Direction of the film or paper at right angles to the length direction. This is also termed "cross direction".

2.9 differential dimensional change: Difference between the dimensional changes of the material in the two principal directions (length and width).

NOTE — Polyester-based films frequently have maximum and minimum dimensional changes in directions other than the length or width. These can be determined by rotating and viewing the uncoated base between a pair of crossed polarizers. When the direction corresponding to either the maximum or minimum dimensional change is coincident with the optical axis of one polarizer, there is minimum light transmission through the base.

2.10 conditioning: Exposure of a sample to air at a given relative humidity and temperature until equilibrium is reached.

2.11 preconditioning: Establishment of a moisture content history by conditioning the sample at a relative humidity above or below the conditioning relative humidity used for measurement. The purpose of preconditioning is to control the effects of hysteresis (see 2.12).

2.12 dimensional hysteresis: Difference in the absolute dimensions of a sample in equilibrium with air at a given relative humidity, when conditioned from a higher relative humidity and when conditioned from a lower relative humidity (see annex B).

3 Measurement technique

There are a number of different techniques used for measuring the dimensional change of sensitized materials. Specifications of measuring equipment are beyond the scope of this International Standard, but several approaches are described in annex A.

4 Sampling

4.1 Selection of samples

Samples intended for dimensional stability tests shall exhibit no obvious physical defects, be representative of the whole of the material being tested, be handled in the same manner as in actual use, and be treated uniformly. When different materials are to be compared, they shall preferably have been subjected to the same conditioning history. The length direction should be indicated if known.

4.2 Handling of specimens

Specimens shall be prepared under controlled conditions and then separated into groups which are subjected to different atmospheric conditions. The operator shall take care not to breathe on the specimens and shall wear moisture-resistant gloves while handling them since moisture from the skin may reduce the accuracy of the results.

4.3 Processing of specimens

Specimens shall be exposed and processed by methods and equipment normal for the product. When the effects of processing machines, tensions, or drying conditions are being investigated, the film or paper shall be processed in the sizes of practical interest. Specimens may be developed as negatives or as positives, but this can affect the dimensional change properties of some materials. Silver-gelatin films generally show less dimensional change when they have low density rather than high density.

5 Conditioning

5.1 Constant humidity chamber

Either a walk-in constant humidity room or a cabinet may be used.

5.1.1 Constant humidity room

The relative humidity (RH) shall be held constant to ± 1 % RH or better in areas of the room where specimens are measured. The room shall be vapour sealed and insulated on all six sides. The room shall be mechanically air-conditioned and the air circulated at a linear velocity of at least 15 cm/s. The number of personnel permitted in the room at any one time during testing shall be limited. The relative humidity of the room shall be checked regularly, preferably by means of an electric hygrometer calibrated by a dew-point method.

5.1.2 Constant humidity cabinet

A convenient size for a humidity cabinet is approximately 1 m in height and 0,5 m in width and depth. It shall be constructed of materials which will ensure good insulation. Suitable provision shall be made for thermostatically controlling the temperature within the cabinet. Air shall be circulated throughout the cabinet at a linear velocity of at least 30 cm/s. The cabinet shall be equipped with ports filled with moisture-impermeable (e.g. rubber or plastic) gloves for entrance of the operator's hands. The relative humidity of the cabinet shall be checked regularly, preferably by means of an electric hygrometer calibrated by a dew-point method.

The relative humidity within the cabinet shall be controlled as closely as possible. Where the cabinet is mechanically air-conditioned, the relative humidity shall be constant to ± 1 % RH or better. Where a saturated salt solution is used for control, provision shall be made at the bottom of the cabinet for inserting suitable trays, which shall hold about 1 litre of salt solution. A solution tray with a large surface area is needed and about 100 cm² is suitable.

5.2 Standard temperature and humidity

The standard temperature shall be 23 °C \pm 0,5 °C except for the test specified in clause 7. The relative humidity is specified in the respective test procedure subclauses and depends upon the property being measured.

5.3 Conditioning of specimens

5.3.1 General

Specimens shall be suspended in the conditioning atmosphere by means of a hook or a rod through a hole in the middle of one end near the edge of the specimen. The specimens shall be separated to prevent contact with each other. An alternative method of conditioning is to place specimens in racks spaced so that there is free circulation of the air on both sides of the material. The specimens shall not be removed from the conditioning atmosphere for measuring. Condition specimens until practical moisture equilibrium has been reached.

The time required to achieve this shall be established by actual measurements on representative specimens or based on prior experience.

5.3.2 Film

The conditioning time for film will be about 4 h but will vary according to access of the conditioning air, the film type, base thickness, etc. Conditioning time shall not exceed 24 h.

At relative humidities of 60 % and above, films and papers sometimes undergo an irreversible change in size with time. For this reason, the conditioning time shall be standardized for comparison purposes.

5.3.3 Paper

Double-weight fibre-base papers will require about 1 day of conditioning; resin-coated papers require at least 7 days.

6 Test for humidity coefficient of expansion

6.1 Procedure

Five specimens shall be preconditioned¹⁾ at 10 % to 15 % RH, then conditioned at 15 % to 25 % RH (but at least 5 % RH above the preconditioning relative humidity) and measured. They shall then be conditioned again at 50 % to 60 % RH and remeasured.²⁾ The conditioning temperature shall be constant as specified in 5.2. The two conditioning humidities shall be measured to an accuracy of ± 1 % RH in accordance with 5.1.1.³⁾

The test may be made on both unprocessed and processed specimens depending on the measuring method used (see annex A). The humidity coefficients of expansion of unprocessed and processed film are generally not the same.

(standards.iteh.ai)

6.2 Calculations

ISO 6221:1996

Since the dimensional change curve versus relative humidity is not always linear (see annex B), this test method gives only an average coefficient over the range measured. The dimensional change between the two measurements of five specimens shall be averaged and the humidity coefficients of expansion shall be calculated in accordance with the following formula:

$$H = \frac{l_2 - l_1}{l_1 \times \Delta RH}$$

where

H is the humidity coefficient of expansion;

l_1 is the gauge distance or the dimension measured at the initial conditioning temperature and relative humidity;

l_2 is the gauge distance or the dimension measured at the final conditioning temperature and relative humidity;

ΔRH is the difference between the two conditioning relative humidities used, as a percentage.

1) Preconditioning times of 1 h to 2 h are recommended for photographic film, 4 h for fibre-base paper, and 7 days for resin-coated paper.

2) This range of relative humidity is selected because the dimensions with respect to the relative humidity curve for some materials is abnormal, i.e. above 60 % RH (see annex B).

3) Humidity measurements to within ± 1 % RH are difficult and are discussed in Technical Report ANSI/NAPM TR1-1995, *Humidity Measurement*, which may be obtained from the American National Standards Institute, 11 West 42nd St., New York, NY 10036, USA.

6.3 Test report

The test report shall contain the following:

- a) humidity coefficients of expansion for both the length and width directions;
- b) two conditioning relative humidities and temperature;
- c) a statement as to whether the specimens were unprocessed, processed to high density, or processed clear.

7 Test for thermal coefficient of expansion

NOTE — Dimensional changes of photographic paper with reasonable changes in temperature (but at the same moisture content) are so small that measurement is very difficult and has little practical significance. This method is of importance for photographic film.

7.1 Procedure

Five specimens shall be conditioned, first at 45 °C to 50 °C and measured, and then conditioned at 10 °C to 25 °C and measured again.⁴⁾ A conditioning time of 4 h at each temperature is recommended. Both the specimens and the measuring equipment shall be at thermal equilibrium. The relative humidity shall be the same at both temperatures and controlled as specified in 5.1. A low humidity is more practical for laboratory work, but other relative humidities may be used.⁵⁾ The test can be made on either unprocessed or processed material, depending on the measuring method used (see annex A). The measuring equipment shall not be affected by the thermal changes or else the measurements shall be corrected for thermal effects.

ISO 6221:1996

<https://standards.iteh.ai/catalog/standards/sist/73274368-0c9c-4bac-9b6e-47a10ad4398e/iso-6221-1996>

7.2 Calculations

The dimensional change between the two measurements of five specimens shall be averaged and the thermal coefficients of expansion shall be calculated in accordance with the following formula:

$$\alpha = \frac{l_3 - l_4}{l_4 \times \Delta T}$$

where

- α is the thermal coefficient of expansion;
- l_3 is the gauge distance or the dimension measured at the initial conditioning temperature and relative humidity;
- l_4 is the gauge distance or dimension measured at the final conditioning temperature and relative humidity;
- ΔT is the difference between the two conditioning temperatures used, in degrees Celsius.

Depending on the type and composition of the measuring equipment, it may be necessary to correct for the thermal expansion of the gauge or of the reference standard.

4) The high-temperature measurement is made first so that any permanent shrinkage which may occur during conditioning will not affect the result.

5) The thermal coefficient of expansion varies slightly with relative humidity for some materials.

7.3 Test report

The test report shall contain the following:

- a) thermal coefficients of expansion for both the length and width directions;
- b) conditioning temperatures and relative humidity;
- c) a statement as to whether the samples were unprocessed, processed to high density, or processed clear.

8 Test for dimensional change due to processing

8.1 General

The dimensional change due to processing of photographic films and papers can be markedly affected by the following three variables in the test procedure.

8.1.1 Relative humidity for preconditioning of raw specimen

The dimensions of the unprocessed specimen at a given relative humidity can be dependent to a large extent upon the earlier humidity used for preconditioning (preconditioning humidity history). This is due to the hysteresis and relaxation effects described in annex B. It is necessary to specify whether the specimen had been preconditioned from a lower or from a higher humidity prior to the original measurement on the unprocessed material. This is indicated by the letter "L" for the former and "H" for the latter. When a specimen is measured from the original box (or packaging) without preconditioning, the letter "B" is used.

8.1.2 Relative humidity for preconditioning of processed specimen

The preconditioning humidity history is as important for the dimensions of the processed specimen as for the raw specimen described in 8.1.1. The letters "L" and "H" are also used to indicate the humidity history of the processed material. The letter "H" is also used when the specimen is dried after processing at the measuring humidity.

Although the drying conditions after processing affect the dimensional change due to processing, the effect is eliminated when the processed specimen is preconditioned. If measurements are made on a processed specimen that is not preconditioned after processing, the letter "M" is used.

8.1.3 Measuring relative humidity

Specimens shall be conditioned to moisture equilibrium using the same relative humidity for both the raw and processed measurements. Otherwise a reversible humidity change will be included in the measured dimensional change. However, the dimensional change due to processing can be very dependent upon the relative humidity at which those measurements are made and this shall be indicated when reporting the results.

8.2 Coding system

A wide variety of test procedures can be used for the measurement of dimensional change due to processing by varying the preconditioning history of the raw and processed specimens and the relative humidity at which these measurements are made. To characterize the procedure used, a coding system is used. For example, procedure LH-50 signifies that the raw specimen had been preconditioned from a low humidity (L), the processed specimen had been preconditioned from a high humidity (H), and all measurements were made at 50 % RH. Likewise, procedure LL-10 indicates that both the raw and processed specimen had been preconditioned at a lower humidity than the 10 % RH at which the specimens were measured. In practice, the range encompassed by LH-50 (tray processed and air dried) and HL-50 (machine processed and machine dried) generally reflects the expected variation in processing dimensional change. The procedure BM-50 indicates that no preconditioning was done for either the raw specimen from the original box (or packaging), or the processed specimen from the machine.

8.3 Procedure

Five specimens shall be preconditioned.⁶⁾ The relative humidity for preconditioning shall be chosen to provide the desired low (L) or high (H) humidity history and shall be at least 5 % RH below or above the measuring humidity. The specimens shall then be conditioned to the measuring relative humidity and the specimen dimensions shall be measured (or exposed if a photographic image is to be used for measurement as described in annex A). The specimens shall be processed and dried as outlined in 4.3. The specimens shall subsequently be preconditioned to the desired low or high preconditioning humidity, conditioned at the measuring relative humidity and remeasured.⁷⁾ The conditioning temperature shall be the same before and after processing and shall be controlled as specified in 5.2; the conditioning time shall be as specified in 5.3.

8.4 Calculations

The dimensional changes between the two measurements of five specimens shall be averaged and the processing dimensional change calculated, as a percentage, according to the following formula:

$$P = \frac{l_6 - l_5}{l_5} \times 100$$

where

- P is the dimensional change due to processing, as a percentage (a negative sign indicates shrinkage and a positive sign indicates expansion);
- l_5 is the gauge distance or the dimension measured at the initial conditioning temperature and relative humidity;
- l_6 is the gauge distance or the dimension measured at the final conditioning temperature and relative humidity.

ISO 6221:1996

8.5 Test report <https://standards.iteh.ai/catalog/standards/sist/73274368-0c9c-4bac-9b6e-47a10ad4398e/iso-6221-1996>

The test report shall contain the following:

- a) procedure used (for example LH-50);
- b) dimensional changes due to processing for both the length and width directions;
- c) processing conditions (including drying conditions), clearly indicating whether processed to a high density or processed clear.

9 Test for dimensional change due to processing plus ageing

9.1 Ageing conditions

The ageing conditions used shall be selected from the following:

- a) normal conditions: 23 °C ± 2 °C and (50 ± 5) % RH;
- b) summer conditions: 32 °C ± 2 °C and (50 ± 5) % RH;
- c) moist tropical conditions: 32 °C ± 2 °C and (90 ± 5) % RH;
- d) dry accelerated conditions: 50 °C ± 2 °C and (20 ± 5) % RH.

6) Preconditioning times of 1 h to 2 h are recommended for photographic film, 4 h for fibre-base paper, and 7 days for resin-coated paper.

7) When specimens are dried at the measuring humidity the letter "M" is used without the need for a separate preconditioning step.