
Aeronavtika - Barve in laki - Dvokomponentni temeljni premaz, korozijsko obstojen, kromiran, ki se suši pri sobni temperaturi - 002. del: Visoka korozijska odpornost

Aerospace series - Paints and varnishes - Corrosion resistant chromated two component cold curing primer - Part 002: High corrosion resistance

Luft- und Raumfahrt - Beschichtungsstoffe - Korrosionsbeständiger Zweikomponenten-Primer, kalthärtend, chromathaltig - Teil 002: Hohe Korrosionsbeständigkeit

Série aéronautique - Peintures et vernis - Peinture primaire anti-corrosion chromatée, à deux composants polymérisant à température ambiante - Partie 002 : Haute résistance à la corrosion

Ta slovenski standard je istoveten z: EN 2435-002:2006

ICS:

49.040	Prevleke in z njimi povezani postopki, ki se uporabljajo v letalski in vesoljski industriji	Coatings and related processes used in aerospace industry
--------	---	---

SIST EN 2435-002:2009

en,de

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 2435-002:2009

<https://standards.iteh.ai/catalog/standards/sist/cb790eaa-912e-4b5e-a979-667a04691e24/sist-en-2435-002-2009>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 2435-002

June 2006

ICS 49.040

English Version

**Aerospace series - Paints and varnishes - Corrosion resistant
chromated two component cold curing primer - Part 002: High
corrosion resistance**

Série aéronautique - Peintures et vernis - Peinture primaire
anti-corrosion chromatisée, à deux composants polymérisant
à température ambiante - Partie 002 : Haute résistance à la
corrosion

Luft- und Raumfahrt - Anstrichstoffe -
Korrosionsbeständiger Zweikomponenten-Grundanstrich,
kalthärtend, chromathaltig - Teil 002: Hohe
Korrosionsbeständigkeit

This European Standard was approved by CEN on 27 February 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....	3
0 Introduction	4
1 Scope	4
2 Normative references	4
3 Definitions	5
4 Classification.....	5
5 Batch release and qualification testing	5

iTeh STANDARD PREVIEW **(standards.iteh.ai)**

SIST EN 2435-002:2009

<https://standards.iteh.ai/catalog/standards/sist/cb790eaa-912e-4b5e-a979-667a04691e24/sist-en-2435-002-2009>

Foreword

This European Standard (EN 2435-002:2006) has been prepared by the AeroSpace and Defense Industries Association of Europe - Standardization (ASD-STAN).

After enquiries and votes carried out in accordance with the rules of this Association, this Standard has received the approval of the National Associations and the Official Services of the member countries of ASD, prior to its presentation to CEN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by December 2006, and conflicting national standards shall be withdrawn at the latest by December 2006.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 2435-002:2009

<https://standards.iteh.ai/catalog/standards/sist/cb790eaa-912e-4b5e-a979-667a04691e24/sist-en-2435-002-2009>

EN 2435-002:2006 (E)

0 Introduction

This standard is part of a series of EN non-metallic materials standards for aerospace applications.

The general organisation of this series is described in EN 4385.

This standard is a level 3 document as defined in EN 4385.

Definition of subcase numbering in Tables 2 to 5 is given in TR 7000-9.

1 Scope

This standard defines the requirements for a two component, chromated epoxy or polyurethane, high corrosion resistant primer with a degree of resistance to aircraft fluids which can be used with or without a finish for aerospace applications.

The properties specified in this standard are obtained on defined aluminium alloy test pieces prepared in accordance with EN 3837 and ISO 3270. The ability of the material to be used for a specific application (e.g. alternative substrate, alternative primer, specific drying conditions etc.) shall be determined by supplementary tests to confirm that the requirements of this standard are met.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 2334, Aerospace series — *Chromic-sulphuric acid pickle of aluminium and aluminium alloys*

EN 2379, Aerospace series — *Fluids for assessment of non-metallic materials*¹⁾

EN 2434-004, Aerospace series — *Paints and varnishes — Two component cold curing polyurethane finish — Part 004: High flexibility*¹⁾

EN 2709, Aerospace series — *Aluminium alloy 2024-T3510 bar and section — $1,2 \leq (a \text{ or } D) \leq 150 \text{ mm}$ with peripheral coarse grain control*¹⁾

EN 3837, Aerospace series — *Paints and varnishes — Nature and method for surface preparation of test pieces in aluminium alloys*¹⁾

EN 3840, Aerospace series — *Paints and varnishes — Technical specification*¹⁾

EN 4385, Aerospace series — *Non-metallic materials — General organisation of standardisation — Links between types of standards*¹⁾

ISO 1513, *Paints and varnishes — Examination and preparation of samples for testing*

ISO 3270, *Paints and varnishes and their raw materials — Temperature and humidities for conditioning and testing*

ISO 3696, *Water for analytical laboratory use — Specification and test methods*

TR 7000-9, Aerospace series — *Non-metallic materials — Rules for the drafting and presentation of material standards — Part 9: Paints and varnishes*²⁾

1) Published as ASD Prestandard at the date of publication of this standard.

2) Published as ASD Technical Report at the date of publication of the standard.

3 Definitions

Not applicable.

4 Classification

The primer is classified according to the nature of the most typical chemical reaction that occurs between the two components:

Type A: epoxy — (reaction between an epoxy resin and an activator with amino functional groups).

Type B: polyurethane — (reaction between an hydroxyl functional resin and a polyisocyanate activator).

5 Batch release and qualification testing

5.1 Batch release testing

For batch acceptance the tests marked with the symbol * in Tables 2 to 4 shall be performed.

5.2 Qualification tests

For product qualification, all tests mentioned in this standard, in the Tables 1 to 5, shall be performed.

Table 1 — General requirements

1.001	Material description	Two component cold curing chromated primer with high corrosion resistance
1.002	Formulation	Base — a base containing essentially chromate corrosion inhibitor associated, or not, with pigments and fillers dispersed in a mixture of resins and solvents. Activator — an activator solution Thinner — if required
1.003	Form and method of production	These components shall be mixed in simple whole number proportions, by volume or by weight, in accordance with the manufacturer's instructions.
1.004	Technical specification	EN 3840
1.009	Application and use	Dry film thickness of $(20 \pm 5) \mu\text{m}$.
1.010	Storage	See EN 3840
1.011	Shelf life	See EN 3840
1.013	Processing conditions	ISO 3270 for 7 days before testing unless otherwise specified.
1.093	Quality assurance	See EN 3840
1.094	Designation	Primer EN 2435-002 Type A or Type B
1.095	Packaging	See EN 3840
1.096	Identification marking	See EN 3840
1.097	Flash point	See EN 3840
1.098	Health and safety	See EN 3840

Table 2 — Physical and chemical characteristics

2.014	Condition *	1	ISO 1513	
		6	As received in original container.	
		7	Shall be free from extraneous matter and show no skinning, gelling, hard settlement or other defect which will prevent satisfactory application to produce a defect free film.	
2.011	Application properties and finish *	1	None	
		3	EN 3837 — A ₂	2024-T3 Clad
		4	EN 3837 Process A or B or C	EN 2334 Pickle or CAA or CCC
		5	Primer to this standard.	
		7	Paint film shall show an opaque even finish, free from runs, sags, wrinkling, pin holing or other defect.	
2.034	Sedimentation rating	1	EN 3840	
			Test 5	
		6	Base + activator + thinner	
2.012	Pot life *	1	EN 3840	
			Test 20 followed by Test 8 ^a or Test 9 ^a	
		6	Base + activator + thinner	
2.029	Viscosity *	7	s or Pa s	≤ 2 × initial value after 4 h
		1	EN 3840	
			Test 8 ^a or Test 9 ^a	
2.035	Fineness of grind *	6	Base + activator + thinner	
		7	s or Pa s	± 10 % ^{b c}
		1	EN 3840	
2.027	Non volatile matter		Test 10	
		6	Base + activator	
		7	µm	≤ 30
2.027	Volatile organic compound (VOC) content	1	EN 3840	
			Test 49	
		6	Base + activator + thinner	
2.057	Density *	7	g/l	≤ reference value ^{b c}
		1	EN 3840	
			Test 3	
2.057	Density *	6	Base	
		7	g/cm ³	± 2 ^{b c e}

continued

Table 2 — Physical and chemical characteristics (concluded)

2.057	Density hydrometer *	1	EN 3840		
			Test 4		
		6	Activator + thinner		
		7		Activator	Thinner
			g/cm ³	± 1 ^{b c}	± 1 ^{b c}
2.036	Flash point	1	EN 3840		
			Test 7		
		7	°C	Base	Activator
			≥ reference value ^c	≥ reference value ^c	≥ reference value ^c
2.041	Surface dry time	1	EN 3840		
			Test 21		
		3	EN 3837 — A ₂		2024-T3 Clad
		4	EN 3837 Process A or B or C		EN 2334 Pickle or CAA or CCC
		5	Primer to this standard.		
		6	ISO 3270		
		7	h	≤ 1 ^d	
2.041	Drying time — Print free	1	EN 3840		
			Test 22		
		3	EN 3837 — A ₂		2024-T3 Clad
		4	EN 3837 Process A or B or C		EN 2334 Pickle or CAA or CCC
		5	Primer to this standard.		
		6	ISO 3270		
		7	h	≤ 4 using a load of 1 000 g ^d	
2.041	Through dry time *	1	EN 3840		
			Test 23		
		3	EN 3837 — A ₂		2024-T3 Clad
		4	EN 3837 Process A or B or C		EN 2334 Pickle or CAA or CCC
		5	Primer to this standard.		
		6	ISO 3270		
		7	h	≤ 16	
2.999	Notes	* See 5.1 ^a Test 8 shall be used for non-thixotropic paints and test 9 for thixotropic paints. ^b The deviation is that compared to the reference value. ^c The reference value is that established during qualification. ^d Unless otherwise specified. ^e Test could also be used for activator and thinner if required.			