



# Standard Test Method for Precipitation Number of Lubricating Oils<sup>1</sup>

This standard is issued under the fixed designation D 91; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

*This test method has been adopted for use by government agencies to replace Method 3101 of Federal Test Method Standard No. 791b.*

## 1. Scope

1.1 This test method covers the determination of the precipitation number of steam cylinder stocks and black oils, and can be used for other lubricating oils.

1.2 The values stated in acceptable SI units are to be regarded as the standard.

1.3 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

## 2. Referenced Documents

### 2.1 ASTM Standards:

- D 86 Test Method for Distillation of Petroleum Products<sup>2</sup>
- D 611 Test Methods for Aniline Point and Mixed Aniline Points of Petroleum Products and Hydrocarbon Solvents<sup>2</sup>
- D 1298 Test Method for Density, Relative Density (Specific Gravity), or API Gravity of Crude Petroleum and Liquid Petroleum Products by Hydrometer Method<sup>2</sup>
- D 4057 Practice for Manual Sampling of Petroleum and Petroleum Products<sup>3</sup>
- D 4177 Practice for Automatic Sampling of Petroleum and Petroleum Products<sup>3</sup>

## 3. Terminology

### 3.1 Definitions of Terms Specific to This Standard:

3.1.1 *ASTM precipitation number, n of lubricating oils*—the number of millilitres of precipitate formed when 10 mL of lubricating oil are mixed with 90 mL of ASTM precipitation naphtha, and centrifuged under the conditions of the test.

## 4. Significance and Use

4.1 Fully refined petroleum oils normally contain no naphtha insoluble material. Semirefined or black oils frequently contain some naphtha insoluble material (sometimes referred to as *asphaltenes*). This test measures the amount of

naphtha insoluble material in the oil. This quantity is reported as the precipitation number.

## 5. Apparatus

5.1 *Centrifuge Tube*, cone-shaped, conforming to the dimensions given in Fig. 1, and made of thoroughly annealed glass. The graduations, numbered as shown in Fig. 1, shall be clear and distinct, and the mouth shall be constructed in a shape suitable for closure with a cork. Scale-error tolerances and smallest graduations between various calibration marks are given in Table 1 and apply to calibrations made with air-free water at 20°C.

5.2 *Centrifuge*, meeting all the safety requirements for normal use and capable of whirling two or more filled centrifuge tubes at a speed which can be controlled to give a relative centrifugal force (rcf) between 600 and 700 at the tip of the tubes. The revolving head, trunnion rings, and trunnion cups, including the rubber cushion, shall be soundly constructed to withstand the maximum centrifugal force capable of being delivered by the power source. The trunnion cups and cushions shall firmly support the tubes when the centrifuge is in motion. The centrifuge shall be enclosed by a metal shield or case strong enough to eliminate danger if any breakage occurs. Calculate the speed of the rotating head by means of the following equation:

$$\text{rpm} = 1337 \sqrt{\text{rcf}/d} \quad (1)$$

where:

rcf = relative centrifugal force, and

*d* = diameter of swing, in mm, measured between tips of opposite tubes when in rotating position.

Table 2 shows the relationship between diameter swing, rcf, and revolutions per minute.

## 6. Reagent

6.1 *ASTM Precipitation Naphtha* (**Warning**—see Note 1) shall conform to the following requirements:

Test	Requirement	ASTM Designation
Density at 15°C	0.692 to 0.702	D 1298
Aniline point	58 to 60°C	D 611
Initial boiling point	not less than 50°C	D 86
50 % point	70 to 80°C	D 86
End point	not more than 130°C	D 86

<sup>1</sup> This test method is under the jurisdiction of ASTM Committee D-2 on Petroleum Products and Lubricants and is the direct responsibility of Subcommittee D02.06 on Analysis of Lubricants.

Current edition approved Dec. 10, 1997. Published June 1998.

Originally published as D 91 – 21 T. Last previous edition D 91 – 92.

<sup>2</sup> *Annual Book of ASTM Standards*, Vol 05.01.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 05.02.