



# SLOVENSKI STANDARD

SIST EN 754-2:2008

01-maj-2008

BUXca Yý U.

SIST EN 754-2:1998

---

5`i a ]b]^[b`Ui a ]b]Yj Yn`]h]bY!`<`UXbc`j`Y YbY`dU]W#Xfc[ c j ]]b`Wj ]!`&`rXY.  
A Y Ubg\_Y`Uglbcgh]

Aluminium and aluminium alloys - Cold drawn rod/bar and tube - Part 2: Mechanical properties

Aluminium und Aluminiumlegierungen - Gezogene Stangen und Rohre - Teil 2:  
Mechanische Eigenschaften

Aluminium et alliage d'aluminium - Barre et tubes étirés - Partie 2: Caractéristiques  
mécaniques

[SIST EN 754-2:2008](#)

[https://standards.iteh.ai/catalog/standards/sist/33e2d76b-ef4b-4dcb-ba73-](https://standards.iteh.ai/catalog/standards/sist/33e2d76b-ef4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008)

[1a344587c33c/sist-en-754-2-2008](https://standards.iteh.ai/catalog/standards/sist/33e2d76b-ef4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008)

**Ta slovenski standard je istoveten z: EN 754-2:2008**

---

**ICS:**

77.150.10

**SIST EN 754-2:2008**

**en,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST EN 754-2:2008

<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-ef4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>

English Version

**Aluminium and aluminium alloys - Cold drawn rod/bar and tube -  
Part 2: Mechanical properties**

Aluminium et alliages d'aluminium - Barres et tubes étirés -  
Partie 2: Caractéristiques mécaniques

Aluminium und Aluminiumlegierungen - Gezogene Stangen  
und Rohre - Teil 2: Mechanische Eigenschaften

This European Standard was approved by CEN on 10 February 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 754-2:2008](https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>



EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

## Contents

Page

Foreword.....	3
<b>1 Scope .....</b>	<b>5</b>
<b>2 Normative references .....</b>	<b>5</b>
<b>3 Mechanical property limits .....</b>	<b>5</b>
<b>3.1 General.....</b>	<b>5</b>
<b>3.2 Elongation .....</b>	<b>5</b>
<b>3.3 Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys.....</b>	<b>6</b>
<b>3.4 Detailed tables of mechanical properties.....</b>	<b>7</b>
<b>Annex A (informative) List of tempers used in Tables 1 to 35.....</b>	<b>42</b>
<b>Bibliography .....</b>	<b>44</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 754-2:2008](https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e44b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e44b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>

## Foreword

This document (EN 754-2:2008) has been prepared by Technical Committee CEN/TC 132 "Aluminium and aluminium alloys", the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2008, and conflicting national standards shall be withdrawn at the latest by September 2008.

This document supersedes EN 754-2:1997.

Within its programme of work, Technical committee CEN/TC 132 entrusted CEN/TC 132/WG 5 "*Extruded and drawn products*" to revise EN 754-2:1997

The following technical modifications have been introduced during the revision:

- General: Typical Brinell hardness values are introduced in the tables for mechanical properties for information only  
The following new alloys are included; EN AW-5049, EN AW-6262A and EN AW-6065
- Subclause 3.1: Requirements for the use of condition F is described
- Subclause 3.2: A value should be used for elongation if not otherwise agreed, with exception of certain products
- Annex A: Informative Annex A added explaining temper designation used in all tables
- Former annexes A and B are deleted (content moved to Part 1)

EN 754 comprises the following parts under the general title "*Aluminium and aluminium alloys — Cold drawn rod/bar and tube*":

- *Part 1: Technical conditions for inspection and delivery*
- *Part 2: Mechanical properties*
- *Part 3: Round bars, tolerances on dimensions and form*
- *Part 4: Square bars, tolerances on dimensions and form*
- *Part 5: Rectangular bars, tolerances on dimensions and form*
- *Part 6: Hexagonal bars, tolerances on dimensions and form*
- *Part 7: Seamless tubes, tolerances on dimensions and form*
- *Part 8: Porthole tubes, tolerances on dimensions and form*

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

## EN 754-2:2008 (E)

CEN/TC 132 affirms it is its policy that in the case when a patentee refuses to grant licenses on standardized standards products under reasonable and not discriminatory conditions then this product shall be removed from the corresponding standard.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 754-2:2008

<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>

## 1 Scope

This document specifies the mechanical property limits resulting from tensile testing applicable to aluminium and aluminium alloy cold drawn rod/bar and tube.

Technical conditions for inspection and delivery, including product and testing requirements, are specified in EN 754-1. Temper designations are defined in EN 515. The chemical composition limits for these materials are given in EN 573-3.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references only the edition cited applies. For undated references the latest edition of the referenced document (including any amendments) applies.

EN 754-1:2008, *Aluminium and aluminium alloys — Cold drawn rod/bar and tube — Part 1: Technical conditions for inspection and delivery*

EN 10002-1, *Metallic materials — Tensile testing — Part 1: Method of test at ambient temperature*

## 3 Mechanical property limits

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

### 3.1 General

The mechanical properties shall be in conformity with those specified in Tables 1 to 35 or those agreed upon between supplier and purchaser and stated in the order document.

<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-11490-63005a-01754-2008>

For all alloys the condition F (as fabricated) can be used, but without guaranteed mechanical properties.

Tables 1 to 35 contain limits of mechanical property values obtained by tensile testing according to EN 10002-1 after sampling and test piece preparation according to EN 754-1.

NOTE The mechanical properties refer to test pieces taken in the longitudinal direction. Mechanical properties of test pieces taken in other directions can differ from those for the longitudinal direction quoted in this standard.

Brinell hardness values given in Tables 1 to 35 expressed as HBW values are for information only.

### 3.2 Elongation

If not otherwise agreed, the  $A$  value shall be used.

The  $A$  value for elongation is the % elongation measured over a gauge length of  $5,65\sqrt{S_0}$  (where  $S_0$  is the initial cross-sectional area of the test-piece), and expressed in percent.

For certain products the supplier may choose (if not otherwise specified in the order documents) to use the elongation based on  $A_{50\text{mm}}$ . Consequently values for the  $A_{50\text{mm}}$  are included in the following tables.

The  $A_{50\text{mm}}$  value is the elongation measured over a gauge length of 50 mm and expressed in percent.

Test pieces and their location in the specimen are given in EN 754-1.

3.3 Reference list of the tables of mechanical properties of the relevant aluminium and aluminium alloys

			Page
Table 1 :	Aluminium EN AW-1050A	[Al 99,5]	7
Table 2 :	Aluminium EN AW-1200	[Al 99,0]	8
Table 3 :	Alloy EN AW-2007	[Al Cu <sub>4</sub> PbMgMn]	9
Table 4 :	Alloy EN AW-2011	[Al Cu <sub>6</sub> BiPb]	10
Table 5 :	Alloy EN AW-2011A	[Al Cu <sub>6</sub> BiPb(A)]	11
Table 6 :	Alloy EN AW-2014	[Al Cu <sub>4</sub> SiMg]	12
Table 7 :	Alloy EN AW-2014A	[Al Cu <sub>4</sub> SiMg(A)]	13
Table 8 :	Alloy EN AW-2017A	[Al Cu <sub>4</sub> MgSi(A)]	14
Table 9 :	Alloy EN AW-2024	[Al Cu <sub>4</sub> Mg <sub>1</sub> ]	15
Table 10 :	Alloy EN AW-2030	[Al Cu <sub>4</sub> PbMg]	16
Table 11 :	Alloy EN AW-3003	[Al Mn <sub>1</sub> Cu]	17
Table 12 :	Alloy EN AW-3103	[Al Mn <sub>1</sub> ]	18
Table 13 :	Alloy EN AW-5005	[Al Mg <sub>1</sub> (B)]	19
Table 14 :	Alloy EN AW-5005A	[Al Mg <sub>1</sub> (C)]	20
Table 15 :	Alloy EN AW-5019	[Al Mg <sub>5</sub> ]	21
Table 16 :	Alloy EN AW-5049	[Al Mg <sub>2</sub> Mn <sub>0,8</sub> ]	22
Table 17 :	Alloy EN AW-5251	[Al Mg <sub>2</sub> Mn <sub>0,3</sub> ]	23
Table 18 :	Alloy EN AW-5052	[Al Mg <sub>2,5</sub> ]	24
Table 19 :	Alloy EN AW-5154A	[Al Mg <sub>3,5</sub> (A)]	25
Table 20 :	Alloy EN AW-5754	[Al Mg <sub>3</sub> ]	26
Table 21 :	Alloy EN AW-5083	[Al Mg <sub>4,5</sub> Mn <sub>0,7</sub> ]	27
Table 22 :	Alloy EN AW-5086	[Al Mg <sub>4</sub> ]	28
Table 23 :	Alloy EN AW-6012	[Al MgSiPb]	29
Table 24 :	Alloy EN AW-6060	[Al MgSi]	30
Table 25 :	Alloy EN AW-6061	[Al Mg <sub>1</sub> SiCu]	31
Table 26 :	Alloy EN AW-6262	[Al Mg <sub>1</sub> SiPb]	32
Table 27 :	Alloy EN AW-6262A	[Al Mg <sub>1</sub> SiSn]	33
Table 28 :	Alloy EN AW-6063	[Al Mg <sub>0,7</sub> Si]	34
Table 29 :	Alloy EN AW-6063A	[Al Mg <sub>0,7</sub> Si(A)]	35
Table 30 :	Alloy EN AW-6065	[Al Mg <sub>1</sub> Bi <sub>1</sub> Si]	36
Table 31 :	Alloy EN AW-6082	[Al Si <sub>1</sub> MgMn]	37
Table 32 :	Alloy EN AW-7020	[Al Zn <sub>4,5</sub> Mg <sub>1</sub> ]	38
Table 33 :	Alloy EN AW-7022	[Al Zn <sub>5</sub> Mg <sub>3</sub> Cu]	39
Table 34 :	Alloy EN AW-7049A	[Al Zn <sub>8</sub> MgCu]	40
Table 35 :	Alloy EN AW-7075	[Al Zn <sub>5,5</sub> MgCu]	41

ITC STANDARD REVIEW  
 (standards.iteh.ai)  
 SIST EN 754-2:2008  
<https://standards.iteh.ai/catalog/standards/sist/3c2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>



## 3.4 Detailed tables of mechanical properties

Table 1 — Aluminium EN AW-1050A [Al 99,5]

Drawn rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 80	≤ 60	60	95	-	-	25	22	20
H14	≤ 40	≤ 10	100	135	70	-	6	5	30
H16	≤ 15	≤ 5	120	160	105	-	4	3	35
H18	≤ 10	≤ 3	145	-	125	-	3	3	43
Drawn tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
O, H111	≤ 20	60	95	-	-	25	22	20	
H14	≤ 10	100	135	70	-	6	5	30	
H16	≤ 5	120	160	105	-	4	3	35	
H18	≤ 3	145	-	125	-	3	3	43	
<sup>a</sup> $D$ = Diameter for round bar <sup>b</sup> $S$ = Width across flats for square and hexagonal bar; thickness for rectangular bar									

Table 2 — Aluminium EN AW-1200 [Al 99,0]

Drawn rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
O, H111	≤ 80	≤ 60	70	105	-	-	20	16	23
H14	≤ 40	≤ 10	110	145	80	-	5	4	37
H16	≤ 15	≤ 5	135	170	115	-	3	3	45
H18	≤ 10	≤ 3	150	-	130	-	3	3	50
Drawn tube									
Temper	Wall thickness $t$ mm	$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value	
		min.	max.	min.	max.	min.	min.		
O, H111	≤ 20	70	105	-	-	20	16	23	
H14	≤ 10	110	145	80	-	5	4	37	
H16	≤ 5	135	170	115	-	3	3	45	
H18	≤ 3	150	-	130	-	3	3	50	

<sup>a</sup>  $D$  = Diameter for round bar  
<sup>b</sup>  $S$  = Width across flats for square and hexagonal bar, thickness for rectangular bar

[SIST EN 754-2:2008](https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008)  
<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>

Table 3 — Alloy EN AW-2007 [Al CuPbMgMn]

Drawn rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T3 <sup>c</sup>	$\leq 30$	$\leq 30$	370	-	240	-	7	5	95
	$30 < D \leq 80$	$30 < S \leq 80$	340	-	220	-	6	-	95
T351 <sup>c</sup>	$\leq 80$	$\leq 80$	370	-	240	-	5	3	95
Drawn tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T3 <sup>c</sup>	$\leq 20$		370	-	250	-	7	5	95
T3510 T3511 <sup>c</sup>	$\leq 20$		370	-	240	-	5	3	95
<sup>a</sup> $D$ = Diameter for round bar <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar <sup>c</sup> Properties may be obtained by press quenching									

(standards.iteh.ai)

SIST EN 754-2:2008

<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e44b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>

Table 4 — Alloy EN AW-2011 [Al Cu6BiPb]

Drawn rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T3	$\leq 40$	$\leq 40$	320	-	270	-	10	8	90
	$40 < D \leq 50$	$40 < S \leq 50$	300	-	250	-	10	-	90
	$50 < D \leq 80$	$50 < S \leq 80$	280	-	210	-	10	-	90
T8	$\leq 80$	$\leq 80$	370	-	270	-	8	6	115
Drawn tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T3 <sup>c</sup>	$\leq 5$		310	-	260	-	10	8	90
	$5 < t \leq 20$		290	-	240	-	8	6	90
T8	$\leq 20$		370	-	275	-	8	6	115
<sup>a</sup> $D$ = Diameter for round bar <sup>b</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar <sup>c</sup> Properties may be obtained by press quenching									

[SIST EN 754-2:2008](https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008)  
<https://standards.iteh.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>

Table 5 — Alloy EN AW-2011A [Al Cu6BiPb(A)]

Drawn rod/bar									
Temper	Dimensions mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
	$D^a$	$S^b$	min.	max.	min.	max.	min.	min.	
T3	$\leq 40$	$\leq 40$	320	-	270	-	10	8	90
	$40 < D \leq 50$	$40 < S \leq 50$	300	-	250	-	10	-	90
	$50 < D \leq 80$	$50 < S \leq 80$	280	-	210	-	10	-	90
T8	$\leq 80$	$\leq 80$	370	-	270	-	8	6	115
Drawn tube									
Temper	Wall thickness $t$ mm		$R_m$ MPa		$R_{p0,2}$ MPa		$A$ %	$A_{50\text{ mm}}$ %	$HBW$ Typical value
			min.	max.	min.	max.	min.	min.	
T3 <sup>c</sup>	$\leq 5$		310	-	260	-	10	8	90
	$5 < t \leq 20$		290	-	240	-	8	6	90
T8	$\leq 20$		370	-	275	-	8	6	115
<sup>a</sup> $D$ = Diameter for round bar <sup>c</sup> $S$ = Width across flats for square and hexagonal bar, thickness for rectangular bar <sup>c</sup> Properties may be obtained by press quenching									

SIST EN 754-2:2008

<https://standards.itech.ai/catalog/standards/sist/33e2d76b-e4b-4dcb-ba73-1a344587c33c/sist-en-754-2-2008>