

SLOVENSKI STANDARD
SIST EN 13491:2005/A1:2007
01-januar-2007

Geosintetične zapore - Zahtevane lastnosti pri uporabi za zaščito pred tekočinami pri gradnji predorov in pri podzemnih gradnjah

Geosynthetic barriers - Characteristics required for use as a fluid barrier in the construction of tunnels and underground structures

Geosynthetische Dichtungsbahnen - Eigenschaften, die für die Anwendung beim Bau von Tunneln und Tiefbauwerken erforderlich sind

Géomembranes, géosynthétiques bentonitiques - Caractéristiques requises pour l'utilisation comme barrière contre les liquides dans la construction des tunnels et des structures souterraines

<https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007>

Ta slovenski standard je istoveten z: EN 13491:2004/A1:2006

ICS:

59.080.70	Geotekstilije	Geotextiles
93.060	Gradnja predorov	Tunnel construction

SIST EN 13491:2005/A1:2007 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 13491:2005/A1:2007](https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007)

<https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 13491:2004/A1

August 2006

ICS 59.080.70; 91.100.50

English Version

Geosynthetic barriers - Characteristics required for use as a fluid barrier in the construction of tunnels and underground structures

Géomembranes, géosynthétiques bentonitiques -
Caractéristiques requises pour l'utilisation comme barrière
contre les liquides dans la construction des tunnels et des
structures souterraines

Geosynthetische Dichtungsbahnen - Eigenschaften, die für
die Anwendung beim Bau von Tunneln und Tiefbauwerken
erforderlich sind

This amendment A1 modifies the European Standard EN 13491:2004; it was approved by CEN on 12 July 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the Central Secretariat or to any CEN member.

This amendment exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the Central Secretariat has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 13491:2005/A1:2007](https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007)

<https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

EN 13491:2004/A1:2006 (E)

Foreword

This document (EN 13491:2004/A1:2006) has been prepared by Technical Committee CEN/TC 189 “Geosynthetics”, the secretariat of which is held by IBN.

This Amendment to the European Standard EN 13491:2004 shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2007, and conflicting national standards shall be withdrawn at the latest by February 2007.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of this document.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 13491:2005/A1:2007](https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007)

<https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dea-8447-d395ac959bb6/sist-en-13491-2005-a1-2007>

List of amendments

Clause	Par, sentence, table	Current text	Proposed modification
2			- Add "ISO 527-4, <i>Plastics - Determination of tensile properties - Part 4: Test conditions for isotropic and orthotropic fibre-reinforced plastic composites</i> " - <i>Date ISO 527-1</i> , "ISO 527-1:1993" - <i>Date EN 13493</i> , "EN 13493:2005"
4.3	Table 1, after row 4		<i>Add a row #5</i> : content: see below <i>Note</i> : all subsequent rows to be renumbered
	5	Gas permeability	S S S ASTM D 1434 ASTM D 1434 EN 13493:2005, Annex C See 4.4.8
4.3	Table 1, row 5 tensile strength, last column	For GBR-P use ISO 527, parts 1 and 3, test specimen type 5 at a speed of 100 mm/min and report the maximum strength according to the test method	For GBR-P use ISO 527 parts 1 and 3, test specimen type 5 at a speed of 100 mm/min. For reinforced GBR-P use ISO 527 parts 1 and 4, specimen type 2 with width 50 mm, at a speed of 5 mm per minute. Report in all cases the maximum strength measured according to the test method.
4.3	Table 1, Row 6, elongation, last column	For GBR-P use ISO 527 part 1 and 3, test specimen type 5 at a speed of 100 mm/min; calculation of elongation as defined in ISO 527-1, 10.2, using grip separation measurement..	For GBR-P use ISO 527 parts 1 and 3, test specimen type 5 at a speed of 100 mm/min. For reinforced GBR-P use ISO 527 parts 1 and 4, specimen type 2, width 50 mm, at a speed of 5 mm per minute. Elongation at maximum strength shall in all cases be calculated as defined in ISO 527-1:1993, 10.2, using grip separation measurement.
4.4	After 4.4.7		<i>Add a paragraph 4.4.8 Gas permeability</i> : Data on gas permeability are required when a health or safety risk from ground gas may occur or when it is environmentally induced. The decision to include this requirement should be taken by the design engineer.

EN 13491:2004/A1:2006 (E)

			NOTE At present there is no standardised test method for the determination of gas permeability of GBR-Cs. The test procedure described in EN 13493:2005, Annex C is currently experimental and can be used for information.
Annex B.1	1 st par., 5 th indent	EN 13493 Geosynthetic barriers - Characteristics required for use in the construction of solid waste storage and disposal sites and storages for hazardous solid materials.	EN 13493, <i>Geosynthetic barriers - Characteristics required for use in the construction of solid waste storage and disposal sites</i>
B.3.2	Beginning of clause		<u>add sentence</u> : Specimens for testing shall be cut from the exposed sample after the exposure period.
B.3.2	first indent	"with one day"	"within three days"
B.3.2	Table B.1, 2 nd row, 1 st column	one day	three days
B.3.2	Table B.1: 4 th row		<u>remove row</u> (25 years)
B.3.2	After table		<u>Add sentence</u> "In the case of exposures on site of more than one year, the manufacturer shall provide a statement of the duration of resistance to weathering together with a technical justification."
B.6	1 st par., 1 st sentence	All GBR-P installed in the applications listed in B.1 above shall be tested for their resistance to stress cracking in accordance with ASTM D 5397-99 (Appendix).	All polymeric materials, including the polymeric membrane element of GBR-Cs, shall be tested. Specimens will be taken in the weakest direction according to the measured tensile yield strength. Normally this will be the cross machine direction i.e. the direction of the notch will be aligned with the machine direction. The test report shall state whether any failure to achieve 200 h is due to elongation without break and such failure shall be disregarded. In the case of GBR-Ps with textured surfaces the test shall be performed on a sample of the same material with smooth surfaces. Such sample shall be taken from one of the following sources: a) smooth surface GBR-P at the pre-textured stage of manufacture (if

<https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dca-8447-df5ca159bb/sist-en-13491-2005-a1-2007>
 ITeh STANDARD PREVIEW

			applicable); b) on a sample taken from any smooth surface welding selvedge provided at the edge of the roll.
B.7	2 nd par., 3 rd indent	the loss in mass of the sample shall not be greater than 25 per cent	the loss in mass of the sample shall not be greater than 5 per cent under Methods A and B, and 25 per cent under Method C. Method C is only required for applications covered by EN 13492 and EN 13493.
B.8	1 st par.	All geosynthetic barriers installed in the applications listed in B.1 shall be tested for their resistance to oxidation according to prEN 14575 and to B.2. The conditions of exposure shall be 85 °C and 90 days. The retained tensile properties shall comply with the criteria stated in B.2.	All geosynthetic barriers (EN ISO 13438 shall be applicable for the geotextile elements and reinforcement yarns of GBR-C barriers) installed in the applications listed in B.1 shall be tested for their resistance to oxidation according to EN 14575 and to B.2. The conditions of exposure shall be 85 °C and 90 days. The retained tensile properties shall comply with the criteria stated in B.2.

<https://standards.iteh.ai/catalog/standards/sist/6bb9d6a4-07b9-4dca-8447-d395ac959bb6/sist-en-13491-2005-a1-2007>

ITEH STANDARD PREVIEW
(standards.iteh.ai)