

### SLOVENSKI STANDARD SIST EN 1993-1-12:2007

01-junij-2007

Evrokod 3: Projektiranje jeklenih konstrukcij - 1-12. del: Dodatna pravila za razširitev uporabe EN 1993 za jekla do trdnosti S 700.

Eurocode 3 - Design of steel structures - Part 1-12: Additional rules for the extension of EN 1993 up to steel grades S 700

Eurocode 3: Bemessung und Konstruktion von Stahlbauten - Teil 1-12: Zusätzliche Regeln zur Erweiterung von EN 1993 auf Stahlsorten bis \$ 700.

Eurocode 3 - Calcul des structures en acier - Partie 1-12 : Regles additionnelles pour l'utilisation de l'EN 1993 jusqu'a la nuance d'acier \$ 700

https://standards.iteh.ai/catalog/standards/sist/da98a235-5460-47c7-833a-

Ta slovenski standard je istoveten z: EN 1993-1-12:2007

#### ICS:

91.010.30 V^@ ã } ãs ãs ãs Technical aspects
91.080.10 Kovinske konstrukcije Metal structures

SIST EN 1993-1-12:2007 en;de

# iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST EN 1993-1-12:2007</u> https://standards.iteh.ai/catalog/standards/sist/da98a235-5460-47c7-833a-45f899bab7af/sist-en-1993-1-12-2007

### EUROPEAN STANDARD NORME EUROPÉENNE

**EUROPÄISCHE NORM** 

EN 1993-1-12

February 2007

ICS 91.010.30: 91.080.10

#### **English Version**

## Eurocode 3 - Design of steel structures - Part 1-12: Additional rules for the extension of EN 1993 up to steel grades S 700

Eurocode 3 - Calcul des structures en acier - Partie 1-12 : Règles additionnelles pour l'utilisation de l'EN 1993 jusqu'à la nuance d'acier S 700 Eurocode 3: Bemessung und Konstruktion von Stahlbauten
- Teil 1-12: Zusätzliche Regeln zur Erweiterung von EN
1993 auf Stahlsorten bis S 700

This European Standard was approved by CEN on 6 July 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

https://standards.iteh.ai/catalog/standards/sist/da98a235-5460-47c7-833a-45f899bab7af/sist-en-1993-1-12-2007



EUROPEAN COMMITTEE FOR STANDARDIZATION COMITÉ EUROPÉEN DE NORMALISATION EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

#### EN 1993-1-12:2007 (E)

Con	tents	Page	
Foreword			
1	Gene	eral	3
	1.1	Scope	
	1.2	Normative references	4
	1.3	Symbols	4
2	Additional rules to EN 1993-1-1 to EN 1993-1-11		
	2.1	Additional rules to EN 1993-1-1	5
	2.2	Additional rules to EN 1993-1-2	6
	2.3	Additional rules to EN 1993-1-3	6
	2.4	Additional rules to EN 1993-1-4	6
	2.5	Additional rules to EN 1993-1-5	7
	2.6	Additional rules to EN 1993-1-6	7
	2.7	Additional rules to EN 1993-1-7	7
	2.8	Additional rules to EN 1993-1-8	7
	2.9	Additional rules to EN 1993-1-9	8
	2.10	Additional rules to EN 1993-1-10	8
	2.11	Additional rules to EN 1993-1-11	
3	Addi	tional rules to application parts EN 1993-2 to EN 1993-6	9

# iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 1993-1-12:2007 https://standards.iteh.ai/catalog/standards/sist/da98a235-5460-47c7-833a-45f899bab7af/sist-en-1993-1-12-2007

#### **Foreword**

This European Standard EN 1993-1-12, "Eurocode 3: Design of steel structures: Part 1-12: Additional rules for the extension of EN 1993 up to steel grades S 700", has been prepared by Technical Committee CEN/TC250 « Structural Eurocodes », the Secretariat of which is held by BSI. CEN/TC250 is responsible for all Structural Eurocodes.

This European Standard shall be given the status of a National Standard, either by publication of an identical text or by endorsement, at the latest by August 2007, and conflicting National Standards shall be withdrawn at latest by March 2010.

According to the CEN-CENELEC Internal Regulations, the National Standard Organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

#### National annex for EN 1993-1-12

This standard gives alternative procedures, values and recommendations with notes indicating where national choices may have to be made. Therefore the National Standard implementing EN 1993-1-12 should have a National annex containing all Nationally Determined Parameters to be used for the design of steel structures to be constructed in the relevant country.

National choice is allowed in EN 1993-1-12:2007

```
https://standards.iteh.ai/catalog/standards/sist/da98a235-5460-47c7-833a-45f899bab7af/sist-en-1993-1-12-2007
```

- **2.1** (3.1(2))
- **2.1** (3.2.2(1))
- **2.1** (5.4.3(1))
- **2.1** (6.2.3(2))
- **2.8** (4.2(2))
- **3**(1)

#### 1 General

#### 1.1 Scope

- (1) This EN 1993-1-12 gives rules that can be used in conjunction with parts
- EN1993-1-1
- EN 1993-1-2
- EN 1993-1-3
- EN 1993-1-4
- EN 1993-1-5
- EN 1993-1-6
- EN 1993-1-7
- EN 1993-1-8

#### EN 1993-1-12:2007 (E)

- EN 1993-1-9
- EN 1993-1-10
- EN 1993-1-11
- EN 1993-2
- EN 1993-3-1
- EN 1993-3-2
- EN 1993-4-1
- EN 1993-4-2
- EN 1993-4-3
- EN 1993-5
- EN 1993-6

to enable steel structures to be designed with steel of grades greater than S460 up to S700.

(2) Where it is necessary to alter a rule in other parts to enable up to S700 to be used, it is stated what needs to be done, either by noting that a rule is not to be used with steel grades greater than S460, then giving the one that is required, or by giving an additional rule or rules.

#### 1.2 Normative references

#### iTeh STANDARD PREVIEW

(1) This European Standard incorporates, by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies.

45f899bab7af/sist-en-1993-1-12-2007

EN 499 Welding consumables – Covered electrodes for manual metal arc welding of non alloy and fine grain steels – Classification

EN 10025-6 Hot rolled products of structural steels - Part 6: Technical delivery conditions for flat products of high yield strength structural steels in the quenched and tempered condition

EN 10149-1 Hot-rolled flat products made of high yield strength steels for cold forming – Part 1: General delivery conditions

EN 10149-2 Hot-rolled flat products made of high yield strength steels for cold forming – Part 2: Delivery conditions for thermomechanically rolled steels

EN 12534 Welding consumables – Wire electrodes, wires, rods and deposits for gas shielded metal arc welding of high strength steels – Classification

EN 12535 Welding consumables – Tubular cored electrodes for gas shielded metal arc welding of high strength steels – Classification

#### 1.3 Symbols

(1) Symbols used in this standard are defined in the standards referred to.

#### 2 Additional rules to EN 1993-1-1 to EN 1993-1-11

#### 2.1 Additional rules to EN 1993-1-1

#### **3.1**(2) Additional note:

**NOTE** The National Annex may specify steel grades greater than S460 up to S700 for general use or for use in specific applications. The grades in Tables 1 and 2 and the nominal values that may be used for their yield strengths and ultimate strength are recommended for use, provided that the rules in this Part 1.12 are followed.

Table 1 — Nominal values of yield strength  $f_y$  and ultimate tensile strength  $f_u$  for hot rolled structural steel

EN10025-6	Nominal thickness of the element t mm					
Steel grade and	<i>t</i> ≤50 mm		50 mm< <i>t</i> ≤100 mm		100 mm< <i>t</i> ≤150 mm	
qualities	$f_{\rm v} [{\rm N/mm}^2]$	$f_{\rm u} [{\rm N/mm}^2]$	$f_{\rm v} [{\rm N/mm}^2]$	$f_{\rm u} [{\rm N/mm}^2]$	$f_{\rm v} [{\rm N/mm}^2]$	$f_{\rm u} [{\rm N/mm}^2]$
S 500Q/QL/QL1	500	590	480	590	440	540
S 550Q/QL/QL1	550	640	530	640	490	590
S 620Q/QL/QL1	620	700	580	700	560	650
S 690Q/QL/QL1	690	770	650	760	630	710

Table 2 — Nominal values of yield strength  $f_{\rm y}$  and ultimate tensile strength  $f_{\rm u}$  for hot rolled iTeh STANIat products PREVIEW

THE STITLE STREET							
EN 10149-2 <sup>a</sup> )	1,5 mm ≤ <i>t</i>	$nm \le t \le 8 \text{ mm} \qquad 8 \text{ mm} < t \le 16$					
	$f_{ m y}$	$f_{ m u}$	$f_{y}$	$f_{\mathrm{u}}$			
	$[N/mm^2]$	$[N/mm^2]$	$_{7}[N/mm^{2}]$	$[N/mm^2]$			
S 500MC	500 stand	137ds 550 13rds 551/ds 98	233500	550			
S 550MC 4	5f8991550 af/sist	en_ 600 <sub>-1-1</sub>	2-20550	600			
S 600MC	600	650	600	650			
S 650MC	650	700	630	700			
S 700MC	700	750	680	750			
- \							

a) Verification of the impact energy in accordance with EN 10149-1 Clause 11, Option 5 should be specified.

#### **3.2.2**(1) Additional note:

**NOTE** The limiting values of the ratio  $f_u/f_y$ , the elongation at failure and the ultimate strain  $\varepsilon_u$  for steels greater than S460 up to S700 may be defined in the National Annex. The following values are recommended:

- $f_u/f_v \ge 1,05$ ;
- elongation at failure not less than 10 %;
- $\varepsilon_{\rm u} \geq 15 f_{\rm v}/E$ .

#### **3.2.2**(2) Additional notes:

**NOTE 1** Steels with grades greater than S460 up to S700 conforming to one of the steel grades listed in Tables 1 and 2 should be accepted as satisfying these requirements.

**NOTE 2** The ability of a steel structure to absorb deformation is related to both the elongation and the toughness properties of its constituent steel products. The global performance required depends on the anticipated deformations. The local performance required depends on the details used. Due to higher stress levels, structures of steels according to Tables 1 and 2 require special care in both the control of deformations

#### EN 1993-1-12:2007 (E)

and in detailing to avoid notches and other stress concentrations. The global analysis should consider imposed deformations where relevant.

#### **5.4.1** (3) Additional rule:

Not applicable to steels with grades greater than S460 up to S700.

#### **5.4.1** (4)B Additional rule:

Not applicable to steels with grades greater than S460 up to S700.

#### **5.4.3**(1) Additional rule:

For steels of grades greater than S460 up to S700, the global analysis using non-linear plastic analysis considering partial plastification of members in plastic zones only, applies.

**NOTE**: The National Annex may specify additional rules for steels according to Tables 1 and 2. Rules for design with FEM are given in Informative Annex C of EN 1993-1-5.

#### **6.2.3**(2) Additional rule:

For steels with grades greater than S460 up to S700 the design resistance of a net section should be taken as

$$N_{t,Rd} = \frac{0.9A_{net}f_u}{\gamma_{M12}}$$
 (standards.iteh.ai) (6.7a)

where  $\chi_{M12}$  is the partial factor for section-resistance for steels with grades greater than S460 up to \$700:h.ai/catalog/standards/sist/da98a235-5460-47c7-833a-45f899bab7af/sist-en-1993-1-12-2007

**NOTE**: The National Annex may specify the value of  $\chi_{112}$ . The value  $\chi_{112} = \chi_{112} = 1,25$  is recommended.

#### **6.2.3**(3) Additional rules:

Steels with grades greater than S460 up to S700 should not be used for applications where capacity design is required.

#### **Table 6.2** Additional rule:

The rules for S 460 also apply for steels with grades greater than S460 up to S700.

#### 2.2 Additional rules to EN 1993-1-2

The standard is applicable to steels with grades greater than S460 up to S700 without further additional rules

#### 2.3 Additional rules to EN 1993-1-3

The standard is applicable to steels with grades greater than S460 up to S700 without further additional rules

#### 2.4 Additional rules to EN 1993-1-4

EN 1993-1-4 is not applicable.

#### 2.5 Additional rules to EN 1993-1-5

The standard is applicable to steels with grades greater than S460 up to S700 without further additional rules.

#### 2.6 Additional rules to EN 1993-1-6

Annex B is not applicable to steels with grades greater than S460 up to S700.

#### 2.7 Additional rules to EN 1993-1-7

The standard is applicable to steels with grades greater than S460 up to S700 without further additional rules.

#### 2.8 Additional rules to EN 1993-1-8

#### **1.1**(1) Additional rules:

EN 1993-1-8 may be applied also to steels with grades greater than S460 up to S700 if the following additional rules are applied.

- **3.6.1**(1) For steels with grades greater than S460 up to S700 and bolts loaded in shear in oversize and slotted holes should only be used for category C connections.
- **3.10.3**(2) Not applicable to steels with grades greater than S460 up to S700.
- **3.10.4** Not applicable to steels with grades greater than \$460 up to \$700.
- **3.12**(2) This clause also applies to connections in steels with grades greater than \$460 up to \$700.

45f899bab7af/sist-en-1993-1-12-2007

**4.2**(2) Additional rule:

For steels with grades greater than S460 up to S700 the filler metal may have lower strength than the base material.

**NOTE** The National Annex may give restrictions for the use of such undermatched electrodes.

#### **4.5.3.2**(6) Additional rule:

For under matched electrodes that are used for steels with grades greater than S460 up to S700 *f*u should be substituted with the ultimate strength of the filler metal *f*eu according to Table 3 for electrodes according to EN 499, EN 12534 and EN 12535. βw should be taken as 1,0.

Table 3 — Ultimate strength  $f_{eu}$  of electrodes

Strength class	35	42	55	62	69
Ultimate strength feu N/mm <sup>2</sup>	440	500	640	700	770

#### **4.7.1**(1) Additional rule:

The resistance of welded connections with undermatched electrodes with steel grades greater than S460 up to S700 should be based on the strength of the filler metal.