



SLOVENSKI STANDARD
SIST ISO 12742:2001
01-junij-2001

Koncentrati sulfidov bakra, svinca in cinka - Ugotavljanje meja prenosljive vlage - Metoda Flow table

Copper, lead and zinc sulfide concentrates -- Determination of transportable moisture limits -- Flow table method

iTeh STANDARD PREVIEW

Concentrés sulfurés de cuivre, de plomb et de zinc -- Détermination des limites d'humidité transportable -- Méthode de la table d'écoulement

[SIST ISO 12742:2001](https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-1b9ac66ca852/sist-iso-12742-2001)

Ta slovenski standard je istoveten z: ISO 12742:2000

ICS:

73.060.99 Druge rude Other metalliferous minerals

SIST ISO 12742:2001 **en**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 12742:2001

<https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001>

INTERNATIONAL
STANDARD

ISO
12742

First edition
2000-03-15

**Copper, lead and zinc sulfide
concentrates — Determination of
transportable moisture limits —
Flow table method**

*Concentrés sulfurés de cuivre, de plomb et de zinc — Détermination des
limites d'humidité transportable — Méthode de la table d'écoulement*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 12742:2001

<https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001>



Reference number
ISO 12742:2000(E)

© ISO 2000

ISO 12742:2000(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 12742:2001](https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001)

<https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 734 10 79
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 12742 was prepared by Technical Committee ISO/TC 183, *Copper, lead and zinc ores and concentrates*.

Annex A forms a normative part of this International Standard.

ITEH STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 12742:2001](https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001)

<https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 12742:2001

<https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001>

Copper, lead and zinc sulfide concentrates — Determination of transportable moisture limits — Flow table method

WARNING — This International Standard may involve hazardous materials, operations and equipment. It is the responsibility of the user of this International Standard to establish appropriate health and safety practices and determine the applicability of regulatory limitations prior to use.

1 Scope

This International Standard specifies a flow table method for the determination of the transportable moisture limit (TML) of copper, lead and zinc concentrates which may liquefy during transport.

This International Standard is applicable to the determination of the TML of concentrates containing 10 % (m/m) to 80 % (m/m) of lead, or 10 % (m/m) to 65 % (m/m) of zinc, or 10 % (m/m) to 55 % (m/m) of copper. It is applicable to TMLs in the range 3 % (m/m) to 28 % (m/m).

2 Normative references

[SIST ISO 12742:2001](https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-f9ac60ca852/sist-iso-12742-2001)

[https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-](https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-f9ac60ca852/sist-iso-12742-2001)

[f9ac60ca852/sist-iso-12742-2001](https://standards.iteh.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-f9ac60ca852/sist-iso-12742-2001)

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 10251:1997, *Copper, lead and zinc sulfide concentrates — Determination of mass loss in bulk material on drying.*

ISO 12743:1998, *Copper, lead and zinc sulfide concentrates — Sampling procedures for determination of metal and moisture content.*

3 Principle

Adjustment of the moisture content of the sample by mixing with water. Conversion of the mixture to a conical shape using a mould and tamper. Placement of the sample on the flow table and removal of the mould. Determination of the flow characteristic by repeated dropping of the flow table while observing the behaviour of the sample. When sufficient water has been added to the sample so that plastic deformation occurs during the dropping of the flow table, the sample is considered to be at its flow moisture point.

Calculation of the TML as 90 % of the flow moisture point.

ISO 12742:2000(E)

4 Apparatus

NOTE Copper, lead and zinc concentrates may gain or lose moisture rapidly when exposed to air. The laboratory should be designed so that excessive temperatures, air currents and humidity variations are avoided.

4.1 Flow table and frame, as specified in annex A.

The flow table mounting shall be as specified in Figure A.1.

4.2 Mould, as specified in Figure A.1.

4.3 Tamper.

The required tamping pressure may be achieved by using calibrated, spring-loaded tampers or some other suitable design of tamper that allows a controlled pressure to be applied via a 30 mm diameter tamper head as specified in Figure A.2.

4.4 Balance, top loading, having the sensitivity specified in Table 1.

Table 1 — Sensitivity of balance and precision of weighing

Mass of sample plus tray g	Precision of balance and weighing g
100	0,01
200	0,02
300	0,03
400	0,04
500	0,05

4.5 Measuring cylinder, 100 ml to 200 ml capacity.

4.6 Burette, 10 ml capacity.

4.7 Water applicator, for adding a fine spray of water to the sample, having a capacity greater than 200 ml and 5 ml calibration divisions.

4.8 Mixing bowl, hemispherical of 30 cm diameter.

4.9 Rubber gloves.

4.10 Drying trays or pans, having dimensions that permit the sample to be spread to a thickness of less than 30 mm.

The trays shall be made of corrosion-resistant and heat-resistant material such as stainless steel, glass or enamel plate.

4.11 Drying oven, ventilated, with forced circulation of air or inert gas, regulated at a temperature of $105\text{ °C} \pm 5\text{ °C}$.

5 Sampling

5.1 General

TML figures are required to be updated on a periodic basis, usually six monthly or when there is a known change to the process used to produce the material. The reported figure should be the mean of samples taken during the period.

To ensure that the TML result is representative, increments of the material shall be taken either

- a) while a stockpile is being built up or broken down or
- b) while loading or discharging a vessel.

These increments are combined to form the sample used to determine TML.

NOTE 1 The sample used to determine TML should not be used to determine moisture.

NOTE 2 Stationary sampling of stockpiles should never be used for the determination of TML. This method of sampling can only be used to provide an indicative moisture value for use during the planning of shipping schedules.

5.2 Laboratory sample

Samples for the determination of TML shall be taken in accordance with ISO 12743. The laboratory sample shall not weigh less than 5 kg. To minimize changes to the flow characteristics of the sample it shall not be oven dried or ground during its preparation.

5.3 Separation of test sample into test portions

Place the laboratory sample in the mixing bowl (4.8) and gently mix it thoroughly. Remove four test portions (A, B, C and D) from the mixing bowl as follows:

- a) Test portion A

Take approximately 1,2 kg of sample which is to be used for determining the moisture content of the sample "as received". This test is performed in accordance with ISO 10251. With routine samples, the result of this test provides the operator with a guide as to how much water to add to the samples, thereby speeding up the TML test.

- b) Test portion B

Take approximately 1,2 kg of sample. This sample is to be used for the preliminary TML test. Store this sample in an appropriately labelled airtight container.

- c) Test portion C

Take approximately 1,2 kg of sample. This sample is to be used for the first duplicate of the final TML test. Store this sample in an appropriately labelled airtight container.

- d) Test portion D

Take approximately 1,2 kg of sample. This sample is to be used for the second duplicate of the final TML test. Store this sample in an appropriately labelled airtight container.

ISO 12742:2000(E)

6 Procedure

6.1 General

Copper, lead and zinc concentrates may undergo rapid changes in moisture when exposed to air, so all stages of the test should be accomplished in the shortest time period and shall definitely be completed within the day of commencement. Where possible, sample containers should be covered with plastic film or any other suitable airtight cover.

As more accurate results are obtained when the moisture of the test portion is close to the flow moisture point, a preliminary test shall be carried out. The result of this test is used to adjust the moisture of the final test portion to 1 % to 2 % below the flow moisture point.

6.2 Preparation of test portions

6.2.1 General

Test portions B, C and D are prepared, with test portion B prepared first to determine the preliminary flow moisture point in accordance with 6.2.2 to 6.3.5.

Once the preliminary flow moisture point has been determined, test portions C and D are then prepared and the main flow moisture point determined in accordance with 6.4.2 to 6.4.6.

6.2.2 Filling the mould

Place the mould on the centre of the flow table and fill it in three stages with the test portion as follows:

- a) the first charge, after tamping, shall aim to fill the mould to approximately one third of its depth;
- b) the second charge, after tamping, shall fill the mould to about two thirds of its depth;
- c) the third and final charge, after tamping, shall reach to just below the top of the mould (see Figure 1).

The quantity of test portion required to achieve each of these stages will vary from one material to another, but is readily established after experience has been gained on the packing characteristics of the material being tested.

6.2.3 Tamping pressure

The aim of tamping is to simulate the amount of compaction prevailing at the bottom of a shipboard cargo for the material being tested. The correct pressure to be applied via the tamper is calculated as follows:

$$p_T = \rho_D \times d_{\max} \times g \quad (1)$$

where

- p_T is the tamping pressure, in pascals;
- ρ_D is the bulk density, in kilograms per cubic metre;
- d_{\max} is the maximum depth of the cargo, in metres;
- g is the acceleration due to gravity (= 981 cm/s²).

If, when calculating the tamping pressure, there is no information available concerning the cargo depth use the maximum likely depth.

Alternatively, the pressure may be estimated from Table 2.

Table 2 — Tamping pressures for selected concentrates ^a

Typical concentrate type	Bulk density kg/m ³	Maximum cargo depth			
		2 m	5 m	10 m	20 m
Copper	2000	39 [2,8]	98 [6,9]	196 [13,9]	392 [27,7]
Lead	2100	41 [2,9]	103 [7,3]	206 [14,6]	412 [29,1]
Zinc	1950	38 [2,7]	96 [6,8]	192 [13,5]	384 [27,1]

^a Values in brackets are equivalent kgf when applied via a 30 mm diameter tamper head.

6.2.4 Tamping procedure

The number of tamping actions (applying the correct, steady pressure each time) should be about 35 for the bottom layer, 25 for the middle layer and 20 for the top layer. Tamping shall be performed successively over the complete area including the edges of the sample, to form a uniform surface for each layer (see Figure 1).

6.2.5 Removal of the mould

Tap the mould on its side until it becomes loose, leaving the material in the shape of a truncated cone on the flow table.

iTech STANDARD PREVIEW
(standards.itech.ai)

6.3 Determination of flow moisture point

SIST ISO 12742:2001

<https://standards.itech.ai/catalog/standards/sist/a0cb5cdd-e9e1-4693-b2e6-ff9ac60ea852/sist-iso-12742-2001>

6.3.1 General

The determination of the flow moisture point is carried out by controlled dropping of the flow table and observation of the sample, followed by addition of water if necessary as outlined in the following steps.

6.3.2 Dropping the flow table

Immediately after removing the mould, raise and drop the flow table up to 50 times through a height of 12,5 mm at a rate of 25 times/min. Whilst the flow table is going through these cycles, observe the behaviour of the material using the information provided in 6.3.3 as a guide for determining the flow state.

6.3.3 Identification of the flow state

The impacting action of the flow table causes the grains of the material to re-arrange themselves to produce compaction of the mass. As a result, the fixed volume of moisture contained in the material at any given level increases as a percentage of the total volume. A flow state is considered to have been reached when the moisture content and compaction of the material produce such a level of saturation that plastic deformation occurs. At this stage, the moulded sides of the cone may deform, giving a convex or concave profile (see Figure 2). With repeated action of the flow table, the cone continues to slump and to flow outwards. In certain materials, cracks may also develop on the top surface.