
Textiles — Test for colour fastness —

Part B01:

Colour fastness to light: Daylight

AMENDMENT 1

iTeh STANDARD PREVIEW

Textiles — Essais de solidité des teintures —

(Partie B01: Solidité des teintures à la lumière: Lumière du jour

Amendement 1

[ISO 105-B01:1994/Amd.1:1998](https://standards.iso.org/iso/105-b01:1994/Amd.1:1998)

<https://standards.iteh.ai/catalog/standards/sist/328ada13-83cc-4dfd-bdf7-99698b935d3a/iso-105-b01-1994-amd-1-1998>



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Amendment 1 to ISO 105-B01:1994 was prepared by Technical Committee ISO/TC 38, *Textiles*, Subcommittee SC 1, *Tests for coloured textiles and colorants*.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/328ada13-83cc-4dfd-bdf7-99698b935d3a/iso-105-b01-1994-amd-1-1998>

© ISO 1998

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Textiles — Tests for colour fastness —

Part B01:

Colour fastness to light: Daylight

AMENDMENT 1

Page 1, 4.1

4.1 Reference materials

After first sentence insert:

The relationship between references 1 to 8 and L2 to L9 as shown with the method are approximate. Results from testing which use reference standards from both sources should be compared only with the knowledge that fading characteristics may differ.

4.1.2

Insert the following at end of first paragraph of 4.1.2:

Data in annex B are presented to illustrate the relationship of each of the blue wool references on exposure to fixed amounts of radiant energy. A detailed summary of these test results is found in document reference number ISO/TC 38/SC 1/N 993.

Page 3, 4.2.1

4.2.1 Exposure rack

Delete “5,0 mm to 10,0 mm” in line 3 on page 3 and replace by “(3,5 ± 1) mm”.

Page 4

Delete 6.1.2 to 6.1.3 and replace by:

6.1.2 Arrange the specimen to be tested and the references as shown in figure 2 with an opaque cover AB across the middle one-third of the specimen and references. Expose to daylight under the conditions described in 4.2.1. Follow the effect of light by removing the cover AB and inspecting the specimen frequently until the contrast between the exposed and the unexposed portions of the specimen is equal to grey scale grade 4. Cover a second one-third of the specimen and references with an additional opaque cover (CD in figure 2). At this stage attention shall be given to the possibility of photochromism (see ISO 105-B05).

6.1.4 Renumber as 6.1.3.

6.1.5 Renumber as 6.1.4.

Delete 6.2.2 to 6.2.4 and replace by:

6.2.2 Arrange the specimens to be tested and the references as shown in figure 3, with covers A'B' and AB each covering one-fifth of the total length of each specimen and reference. Expose to daylight under the conditions described in 4.2.1. Follow the effect of light by lifting cover AB periodically and inspecting the references. When a change in reference 2 can be perceived equal to grey scale grade 3 and in L2 to grade 4 inspect the specimens and rate their colour fastness by comparing any change that has occurred with the changes that have occurred in references 1, 2 and 3 or L2. (This is a preliminary assessment of colour fastness). At this stage attention shall be given to the possibility of photochromism (see ISO 105-B05).

6.2.3 Replace the cover AB in exactly the same position and continue to expose until a change in reference 3 or L3 can be perceived equal to grey scale grade 4; at this point fix an additional cover CD in the position shown in figure 3, overlapping the cover AB.

6.2.4 Continue to expose until a change in colour in reference 4 or L4 can be perceived equal to grey scale grade 4; then fix the final cover EF in the position shown in figure 3, the other covers remaining in position.

Page 6, 7.5

Delete the test of 7.5 and replace by:

7.5 If the colour fastness is equal to or higher than 4 or L3, any preliminary assessment (see 6.2.2) becomes significant. If this preliminary assessment is 3 or L2, it shall be included in the rating in parentheses. For example, a rating of 6(3) indicates that the specimen changes very slightly in the test when reference 3 just begins to fade, but that on continuing exposure the resistance to light is equal to that of reference 6.

[ISO 105-B01:1994/Amd 1:1998
https://standards.iteh.ai/catalog/standards/sist/328ada13-83cc-4dfd-bdf7-99698b935d3a/iso-105-b01-1994-amd-1-1998](https://standards.iteh.ai/catalog/standards/sist/328ada13-83cc-4dfd-bdf7-99698b935d3a/iso-105-b01-1994-amd-1-1998)

Annex B

(informative)

Light exposure equivalents for blue wool lightfastness references L2 to L9 ¹⁾

Blue wool reference	Xenon only kJ/m ² /nm @ 420 nm	Xenon only kJ/m ² 300 - 400 nm
L2	21	864
L3	43	1 728
L4	85 ²⁾	3 456
L5	170	6 912
L6	340 ²⁾	13 824
L7	680	27 648
L8	1 360	55 296
L9	2 720	110 592

1) For colour change of Step 4 on the grey scale for colour change.
2) Verified by experiment. All other values are calculated

iTeh STANDARD PREVIEW
(standards.iteh.ai)

Annex B

Bibliography is now to be re-lettered Annex C

<https://standards.iteh.ai/catalog/standards/sist/328ada13-83cc-4dfd-bdf7-99698b935d3a/iso-105-b01-1994-amd-1-1998>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 105-B01:1994/Amd 1:1998
<https://standards.iteh.ai/catalog/standards/sist/328ada13-83cc-4dfd-bdf7-99698b935d3a/iso-105-b01-1994-amd-1-1998>

ICS 59.080.01

Descriptors: textiles, dyes, tests, environmental tests, daylight tests, colour-fastness tests, determination, colour fastness.

Price based on 3 pages
