

Designation: D 4356 - 84 (Reapproved 2002)

Standard Practice for Establishing Consistent Test Method Tolerances¹

This standard is issued under the fixed designation D 4356; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This practice should be used in the development of any test method in which the determination value is calculated from measurement values by means of an equation. The practice is not applicable to such determination values as those calculated from counts of nonconformities, ratios of successes to failures, gradings, or ratings.

1.2 The purpose of this practice is to provide guidance in the specifying of realistic and consistent tolerances for making measurements and for reporting the results of testing.

1.3 This practice can be used as a guide for obtaining the minimum test result tolerance that should be specified with a particular set of specified measurement tolerances, the maximum permissible measurement tolerances which should be specified to achieve a specified test result tolerance, and more consistent specified measurement tolerances.

1.4 These measurement and test result tolerances are not statistically determined tolerances that are obtained by using the test method but are the tolerances specified in the test method.

1.5 In the process of selecting test method tolerances, the task group developing or revising a test method must evaluate not only the consistency of the selected tolerances but also the technical and economical feasibility of the measurement tolerances and the suitability of the test result tolerance for the purposes for which the test method will be used. This practice provides guidance only for establishing the consistency of the test method tolerances.

1.6 This practice is presented in the following sections:

	Number
Scope	1
Referenced Documents	2
TERMINOLOGY	
Definitions	3
Discussion of Terms	4
Expressing Test Method Tolerances	5
Tolerance Symbols	6
SUMMARY AND USES	
Summary of Practice	7
Uses and Significance	8
MATHEMATICAL RELATIONSHIPS	

¹ This practice is under the jurisdiction of ASTM Committee E11 on Quality and Statistics and is the direct responsibility of Subcommittee E11.20 on Test Method Evaluation and Quality Control.

Current edition approved March 30, 1984. Published August 1984.

Propagation Equations	9
Tolerance Terms	10
Determination Tolerances	11
Consistency Criteria	12
APPLICATION OF PRINCIPLES	
Procedure	13
Mass per Unit Area Example	14
ANNEXES	
General Propagation Equation	Annex A1
Specific Propagation Equations	Annex A2

1.7 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

2. Referenced Documents

- 2.1 ASTM Standards:
- D 123 Terminology Relating to Textiles²
- D 2905 Practice for Statements on Number of Specimens for Textiles²
- E 29 Practice for Using Significant Digits in Test Data to Determine Conformance with Specifications³
- E 456 Terminology Relating to Quality and Statistics³

3. Terminology

3.1 Definitions:

3.1.1 determination process, n-the act of carrying out the series of operations specified in the test method whereby a single value is obtained. (Syn. *determination*. See Section 4.)

3.1.1.1 Discussion—A determination process may involve several measurements of the same type or different types, as well as an equation by which the determination value is calculated from the measurement values observed.

3.1.2 determination tolerance, n-as specified in a test *method*, the exactness with which a determination value is to be calculated and recorded.

3.1.2.1 Discussion—In this practice, the determination tolerance also serves as the bridge between the test result tolerance and the measurement tolerances. The value of the determination tolerance calculated from the specified test result tolerance is compared with the value calculated from the specified measurement tolerances.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

² Annual Book of ASTM Standards, Vol 07.01.

³ Annual Book of ASTM Standards, Vol 14.02.

3.1.3 determination value, n—the numerical quantity calculated by means of the test method equation from the measurement values obtained as directed in a test method. (Syn. *determination*. See Section 4.)

3.1.4 *measurement process*, *n*—the act of quantifying a property or dimension. (Syn. *measurement*. See Section 4.)

3.1.4.1 *Discussion*—One test method determination may involve several different kinds of measurement.

3.1.5 *measurement tolerance*, *n*—as specified in a test *method*, the exactness with which a measurement is to be made and recorded.

3.1.6 measurement tolerance propagation equation, n—the mathematical formula, derived from the test method equation, which shows the dependence of the determination tolerance on the measurement tolerances. (Syn. propagation equation.)

3.1.6.1 *Discussion*—Propagation equations and the propagation of errors are discussed in Annex A1.

3.1.7 *measurement value*, *n*—the numerical result of quantifying a particular property or dimension. (Syn. *measurement*. See Section 4.)

3.1.7.1 *Discussion*—Measurement values in test methods are of two general types: those whose magnitude is specified in the test method, such as the dimensions of a specimen, and those whose magnitude is found by testing, such as the measured mass of a specimen.

3.1.8 propagation equation, n—Synonym of measurement tolerance propagation equation.

3.1.9 *test method equation*, n—the mathematical formula specified in a test method, whereby the determination value is calculated from measurement values.

3.1.10 *test method tolerances*, *n*—*as specified in a test method*, the measurement tolerances, the determination tolerance, and the test result tolerance.

3.1.11 *test result*, *n*—a value obtained by applying a given test method, expressed either as a single determination or a specified combination of a number of determinations.

3.1.11.1 *Discussion*—In this practice the test result is the average of the number of determination values specified in the test method.

3.1.12 *test result tolerance*, *n*—*as specified in a test method*, the exactness with which a test result is to be recorded and reported.

3.1.13 *tolerance terms*, *n*—the individual members of a measurement tolerance propagation equation in which each member contains only one test method tolerance.

3.1.14 For the definitions of other terms used in this practice, refer to Terminology D 123 and Terminology E 456.

4. Discussion of Terms

4.1 Test Results, Determinations, and Measurements:

4.1.1 A test result is always a value (numerical quantity), but *measurement* and *determination* are often used as referring to general concepts, processes or values—the context indicating which meaning is intended. In this practice it is necessary to make these distinctions explicit by means of the terms given in Section 3.

4.1.2 The necessary distinctions can be illustrated by a test method for obtaining the mass per unit area of a fabric. Two kinds of measurement are required for each test specimen, length and mass. Two different length measurements are made, the length and the width of the specimen. One determination value of the mass per unit area is calculated by dividing the mass measurement value by the product of the length measurement value and the width measurement value from one specimen.

4.1.3 If the test method directs that mass per unit area determinations are to be made on three test specimens, the test result is the average of the three determination values, each obtained as directed in 4.1.2.

4.2 Test Method Tolerances:

4.2.1 The specified measurement tolerances tell the operator how closely observations are to be made and recorded. "Weigh the specimen to the nearest 0.01 g" and "Measure the length of the specimen to the nearest 0.02 in." are examples of typical measurement tolerance specifications in a test method.

4.2.2 The specified determination and test result tolerances tell the operator how many significant digits should be recorded in the determination value and in the test result, respectively.

5. Expressing Test Method Tolerances

5.1 Tolerances in test methods are commonly specified in one of four ways which are combinations of two general distinctions. A test method tolerance may be absolute or relative and may be expressed either as a range having an upper and a lower limit or as the result of rounding-off. These distinctions are illustrated by the following equivalent instructions that are possible in weighing a 5.00 g test specimen:

	Absolute	Relative
Upper and Lower Limit	within ± 0.005 g	within ±0.1 %
Rounding-off	to the nearest 0.01 g	to the nearest 0.2 %

5.2 Within one method, state all test method tolerances in either the rounding-off mode or the upper and lower limit mode. The rounding-off mode is preferred for all test methods. Use a series of absolute tolerances for successive levels of a measurement or determination in preference to a relative tolerance.

5.3 The numerical value of a tolerance expressed in terms of rounding-off is twice that for the same tolerance expressed as an upper and lower limit. A discussion of rounding-off appears in Section 3 of Practice E 29 and in Chapter 4 of Ref $(1)^4$. Numbers are usually rounded-off to the nearest 1, 2, or 5 units in the last place.

6. Tolerance Symbols

6.1 An absolute tolerance is symbolized by a capital delta, Δ , followed by a capital letter designating a measurement value, a determination value or a test result. Thus, ΔA .

6.2 A relative tolerance is symbolized by the absolute tolerance, ΔA , divided by the corresponding measurement value, determination value, or test result, A. Thus, $\Delta A/A$.

6.3 Relative tolerances are expressed as percentages by $100\Delta A/A$. All relative tolerances for a specific test method must be expressed in the same way throughout, either as fractions or as percentages.

⁴ The boldface numbers in parentheses refer to the list of references at the end of this standard.

SUMMARY AND USES

7. Summary of Practice

7.1 A specific measurement tolerance propagation equation relating the determination tolerance to the measurement tolerances is derived by applying an adaptation of the law of error propagation to the test method equation. In this measurement tolerance propagation equation, the determination tolerance term should equal the sum of individual measurement tolerance terms.

7.2 Tentative measurement and determination tolerance values are substituted in the propagation equation terms, and the consistency of the selected test method tolerances is judged by the relative magnitudes of the tolerance terms.

7.3 Successive adjustments in the selected test method tolerance values are made until a consistent set of test method tolerances is established.

8. Significance and Use

8.1 In any test method, every direction to measure a property of a material should be accompanied by a measurement tolerance. Likewise, determination and test result tolerances should be specified. This practice provides a method for evaluating the consistency of the test method tolerances specified.

8.2 This practice should be used both in the development of new test methods and in evaluating old test methods which are being revised.

8.3 The test result tolerance obtained using this practice is not a substitute for a precision statement based on interlaboratory testing. However, the measurement tolerances selected by means of this practice will be an important part of the test method conditions affecting the precision of the test method.

MATHEMATICAL RELATIONSHIPS 7505

9. Propagation Equations

9.1 The test method equations by which determination values are calculated from measurement values in textile testing usually involve simple sums or differences, products or ratios, or combinations of these. Measurement tolerance propagation equations for each of these types of relationships are derived in Annex A2 by applying the general measurement tolerance propagation equation, developed in Annex A1, to each of the typical test method equations. Propagation equations for a number of textile test method equations are given in Table A2.1.

9.2 In the following discussion, the determination of mass per unit area is used to illustrate the principles involved in obtaining consistent tolerances.

9.2.1 Eq 1 is a typical mass per unit area equation.

$$W = KM/DE \tag{1}$$

where:

- W = the mass per unit area,
- K = a constant to change W from one set of units to another,
- M = the specimen mass,

D = the specimen width, and

E = the specimen length.

9.2.2 The corresponding propagation equation is Eq 2, derived in A2.4.1.

$$(\Delta W/W)^2 / 2 = (\Delta M/M)^2 + (\Delta D/D)^2 + (\Delta E/E)^2$$
(2)

where:

$(\Delta W/W)^2/2$	=	the mass per unit area determination toler-
		ance term,
$(\Delta M/M)^2$	=	the mass measurement tolerance term,
$(\Lambda D/D)^2$		the second the manufacture and the leaves a second

$\Delta D D $	_	uic	wium	measurement	torerance	term,	and
A DUDY2		.1	1 .1		. 1		

 $(\Delta E/E)^2$ = the length measurement tolerance term.

10. Tolerance Terms

10.1 As shown in Annex A2, every propagation equation can be expressed in the form of $r = a + b + c \dots$, in which each of the terms of this equation contains only one test method tolerance. The *r* term contains the determination tolerance, ΔR , and the other terms contain such measurement tolerances as ΔA , ΔB , and ΔC . The terms *r*, *a*, *b*, and *c* are tolerance terms.

10.1.1 For the mass per unit area example $r = (\Delta W/W)^2/2$, $a = (\Delta M/M)^2$, $b = (\Delta D/D)^2$, and $c = (\Delta E/E)^2$, as can be seen from Eq 2.

NOTE 1—The number of measurement tolerance terms is not restricted to 3, of course, but matches the number of measurements, q, for which tolerances are specified.

10.2 The key to this practice is the recognition that there are two ways of calculating the determination tolerance term:

10.2.1 The determination tolerance term, r, can be calculated from a specified value of ΔR using the expression for r given in the propagation equation. For example, in Eq 2 $r = (\Delta W/W)^2/2$. By substituting a typical value for W and a specified value for ΔW , a value of r is obtained.

10.2.2 The determination tolerance term can also be calculated as the sum of the measurement tolerance terms *a*, *b*, *c*, etc., which have been calculated from specified values of ΔA , ΔB , ΔC , etc. For the mass per unit area example, an estimate of the value of *r* may be obtained from values of *a*, *b*, and *c* found by substituting values of ΔM , M, ΔD , D, ΔE , and *E* in the tolerance term expressions $(\Delta M/M)^2$, $(\Delta D/D)^2$ and $(\Delta E/E)^2$.

10.3 These two ways of calculating the determination tolerance term usually produce different results, often radically different. In order to deal with this inconsistency, the second way of calculating the determination tolerance term is labelled u, which equals a + b + c + ...

10.3.1 Therefore, in the following sections, r is the determination tolerance term value calculated from the specified determination tolerance by means of the expression for r supplied in the propagation equation, and u is the determination tolerance term value calculated from the specified measurement tolerances by means of the expressions for the measurement tolerance terms, a, b, c, etc., supplied in the propagation equation.

10.3.2 The term, r, is the specified determination tolerance term and u is the effective determination tolerance term.

11. Determination Tolerances

11.1 The propagation equation relates the determination tolerance to the specified measurement tolerances. However, in

a test method it is usually the test result tolerance that is specified rather than the determination tolerance. Therefore, a bridge from the test result tolerance to the determination tolerance is necessary. This is supplied by Eq 3.

$$\Delta R = \Delta Q \sqrt{n} \tag{3}$$

where:

 ΔR = the determination tolerance, to three significant digits,

 ΔQ = the test result tolerance, to one significant digit, and n = the number of determinations per test result.

See A1.3 for a derivation of Eq 3.

NOTE 2—While only one significant digit should be used for test result and measurement tolerances, three significant digits should be retained in the determination tolerance since it is a mathematical extension of the test result tolerance. In an extended calculation it is good practice to protect significant information being transmitted through intermediate stages of the calculation by retaining one or two extra significant digits on intermediate values used in the calculation.

12. Consistency Criteria

12.1 Two types of inconsistencies have been observed in test method tolerances. The first occurs between the specified determination tolerance and the value of the effective determination tolerance actually obtainable from the specified measurement tolerance, as discussed in 10.3. The second occurs between the specified measurement tolerances. In comparing the measurement tolerance terms of two measurements, it is often found that the one term will be more than 10 times the other so that the larger term dominates (and the smaller term is negligible) in its effect on the effective determination tolerance term, *u*. Such inconsistencies need to be examined. The means used in this practice is to study the tolerance term ratios u/r, a/r, b/r, c/r, etc.

12.2 Corresponding to these two inconsistencies are two norms which are stated in Eq 4 and Eq 5.

$$0.2 \le u/r \le 2.0\tag{4}$$

$$0.2/q \le a/r, b/r, c/r, \text{etc.} \le 2.0/q$$
 (5)

where:

u = the sum of the measurement tolerance terms, *r* = the specified determination tolerance term, *q* = the number of measurements, and *a, b, c,* etc., = the measurement tolerance terms.

12.3 These ranges of acceptable ratio values should not be used rigidly. Rather, they should be taken as guidelines for constructive evaluation of the test method tolerances specified. For instance, an unusually low measurement tolerance term may be acceptable because there is little or no added cost in achieving the specified measurement tolerance instead of a larger one.

APPLICATION OF PRINCIPLES

13. Procedure

13.1 *Introduction*—The procedure in this practice falls into four steps. In the first step the propagation equation is obtained and all available information on the test method tolerances and measurement values is assembled. This is done only once. The remaining three steps probably will be repeated at least once

before an acceptable set of specified test method tolerances and measurement values is obtained.

13.1.1 In Step 2, acceptable measurement tolerance ranges are calculated from the desired determination tolerance, the specified measurement values, and the consistency criterion stated in 12.2.

13.1.2 In Step 3, the selection of new tolerance and measurement values follows after comparing the starting values assembled in the first step with the acceptable ranges calculated in the second step. In making this selection, consideration is given to the feasibility of attaining the selected measurement tolerances with the apparatus and procedure given in the test method.

13.1.3 In Step 4, the selected values from Step 3 are next evaluated for consistency. To do this, these values are put in tolerance term form and the tolerance ratios are compared directly with the consistency criteria.

13.1.4 This consistency evaluation usually will suggest further study of the test method to see what changes can be made to achieve adequate consistency. If changes in any of the test method tolerances or in any of the specified measurement values are made, Steps 2, 3, and 4 must be repeated.

13.2 Step 1, Preliminaries:

13.2.1 *Propagation Equation*—Obtain the measurement tolerance propagation equation corresponding to the test method equation. If the equation is not listed in Table A2.1, follow the directions given in Annex A2.

13.2.2 *Tolerance Terms*—Identify the individual tolerance terms in the propagation equation and label them *r*, *a*, *b*, *c*, etc. as described in Section 10.

13.2.3 *Measurement Values*—When any of the tolerance terms contains measurement value(s) found by testing, select at least two values of R which are representative of the range in which the test method is to be used. Calculate the corresponding measurement values from the selected determination values using the test method equation.

13.2.3.1 As described in 3.1.7, measurement values are of two kinds. One is specified in the test method, for example, the dimensions of a specimen. The other is found by testing and varies with the material being tested, the mass of a specimen, for instance. Changes in the determination value, R, will result from changes in measurement values found by testing.

13.2.3.2 The magnitudes of these measurement values affect the relationship between the measurement tolerances and the determination tolerance. Therefore, specific values of each must be selected.

13.2.3.3 The process of evaluating the tolerances for consistency and feasibility may lead to changes in the specified measurement values in order to achieve one or the other objective.

13.2.4 *Starting Tolerance Values*—List all available test method tolerances, and label them as described in Section 6. Convert relative tolerances to absolute tolerances, using the selected measurement values, so that the effect of the latter may be seen more readily.

13.2.4.1 When the test method specifies that more than one determination is to be made for a test result, calculate the starting determination tolerance value, to three significant

digits, from the selected test method tolerance value and the number of determinations specified in the test method, using Eq 3 (11.1). Even if no other test method tolerance is specified, specify a determination tolerance value, ΔR .

NOTE 3—Refer to Practice D 2905 for guidance in using available precision data to obtain starting values of *n* to achieve the selected test method tolerance, ΔQ , from the determination tolerance, ΔR .

13.3 Step 2, Acceptable Tolerance Ranges:

13.3.1 Calculate the specified determination tolerance term, r, to two significant digits, from ΔR for each of the values of R selected.

13.3.2 For each value of R, calculate a lower and an upper limit for a/r, b/r, c/r, etc. from Eq 5 in 12.2, using a value of q equal to the number of measurements in the test method equation. Retain only two significant digits.

13.3.3 Multiply each of the above limit values by the corresponding value of r to obtain the lower and upper limit values of a, b, c, etc. Retain only two significant digits.

13.3.4 Calculate lower and upper limit values of the individual measurement tolerances from a, b, c, etc. using the formulas identified as directed in 13.2. Retain only one significant digit.

13.3.5 Display the values obtained in 13.3 in a table for convenience in evaluating.

13.4 Step 3, New Values:

13.4.1 Compare the specified tolerance values with the lower and upper tolerance limits calculated as directed in 13.3.

13.4.2 If any tolerance is less than the lower limit, it is usually wise to delay further consideration until the other tolerances have been dealt with. Then, decide whether there would be any appreciable saving in equipment, material, or labor that would make going to a larger tolerance worthwhile. A small tolerance on one measurement may permit the use of an "oversize" tolerance for another measurement in meeting the consistency criterion for the determination tolerance.

13.4.3 If any measurement tolerance is greater than the upper limit, consider what changes in measurement tolerance are feasible. In general, select the smallest practical tolerance for use in the next step.

13.5 *Step 4, Consistency Evaluation*—After a new set of test method tolerances has been selected and evaluated for feasibility, it is ready for consistency evaluation.

13.5.1 Substitute the selected values of test method tolerances and measurement values, together with the corresponding determination values, in the appropriate tolerance terms and calculate values of r, a, b, c, etc. to two significant digits.

13.5.2 Calculate the sum of the measurement tolerance term values, $u = a + b + c + \dots$

13.5.3 Calculate the ratios u/r; a/r; b/r; c/r; etc. to two significant digits.

13.5.4 Compare u/r with 0.2 and 2.0. If u/r is greater than 2.0, study the measurement tolerance terms for the cause(s). If u/r is less than 0.2, consider reducing the determination and test method tolerances. Also keep in mind that the value of the test result tolerance is determined by the determination tolerance value and the number of determinations specified by the test method according to Eq 3. Thus, r can be reduced or increased by changing n.

13.5.5 Compare each of a/r, b/r, c/r, etc. with 0.2/q and 2/q. 13.5.5.1 This comparison should disclose no surprises, since a measurement tolerance below the lower limit established in 13.3 will have a ratio lower than 0.2/q and vice versa. However, comparing these ratios with the consistency criterion will reveal the extent of the inconsistency that exists.

13.5.5.2 If the ratio is greater than 2.0/q, study the tolerance and any measurement value included in the tolerance term. Will a change in measurement value decrease the tolerance term value?

13.6 *Successive Trials*—The remainder of the procedure consists of a succession of trials in which changes are made in test method tolerances and specified measurement values until a set of values is obtained which is both feasible and reasonably consistent. There are three aspects to the feasibility evaluation, which are summed up in the following questions the task group members must answer to their satisfaction.

13.6.1 Is the test result tolerance small enough to meet the needs of the users of the test method? Is it smaller than need be?

13.6.2 Can each measurement tolerance be achieved with the apparatus and procedure given in the test method?

13.6.3 If changes in the test method (new apparatus, larger specimens, more determinations, changes in technique, etc.) are necessary to achieve consistency, will the cost of testing be increased unreasonably?

14. Mass per Unit Area Example

14.1 Test Method Directions—The example chosen to illustrate the procedure described in Section 13 starts with the following directions: Cut five specimens 2.5 ± 0.05 in. by 10.0 ± 0.05 in., weigh each specimen to the nearest 0.01 g, and calculate the average mass per unit area in ounces per square yard to the nearest 0.1 oz/yd². Typical areal densities for this material range from 10 to 60 oz/yd².

14.2 Step 1, Preliminaries:

14.2.1 *Propagation Equation*:

14.2.1.1 The test method equation is Eq 6.

$$W = KM/DE \tag{6}$$

where:

- $W = \text{mass per unit area, oz/yd}^2$,
- K = constant to convert the measurement dimensionalunits to oz/yd²,
- M = specimen mass, g,
- D = specimen width, in., and
- E = specimen length, in.

14.2.1.2 As shown in 9.1.2 and A2.4, the corresponding propagation equation is Eq 7.

$$(\Delta W/W)^{2}/2 = (\Delta M/M)^{2} + (\Delta D/D)^{2} + (\Delta E/E)^{2}$$
(7)

where:

- ΔW = specified determination tolerance,
- ΔM = specified measurement tolerance for specimen mass,
- ΔD = specified measurement tolerance for specimen width, and
- ΔE = specified measurement tolerance for specimen length.
 - 14.2.2 Tolerance Terms:

14.2.2.1 The tolerance terms in this propagation equation are given by Eq 8, Eq 9, Eq 10, and Eq 11.

$$r = \left(\Delta W/W\right)^2 /2,\tag{8}$$

$$a = (\Delta M/M)^2 , \qquad (9)$$

$$b = (\Delta D/D)^2$$
, and (10)

 $c = (\Delta E/E)^2 \,. \tag{11}$

14.2.2.2 The effective determination tolerance term is given

$$u = a + b + c \tag{12}$$

14.2.2.3 The specified determination tolerance term is r, as given by Eq 8.

14.2.3 Determination and Measurement Values:

14.2.3.1 The propagation equation contains both absolute tolerances (ΔW , ΔM , ΔD , and ΔE) and determination and measurement values (W, M, D, and E) for which values must be selected.

14.2.3.2 The specimen dimensions are specified as D = 2.5 in. and E = 10.0 in.

14.2.3.3 The specimen mass is calculated from the expected range of test results by means of Eq 1, with K = 45.72 to convert from g/in.² to oz/yd². For the initial consistency evaluation, choose two values for W: 10 oz/yd² and 60 oz/yd². The corresponding values of M are 5.47 g and 32.8 g.

14.2.4 Starting Tolerance Values:

14.2.4.1 The rounded-off mode of expressing the absolute tolerances is used.

14.2.4.2 The test method directions in 14.1 give the measurement tolerances as M = 0.01 g, D = 0.1 in., and E = 0.1 in.

14.2.4.3 The specified determination tolerance is calculated from the specified test result tolerance of 0.1 oz/yd² and the specified number of determinations, 5, using Eq 8. $\Delta W = 0.1 \sqrt{5} = 0.224 \text{ oz/yd}^2$.

14.2.5 *Summary of Values*—All of these initial values are given in Table 1.

14.3 Step 2, Acceptable Tolerance Ranges:

14.3.1 Calculate the specified determination tolerance term, r, from W = 0.224 oz/yd² for the two values of W selected, using Eq 8.

14.3.2 For each value of *W*, calculate a lower and an upper limit value for a/r; b/r; and c/r from Eq 5 in 12.2 using q = 3, since there are three measurements.

14.3.3 Multiply each of the values calculated as directed in 14.3.2 by the corresponding value of r. These are the lower and upper limits of a, b, and c.

14.3.4 Obtain lower and upper limit values of the measurement tolerances ΔM , ΔD , and ΔE from the above values of *a*,

TABLE 1 Mass Per Unit Area Example—Starting Determination, Measurement, and Tolerance Values

Equation Element	Tolerances	Determination and Measurement Values	
Mass per unit area, <i>W</i>	$\Delta W = 0.224 \text{ oz/yd}$	10 oz/yd ²	60 oz/yd ²
Specimen Mass, <i>M</i>	$\Delta M = 0.01 \text{ g}$	5.47 g	32.8 g
Specimen Width, <i>D</i>	$\Delta D = 0.1 \text{ in.}$	2.5 in.	2.5 in.
Specimen Length, <i>E</i>	$\Delta E = 0.1 \text{ in.}$	10.0 in.	10.0 in.

b, and c, using Eq 9, Eq 10, and Eq 11. For instance $\Delta M = M$ $\sqrt{a} = 5.47 \text{ x } \sqrt{(17 \times 10^{-6})} = 0.02 \text{ g, for the 10 oz/yd}^2$ material.

14.3.5 All of the above values in 14.3 are summarized in Table 2.

14.4 Step 3, New Values:

14.4.1 The specified mass tolerance of 0.01 g is obviously smaller than need be to meet the consistency criteria. However, with present-day laboratory balances, it is no easier or less expensive to measure to a tolerance of between 0.02 and 0.07 g. Therefore leave ΔM at 0.01 g.

14.4.2 The specified specimen dimension tolerance of 0.1 in. is larger than the upper limit for all but the length measurement at 10 oz/yd². A study of the dimension measurement process indicates a tolerance of 0.02 in. should be feasible. This is lower than need be for the length measurement at 10 oz/yd² but just below the upper limit for 60 oz/yd². For the width measurement, however, 0.02 in. is still much too large at 60 oz/yd². An obvious solution to this problem would be to increase the specimen width to 10 in. so that the tolerance ranges for *D* would be the same as for *E*. However, this would quadruple the amount of material required and increase the cost of testing. Alternatively, a 5 by 5 in. specimen would have no longer area than the 2.5 by 10.0 in. specimen, and the tolerance range for the width would be the same as for *E*, better for *D* and worse for *E*.

14.5 Step 4, Consistency Evaluation:

14.5.1 Table 3 shows the effect of going to a 5 by 5 in. specimen and measuring the specimen dimensions to the nearest 0.02 in. In the upper half of the table are given the values of the tolerance terms a, b, c, and u; and in the bottom half, the tolerance ratios a/r, b/r; c/r and u/r.

14.5.2 Table 4 shows the effect of going to a 10 by 10 in. specimen and measuring the specimen dimensions to the nearest 0.02 in.

14.5.3 Keeping in mind the ratio criterion range of 0.067 to 0.67, from these two tables it can be seen that while the 5 by 5 in. specimen size is adequate for the material having a mass per unit area of 10 oz/yd² (and up to 32 oz/yd²), it is still not satisfactory for 60 oz/yd² material. On the other hand, the 10 by 10 in. specimen size is about right for the 60 oz/yd² material, and much larger than need be for 10 oz/yd².

14.5.4 Thus, the task group appears to be faced with the choice of using larger specimens for heavier materials or of accepting a greater test result tolerance for heavier materials. A

TABLE 2 Mass per Unit Area Example—Acceptable Tolerance Ranges

W	$\begin{array}{c} 10 \text{ oz/yd}^2 \\ 0.224 \text{ oz/yd}^2 \\ 250 \times 10^{-6} \end{array}$		60 oz/yd^2 0.224 oz/yd ² 7.0 × 10 ⁻⁶	
	Lower	Upper	Lower	Upper
a/r, b/r, c/r a, b, c ΔM ΔD ΔE	0.067 17×10^{-6} 0.02 g 0.01 in. 0.04 in.	0.67 170×10^{-6} 0.07 g 0.03 in. 0.13 in.	$\begin{array}{c} 0.067 \\ 0.47 \times 10^{-6} \\ 0.02 \ g \\ 0.002 \ in. \\ 0.007 \ in. \end{array}$	$\begin{array}{c} 0.67 \\ 4.7 \times 10^{-6} \\ 0.07 \text{ g} \\ 0.005 \text{ in.} \\ 0.022 \text{ in.} \end{array}$