
**Plastics piping and ducting systems —
Injection-moulded thermoplastics
fittings — Methods for visually assessing
the effects of heating**

*Systèmes de canalisations et de gaines en plastiques — Raccords
thermoplastiques moulés par injection — Méthodes d'essai pour
estimer visuellement les effets de la chaleur*

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

ISO 580:2005

<https://standards.iteh.ai/catalog/standards/sist/c75c7dab-8938-4446-b4bc-c42051f3293d/iso-580-2005>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 580:2005

<https://standards.iteh.ai/catalog/standards/sist/c75c7dab-8938-4446-b4bc-c42051f3293d/iso-580-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 580 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

This third edition cancels and replaces the second edition (ISO 580:1990), which has been technically revised.

[ISO 580:2005](https://standards.iteh.ai/catalog/standards/sist/c75c7dab-8938-4446-b4bc-c42051f3293d/iso-580-2005)

<https://standards.iteh.ai/catalog/standards/sist/c75c7dab-8938-4446-b4bc-c42051f3293d/iso-580-2005>

Introduction

The test for determination of the resistance to heat according to the two test methods specified in this International Standard is applicable for distinguishing between properly and improperly moulded thermoplastics pipe fittings.

It can be used to

- determine whether cold slugs (pieces of material that enter the mould at a temperature significantly lower than the rest of the mass) or unfused areas are present,
- reveal cavities and porosity,
- determine the amount of moulded-in stress produced by the moulding process,
- reveal contamination, and
- show the integrity of the fusion line.

A stress-free part will generally have better properties and higher strength than parts with a higher degree of residual stress and will generally be less reactive when exposed to chemicals. By placing moulded fittings in a heated medium (air or liquid) at elevated temperature for a period of time dependant on their wall thickness, it is possible to detect internal stress.

Since the stresses start to be released as soon as the material passes to the rubbery state, it is only necessary to maintain the moulded pieces at a higher temperature for a defined period of time.

NOTE Injection-moulded fittings can be made by a number of techniques, whereby the material is injected into the mould cavity. These include single- or multi-point injection, diaphragm gating and ring gating. The technique used in the manufacture of mouldings will affect the way in which they are assessed.

Plastics piping and ducting systems — Injection-moulded thermoplastics fittings — Methods for visually assessing the effects of heating

1 Scope

This International Standard specifies two methods for assessing the effects of heating on injection-moulded thermoplastics pipe fittings — method A, using an air oven, and method B, using a liquid bath. In case of disagreement, method A is the reference method.

This International Standard is applicable to cement-welded fittings as well as to flanged fittings and fittings incorporating elastomeric seals and to fittings consisting of the assembly of several moulded parts (e.g. union connectors). It is applicable to both pressure and non-pressure fittings.

2 Principle

Complete mouldings are subjected to an elevated specified temperature in an air-circulating oven or a liquid bath for a given period of time, depending upon the wall thickness of the fitting and the material being moulded.

The surfaces of the moulding are examined before and after heating, and any cracks, blisters, delaminations or opening of fusion lines are measured and expressed as a percentage of the wall thickness.

3 Test parameters

The following test parameters are specified by the subclauses referenced as follows and in Table 1 for the particular material used in the manufacturer of the fitting, unless the referring standard (a standard making reference to this International Standard in its own provisions) or regulations specify otherwise:

- a) the test temperature, T (see 4.1.1 and 4.3);
- b) the number of test pieces (see 4.2.2);
- c) the heating time, t (see 4.3.3);
- d) the test method to be used and, for method B (liquid bath) only, the test liquid.
- e) the acceptable limits for the occurrence or dimensions of any cracks or other features found (see 4.3.6).

Unless otherwise specified in the referring standard or regulations, the test parameters shall be in accordance with Table 1.

Table 1 — Test parameters to be used in absence of guidance in the referring standard

Material	Temperature T ± 2 °C	Heating time	
		Mean wall thickness e_m mm	Duration t min
ABS	150	$e_m \leq 3$	15
PE	110	$3 < e_m \leq 10$	30
PP	150	$10 < e_m \leq 20$	60
PVC-U		$20 < e_m \leq 30$	140
PVC-C		$30 < e_m \leq 40$	220
SAN+PVC		$40 < e_m$	240

4 Method A

4.1 Apparatus

4.1.1 Air-circulating oven, thermostatically controlled, equipped with a thermostat so that the temperature of the working zone can be maintained at the prescribed test temperature throughout the test and of sufficient heating capacity to enable the test temperature to be regained within 15 min of insertion of the test pieces.

4.1.2 Thermometer, graduated in 0,5 °C. Or a type "T" thermocouple with a resolution of 0,1 °C and an accuracy of at least $\pm 0,8$ °C.

4.2 Test pieces

4.2.1 Preparation

After removing any runners, take the complete mouldings as test pieces. If the fitting incorporates an elastomeric sealing ring, remove the ring before testing.

In the case of fittings assembled from more than one element, separate the components and test them out of contact with each other.

4.2.2 Number

The number of test pieces shall be as specified in the product standard. In the absence of any information on the number of test pieces, use at least three pieces.

4.3 Procedure

4.3.1 Set the oven temperature (4.1.1) at the test temperature ($T \pm 2$) °C in accordance with the product standard or Table 1.

4.3.2 Put the test pieces in the oven and arrange them so that they are standing on one side of their sockets wherever possible, avoiding contact with another test piece or the sides of the oven.

4.3.3 Leave the test pieces in the oven until the oven returns to the test temperature ($T \pm 2$) °C and for a further period, t , dependent on the mean wall thickness, e_m , of the thickest part of the test piece(s) in accordance with the product standard or Table 1.

4.3.4 Remove the test pieces from the oven, taking care not to deform or damage them.

4.3.5 Cut the test pieces with a sharp knife or razor blade while they are still hot, to enable the dimensions of cracks, blisters, delaminations and weld-line openings, if any, to be measured as required. Allow the test pieces and/or parts therefrom to cool in air until they can be handled without deformation.

If not otherwise specified in the referring standard, the following number of cuts should be made:

- for cylindrical components of $d_n \leq 160$ mm, not less than two cuts equally spaced around the periphery of the mouth of each socket or spigot of the component;
- for cylindrical components of $d_n > 160$ mm, not less than four cuts equally spaced around the periphery of the mouth of each socket or spigot of the component.

For d_n , see Figure 1.

4.3.6 Examine each test piece for, and record, any surface changes, such as cracks, delaminations and weld-line openings as well as changes inside the wall, e.g. blisters, and in the gating area. Determine the extent of such defects in the gating area as a percentage of the wall thickness as follows.

- a) For sprue-gated mouldings (see Figure 1): around the injection point(s) within a radius as specified in the referring standard. In the absence of any information in the referring standard, use $R = 0,3d_n$ with a maximum value of 50 mm.
- b) For ring- or diaphragm-gated mouldings (see Figure 1): within a length, L , of the cylindrical portion of the gating area as specified in the referring standard or, in absence of any information, within a length $L = 0,3d_n$. In the case of cracks running through the whole wall thickness of the gating area, determine also the length of the crack.
- c) For mouldings containing fusion lines, determine the widest and deepest part(s) of any open part of the fusion line.
- d) For all other parts of the moulding beyond the gating area, examine the surface for any change, such as cracks, blisters, and delaminations of the wall.

If not specified in the referring standard, the specifications given in Annex A should be used for the examination of a test piece.




Figure 1 — Injection gating areas

5 Method B

5.1 Apparatus

5.1.1 Heating bath, thermostatically controlled, at the prescribed test temperature, $(T \pm 2) ^\circ\text{C}$. The volume and agitation of the bath shall be such that the temperature remains within the specified temperature range when the test pieces are immersed.

The liquid chosen shall be stable at the specified temperature and shall not otherwise affect the test piece.

It shall be ensured that the liquid does not cause any safety or health risks.

NOTE 1 Glycerine, glycol, mineral oil free from aromatic hydrocarbons, or a solution of calcium chloride may be suitable, depending upon which of the materials covered by this method is under test. For example, all these liquids are suitable for PVC-U, but the use of glycols is not appropriate for ABS fittings, for which the selection of an appropriate mineral oil is preferable.

NOTE 2 Attention is drawn to any relevant legislation which requires that the use of the liquid chosen does not cause any safety or health risks.

5.1.2 Holder, to support the test piece(s) within the heating bath. The fittings shall be supported in such a way as to not cause additional distortion.

5.1.3 Thermometer, graduated in 0,5 °C. Or a type "T" **thermocouple** with a resolution of 0,1 °C and an accuracy of at least $\pm 0,8$ °C.

5.2 Test pieces

See 4.2.

5.3 Procedure

5.3.1 Set up the liquid bath (see 5.1.1) to the prescribed test temperature ($T \pm 2$) °C.

5.3.2 Put the test pieces in the liquid bath and arrange them so that they are not touching each other or the sides of the bath.

5.3.3 Leave the test pieces in the bath for a test period, t , as specified in the referring standard for the mean wall thickness, e_m , of the thickest part of the test piece.

If not otherwise specified in the referring standard, use a test period, t , in accordance with Table 1.

5.3.4 Remove the test pieces from the bath, taking care not to deform or damage them.

5.3.5 Cut the test pieces in accordance with 4.3.5.

5.3.6 Examine the test pieces in accordance with 4.3.6.

5.3.7 Record the composition of the liquid used in conjunction with the results obtained [see also Clause 6, c)].

ISO 580:2005
<https://standards.iteh.ai/catalog/standards/sist/c75c7dab-8938-4446-b4bc-c42051f3293d/iso-580-2005>

6 Test report

The test report shall include the following information:

- a) reference to this International Standard and to the referring standard;
- b) identification of the fittings tested (diameter, wall thickness, type, etc.);
- c) method used, i.e. A or B, and, if method B, the composition of the liquid used;
- d) test temperature;
- e) test duration;
- f) number of mouldings tested;
- g) details of visible differences from the original surface appearance, such as blisters, delaminations, cracks or opening of fusion lines;
- h) maximum dimensions of cracks, blisters etc. expressed as a percentage of the wall thickness;
- i) any factors which may have affected the results, such as any incidents or any operating details not specified in this standard;
- j) date of test.