



Binders for paints and varnishes — Determination of free-formaldehyde content of amino resins — Sodium sulfite titrimetric method

TECHNICAL CORRIGENDUM 1

Liants pour peintures et vernis — Dosage du formaldéhyde libre dans les résines aminoplastes — Méthode titrimétrique au sulfite de sodium

RECTIFICATIF TECHNIQUE 1

Technical corrigendum 1 to International Standard ISO 9020:1994 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 10, *Test methods for binders for paints and varnishes*.

(standards.iteh.ai)

Page 2

ISO 9020:1994/Cor 1:1996

<https://standards.iteh.ai/catalog/standards/sist/97f69041-c3c1-4eea-9f98-b1c33eae4/iso-9020-1994-cor-1-1996>

Replace subclause 4.5 by the following text:

4.5 Iodine, standard volumetric solution, $c(I_2) = 0,05$ mol/l, i.e. 12,690 g/l. If necessary, standardize the solution against sodium thiosulfate standard reference solution, $c(Na_2S_2O_3) = 0,1$ mol/l.

Page 4

Subclause 8.1

Include an adjustment factor f in the equation, which should read:

$$w(\text{CH}_2\text{O, free}) = \frac{V \times 1,5 \times 0,1 \times f}{m}$$

where

V is the volume, in millilitres, of iodine solution (4.5) used;

f is an adjustment factor to take into account any difference in concentration of the iodine solution (4.5) before standardization, $c(I_2)$ nominal, and after standardization, $c(I_2)$ actual:

$$f = \frac{c(I_2) \text{ actual}}{c(I_2) \text{ nominal}}$$

m is the mass, in grams, of the test portion;

1,5 is the mass, in milligrams, of formaldehyde corresponding to 1,00 ml of iodine solution, $c(I_2) = 0,5$ mol/l;

0,1 is the conversion factor necessary to convert milligrams to grams and to express w as a percentage.

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

ISO 9020:1994/Cor 1:1996

<https://standards.iteh.ai/catalog/standards/sist/97f69041-c3c1-4eea-9f98-b9bflc33eae4/iso-9020-1994-cor-1-1996>