



Designation: B 493 – 01 (Reapproved 2003)

Standard Specification for Zirconium and Zirconium Alloy Forgings¹

This standard is issued under the fixed designation B 493; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

1.1 This specification² covers three grades of zirconium and zirconium alloy forgings.

1.2 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 The following safety hazards caveat pertains only to the test method portion, Section 12, of this specification: *This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 *ASTM Standards*:

E 8 Test Methods for Tension Testing of Metallic Materials³

3. Terminology

3.1 *Lot Definitions*:

3.1.1 *castings*—a lot shall consist of all castings produced from the same pour.

3.1.2 *ingot*—no definition required.

3.1.3 *rounds, flats, tubes, and wrought powder metallurgical products (single definition, common to nuclear and non-nuclear standards)*—a lot shall consist of a material of the same size, shape, condition, and finish produced from the same ingot or powder blend by the same reduction schedule and the same heat treatment parameters. Unless otherwise agreed between manufacturer and purchaser, a lot shall be limited to the product of an 8 h period for final continuous anneal, or to a single furnace load for final batch anneal.

3.1.4 *sponge*—a lot shall consist of a single blend produced at one time.

3.1.5 *weld fittings*—definition is to be mutually agreed upon between manufacturer and the purchaser.

4. Classification

4.1 The forgings are furnished in three grades as follows:

4.1.1 *Grade R60702*—Unalloyed zirconium.

4.1.2 *Grade R60704*—Zirconium-tin alloy.

4.1.3 *Grade R60705*—Zirconium-niobium alloy.

5. Ordering Information

5.1 Orders for material under this specification shall include the following information:

5.1.1 Quantity (weight and number of pieces),

5.1.2 Name of material (zirconium forgings),

5.1.3 Finish (Section 9),

5.1.4 Dimension (diameter, thickness, length, width, or as specified in appropriate drawings),

5.1.5 ASTM designation and year of issue,

5.1.6 Grade number (see 3.1), and

5.1.7 Additions to the specification and supplementary requirements, if required.

NOTE 1—A typical ordering description is as follows: 8000-lb zirconium forgings, mechanically descaled 10 by 12 by 12-in. rectangular bar, ASTM B 493, dated __, Grade R60702.

6. Materials and Manufacture

6.1 The forgings shall be formed with conventional forging equipment normally found in primary ferrous and nonferrous metal plants.

6.2 Forgings shall be furnished in the annealed conditions.

7. Chemical Composition

7.1 The material shall conform to the requirements as to chemical composition prescribed in Table 1.

7.2 The manufacturer's ingot analysis shall be considered the chemical analysis for forgings, except for hydrogen and nitrogen, which shall be determined on the finished product.

¹ This specification is under the jurisdiction of ASTM Committee B10 on Reactive and Refractory Metals and Alloys and is the direct responsibility of Subcommittee B10.02 on Zirconium and Hafnium.

Current edition approved May 10, 2003. Published May 2003. Originally approved in 1969. Last previous edition approved in 2001 as B 493 – 01.

² For ASME Boiler and Pressure Vessel Code applications see related Specification SB-493 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 03.01.