

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 5267-2:2002

<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>

INTERNATIONAL STANDARD

ISO
5267-2

Second edition
2001-09-15

Pulps — Determination of drainability — Part 2: “Canadian Standard” freeness method

Pâtes — Détermination de l'égouttabilité —

Partie 2: Méthode de mesure de l'indice d'égouttage «Canadian Standard»

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 5267-2:2002

<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>



Reference number
ISO 5267-2:2001(E)

© ISO 2001

ISO 5267-2:2001(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST ISO 5267-2:2002

<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>

© ISO 2001

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Term and definition	1
4 Principle.....	2
5 Apparatus	2
6 Preparation of sample	2
7 Procedure	3
8 Expression of results	3
9 Test report	3
Annex A (normative) The "Canadian Standard" freeness tester	4
Annex B (normative) Maintenance of the "Canadian Standard" freeness tester	10
Annex C (normative) Calibration Service	11
Annex D (informative) Table of freeness corrections to 0,30 % stock concentration.....	12
Annex E (informative) Table of freeness corrections to 20 °C	13
Bibliography	14

ISO 5267-2:2001(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 5267 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 5267-2 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulp*.

This second edition cancels and replaces the first edition (ISO 5267-2:1980) which has been technically revised.

ISO 5267 consists of the following parts, under the general title *Pulps — Determination of drainability*:

— *Part 1: Schopper-Riegler method*

— *Part 2: "Canadian Standard" freeness method*

SIST ISO 5267-2:2002

<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>

Annexes A, B and C form a normative part of this part of ISO 5267. Annexes D and E are for information only.

Introduction

The “Canadian Standard” freeness test is designed to provide a measure of the rate at which a dilute suspension of pulp is dewatered under specified conditions. It has been shown that the drainability is related to the surface conditions and swelling of the fibres, and constitutes a useful index of the amount of mechanical treatment to which the pulp has been subjected.

The rate at which a suspension dewateres depends on the conditions of measurement, particularly the geometric characteristics of the instrument. The only practical means of achieving the required degree of accuracy for the measurement of “Canadian Standard” freeness is by the calibration procedure specified in annex C. The reproducibility of this method is entirely dependent on these arrangements being established within and between countries.

Results of this test do not necessarily correlate with the drainage behaviour of a pulp on a commercial paper machine.

A method for the determination of drainability in terms of the Schopper-Riegler number is specified in ISO 5267-1.

NOTE There are two slightly different types of “Canadian Standard” freeness testers in use, as described in annex A. These generally provide similar results, although some differences may occur.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 5267-2:2002](https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002)

<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 5267-2:2002

<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>

Pulps — Determination of drainability —

Part 2: “Canadian Standard” freeness method

1 Scope

This part of ISO 5267 specifies a method for determination of the drainability of a pulp suspension in water in terms of the “Canadian Standard” freeness in millilitres.

In principle, this method is applicable to all kinds of pulp in aqueous suspension.

NOTE Treatments which produce a large proportion of fines may induce an anomalous rise in freeness (false freeness), as a rule at values below 100 ml.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 5267. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 5267 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 4094, *Paper, board and pulps — International calibration of testing apparatus — Nomination and acceptance of standardizing and authorized laboratories*

ISO 4119, *Pulps — Determination of stock concentration*

ISO 5269-1, *Pulps — Preparation of laboratory sheets for physical testing — Part 1: Conventional sheet-former method*

ISO 5269-2, *Pulps — Preparation of laboratory sheets for physical testing — Part 2: Rapid-Köthen method*

ISO 14487, *Pulps — Standard water for physical testing*

3 Term and definition

For the purposes of this part of ISO 5267, the following term and definition applies.

3.1

“Canadian Standard” freeness

volume, expressed in millilitres, of the filtrate collected from the side orifice of the “Canadian Standard” freeness tester after correcting for the temperature and stock concentration of the sample under test

ISO 5267-2:2001(E)

4 Principle

Drainage through a fibre mat formed during the test on a perforated screen plate of a given volume of an aqueous pulp suspension into a funnel provided with a bottom and a side orifice. Determination is made of the volume of filtrate discharged from the side orifice. The volume of the discharged filtrate, in millilitres, is the “Canadian Standard” freeness of the pulp.

5 Apparatus

Ordinary laboratory apparatus and:

5.1 “Canadian Standard” freeness tester, as described in annex A.

NOTE Instructions for maintenance of the apparatus are given in annex B. Details of the Calibration Service for the apparatus are given in annex C. Information concerning authorized laboratories is also given in annex C.

5.2 Measuring cylinders, calibrated in millilitres and capable of measuring volume with an error less than 1,0 ml for volumes up to 100 ml; an error less than 2,0 ml for volumes between 100 ml and 250 ml; and an error less than 5,0 ml for volumes above 250 ml.

5.3 Balance, capable of reading accurately to 0,01 g.

NOTE Although for the determination of the mass of the side orifice discharge a balance of 0,1 g accuracy is sufficient, for the determination of stock concentration the necessary accuracy of the balance is 0,01 g.

5.4 Standard water, for physical testing, as described in ISO 14487.

6 Preparation of sample

SIST ISO 5267-2:2002

[https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-](https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-878d120c3819/iso-5267-2-2002)

As the drainage of a pulp suspension is affected considerably by dissolved solids and the pH of the water used in the determination, standard water in accordance with ISO 14487 shall be used throughout the test.

A sample of an aqueous suspension of the disintegrated pulp shall be taken. If the concentration is not known exactly, the suspension shall be thickened or diluted to approximately 0,32 % by mass using standard water, and the stock concentration determined in accordance with ISO 4119. Then the suspension shall be diluted to a stock concentration of 0,30 % \pm 0,01 % by mass and the temperature adjusted to 20,0 °C \pm 0,5 °C (see note 3). Throughout the preparation of the sample, care shall be taken to avoid the formation of air bubbles in the suspension.

NOTE 1 With time, an aqueous pulp suspension withdrawn from the stock preparation system or laboratory pulp evaluation equipment can undergo a change in freeness. To avoid the effect of this reversion phenomenon, pulp suspensions subjected to testing more than 30 min after sampling shall first be treated in the disintegration apparatus for 6 000 revolutions of the propeller at 1,2 % to 1,5 % concentration.

NOTE 2 The test result is sensitive to the quantity of pulp fines, or “crill”, in the suspension. Thickened pulp samples may lose some of this fibre fraction. To avoid such losses during the course of thickening, the filtrate shall be recirculated through the pulp pad until the filtrate is clear and the pulp redispersed by disintegration, as described in note 1. This procedure shall be used to concentrate dilute pulp suspensions to the stock concentration required for the freeness test.

NOTE 3 Where necessary (e.g. process control), a temperature other than 20 °C may be used but it is not in accordance with this part of ISO 5267 and must be reported. The correlation tables presented in this part of ISO 5267 (informative annexes D and E) were developed from groundwood freeness evaluation studies. The accuracy of the correction tables for chemical pulp freeness evaluation has not been determined.

NOTE 4 In some applications, e.g. process control, it may be convenient to accept larger deviations than 0,01 % for stock concentration and \pm 0,5 °C for temperature. The volume measured should be corrected with the aid of correction tables given in annexes D and E. The result so obtained does not conform to this part of ISO 5267.

7 Procedure

Clean the funnel and drainage chamber of the “Canadian Standard” freeness apparatus (5.1) thoroughly, and finally rinse with water. Place the drainage chamber in position. Adjust the temperature of the apparatus by rinsing with water at $20,0\text{ }^{\circ}\text{C} \pm 0,5\text{ }^{\circ}\text{C}$ (see note 3 in clause 6).

Place the measuring cylinder (5.2) or a tared beaker (see note in 5.3) in position to receive the discharge from the side orifice.

Whilst stirring, transfer $1\ 000\text{ ml} \pm 5\text{ ml}$ of homogeneous pulp suspension to a clean measuring cylinder.

Close the bottom of the chamber of the freeness tester and open the top lid and the air-cock. Mix the sample by closing the top of the cylinder with the hand and invert the cylinder through 180° three times, without losing the stock. As much as possible, avoid introducing air into the stock at this stage.

Pour the stock gently but as rapidly as possible into the chamber. At the end of the pouring, the stock should be almost motionless in the chamber. This can be achieved by pouring the stock around the inside of the chamber and finishing the pouring in the centre. Immediately close the top lid and the air-cock and open the bottom lid. Allow 5 s to elapse from the time of opening the bottom lid, then open the air-cock in a single motion to start the flow.

When the discharge from the side orifice has stopped, read the volume of this discharge to the nearest 1 ml for values below 100 ml, to the nearest 2 ml for values between 100 ml and 250 ml, and to the nearest 5 ml for values exceeding 250 ml. For greater accuracy, weigh the tared beaker and its contents to the nearest 0,1 g and convert the mass to volume (ml).

Combine, in a 2 000 ml beaker, the pulp from the chamber, side orifice discharge and bottom orifice discharge and drain the slurry in a sheet machine in accordance with ISO 5269-1 or ISO 5269-2 with a wire, or on a filter paper. For pulps with a high fines content, it is recommended to drain the pulp slurry on a tared filter paper in a Buchner funnel. Oven-dry the pad to a constant weight and record. Use this weight to calculate the stock concentration.

Carry out two determinations on each sample. [SIST ISO 5267-2:2002](https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002)
<https://standards.iteh.ai/catalog/standards/sist/a5150424-2f20-4f13-b556-c859c63cea28/sist-iso-5267-2-2002>

8 Expression of results

Report the mean of two determinations as the “Canadian Standard” freeness (ml). Duplicate determinations differing by more than 2 % from their mean value shall be repeated.

9 Test report

The test report shall include the following particulars:

- a) reference to this part of ISO 5267, i.e. ISO 5267-2;
- b) date and place of testing;
- c) all information necessary for identification of the sample tested;
- d) the test temperature if different from the standard;
- e) the test concentration if different from the standard;
- f) the mean result;
- g) the type of funnel used in the test (modified or original design);
- h) any unusual features observed during the test;
- i) any operations not specified in this part of ISO 5267 or in the International Standard to which reference is made or regarded as optional, which might have affected the results.