

**SLOVENSKI STANDARD  
SIST-TS CEN/TS 15119-2:2008**

**01-september-2008**

Durability of wood and wood-based products - Determination of emissions from preservative treated wood to the environment - Part 2: Wooden commodities exposed in Use Class 4 or 5 (in contact with the ground, fresh water or sea water) - Laboratory method

Dauerhaftigkeit von Holz und Holzprodukten - Abschätzung von Emissionen von mit Holzschutzmitteln behandeltem Holz an die Umwelt - Teil 2: Holzprodukte in Gebrauchsklasse 4 und 5 (im Kontakt mit Erde, Süßwasser oder Meerwasser) - Laborverfahren

Durabilité du bois et des matériaux a base de bois - Estimation des émissions dans l'environnement du bois traité avec des produits de préservation - Partie 2 : Articles en bois exposés en classe d'emploi 4 ou 5 (en contact avec le sol, l'eau douce ou l'eau de mer) - Méthode de laboratoire

(standards.iteh.ai)

**Ta slovenski standard je istoveten z: CEN/TS 15119-2:2008**

**ICS:**

13.020.30	Ocenjevanje vpliva na okolje	Environmental impact assessment
71.100.50	Schutzmittel für Holz	Wood-protecting chemicals

**SIST-TS CEN/TS 15119-2:2008**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST-TS CEN/TS 15119-2:2008

<https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008>

TECHNICAL SPECIFICATION  
 SPÉCIFICATION TECHNIQUE  
 TECHNISCHE SPEZIFIKATION

**CEN/TS 15119-2**

May 2008

ICS 13.020.30; 71.100.50

English Version

**Durability of wood and wood-based products - Determination of emissions from preservative treated wood to the environment - Part 2: Wooden commodities exposed in Use Class 4 or 5 (in contact with the ground , fresh water or sea water) - Laboratory method**

Durabilité du bois et des matériaux à base de bois - Estimation des émissions dans l'environnement du bois traité avec des produits de préservation - Partie 2 : Articles en bois exposés en classe d'emploi 4 ou 5 (en contact avec le sol, l'eau douce ou l'eau de mer) - Méthode de laboratoire

Dauerhaftigkeit von Holz und Holzprodukten - Abschätzung von Emissionen von mit Holzschutzmitteln behandeltem Holz an die Umwelt - Teil 2: Holzprodukte in Gebrauchsklasse 4 und 5 (im Kontakt mit Erde, Süßwasser oder Meerwasser) - Laborverfahren

**iTeh STANDARD PREVIEW**  
 (standards.iteh.ai)

This Technical Specification (CEN/TS) was approved by CEN on 20 November 2007 for provisional application.

The period of validity of this CEN/TS is limited initially to three years. After two years the members of CEN will be requested to submit their comments, particularly on the question whether the CEN/TS can be converted into a European Standard.

CEN members are required to announce the existence of this CEN/TS in the same way as for an EN and to make the CEN/TS available promptly at national level in an appropriate form. It is permissible to keep conflicting national standards in force (in parallel to the CEN/TS) until the final decision about the possible conversion of the CEN/TS into an EN is reached.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION  
 COMITÉ EUROPÉEN DE NORMALISATION  
 EUROPÄISCHES KOMITEE FÜR NORMUNG

**Management Centre: rue de Stassart, 36 B-1050 Brussels**

<b>Contents</b>	<b>Page</b>
Foreword.....	3
Introduction .....	4
1 <b>Scope</b> .....	5
2 <b>Description of the test method</b> .....	5
3 <b>Test report</b> .....	10
<b>Annex A (informative) Recording forms</b> .....	11
<b>Bibliography</b> .....	13

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST-TS CEN/TS 15119-2:2008](https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008>

## Foreword

This document (CEN/TS 15119-2: 2008) has been prepared by Technical Committee CEN/TC 38 “Durability of wood and wood-based products”, the secretariat of which is held by AFNOR.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to announce this Technical Specification: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

This document is derived from a Technical Report (CEN/TR 15119), submitted to OECD as a draft Test Guideline, following a request from OECD for the development of an OECD wide environmental exposure scenario document for wood preservatives in the framework of the EU Biocides Directive 98/8/EC.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST-TS CEN/TS 15119-2:2008](https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008)

<https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008>

## Introduction

The emissions from preservative treated wood to the environment need to be quantified to enable an environmental risk assessment of the treated wood. This document describes a laboratory method for the estimation of emissions from preservative treated wood in the case where the preservative treated wood is not covered and is in contact with the ground, fresh water or seawater. There are three situations in this case where emissions could enter the environment:

- a) emissions from preservative treated wood in contact with the ground. Use Class 4A. Emissions from the surface of the treated wood could enter the soil via the soil water;
- b) emissions from treated wood in contact with fresh water. Use Class 4B. Emissions from the surface of the treated wood could enter the water;
- c) emissions from treated wood in contact with sea water. Use Class 5. Emissions from the surface of the treated wood could enter the sea.

The method is a laboratory procedure for obtaining water samples (emissate) from treated wood in contact with water, at increasing time intervals. The quantities of emissions in the emissate are related to the surface area of the wood and the length of exposure, to estimate a flux in milligrams per square metre per day. The flux after increasing periods of exposure (e.g. 1 year, 10 years) can be estimated.

NOTE The emissate can also be tested for eco-toxicological effects.

The quantity of emissions can be used in an environmental risk assessment of the treated wood.

<https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008>

## 1 Scope

This Technical Specification specifies a laboratory method for obtaining water samples from treated wood which has been in conditions designated to simulate continuous contact with the ground or with water (Use Class 4 or 5), at time intervals after exposure.

## 2 Description of the test method

### 2.1 General considerations

The principal agent for causing emissions from wood exposed to soil is the soil water. The mechanism of leaching at the wood surface by the soil water is assumed to be identical in nature and severity to leaching from a wood surface in continuous contact with water.

The mechanism of leaching at the wood surface by fresh water is assumed to be identical in nature and severity to leaching from a wood surface by seawater.

The wood, in the case of wood treated with a wood preservative, shall be representative of commercially used wood. It shall be treated in accordance with the preservative manufacturer's instructions and in compliance with appropriate standards and specifications. The parameters for the post-treatment conditioning of the wood prior to the commencement of the test shall be stated.

The wood samples used shall be representative of the commodities used.

The composition, amount and pH value of the water used in the test are important in determining the quantity, content and nature of emissions from wood.

Water samples will be taken at a minimum interval of one day and a maximum interval of 7 days, on a sampling scheme covering at least 19 days.

### 2.2 Principle

Water samples are collected after continuous contact with treated wood at increasing time intervals. To simulate the emission of wood preservatives from wood that is exposed to continuous contact with water test specimens are immersed in water and samples of the water are collected at different intervals. The volume of water relative to the surface area exposed to the water is equivalent to the ratio found in wood exposed in service in some Use Class 4 situations (1 m<sup>3</sup> per 40 m<sup>2</sup> or 25 l per m<sup>2</sup>). The water (emissate) is collected and is chemically analysed at seven or more sample times over the 19 days; it is suitable for ecotoxicity testing. Emission rates in milligrams per square metre per day are calculated from analytical results. The sampling periods are recorded. Tests with untreated samples can be discontinued if there is no background detected in the first three data points

### 2.3 Product and reagent

#### 2.3.1 Water

Water complying with grade 3 of EN ISO 3696 or water especially designed for environmental investigations is ideal. Deionised water can also be used. The pH value shall normally be in the range 5 to 7. The pH value shall not be adjusted unless special conditions might justify setting the pH to a specified value between 5 and 7.

Water temperature shall be (20 ± 2) °C.

The pH value and water temperature shall be stated in the test report.

**CEN/TS 15119-2:2008 (E)****2.3.2 Preservative**

The identity of the preservative product used to treat the wood samples shall be stated in the test report. It shall state the name and other designation of the preservative, and the trade or common name of the active ingredient(s), substances of concern (as defined in the EU Directive 98/8/EC) or a generic description of co-formulants and the composition expressed in terms of the mass fraction of each of the ingredients.

**2.4 Apparatus****2.4.1 Immersion container**

The container shall be made of a material that is inert to water and the treated timber and large enough to allow the test specimens to have all their faces exposed to water and to contain sufficient water for the ratio of the exposed surface area of the test specimen to the volume of water to which it is exposed, to be 40 (i.e.  $40 \text{ m}^2 \times \text{m}^{-3}$  or  $0,4 \text{ cm}^2 \times \text{cm}^{-3}$ ). The volume of water required is therefore 25 l per  $\text{m}^2$  of exposed surface area of the test specimen (this is equivalent to  $2,5 \text{ cm}^3$  per  $\text{cm}^2$ ).

NOTE For example, for five wood test specimens 25 mm wide by 50 mm long, 15 mm thick, end sealed, where the surface area exposed to water is  $200 \text{ cm}^2$  the volume of water required is 500 ml.

**2.4.2 Assembly for test specimens**

No equipment used to hold the test specimens below the level of the water shall be made of a material that will react with the water or the treated timber. The test samples should be restrained in a test frame which allows all 5 test specimens to be manoeuvred simultaneously and which allows free access of water to all surfaces.

ITEH STANDARD PREVIEW  
(standards.iteh.ai)

**2.5 Test specimens**

SIST-TS CEN/TS 15119-2:2008

**2.5.1 Species of wood** <https://standards.iteh.ai/catalog/standards/sist/113a3a4a-34d0-41cd-8a31-d164cc99fd0e/sist-ts-cen-ts-15119-2-2008>

The wood species shall be typical of the wood species used for the efficacy testing of wood preservatives e.g. *Pinus sylvestris* (Linnaeus) (Scots pine).

NOTE Additional tests may be made using other species but, if so, this should be stated in the test report.

**2.5.2 Quality of wood and wood moisture content**

Use straight grained wood without knots. Material of a resinous appearance shall be avoided.

NOTE The wood should be typical of wood that is available commercially.

The source, density and number of annual growth rings per 10 mm shall be stated in the test report.

**2.5.3 Size of test specimens**

Wood test specimens have minimum dimensions of 25 mm wide by 50 mm in length, 15 mm thick, with the longitudinal faces parallel to the grain of the wood. Test specimens shall consist of 100 % sapwood. Each test specimen is marked so that it can be identified throughout the test.

The wood test specimens shall be plain sawn and the surfaces shall not be sanded.



#### 2.5.4 Number of test specimens

Two sets of treated test specimens in two immersion containers (2.4.1) are used and the mean value taken as the emission value. One set of untreated test specimens in one immersion container is also used. The number of wood test specimens depends on the specimen's size. The total surface of wood test specimens to be immersed in one immersion container is at least 200 cm<sup>2</sup>, and the minimum number of test specimens per immersion container is three. For one test there is at least nine (three sets of three) test specimens: six test specimens are treated with preservative, three test specimens are untreated. Sufficient test specimens are prepared to allow a selection of six which are within  $\pm 5\%$  of the mean value of the retentions of the group of test specimens, and one for the estimation of the oven dry moisture content of the test specimens before treatment.

NOTE For the minimum size of specimens given in 2.5.3., the number of specimens to obtain 200 cm<sup>2</sup> is 5; the total number of specimens needed is therefore 16: 10 treated, 5 untreated and 1 for the estimation of the oven dry moisture content.

#### 2.5.5 End seal

The end seal shall be a substance which, when applied to the end-grain of test specimens, prevents penetration of the preservative under test.

NOTE Two coats of a silicone sealant have been found to be suitable.

### 2.6 Procedure

#### 2.6.1 General

The test shall be carried out in a room that has a temperature of  $(20 \pm 2)$  °C. The air humidity of the laboratory shall also be monitored.

#### 2.6.2 Preparation of the treated test specimens

All wood test specimens are end sealed with a substance as described in 2.5.5, before treatment. In case of impregnation, it is recommended to apply sealant again after the conditioning period (2.6.3).

The wood test specimen to be treated with the preservative under test shall be weighed and then treated by the method specified by the supplier of the preservative. At the end of the treatment process the test specimens shall be reweighed so that uptakes can be determined.

#### 2.6.3 Conditioning of the test specimens after treatment

After treatment, the treated test specimen shall be conditioned in accordance with the recommendations made by the supplier of the test preservative. A description of the procedures used shall be stated in the test report.

#### 2.6.4 Preparation and selection of test specimens

The mean retention of the group of test specimens shall be calculated and at least six representative test specimens with a retention within  $\pm 5\%$  of the mean for the group shall be selected.

#### 2.6.5 Immersion method

##### 2.6.5.1 Preparation of apparatus

Prior to each test the immersion container (2.4.1) should be washed and dried and the required volume of water (2.3.1 and 2.4.1) should be placed in it.