
Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance —

**Part 8:
Assessment of degree of delamination and corrosion around a scribe**

ISO 4628-8:2005

<https://standards.iteh.org/standards/522/ISO-4628-8-2005> *Peintures et vernis — Évaluation de la dégradation des revêtements — Désignation de la quantité et de la dimension des défauts, et de l'intensité des changements uniformes d'aspect —*

Partie 8: Évaluation du degré de décollement et de corrosion autour d'une rayure



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4628-8:2005

<https://standards.iteh.ai/catalog/standards/sist/52286506-47e8-4ed1-90da-0ca5f63a4dba/iso-4628-8-2005>

© ISO 2005

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

| | |
|--|-----------|
| Foreword | iv |
| Introduction | v |
| 1 Scope | 1 |
| 2 Normative references | 1 |
| 3 Terms and definitions | 1 |
| 4 Principle | 2 |
| 5 Procedure | 2 |
| 6 Calculation and expression of results | 4 |
| 7 Test report | 5 |
| Bibliography | 7 |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 4628-8:2005](https://standards.iteh.ai/catalog/standards/sist/52286506-47e8-4ed1-90da-0ca5f63a4dba/iso-4628-8-2005)

<https://standards.iteh.ai/catalog/standards/sist/52286506-47e8-4ed1-90da-0ca5f63a4dba/iso-4628-8-2005>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 4628-8 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

ISO 4628 consists of the following parts, under the general title *Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance*:

- *Part 1: General introduction and designation system*
- *Part 2: Assessment of degree of blistering*
- *Part 3: Assessment of degree of rusting*
- *Part 4: Assessment of degree of cracking*
- *Part 5: Assessment of degree of flaking*
- *Part 6: Assessment of degree of chalking by tape method*
- *Part 7: Assessment of degree of chalking by velvet method*
- *Part 8: Assessment of degree of delamination and corrosion around a scribe*
- *Part 10: Assessment of degree of filiform corrosion*

ISO 4628-1 defines the system to be used for designating the quantity and size of defects and the intensity of changes in appearance of coatings and outlines the general principles of the system. This system is intended to be used, in particular, for defects caused by ageing and weathering, and for uniform changes such as colour changes, for example yellowing.

The other parts of ISO 4628 provide pictorial standards or other means for evaluating particular types of defect. As far as possible, already existing evaluation schemes have been used as the basis.

Introduction

After exposure of a coated and scribed test panel in a corrosive environment, the following phenomena can occur around the scribe:

- delamination;
- corrosion.

A combination of both phenomena can also occur.

It is recommended that delamination and corrosion around the scribe be evaluated separately to obtain more detailed information about the coating system.

In addition to the procedure described in this part of ISO 4628, assessments of delamination and corrosion around the scribe can be carried out using optical image processing.

Rating of other defects is described in other parts of ISO 4628.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 4628-8:2005](https://standards.iteh.ai/catalog/standards/sist/52286506-47e8-4ed1-90da-0ca5f63a4dba/iso-4628-8-2005)

<https://standards.iteh.ai/catalog/standards/sist/52286506-47e8-4ed1-90da-0ca5f63a4dba/iso-4628-8-2005>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 4628-8:2005

<https://standards.iteh.ai/catalog/standards/sist/52286506-47e8-4ed1-90da-0ca5f63a4dba/iso-4628-8-2005>

Paints and varnishes — Evaluation of degradation of coatings — Designation of quantity and size of defects, and of intensity of uniform changes in appearance —

Part 8:

Assessment of degree of delamination and corrosion around a scribe

1 Scope

This part of ISO 4628 specifies a method for assessing delamination and corrosion, caused by a corrosive environment, around a scribe in a coating on a test panel or other test specimen.

NOTE An example of a corrosive environment is salt spray (fog) as used in the method of exposure described in ISO 7253 or ISO 9227 (see the Bibliography).

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3270, *Paints and varnishes and their raw materials — Temperatures and humidities for conditioning and testing*

ISO 21227-1, *Paints and varnishes — Evaluation of defects on coated surfaces using optical imaging — Part 1: General guidance*

ISO 21227-3, *Paints and varnishes — Evaluation of defects on coated surfaces using optical imaging — Part 3: Assessment of delamination and corrosion around a scribe*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

corrosion

area of visible corrosion products

3.2

delamination

loss of adhesion of a coating

4 Principle

The degree of delamination around a scribe is assessed either directly after the end of the exposure period immediately after removal of the test panel from the exposure environment or after conditioning for a specified period.

The degree of corrosion around the scribe is assessed either immediately after removal of the test panel from the exposure environment or after removal of the coating.

Both the area of delamination and the area of corrosion are determined either by measurement and calculation or by using pictorial standards.

NOTE The extent of other defects may also be determined at the same time as the degree of delamination and degree of corrosion. The methods used are as follows:

- blistering in accordance with ISO 4628-2 [2];
- rusting in accordance with ISO 4628-3 [3];
- cracking in accordance with ISO 4628-4 [4];
- flaking in accordance with ISO 4628-5 [5];
- filiform corrosion in accordance with ISO 4628-10 [6].

iTeh STANDARD PREVIEW (standards.iteh.ai)

5 Procedure

5.1 General

The degree of delamination and degree of corrosion are determined either by measurement and calculation or by comparing the scribes with the pictorial examples given in Figure 1. The measurement and calculation procedures given in 5.2 and 5.3 are generally preferred to the assessment described in 5.4 using pictorial standards.

The assessment of the degree of delamination may be made immediately after removal of the panels from the conditioning environment (see 5.2.1), but can also be carried out after a further conditioning period to determine whether coating adhesion can regenerate itself (see 5.2.2).

The assessment of the degree of corrosion may be made using the coated panel (see 5.3.1) or after stripping off the coating (see 5.3.2).

5.2 Assessment of delamination

5.2.1 Directly after the end of the exposure period

Rinse the test panel with fresh tap water immediately after exposure, blowing off residues of water from the surface using compressed air if necessary, and inspect for visible changes. Carefully remove any loose coating using a knife blade held at an angle, positioning the blade at the coating/substrate interface and lifting the coating away from the substrate.

Depending upon the coating type and degree of delamination, some force may be necessary to remove the coating, but a boundary should be found where the coating becomes tightly adhered to the substrate, this being the limit of delamination.

If desired, compressed air or adhesive tape may be used instead of a knife blade. It is important to remove the loose coating completely.

If necessary, rinse the test panel again with fresh tap water.

Measure, in millimetres, the total width of the zone of delamination at a minimum of six points uniformly distributed along the scribe. Ignore delamination beyond the beginning and end of the original scribe.

Determine the arithmetic mean and record this as the mean overall width of the zone of delamination, d_1 .

5.2.2 After conditioning

The extent to which adhesion can regenerate itself after drying is determined as follows.

Rinse and condition the test panel after exposure. Assess the degree of delamination as described in 5.2.1 after conditioning for 1 h and again after conditioning for 24 h at a temperature of $(23 \pm 2) ^\circ\text{C}$ and a relative humidity of $(50 \pm 5) \%$, as specified in ISO 3270.

5.3 Assessment of corrosion

5.3.1 Directly after the end of the exposure period

Rinse the test panel with fresh tap water immediately after exposure, blowing off residues of water from the surface using compressed air if necessary, and inspect for visible changes. Carefully remove any loose coating using a knife blade held at an angle, positioning the blade at the coating/substrate interface and lifting the coating away from the substrate.

A suitable paint remover or other means, e.g. compressed air or adhesive tape, may be used instead of a knife blade. It is important to remove the loose coating completely.

If necessary, rinse the test panel again with fresh tap water.

Measure, in millimetres, the width of the zone of corrosion at a minimum of six points uniformly distributed along the scribe. Ignore corrosion beyond the beginning and end of the original scribe.

Determine the arithmetic mean and record this as the mean overall width of the zone of corrosion, w_c .

5.3.2 Evaluation of corrosion on stripped test panels

Remove the coating carefully from the test panel with a suitable paint remover that will not exacerbate the corrosion. Rinse the test panel rapidly with clean tap water, blow dry with compressed air and immediately coat completely with a suitable, non-hygroscopic, clear coating material such as an aerosol lacquer.

Rate the zone of corrosion according to the pictorial standards given in Figure 1 or, if possible, measure the area, in square millimetres, using optical imaging as described in ISO 21227-1 and ISO 21227-3. Note any etched areas, which appear bright.

5.4 Assessment using pictorial standards

If required, assess the area of delamination and corrosion using the pictorial standards given in Figure 1.

NOTE These pictorial standards are based on the rating system defined in ISO 4628-1.