

INTERNATIONAL STANDARD

**ISO
9038**

First edition
2002-10-15

Test for sustained combustibility of liquids

Essai de combustion entretenue de liquides

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 9038:2002](https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002)

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>



Reference number
ISO 9038:2002(E)

© ISO 2002

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9038:2002

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Principle	2
5 Apparatus	2
6 Preparation of apparatus	3
7 Samples and sampling	3
8 Procedure	4
9 Interpretation of observations	5
10 Verification and standardization	5
11 Calculation of temperature adjustment	5
12 Precision	6
13 Test report	6

Annexes

iTeh STANDARD PREVIEW

(standards.iteh.ai)

A Combustibility tester.....	7
B Apparatus verification	10

[ISO 9038:2002](https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002)

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 9038 was prepared by Technical Committee ISO/TC 35, *Paints and varnishes*, Subcommittee SC 9, *General test methods for paints and varnishes*.

It cancels and replaces ISO/TR 9038:1991, which has been technically revised.

Annexes A and B form a normative part of this International Standard.

iteh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9038:2002
<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>

Introduction

A product with a flash point within a given range may continue to burn after initial ignition, while a similar product, although it has a similar flash point, may not. This International Standard describes a method for discriminating between those products that, after ignition under controlled laboratory conditions and subsequent removal of the flame, sustain combustion and those which do not.

The method determines whether a flammable product, when maintained at a selected test temperature and under the conditions of test, gives off sufficient flammable vapour at this temperature to cause ignition when an external source of flame is applied in a standard manner, and continues to generate sufficient vapour to burn when the ignition source is removed.

This method of test does not determine the flash point of the product under test but, by means of a pass/fail procedure, merely determines if it sustains combustion at a selected test temperature, as may be required to comply with laws or regulations relating to the storage, transport and use of flammable products. Before performing this test, it will normally be necessary to determine either the actual flash point of the material or the temperature range in which the flash point is located.

The apparatus specified in this International Standard enables a result to be determined by a rapid procedure using a small test portion (2 ml).

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9038:2002](https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002)

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9038:2002

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>

Test for sustained combustibility of liquids

WARNING — The use of this International Standard may involve hazardous materials, operations or equipment. This standard does not purport to address all of the safety problems, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and to determine the applicability of regulatory limitations prior to use.

1 Scope

Many national and international regulations classify liquids as presenting a flammable hazard on the basis of their flash point, as determined by a recognized method. Some of these regulations allow a derogation if the substance cannot “sustain combustion” at some specified temperature or temperatures. This International Standard specifies a pass/fail procedure to determine whether or not a liquid product, that would be classified as “flammable” by virtue of its flash point, has the ability to sustain combustion at the temperature or temperatures specified in the appropriate regulations.

NOTE 1 In the United Nations Recommendations on the Transport of Dangerous Goods, temperatures of 60,5 °C and 75,0 °C are specified.

The procedure is applicable to paints (including water-borne paints), varnishes, paint binders, solvents, petroleum or related products and adhesives, which have a flash point. It is not applicable to painted surfaces in respect of assessing their potential fire hazards.

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f>

NOTE 2 This test method can be used in addition to the test method for flash point in assessing the fire hazard of a product. Particular care needs to be taken in translating results from small-scale tests to large-scale (real-life) situations, as liquids in large quantities may not behave in the same way as small samples because geometry and the surface-to-volume ratio affect rates of heat transfer and evaporation from the surface.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 1513, *Paints and varnishes — Examination and preparation of samples for testing*

ISO 3170, *Petroleum liquids — Manual sampling*

ISO 3171, *Petroleum liquids — Automatic pipeline sampling*

ISO 15528, *Paints, varnishes and raw materials for paints and varnishes — Sampling*

3 Terms and definitions

For the purposes of this International Standard, the following terms and definitions apply.

3.1

sustained combustibility

the behaviour of a material, under specified test conditions, whereby its vapour can be ignited by an external ignition source and, after ignition, sufficient flammable vapour is produced for burning to continue after the source of ignition has been removed

3.2

flash point

the lowest temperature of a test portion, corrected to a barometric pressure of 101,3 kPa, at which application of an ignition source causes the vapour of the test portion to ignite, under the specified conditions of test

4 Principle

A specified volume of sample is introduced into a concave depression, the test portion well, in a metal block that is maintained at the test temperature. After a specified time a test flame is applied.

The ability of the product to sustain combustion is assessed on the basis of its ability to ignite, when exposed to a test flame, and whether it continues to burn after the standard flame has been removed, under the specified conditions of test.

5 Apparatus

5.1 Combustibility tester, as specified in annex A.

5.2 Hotplate or other suitable heating device, fitted with a temperature control device and which, in contact with the bottom of the combustibility tester, provides efficient transfer of heat. The heater control is required to maintain the combustibility tester at the equilibrium temperature, as measured on the integral thermometer (5.4), in a draught-free area, to within $\pm 0,5$ °C for test temperatures up to and including 100 °C.

NOTE 1 The combustibility tester, heater and heater control unit may consist of an integrated apparatus.

NOTE 2 Heating is at or near the base of the aluminium block.

5.3 Gauge, for checking that the height of the centre of the gas jet above the top of the test portion well is $(2,2 \pm 0,1)$ mm. A calibrated metal strip is suitable.

5.4 Thermometer or other suitable temperature-measuring device. A mercury-in-glass thermometer is recommended. This shall be suitable for horizontal operation, of appropriate range and dimensions, with graduations every 1 °C up to 100 °C and be capable of measuring the temperature of the block to an accuracy of $\pm 0,5$ °C. If another temperature-measuring device is used, it shall be of equivalent sensitivity, permitting readings at 0,5 °C intervals. When in position in the block, the thermometer bulb or temperature-measuring sensor shall be surrounded with heat-transfer paste to ensure good heat transfer between the block and the measuring device.

NOTE It is recommended that the accuracy of the thermometer or other measuring device be checked, annually or when indicated by a verification check schedule, by an authorized laboratory or by comparison against a calibrated thermometer with a valid calibration certificate, using the stipulated immersion depth.

5.5 Stopwatch or other suitable timing device, capable of measuring (15 ± 1) s, (30 ± 1) s and (60 ± 2) s. The timing device may be fitted with a means of producing an audible signal.

5.6 Syringe, capable of delivering 2 ml to an accuracy of $\pm 0,05$ ml.

5.7 Test flame and gas supply. The flame may be fuelled by natural gas, coal gas, butane or any other gas found to be suitable. The fuel supply to the gas jet shall be fitted with a suitable regulator, or other means of regulating the gas flow, such that the width of the flame can be adjusted to $(4,0 \pm 0,5)$ mm.

5.8 Draught shield, to minimize draughts, fitted at the back and two sides of the instrument. A shield 350 mm high, 480 mm wide and 240 mm deep is suitable.

NOTE The air speed within 50 mm of the top of the test portion well should preferably be less than 0,05 m/s.

5.9 Barometer, readable to, and with an accuracy of, 0,1 kPa (1 mbar). Do not use aneroid barometers pre-corrected to give sea level readings, such as those used at weather stations and airports.

6 Preparation of apparatus

WARNING — Do not carry out the test in a small confined area (for example a glove box) because of the risk of explosions.

Thoroughly clean and dry the test portion well and assembly before use, taking care not to damage the surface of the well.

Position the metal block on the hotplate (5.2) and place the assembly, or the integral unit, on a level, stable surface and away from strong light (to facilitate observation of a flash, flame, etc.). Ensure that the top of the metal block is exactly horizontal.

Use the gauge (5.3) to check that the jet is $(2,2 \pm 0,1)$ mm above the top of the block (see Figure A.2).

It is essential that the apparatus is set up in a completely draught-free area (see warning above). It may be necessary to surround the tester on three sides with a draught shield (5.8) for protection. If a fume hood is used, minimize the exhaust draught.

NOTE Because the combustibility tester has an open test portion well, it is recommended that the apparatus is always used with a draught shield in place.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

7 Samples and sampling

ISO 9038:2002

<https://standards.iteh.ai/catalog/standards/sist/2b5239be-3d19-4292-871f-3bee713e2b3a/iso-9038-2002>

7.1 Products

7.1.1 Paints, varnishes and related products

Take a representative sample of the product to be tested, as described in ISO 15528, and examine and prepare it for testing, as described in ISO 1513.

7.1.2 Petroleum and related products

Take a representative sample of the product to be tested, as described in ISO 3170 or ISO 3171, as appropriate.

7.1.3 Other products

For products other than paints and petroleum-based materials, e.g. aqueous solutions of alcohols, exercise suitable care to ensure that a representative sample of the product is removed for testing.

7.2 Procedure

A 2 ml test portion is required for each test. Obtain a sample of at least 50 ml of product and store in a clean, tightly closed container in a cool place to minimize vapour loss or pressure build-up. The container shall be made of a material appropriate to the product being sampled and be filled to between 85 % and 95 % of its capacity.

Because of the possibility of loss of volatile constituents, the sample shall receive only the minimum treatment to ensure its homogeneity. After removing each test portion, immediately close the sample container tightly to ensure