



**SLOVENSKI STANDARD**  
**SIST ISO 15237:2005**

**01-november-2005**

---

**Trda mineralna goriva – Določevanje celotnega živega srebra v premogu**

Solid mineral fuels -- Determination of total mercury content of coal

Combustibles minéraux solides -- Dosage du mercure total dans le charbon

**Ta slovenski standard je istoveten z: ISO 15237:2003**

[SIST ISO 15237:2005](https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005)

<https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005>

**ICS:**

73.040            Premogi    Coals

**SIST ISO 15237:2005**    **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 15237:2005

<https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005>

INTERNATIONAL  
STANDARD

ISO  
15237

First edition  
2003-12-01

---

---

**Solid mineral fuels — Determination of  
total mercury content of coal**

*Combustibles minéraux solides — Dosage du mercure total dans le  
charbon*

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 15237:2005](https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005)

<https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005>



Reference number  
ISO 15237:2003(E)

© ISO 2003

**ISO 15237:2003(E)****PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 15237:2005](https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005)

<https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 749 09 47  
E-mail [copyright@iso.org](mailto:copyright@iso.org)  
Web [www.iso.org](http://www.iso.org)

Published in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15237 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 15237:2005](https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005)

<https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005>

**ISO 15237:2003(E)****Introduction**

Mercury occurs naturally in coal. It is an element that can be released during the combustion process.

The determination of the total mercury content of coal cannot be accomplished satisfactorily by traditional ashing and digestion procedures because of the volatility of the element.

Quantitative recovery can be achieved by strict adherence to the procedure set out in this International Standard.

Instrumental methods for a more rapid determination of total mercury content are available. If such a method is to be used, it is important to demonstrate that the method is free from bias, when compared to this reference method and will give levels of repeatability and reproducibility which are the same, or better than, those quoted for the reference method (see Clause 9).

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST ISO 15237:2005](https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005)

<https://standards.iteh.ai/catalog/standards/sist/884de629-248e-45ae-8434-743d8aa0f745/sist-iso-15237-2005>

# Solid mineral fuels — Determination of total mercury content of coal

## 1 Scope

This International Standard specifies a procedure for the determination of the total mercury content of coal.

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 331, *Coal — Determination of moisture in the analysis sample — Direct gravimetric method*

ISO 1170, *Coal and coke — Calculation of analyses to different bases*

ISO 1928:1995, *Solid mineral fuels — Determination of gross calorific value by the bomb calorimetric method, and calculation of net calorific value*

ISO 3696, *Water for analytical laboratory use — Specifications and test methods*

ISO 5068, *Brown coals and lignites — Determination of moisture content — Indirect gravimetric method*

ISO 5069-2, *Brown coals and lignites — Principles of sampling — Part 2: Sample preparation for determination of moisture content for general analysis*

ISO 13909-2, *Hard coal and coke — Mechanical sampling — Part 2: Coal — Sampling from moving streams*

## 3 Principle

The sample is burned in an oxygen bomb, the mercury species formed during combustion being absorbed in water. The mercury species present in the water are reduced by stannous chloride and quantified by flameless cold vapour atomic absorption spectroscopy.

**NOTE** It is reported that lithium borohydride ( $\text{LiBH}_4$ ) and sodium borohydride ( $\text{NaBH}_4$ ) are satisfactory for the reduction instead of stannous chloride; laboratories using these reductants should demonstrate that the performance is equivalent to that using stannous chloride.

## 4 Reagents

**WARNING — Care should be exercised when handling the reagents, many of which are toxic and corrosive.**

During the analysis, unless otherwise stated, use only reagents of recognized analytical grade.

## ISO 15237:2003(E)

**4.1 Water**, conforming to Grade 1 of ISO 3696.

**4.2 Oxygen**, free from combustible matter and having a purity of at least 99,5 %.

**4.3 Nitric acid solution**, 10 % by volume, prepared by diluting 100 ml of concentrated nitric acid (relative density 1,42) to 1 litre with water. The 10 % solution shall have a mercury content less than 0,1 µg/l.

**4.4 Mercury standard stock solution**, 1 000 µg/ml, prepared by dissolving 1,0 g of high purity mercury in 5 ml of 25 % (V/V) nitric acid solution and diluting to 1 000 ml.

NOTE 1 The mercury standard stock solution may also be prepared from commercially available certified mercury solution.

NOTE 2 Other high purity (> 99,9 % ) mercury salts or oxides may be used with appropriate adjustment of the mass taken.

**4.5 Mercury standard solution**, 0,1 µg/ml, prepared by diluting 5,0 ml of mercury standard stock solution (4.4) to 500 ml with water and then diluting 10,0 ml of the intermediate solution to 1 litre with water.

This mercury standard solution should be prepared daily.

**4.6 Potassium permanganate solution**, 50 g/l, prepared by dissolving 5 g of potassium permanganate (KMnO<sub>4</sub>) in water and diluting to 100 ml.

The mercury content of the potassium permanganate should be below 0,05 µg/g

**4.7 Hydroxylammonium chloride solution**, 15 g/l, prepared by dissolving 1,5 g of hydroxylammonium chloride (HONH<sub>3</sub>Cl) in water and diluting to 100 ml.

The mercury content of the hydroxylammonium chloride should be below 0,005 µg/g.

**4.8 Reducing agent, stannous chloride solution**, 100 g/l, prepared by dissolving 10 g of stannous chloride dihydrate (SnCl<sub>2</sub>·2H<sub>2</sub>O) in 45 ml of concentrated hydrochloric acid solution (relative density 1,19) and cautiously diluting to 100 ml with water.

The mercury content of the stannous chloride dihydrate should be below 0,01 µg/g.

NOTE See also note 1 to 9.2 regarding the use of flow injection techniques.

## 5 Apparatus

**5.1 Balance**, capable of weighing to the nearest 0,1 mg.

**5.2 Oxygen combustion bomb**, constructed in accordance with ISO 1928:1995. The ignition wire shall be platinum or chromium-nickel alloy. The combustion bomb shall be constructed of materials that are not affected by the combustion process or products. In particular, the combustion bomb shall be constructed of material that is free from mercury. This can be verified by washing the interior surfaces with dilute nitric acid (50 ml, 10 % V/V), and determining the mercury content of the washings. This shall be < 0,01 µg per bomb. The combustion bomb shall also be designed so that all liquid combustion products can be completely recovered.

**WARNING — The combustion bomb should be inspected regularly for signs of corrosion caused by the strong acid used in the procedure.**

**5.3 Silica combustion crucible**, to fit oxygen combustion bomb.

**5.4 Atomic absorption spectrometer**, with a flameless cold-vapour mercury analysis system, comprised of either a closed recirculating system or an open one-pass system.



## 6 Preparation of sample

The test sample is the general analysis test sample prepared in accordance with ISO 5069-2 or ISO 13909-2 as appropriate. Ensure that the moisture content of the sample is in equilibrium with the laboratory atmosphere, exposing it if necessary, in a thin layer for the minimum time required to achieve equilibrium.

Before commencing the determination, mix the equilibrated sample for at least 1 min, preferably by mechanical means.

If the results are to be calculated other than on the "air-dried" basis (see Clause 10), then, after weighing the test portion, determine the moisture content of a further portion of the test sample by the method described in ISO 331 or ISO 5068 as appropriate.

## 7 Oxygen bomb combustion procedure

### 7.1 General

Clean all internal components of the combustion bomb (the body, cap and electrodes) by immersion in 10 % nitric acid solution for 5 min followed by thorough washing with water before use. Using paper towels, dry the threads on the combustion bomb body and locking ring. Repeat the washing step between each determination.

### 7.2 Combustion of coal

Weigh approximately 1 g of test portion, to the nearest 0,1 mg, into a pre-ignited crucible.

Assemble the ignition system using ignition wire and ignition thread.

Pipette 10 ml of water into the base of the combustion bomb and assemble.

Charge the bomb with oxygen (4.2) to 3 MPa pressure.

Place the assembled combustion bomb in the calorimeter can containing 2 litres of water and fire using the ignition/firing station. Allow the combustion bomb to stand in the calorimeter can for 10 min before removal.

Dry external surfaces of the bomb thoroughly with paper towel, keeping the bomb upright, before carefully venting the bomb gases over a period of 2 min.

## 8 Preparation of test solution

Disassemble the combustion bomb and carefully rinse all internal surfaces, including the crucible, with water, collecting all washings in the bomb.

Using a disposable syringe, transfer the bomb washings to a 100 ml volumetric flask containing 10 ml of 10 % nitric acid solution (4.3). Wash the bomb with water, adding the washings to the volumetric flask. Add 0,5 ml of potassium permanganate solution (4.6) and mix. Dilute to volume with water.

Carry out a blank determination following exactly the procedure described above but omitting the coal sample.

In those cases where the design of the bomb precludes a 1 g test portion being used, a suitable smaller quantity should be taken.

**NOTE** The transfer of the bomb washings by syringe is important since it has been shown that the bomb locking ring in some calorimeters is a source of mercury contamination which is transferred to the threads of the body. If the bomb washings are poured out in these cases, significant mercury contamination results due to contact between washings and the threads on the bomb body. For calorimeter types initially shown to give no contamination, the transfer by syringe is not necessary. In every analysis, the documentation for this is achieved by the blank determination.