



**SLOVENSKI STANDARD**  
**SIST ISO 15247:2001**  
**01-junij-2001**

---

Prečiščeni koncentracijski pripravki žvepovih sulfidov -- Določitev vsebnosti srebra -- Kislinska raztopitev in absorpcijska spektrometrija v plamni

Zinc sulfide concentrates -- Determination of silver content -- Acid dissolution and flame atomic absorption spectrometric method

**iTeh STANDARD PREVIEW**

Concentrés sulfurés de zinc -- Dosage de l'argent -- Méthode par dissolution acide et spectrométrie d'absorption atomique dans la flamme

[SIST ISO 15247:2001](https://standards.itih.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a516dc10f42c/sist-iso-15247-2001)

Ta slovenski standard je istoveten z: **ISO 15247:1999**

---

**ICS:**

73.060.99      Druge rude      Other metalliferous minerals

**SIST ISO 15247:2001**      **en**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 15247:2001

<https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>

INTERNATIONAL  
STANDARDISO  
15247First edition  
1999-04-15

---

---

**Zinc sulfide concentrates — Determination  
of silver content — Acid dissolution and  
flame atomic absorption spectrometric  
method***Concentrés sulfurés de zinc — Dosage de l'argent — Méthode par  
dissolution acide et spectrométrie d'absorption atomique dans la flamme*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

SIST ISO 15247:2001

<https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.



Reference number  
ISO/FDIS 15247:1999(E)

## ISO 15247:1999(E)

Contents	Page
1 Scope .....	1
2 Normative references .....	1
3 Principle .....	1
4 Reagents .....	2
5 Apparatus .....	3
6 Sample .....	3
7 Procedure .....	3
8 Expression of results .....	5
9 Precision .....	5
10 Test report .....	7
Annex A (normative) Procedure for the preparation and determination of the mass of a predried test portion.....	8
Annex B (normative) Flowsheet of the procedure for the acceptance of analytical values for test samples .	10
Annex C (informative) Derivation of precision equations .....	11

<https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>

© ISO 1999

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization  
 Case postale 56 • CH-1211 Genève 20 • Switzerland  
 Internet iso@iso.ch

Printed in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 15247 was prepared by Technical Committee ISO/TC 183, *Copper, lead and zinc ores and concentrates*.

Annexes A and B form an integral part of this International Standard, annex C is for information only.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 15247:2001](https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001)

<https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

SIST ISO 15247:2001

<https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>

# Zinc sulfide concentrates — Determination of silver content — Acid dissolution and flame atomic absorption spectrometric method

## 1 Scope

This International Standard specifies an acid dissolution and flame atomic absorption spectrometric method for the determination of silver content of zinc sulfide concentrates.

The method is applicable to the determination of silver in zinc sulfide concentrates containing up to 60 % (m/m) zinc in the form of zinc blende and related materials.

The method is applicable to silver contents from 10 g/t to 500 g/t.

iteh STANDARD PREVIEW  
(standards.iteh.ai)

## 2 Normative references

[SIST ISO 15247:2001](https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf042c/sist-iso-15247-2001)

[https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-](https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf042c/sist-iso-15247-2001)

[a316dcf042c/sist-iso-15247-2001](https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf042c/sist-iso-15247-2001)

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 385-1:1984, *Laboratory glassware — Burettes — Part 1: General requirements.*

ISO 648:1977, *Laboratory glassware — One mark pipettes.*

ISO 1042:1998, *Laboratory glassware — One-mark volumetric flasks.*

ISO 3696:1987, *Water for analytical laboratory use — Specification and test methods.*

ISO 4787:1984, *Laboratory glassware — Volumetric glassware — Methods for use and testing of capacity.*

ISO 9599:1991, *Copper, lead and zinc sulfide concentrates — Determination of hygroscopic moisture in the analysis sample — Gravimetric method.*

## 3 Principle

Decomposition of the concentrate in hydrochloric and nitric acids. Dissolution of the digestion residue in hydrochloric acid and measurement by flame atomic absorption at 328,1 nm.

## 4 Reagents

During the analysis, use only reagents of recognized analytical grade and water that complies with grade 2 of ISO 3696.

**4.1 Silver metal**, minimum 99,99 % purity.

**4.2 Nitric acid**, ( $\rho_{20}$  1,42 g/ml), chloride content < 0,5 µg/ml.

**4.3 Nitric acid**, (500 ml/l).

To 250 ml of water carefully add, with stirring, 250 ml of nitric acid (4.2).

**4.4 Hydrochloric acid**, ( $\rho_{20}$  1,16 g/ml to 1,19 g/ml).

**4.5 Hydrochloric acid**, (200 ml/l).

To 800 ml of water carefully add, with stirring, 200 ml of hydrochloric acid (4.4).

**4.6 Ammonia solution**, ( $\rho_{20}$  0,89 g/ml).

**4.7 Ammonia solution**, (250 ml/l).

To 750 ml of water add, with stirring, 250 ml of ammonia solution (4.6).

**4.8 Silver standard solutions** STANDARD PREVIEW  
(standards.iteh.ai)

**4.8.1 Silver standard solution**, (1 000 µg/ml)

Weigh 0,500 0 g of silver metal (4.1) into a 250 ml conical beaker, add 50 ml of nitric acid (4.3), cover and heat gently until the metal dissolves. Remove the cover and evaporate gently to near dryness. Add 250 ml of hydrochloric acid (4.4) and warm until the solution clears. Cool, and transfer to a 500 ml volumetric flask. Dilute to volume with water and mix thoroughly.

This solution should be freshly prepared, unless it is being used on a regular basis.

**4.8.2 Silver standard solution**, (100 µg/ml)

Pipette 10 ml of silver standard solution (4.8.1) into a 100 ml volumetric flask containing 45 ml of hydrochloric acid (4.4). Dilute to volume with water and mix thoroughly.

NOTE 1 Standard solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.

NOTE 2 Silver standard solutions should be stored in brown glass bottles.

## 4.9 Calibration solutions

To six 100 ml volumetric flasks, each containing 20 ml of hydrochloric acid (4.4), add from a burette (5.2) 0 ml, 1 ml, 2 ml, 3 ml, 4 ml and 5 ml of silver standard solution (4.8.2). Dilute to volume with water and mix thoroughly.

These standards contain 0 µg, 1 µg, 2 µg, 3 µg, 4 µg and 5 µg of silver per ml and shall be freshly prepared.

NOTE Calibration solutions should be prepared at the same ambient temperature as that at which the determinations will be conducted.



## 5 Apparatus

Ordinary laboratory apparatus and

**5.1 Volumetric glassware**, of class A complying with ISO 385-1, ISO 648 and ISO 1042 and used in accordance with ISO 4787.

**5.2 Burette**, grade A 10 ml capacity, capable of being read to 0,02 ml.

**5.3 Atomic absorption spectrometer (AAS)**, equipped with a glass bead in the spray chamber rather than a flow spoiler.

**5.4 Balance**, precision analytical, capable of being read to 0,1 milligram.

## 6 Sample

### 6.1 Test sample

Prepare an air-equilibrated test sample in accordance with ISO 9599.

NOTE A test sample is not required if predried test portions are to be used (see annex A).

### 6.2 Test portion

Taking multiple increments, extract a test portion from the test sample in such a manner that it is representative of the whole contents of the dish or tray. Weigh to the nearest 0,1 mg approximately 1 g of test sample. At the same time as the test portion is weighed, weigh test portions for the determination of hygroscopic moisture in accordance with ISO 9599.

Alternatively, the method specified in annex A may be used to prepare predried test portions directly from the laboratory sample.

## 7 Procedure

### 7.1 Number of determinations

Carry out the determinations at least in duplicate and as far as possible under repeatability conditions, on each test sample.

NOTE Repeatability conditions exist where mutually independent test results are obtained with the same method on identical test material in the same laboratory by the same operator using the same equipment within short intervals of time.

### 7.2 Blank test

Carry out a blank test in parallel with the analysis using all reagents specified in the determination but omitting the test portion. The purpose of the blank test in this method is to check the quality of the reagents. If a significant blank value is obtained as a result of the blank test, check all reagents and rectify the problem.

### 7.3 Decomposition of test portion

Transfer the test portion to a 250 ml conical beaker and moisten with 1 ml of water.

NOTE 1 All glassware should be washed in ammonia (4.7) and rinsed with water prior to use to remove any silver adhering to the glass surface.

Add 35 ml of nitric acid (4.3), cover with a watch glass and heat at a low temperature until the reaction ceases.

Add 10 ml of hydrochloric acid (4.4), raise the cover slightly and evaporate to dryness. Remove from the hotplate and cool.

Add a further 10 ml of hydrochloric acid (4.4) and again evaporate to dryness.

NOTE 2 Rapid heating may cause samples to splatter or spit. Care should be taken to ensure that this does not occur.

Redissolve in 25 ml of hydrochloric acid (4.5). Heat to boiling, remove from the hotplate and cool.

Transfer the solution to the volumetric flask indicated in Table 1 by washing and diluting to volume with hydrochloric acid (4.5).

**Table 1 — Volumetric flask size**

Ag content g/t	Volumetric flask ml
10 to 250	50
250 to 500	100

#### 7.4 Determination of silver

Determine the silver content of the test portion by flame atomic absorption spectrometry using calibration solutions (4.9). As a guide, the following atomic absorption settings are recommended; however, the instrument should be optimized to give maximum sensitivity and as near as practical to a linear relationship between absorbance and concentration.

- Flame: air-acetylene (oxidizing) <https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>
- Wavelength: 328,1 nm <https://standards.iteh.ai/catalog/standards/sist/a6a66327-a993-4902-b166-a316dcf0f42c/sist-iso-15247-2001>
- Lamp current: 5 mA
- Background correction: none
- Aspiration rate: optimize for maximum signal
- Integration time: 3 s
- Number of integrations: 5

Perform three measurements on each standard solution. Calculate, to three significant figures, the mean absorbance for each standard solution, provided that the range of values does not exceed 0,003 absorbance units. If this range is exceeded, repeat the calibration.

The test solutions should be treated in the same manner. Plot a calibration graph of absorbance versus concentration of silver.

NOTE During all FAAS determinations, the test solutions and calibration solutions should have the same temperature as well as the same acid concentrations.

## 8 Expression of results

The silver content of the test portion,  $w_{\text{Ag}}$ , expressed in grams per tonne, is given by the following equation:

$$w_{\text{Ag}} = \frac{C \times V}{m} \times \frac{100}{100 - H} \quad (1)$$

where

$C$  is the silver content of the analysis solution, in micrograms per millilitre;

$V$  is the volume of the analysis solution, in millilitres (see 7.3);

$m$  is the mass of the test portion, in grams;

$H$  is the hygroscopic moisture content, as a percentage of the test portion (in the case of a predried test portion being used,  $H = 0$ ).

## 9 Precision

### 9.1 Expression of precision

The precision of this analytical method is expressed by the following equations:

$$s_r = 0,009 5 \bar{X} + 0,182 6 \quad (2)$$

$$s_L = 0,031 1 \bar{X} + 0,881 3 \quad (3)$$

where

$\bar{X}$  is the mean content of silver, in grams per tonne, in the sample;

$s_r$  is the within-laboratory standard deviation, in grams of silver per tonne;

$s_L$  is the between-laboratories standard deviation, in grams of silver per tonne.

NOTE Additional information is given in annex C.

### 9.2 Method for obtaining the final result

See annex B.

Calculate the following quantities from the duplicate results  $X_1$  and  $X_2$  and process according to the flowchart in annex B:

Mean of duplicates	$\bar{X} = (X_1 + X_2)/2$	(4)
--------------------	---------------------------	-----

Within-laboratory standard deviation	$s_r = 0,009 5 \bar{X} + 0,182 6$	(2)
--------------------------------------	-----------------------------------	-----

Repeatability limit	$r = 2,8s_r$	(5)
---------------------	--------------	-----

### 9.3 Precision between laboratories

The precision between laboratories is used to determine the agreement between the results reported by two (or more) laboratories. It is assumed that all laboratories followed the same procedure.