



SLOVENSKI STANDARD SIST EN ISO 21068-1:2008

01-december-2008

Kemijska analiza surovin in ognjevzdržnih izdelkov s silicijevim karbidom - 1. del: Splošne informacije in priprava vzorcev (ISO 21068-1:2008)

Chemical analysis of silicon-carbide-containing raw materials and refractory products -
Part 1: General information and sample preparation (ISO 21068-1:2008)

Chemische Analyse von Siliciumcarbid enthaltenden Rohstoffen und feuerfesten
Erzeugnissen - Teil 1: Allgemeine Angaben und Probenvorbereitung (ISO 21068-1:2008)

Analyse chimique des matières premières et des produits réfractaires contenant du
carbure de silicium - Partie 1: Informations générales et préparation des échantillons
(ISO 21068-1:2008)

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>

Ta slovenski standard je istoveten z: EN ISO 21068-1:2008

ICS:

81.080 Ognjevzdržni materiali Refractories

SIST EN ISO 21068-1:2008 en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 21068-1:2008

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 21068-1

August 2008

ICS 81.080

English Version

**Chemical analysis of silicon-carbide-containing raw materials
and refractory products - Part 1: General information and sample
preparation (ISO 21068-1:2008)**

Analyse chimique des matières premières et des produits
réfractaires contenant du carbure de silicium - Partie 1:
Informations générales et préparation des échantillons (ISO
21068-1:2008)

Chemische Analyse von Siliciumcarbid enthaltenden
Rohstoffen und feuerfesten Erzeugnissen - Teil 1:
Allgemeine Angaben und Probenvorbereitung (ISO 21068-
1:2008)

This European Standard was approved by CEN on 11 July 2008.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

Page

Foreword.....3

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

SIST EN ISO 21068-1:2008

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>

Foreword

This document (EN ISO 21068-1:2008) has been prepared by Technical Committee ISO/TC 33 "Refractories" in collaboration with Technical Committee CEN/TC 187 "Refractory products and materials" the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by February 2009, and conflicting national standards shall be withdrawn at the latest by February 2009.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW Endorsement notice (standards.iteh.ai)

The text of ISO 21068-1:2008 has been approved by CEN as a EN ISO 21068-1:2008 without any modification.

[SIST EN ISO 21068-1:2008
https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008](https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008)

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 21068-1:2008

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>

INTERNATIONAL
STANDARD

ISO
21068-1

First edition
2008-08-01

**Chemical analysis of silicon-carbide-
containing raw materials and refractory
products —**

**Part 1:
General information and sample
preparation**

iTeh STANDARD PREVIEW

(standards.iteh.ai)
*Analyse chimique des matières premières et des produits réfractaires
contenant du carbure de silicium —*

Partie 1: Informations générales et préparation des échantillons

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>



Reference number
ISO 21068-1:2008(E)

© ISO 2008

ISO 21068-1:2008(E)**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN ISO 21068-1:2008](https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2008

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction	v
1 Scope	1
2 Normative references	3
3 Definitions	3
4 Sampling and preparation of the test sample	4
4.1 General	4
4.2 Sample pretreatment	4
5 Preliminary analyses	5
6 Expression of results	6
7 Test report	6
Bibliography	7

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN ISO 21068-1:2008](https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008)

<https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ffa880/sist-en-iso-21068-1-2008>

ISO 21068-1:2008(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 21068-1 was prepared by Technical Committee ISO/TC 33, *Refractories*

ISO 21068 consists of the following parts, under the general title *Chemical analysis of silicon-carbide-containing raw materials and refractory products*:

- *Part 1: General information and sample preparation*
- *Part 2: Determination of loss on ignition, total carbon, free carbon and silicon carbide, total and free silica and total and free silicon*
- *Part 3: Determination of nitrogen, oxygen and metallic and oxidic constituents*

Introduction

ISO 21068, Parts 1 to 3, have been developed from the combination of a Japanese standard JIS 2011 [2] and work items originally developed within CEN. As there is a wide variety of laboratory equipment in use, the most commonly used methods are described.

ISO 21068, Parts 1 to 3, are applicable to the analysis of all refractory products as classified in ISO 10081 [10] to [13] (shaped) and ISO 1927 [3] (unshaped) and raw materials containing carbon and/or silicon carbide. Therefore, ISO 21068, Parts 1 to 3, covers the full range of analysis from pure silicon carbide to oxidic refractory composition with low-content silicon carbide and/or nitrides. Primarily, ISO 21068, Parts 1 to 3, provides methods to distinguish between different carbon bound types like total carbon (C_{total}) and free carbon (C_{free}) and derives from these two the silicon carbide content.

If free carbon is present, the standard includes different types of temperature treatment in order to determine the mass changes gravimetrically. Frequently, the resulting residue is used for other determinations.

The determination of other groups of analytes described in ISO 21068, Parts 1 to 3, are free metals, free silicon (S_{free}), free aluminum (Al_{free}), free magnesium (Mg_{free}), free iron (Fe_{free}) and the group of oxides from main to trace components.

ISO 21068, Parts 1 to 3, also describe the chemical analysis of silicon dioxide, total silicon, oxygen and nitrogen and other oxidic bound metals that typically occur in the materials.

It represents a listing of analytical methods which is approximately structured according to material composition. However, it is still the user who should prove the applicability of the method depending on the material and analytical requirements. [SIST EN ISO 21068-1:2008](https://standards.iteh.ai/catalog/standards/sist/741d89e3-d58b-4c64-b040-971ea8ff880/sist-en-iso-21068-1-2008)

The most broadly used analytical techniques such as X-ray fluorescence spectroscopy (XRF) and inductively coupled plasma-optical emission spectrometry (ICP-OES) suffer from the disadvantage that the analytical results are chemical bond independent. For carbon-containing ceramic raw materials and compositions ISO 21068, Parts 1 to 3, provide analytical methods for the determination of free carbon, and SiC in the presence of oxidic compounds in particular SiO_2 .

Because of the diversity of laboratory equipment, the three parts of ISO 21068 summarize broadly used analytical techniques which lead to equivalent results. In principle, the determination of carbon is based in all itemized methods on the oxygen extraction method, where carbon is oxidized at elevated temperatures. Thereafter carbon is analysed as CO_2 .

As well as carbon and carbidic compounds, metallic silicon, aluminium and magnesium are considered. While metallic silicon is in majority a precursor material which remains after the production process of SiC in the raw material, metallic aluminium is added as an antioxidant in carbon-containing refractory formulations.

Mostly oxidic bound components, such as Al_2O_3 , CaO, MgO, TiO_2 , Cr_2O_3 , ZrO_2 and alkalines, can be determined by XRF as described in ISO 12677, ICP-AES or wet chemical methods (see ISO 26845 [25], ISO 21587-1 [22] and ISO 21587-3 [24]). These results can be corrected by formulas provided by ISO 21068, Parts 1 to 3, in consideration of the values obtained by the determination of carbon, SiC, and metallic components.

ISO 21068, Parts 1 to 3, also provide methods for qualitative and quantitative determinations of the nitrogen content and the determination of oxygen. Thereby only the total content of nitrogen and oxygen is given; a precise determination of non-carbide components (oxides and nitrides) is not possible in this way.

ISO 21068, Parts 1 to 3, do not provide methods to distinguish quantitatively between different varieties of nitrides like silicon nitride, silicon oxy-nitride and sialon. For further information about the determination of this group of compounds, see EN 12698-2.