



# SLOVENSKI STANDARD

## SIST EN 197-1:2011

01-december-2011

### Nadomešča:

SIST EN 197-1:2001

SIST EN 197-1:2001/A1:2004

SIST EN 197-1:2001/A3:2008

SIST EN 197-1:2001/oprA2:2006

SIST EN 197-4:2004

SIST EN 197-4:2004/oprA1:2006

---

### Cement - 1. del: Sestava, zahteve in merila skladnosti za običajne cemente

iTeh STANDARD PREVIEW

Cement - Part 1: Composition, specifications and conformity criteria for common cements

[SIST EN 197-1:2011](https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-1940-400000000000/sist-en-197-1-2011)

[https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-](https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-1940-400000000000/sist-en-197-1-2011)

Zement - Teil 1: Zusammensetzung, Anforderungen und Konformitätskriterien für Normalzement

Ciment - Partie 1: Composition, spécifications et critères des conformité des ciments courants

**Ta slovenski standard je istoveten z: EN 197-1:2011**

---

### ICS:

91.100.10 Cement. Mavec. Apno. Malta Cement. Gypsum. Lime.  
Mortar

**SIST EN 197-1:2011**

**en,fr,de**

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[SIST EN 197-1:2011](#)

<https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011>

EUROPEAN STANDARD

**EN 197-1**

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2011

ICS 91.100.10

Supersedes EN 197-1:2000, EN 197-4:2004

English Version

**Cement - Part 1: Composition, specifications and conformity  
criteria for common cements**Ciment - Partie 1 : Composition, spécifications et critères  
des conformité des ciments courantsZement - Teil 1: Zusammensetzung, Anforderungen und  
Konformitätskriterien von Normalzement

This European Standard was approved by CEN on 6 August 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

**SIST EN 197-1:2011**

[https://standards.iteh.ai/catalog/standards/sist/623e3e0-610e-4937-9d040e375534/sist-en-197-1-2011](https://standards.iteh.ai/catalog/standards/sist/623e3e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011)

EUROPEAN COMMITTEE FOR STANDARDIZATION  
COMITÉ EUROPÉEN DE NORMALISATION  
EUROPÄISCHES KOMITEE FÜR NORMUNG**Management Centre: Avenue Marnix 17, B-1000 Brussels**

<b>Contents</b>	<b>Page</b>
Foreword.....	4
Introduction .....	6
<b>1 Scope .....</b>	<b>7</b>
<b>2 Normative references .....</b>	<b>7</b>
<b>3 Terms and definitions.....</b>	<b>8</b>
<b>4 Cement.....</b>	<b>9</b>
<b>5 Constituents .....</b>	<b>10</b>
5.1 General.....	10
5.2 Main constituents .....	10
5.2.1 Portland cement clinker (K).....	10
5.2.2 Granulated blast furnace slag (S) .....	11
5.2.3 Pozzolanic materials (P, Q).....	11
5.2.4 Fly ashes (V, W) .....	11
5.2.5 Burnt shale (T).....	12
5.2.6 Limestone (L, LL).....	13
5.2.7 Silica fume (D).....	13
5.3 Minor additional constituents.....	13
5.4 Calcium sulfate .....	14
5.5 Additives .....	14
<b>6 Composition and notation .....</b>	<b>14</b>
6.1 Composition and notation of common cements.....	14
6.2 Composition and notation of sulfate resisting common cements (SR-Cements) .....	16
6.3 Composition and notation of low early strength common cements .....	17
<b>7 Mechanical, physical, chemical and durability requirements.....</b>	<b>17</b>
7.1 Mechanical requirements.....	17
7.1.1 Standard strength .....	17
7.1.2 Early strength.....	17
7.2 Physical requirements.....	18
7.2.1 Initial setting time .....	18
7.2.2 Soundness.....	18
7.2.3 Heat of hydration .....	18
7.3 Chemical requirements .....	18
7.4 Durability requirements.....	19
7.4.1 General.....	19
7.4.2 Sulfate resistance .....	19
<b>8 Standard designation .....</b>	<b>20</b>
<b>9 Conformity criteria.....</b>	<b>22</b>
9.1 General requirements.....	22
9.2 Conformity criteria for mechanical, physical and chemical properties and evaluation procedure .....	24
9.2.1 General.....	24
9.2.2 Statistical conformity criteria .....	24
9.2.3 Single result conformity criteria.....	27
9.3 Conformity criteria for cement composition.....	28
9.4 Conformity criteria for properties of the cement constituents .....	29

<b>Annex A</b> (informative) <b>List of common cements considered as sulfate resisting by National Standards in different CEN member countries but not included in Table 2 or not fulfilling the requirements given in Table 5</b> .....	<b>30</b>
<b>Annex ZA</b> (informative) <b>Clauses of this European standard addressing the provisions of the EU Construction Products Directive</b> .....	<b>31</b>
<b>ZA.1</b> <b>Scope and relevant characteristics</b> .....	<b>31</b>
<b>ZA.2</b> <b>Procedure for the attestation of conformity of products</b> .....	<b>33</b>
<b>ZA.2.1</b> <b>System of attestation of conformity</b> .....	<b>33</b>
<b>ZA.2.2</b> <b>EC certificate of conformity</b> .....	<b>34</b>
<b>ZA.3</b> <b>CE marking and labelling</b> .....	<b>35</b>
<b>Bibliography</b> .....	<b>38</b>

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 197-1:2011](https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011>

**EN 197-1:2011 (E)****Foreword**

This document (EN 197-1:2011) has been prepared by Technical Committee CEN/TC 51 "Cement and building limes", the secretariat of which is held by NBN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2012, and conflicting national standards shall be withdrawn at the latest by June 2013.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN 197-1:2000, EN 197-4:2004.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EU Directive(s).

For relationship with EU Directive(s), see informative Annex ZA, which is an integral part of EN 197-1.

Annexes A and ZA are informative.

In addition to consolidating EN 197-1:2000/A1:2004, EN 197-1:2000/prA2, EN 197-1:2000/A3:2007, EN 197-4:2004 and EN 197-4:2004/prA1 into a single standard, the principal changes from EN 197-1:2000 are the introduction of additional requirements for common cements with a low heat of hydration and common cements with sulfate resisting properties.

The preparation of a standard for cement was initiated by the European Economic Community (EEC) in 1969 and, at the request of a member state later in 1973, the work was given to the European Committee for Standardization (CEN). The Technical Committee CEN/TC 51 was entrusted with the task of preparing a cement standard for the countries of Western Europe, comprising the EEC and EFTA members.

In the early eighties, CEN/TC 51 decided to include in the standard for cement only those cements which are intended for use in any plain and reinforced concrete and which are familiar in most countries in Western Europe because they have been produced and used in these countries for many years. The EU Construction Products Directive (89/106/EEC) requires the incorporation of all traditional and well-trying cements in order to remove technical barriers to trade in the construction field. There are currently no criteria for the descriptions "traditional" and "well tried" and it was considered necessary to separate the "common cements" from special cements, i.e. those with additional or special properties.

The requirements in this standard are based on the results of tests on cement in accordance with EN 196-1, EN 196-2, EN 196-3, EN 196-5, EN 196-6, EN 196-7, EN 196-8, and EN 196-9. The scheme for the evaluation of conformity of common cements including common cements with low heat of hydration and common cements generally accepted as being sulfate resisting are specified in EN 197-2.

In order to find out which common cements are generally accepted as being sulfate resisting and should be included in EN 197-1, there was an investigation within CEN/TC 51 comprising all national specifications and recommendations in the European Union. The review of these investigations led to the following results:

- a wide variety of cements has been classified in the EU Member States as sulfate resisting. This is due to the different geographical and climatic conditions under which sulfate attacks on mortar and concrete occur at the place of use and the traditionally different rules governing the production and use of sulfate resistant mortars and concretes;
- sulfate resistance is an additional property and therefore sulfate resisting cements have first to conform to the requirements of the standards which define the product, e.g. EN 197-1 for common cements;

- the additional requirements to be met by the nationally specified sulfate resisting cements refer to selected characteristics for which the required limit values are more stringent than those for common cements;
- having satisfied the local requirements for various cement types many countries apply further restrictions to the production of concrete to be used in a sulfate environment, such as minimum cement contents and/or maximum water/cement ratio that vary depending on the cement type and the type and intensity of the sulfate conditions.

Based on the above results common cement types to be harmonized at the European level have been chosen. The predominant part of the common cements considered to be sulfate resisting in the market is covered by this selection. It was not possible to take into account national particularities the use of which is laid down within national standards, national application rules and regulations/provisions.

The strength attained at 28 days is the important criterion in classifying cement for most uses. In order to achieve a specific strength class at 28 days the early strength, at 2 days or at 7 days, can vary and some types of cement may not attain the minimum early strengths specified in EN 197-1 for common cements.

The heat of hydration is linked to the early reactivity and lower early strengths indicate lower heat evolution and lower temperatures in concrete. For these cements additional precautions in use can be necessary to ensure adequate curing and safety in construction.

The purpose of this standard is to specify the composition requirements and conformity requirements for common cements, including common cements with low heat of hydration and common cements with adequate sulfate resistance as well as low early strength blast furnace cements and low early strength blast furnace cements with low heat of hydration.

Cement types and strength classes defined in this European Standard allow the specifier and/or the user to fulfil objectives of sustainability for cement based constructions. Cement types produced by using constituents listed and defined in Clause 5 allow the manufacturer to minimize the use of natural resources in accordance with local conditions of production.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

## Introduction

It is recognised that different cements have different properties and performance. Those performance tests now available (i.e. setting time, strength, soundness and heat of hydration), have been included in this standard. In addition, work is being carried out by CEN/TC 51 to identify any additional tests which are needed to specify further performance characteristics of cement. Until further performance tests are available it is necessary that the choice of cement, especially the type and/or strength class in relation to the requirements for durability depending on exposure class and type of construction in which it is incorporated, follows the appropriate standards and/or regulations for concrete or mortar valid in the place of use.

## iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 197-1:2011](https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011>



## 1 Scope

This European Standard defines and gives the specifications of 27 distinct common cements, 7 sulfate resisting common cements as well as 3 distinct low early strength blast furnace cements and 2 sulfate resisting low early strength blast furnace cements and their constituents. The definition of each cement includes the proportions in which the constituents are to be combined to produce these distinct products in a range of nine strength classes. The definition also includes requirements which the constituents have to meet. It also includes mechanical, physical, and chemical requirements. Furthermore, this standard states the conformity criteria and the related rules. Necessary durability requirements are also given.

In addition to those sulfate resisting cements defined in the present document, other cements conforming either to this standard or to other standards, European or national, have been nationally demonstrated to have sulfate resisting properties. These cements which are listed in Annex A, are considered by different CEN Member countries as sulfate resisting within the limits of their territory.

NOTE 1 In addition to the specified requirements, an exchange of additional information between the cement manufacturer and user can be helpful. The procedures for such an exchange are not within the scope of this standard but should be dealt with in accordance with national standards or regulations or can be agreed between the parties concerned.

NOTE 2 The word "cement" in EN 197-1 is used to refer only to common cements unless otherwise specified.

This European Standard does not cover:

- very low heat special cement covered by EN 14216;
  - supersulfated cement covered by EN 15743;
  - calcium aluminate cement covered by EN 14647;
  - masonry cement covered by EN 413-1.
- iTech STANDARD PREVIEW  
(standards.iteh.ai)  
SIST EN 197-1:2011  
<http://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011>

## 2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- EN 196-1, *Methods of testing cement — Part 1: Determination of strength*
- EN 196-2, *Methods of testing cement — Part 2: Chemical analysis of cement*
- EN 196-3, *Methods of testing cement — Part 3: Determination of setting times and soundness*
- EN 196-5, *Methods of testing cement — Part 5: Pozzolanicity test for pozzolanic cement*
- EN 196-6, *Methods of testing cement — Part 6: Determination of fineness*
- EN 196-7, *Methods of testing cement — Part 7: Methods of taking and preparing samples of cement*
- EN 196-8, *Methods of testing cement — Part 8: Heat of hydration — Solution method*
- EN 196-9, *Methods of testing cement — Part 9: Heat of hydration — Semi-adiabatic method*
- EN 197-2:2000, *Cement — Part 2: Conformity evaluation*
- EN 451-1, *Method of testing fly ash — Part 1: Determination of free calcium oxide content*

**EN 197-1:2011 (E)**

EN 933-9, *Tests for geometrical properties of aggregates — Part 9: Assessment of fines - Methylene blue test*

EN 13639, *Determination of total organic carbon in limestone*

ISO 9277, *Determination of the specific surface area of solids by gas adsorption — BET method*

ISO 9286, *Abrasive grains and crude — Chemical analysis of silicon carbide*

**3 Terms and definitions**

For the purposes of this document, the following terms and definitions apply.

**3.1****reactive calcium oxide (CaO)**

fraction of the calcium oxide which, under normal hardening conditions, can form calcium silicate hydrates or calcium aluminate hydrates

NOTE To evaluate this fraction, the total calcium oxide content (see EN 196-2) is reduced by the fraction corresponding to calcium carbonate ( $\text{CaCO}_3$ ), based on the measured carbon dioxide ( $\text{CO}_2$ ) content (see EN 196-2), and the fraction corresponding to calcium sulfate ( $\text{CaSO}_4$ ), based on the measured sulfate ( $\text{SO}_3$ ) content (see EN 196-2) after subtraction of the  $\text{SO}_3$  taken up by alkalis.

**3.2****reactive silicon dioxide ( $\text{SiO}_2$ )**

fraction of the silicon dioxide which is soluble after treatment with hydrochloric acid (HCl) and with boiling potassium hydroxide (KOH) solution

NOTE The quantity of reactive silicon dioxide is determined by subtracting from the total silicon dioxide content (see EN 196-2) the fraction contained in the residue insoluble in hydrochloric acid and potassium hydroxide (see EN 196-2), both on a dry basis.

<https://standards.iteh.ai/catalog/standards/sist/623e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011>

**3.3****main constituent**

specially selected inorganic material in a proportion exceeding 5 % by mass related to the sum of all main and minor additional constituents

**3.4****minor additional constituent**

specially selected inorganic material used in a proportion not exceeding a total of 5 % by mass related to the sum of all main and minor additional constituents

**3.5****type of common cement**

one of the 27 products (see Table 1) in the family of common cements

**3.6****strength class of cement**

class of compressive strength

**3.7****autocontrol testing**

continual testing by the manufacturer of cement spot samples taken at the point(s) of release from the factory/depot

**3.8****control period**

period of production and dispatch identified for the evaluation of the autocontrol test results

**3.9****characteristic value**

value of a required property outside of which lies a specified percentage, the percentile  $P_k$ , of all the values of the population

**3.10****specified characteristic value**

characteristic value of a mechanical, physical or chemical property which in the case of an upper limit is not to be exceeded or in the case of a lower limit is, as a minimum, to be reached

**3.11****single result limit value**

value of a mechanical, physical or chemical property which – for any single test result – in the case of an upper limit is not to be exceeded or in the case of a lower limit is, as a minimum, to be reached

**3.12****allowable probability of acceptance CR**

for a given sampling plan, allowed probability of acceptance of cement with a characteristic value outside the specified characteristic value

**3.13****sampling plan**

specific plan which states the (statistical) sample size(s) to be used, the percentile  $P_k$  and the allowable probability of acceptance CR

**3.14****spot sample**

sample which is taken at the same time and from one and the same place, relating to the intended tests, and which can be obtained by combining one or more immediately consecutive increments

**iTeh STANDARD PREVIEW**

(standards.iteh.ai)

NOTE See EN 196-7.

[SIST EN 197-1:2011](https://standards.iteh.ai/catalog/standards/sist/623e3e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011)

<https://standards.iteh.ai/catalog/standards/sist/623e3e0-610e-493d-a937-9d040e375534/sist-en-197-1-2011>

**3.15****heat of hydration**

quantity of heat developed by the hydration of a cement within a given period of time

**3.16****low heat common cement**

common cement with a limited heat of hydration

**3.17****sulfate resisting common cement**

common cement which fulfils the requirements for sulfate resisting properties

**3.18****low heat low early strength blast furnace cement**

low early strength blast furnace cement with a limited heat of hydration

**3.19****sulfate resisting low early strength blast furnace cement**

low early strength blast furnace cement which fulfils the requirements for sulfate resisting properties

**4 Cement**

Cement is a hydraulic binder, i.e. a finely ground inorganic material which, when mixed with water, forms a paste which sets and hardens by means of hydration reactions and processes and which, after hardening, retains its strength and stability even under water.

**EN 197-1:2011 (E)**

Cement conforming to this standard, termed CEM cement, shall, when appropriately batched and mixed with aggregate and water, be capable of producing concrete or mortar which retains its workability for a sufficient time and shall after defined periods attain specified strength levels and also possess long-term volume stability.

Hydraulic hardening of CEM cement is primarily due to the hydration of calcium silicates but other chemical compounds may also participate in the hardening process, e.g. aluminates. The sum of the proportions of reactive calcium oxide (CaO) and reactive silicon dioxide (SiO<sub>2</sub>) in CEM cement shall be at least 50 % by mass when the proportions are determined in accordance with EN 196-2.

CEM cements consist of different materials and are statistically homogeneous in composition resulting from quality assured production and material handling processes. The link between these production and material handling processes and the conformity of cement to this standard is elaborated in EN 197-2.

NOTE There are also cements whose hardening is mainly due to other compounds, e.g. calcium aluminate in calcium aluminate cement.

**5 Constituents****5.1 General**

The requirements for the constituents specified in 5.2 to 5.5 shall be determined in principle in accordance with the test methods described in EN 196 unless otherwise specified.

**5.2 Main constituents**

**iTeh STANDARD PREVIEW**  
(standards.iteh.ai)

**5.2.1 Portland cement clinker (K)**

Portland cement clinker is made by sintering a precisely specified mixture of raw materials (raw meal, paste or slurry) containing elements, usually expressed as oxides, CaO, SiO<sub>2</sub>, Al<sub>2</sub>O<sub>3</sub>, Fe<sub>2</sub>O<sub>3</sub> and small quantities of other materials. The raw meal, paste or slurry is finely divided, intimately mixed and therefore homogeneous.

Portland cement clinker is a hydraulic material which shall consist of at least two-thirds by mass of calcium silicates (3CaO · SiO<sub>2</sub> and 2CaO · SiO<sub>2</sub>), the remainder consisting of aluminium and iron containing clinker phases and other compounds. The ratio by mass (CaO)/(SiO<sub>2</sub>) shall be not less than 2,0. The content of magnesium oxide (MgO) shall not exceed 5,0 % by mass.

Portland cement clinker incorporated in sulfate resisting Portland cement (CEM I) and sulfate resisting pozzolanic cements (CEM IV) shall fulfil additional requirements for tricalcium aluminate content (C<sub>3</sub>A). The tricalcium aluminate content of the clinker shall be calculated by Equation (1) as follows:

$$C_3A = 2,65 A - 1,69 F \quad (1)$$

where

A is the percentage of aluminium oxide (Al<sub>2</sub>O<sub>3</sub>) by mass of the clinker as determined in accordance with EN 196-2

F is the percentage of iron (III) oxide (Fe<sub>2</sub>O<sub>3</sub>) by mass of the clinker as determined in accordance with EN 196-2.

NOTE It may happen that a negative C<sub>3</sub>A value is obtained from the calculation. In this case, the value 0 % should be recorded. A test method to determine the C<sub>3</sub>A content of clinker from the analysis of a spot sample of cement is currently under development by CEN/TC 51. Until this method is available, the C<sub>3</sub>A content should be directly measured on the clinker. In the specific case of CEM I, it is permissible to calculate the C<sub>3</sub>A content of clinker from the chemical analysis of the cement. The minimum frequency of testing and the use of alternative methods for the direct or indirect evaluation of C<sub>3</sub>A should be included in the factory production control (see EN 197-2). A typical frequency of testing is two per month in routine situations.

Sulfate resisting Portland cements and sulfate resisting pozzolanic cements are made with Portland cement clinker in which the  $C_3A$  content does not exceed:

- For CEM I: 0 %, 3 % or 5 % as appropriate (see 6.2)
- For CEM IV/A and CEM IV/B: 9 %.

### 5.2.2 Granulated blast furnace slag (S)

Granulated blast furnace slag is made by rapid cooling of a slag melt of suitable composition, as obtained by smelting iron ore in a blast furnace and contains at least two-thirds by mass of glassy slag and possesses hydraulic properties when suitably activated.

Granulated blast furnace slag shall consist of at least two-thirds by mass of the sum of calcium oxide (CaO), magnesium oxide (MgO) and silicon dioxide ( $SiO_2$ ). The remainder contains aluminium oxide ( $Al_2O_3$ ) together with small amounts of other compounds. The ratio by mass  $(CaO + MgO)/(SiO_2)$  shall exceed 1,0.

### 5.2.3 Pozzolanic materials (P, Q)

#### 5.2.3.1 General

Pozzolanic materials are natural substances of siliceous or silico-aluminous composition or a combination thereof. Although fly ash and silica fume have pozzolanic properties, they are specified in separate subclauses (see 5.2.4 and 5.2.7).

Pozzolanic materials do not harden in themselves when mixed with water but, when finely ground and in the presence of water, they react at normal ambient temperature with dissolved calcium hydroxide ( $Ca(OH)_2$ ) to form strength-developing calcium silicate and calcium aluminate compounds. These compounds are similar to those which are formed in the hardening of hydraulic materials. Pozzolanas consist essentially of reactive silicon dioxide ( $SiO_2$ ) and aluminium oxide ( $Al_2O_3$ ). The remainder contains iron oxide ( $Fe_2O_3$ ) and other oxides. The proportion of reactive calcium oxide for hardening is negligible. The reactive silicon dioxide content shall be not less than 25,0 % by mass.

Pozzolanic materials shall be correctly prepared, i.e. selected, homogenised, dried, or heat-treated and comminuted, depending on their state of production or delivery.

#### 5.2.3.2 Natural pozzolana (P)

Natural pozzolanas are usually materials of volcanic origin or sedimentary rocks with suitable chemical and mineralogical composition and shall conform to 5.2.3.1.

#### 5.2.3.3 Natural calcined pozzolana (Q)

Natural calcined pozzolanas are materials of volcanic origin, clays, shales or sedimentary rocks, activated by thermal treatment and shall conform to 5.2.3.1.

### 5.2.4 Fly ashes (V, W)

#### 5.2.4.1 General

Fly ash is obtained by electrostatic or mechanical precipitation of dust-like particles from the flue gases from furnaces fired with pulverised coal.

NOTE 1 For definition of fly ash see EN 450-1.

Ash obtained by other methods shall not be used in cement that conforms to this standard.