

---

---

**Recycled pulps — Estimation of Stickies  
and Plastics —**

**Part 1:  
Visual method**

*Pâtes recyclées — Estimation des matières collantes et des matières  
plastiques —  
Partie 1: Méthode visuelle*

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

[ISO 15360-1:2000](https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000)

<https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000>



**PDF disclaimer**

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

**iTeh STANDARD PREVIEW**  
**(standards.iteh.ai)**

[ISO 15360-1:2000](https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000)

<https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office  
Case postale 56 • CH-1211 Geneva 20  
Tel. + 41 22 749 01 11  
Fax + 41 22 734 10 79  
E-mail [copyright@iso.ch](mailto:copyright@iso.ch)  
Web [www.iso.ch](http://www.iso.ch)

Printed in Switzerland

## Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 15360 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 15360-1 was prepared by Technical Committee ISO/TC 6, *Paper, board and pulps*, Subcommittee SC 5, *Test methods and quality specifications for pulp*.

ISO 15360 consists of the following parts, under the general title *Recycled pulps — Estimation of Stickies and Plastics*:

— Part 1: *Visual method*

— Part 2: *Image analysis method*

ITC STANDARD PREVIEW  
(standards.iteh.ai)  
ISO 15360-1:2000  
<https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000>

Annexes A and B form a normative part of this part of ISO 15360.

## Introduction

The production of pulp from de-inked recovered fibres and from brown or mixed waste grades is increasing in many parts of the world. Many of the recovered papers used in the production of recycled pulps contain adhesives, latex and other materials, which are either intrinsically "tacky" or can become so under appropriate conditions of temperature, pH and pressure. Residual particles of such materials can cause problems when the pulp is subsequently used in paper manufacture. In addition, recycled pulp feedstock is sometimes derived from material that has been plastics coated and the presence of plastics in the finished pulp can also cause problems, especially in the manufacture of coated papers. Moreover, plastics found in recovered paper may also come from a collection which has not been properly sorted.

International Standards exist for the determination of visible dirt and shives in pulp and these could be applied to de-inked pulp. However Stickies and Plastics are often similar to the pulp in colour and, even when large, are difficult to detect by visual inspection. Different techniques have thus to be employed.

This part of ISO 15360 is based on a visual identification and count of the Stickies and Plastics. Instrumental techniques are also available for estimating Stickies and Plastics. However, these are less widely used but may be the basis of a future International Standard for Stickies and Plastics in recycled pulps.

NOTE Different types of laboratory screening equipment, complying with this part of ISO 15360 may be used to isolate the Stickies and Plastics from the cellulose stock. It should be noted that different types of laboratory screening equipment may give different results. Furthermore, screening equipment of the same style fitted with different screens complying with this part of ISO 15360 may also give different results because of the difference in the distribution of slit sizes within the screen.

[ISO 15360-1:2000](https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000)

<https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000>

# Recycled pulps — Estimation of Stickies and Plastics —

## Part 1: Visual method

### 1 Scope

This part of ISO 15360 specifies a method to estimate Stickies and Plastics in a wide variety of pulps including all recycled grades. It is not intended for the estimation of visible dirt and shives which is covered by the ISO 5350 series, or for visible contraries in recycled pulps, which is covered by ISO 15319 [1].

This method will only capture those Stickies and Plastics which are retained on the screen of a given slit size. It should be noted that this will probably not be the total amount of Stickies and Plastics that are actually present in a given pulp sample.

### 2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 15360. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 15360 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 638, *Pulps — Determination of dry matter content.*

ISO 4119, *Pulps — Determination of stock concentration.*

ISO 5263, *Pulps — Laboratory wet disintegration.*

ISO 5269-1, *Pulps — Preparation of laboratory sheets for physical testing — Part 1: Conventional sheet-former method.*

ISO 5350-1, *Pulps — Estimation of dirt and shives — Part 1: Inspection of laboratory sheets.*

ISO 5350-2, *Pulps — Estimation of dirt and shives — Part 2: Inspection of mill sheeted pulp.*

ISO 7213, *Pulps — Sampling for testing.*

### 3 Terms and definitions

For the purposes of this part of ISO 15360, the following terms and definitions apply.

#### 3.1

##### **Stickies**

diverse group of materials that are retained on a laboratory screen (5.2) of given slit aperture (100 µm or 150 µm), and which adhere to objects which they touch; Stickies may adhere objects at ambient temperature or they may adopt adhesive characteristics when subjected to elevated temperature, elevated pressure or change of pH

NOTE 1 The following is a non-exhaustive list of Stickies: products derived from residues of materials such as inks, tars, hot melts, waxes and multivalent metal ion soaps or different types of pressure-sensitive adhesives.

NOTE 2 A Stickers particle can be a composite of adhesive material, together with non-adhesive plastics fragments and cellulose fibres.

#### 3.2

##### **Plastics**

non-adhesive polymers that are retained on a laboratory screen (5.2) of a given slit aperture, but excluding cellulosic materials

NOTE The following is a non-exhaustive list of Plastics: polymeric materials derived from such sources as polyethylene, polypropylene, polyester, UV-cured coatings and polystyrene.

#### 3.3

##### **screen**

that part of the laboratory screening equipment which separates the Stickies and Plastics from the cellulose fibre

iTeh STANDARD PREVIEW  
(standards.iteh.ai)

### 4 Principle

ISO 15360-1:2000

A sample of pulp in disintegrated form is passed through a laboratory screen of given slit aperture until the filtrate is clear. The material retained on the screen is removed and transferred to a filter paper. The Stickies and Plastics are identified and their total numbers and areas are estimated separately.

### 5 Apparatus and equipment

5.1 **Disintegrator** as specified in ISO 5263.

5.2 **Laboratory screening equipment**, fitted with a screen (3.3) complying with the specification described in annex A.

NOTE Various types of laboratory screening equipment may use different terminology to describe the separating medium (e.g. "slots" instead of "slits").

5.3 **Filter paper**; a qualitative, medium/fast grade is recommended.

5.4 **Tweezers**.

5.5 **Illumination device**: a suitable light source for the investigation of filter papers containing Stickies and Plastics particles in reflected light. The light shall be strong enough to ensure that all particles having the minimum area agreed upon are visible.

5.6 **Light table**, as specified in ISO 5350-1 and ISO 5350-2. This is needed only when Stickies are estimated at elevated temperature and pressure, see 7.5.3.

5.7 **Desk-top magnifying glass**, magnification  $\times 2$  to  $\times 4$ , or **microscope**, stereo type, magnification  $\times 10$  to  $\times 40$  (optional only).

**5.8 Dissecting needles.**

**5.9 Heated press**, capable of applying a load of  $690 \text{ kPa} \pm 20 \text{ kPa}$  at a constant temperature of  $150 \text{ }^\circ\text{C} \pm 10 \text{ }^\circ\text{C}$ .

**5.10 Comparison chart**, as shown in annex B.

**5.11 Blotters**, as used for the preparation of laboratory sheets in ISO 5269-1.

**5.12 Oven**, capable of maintaining an air temperature of  $105 \text{ }^\circ\text{C} \pm 2 \text{ }^\circ\text{C}$ .

## 6 Sampling

If the estimation of the Stickies and Plastics is to represent the Stickies and Plastics in a lot of pulp, the number of samples to be tested and their selection shall be in accordance with ISO 7213. If the test is made using another type of sampling, make sure that the test pieces are representative of the sample received.

## 7 Procedure

### 7.1 Temperature

All operations described in this clause, with the exception of 7.5.3 (Stickies at elevated temperature), shall be carried out at room temperature ( $20 \text{ }^\circ\text{C}$  to  $25 \text{ }^\circ\text{C}$ ).

### 7.2 Pretreatment of sample

Determine the dry matter content as described in ISO 638.

Soak air-dried pulp samples for at least 4 h in water (tap water may be used). Wet-lap pulp may be disintegrated immediately (see 5.1). Pulp stock with a consistency of 10 % or less need not be disintegrated.

Using the procedure described in ISO 5263, disintegrate a sample of pulp of mass and concentration appropriate to the screening equipment used. (See the second paragraph of 7.2.) The conditions of disintegration shall be reported in clause 10.

**NOTE** The procedure for visible contraries in recycled pulp (ISO 15319) may be used. This procedure disintegrates 50 g to 60 g oven-dried pulp in 2 700 ml of water, until the stock is just clear of fibre bundles.

When necessary, determine the concentration of the stock as described in ISO 4119.

### 7.3 Screening of the disintegrated stock

Following the manufacturer's instructions for the relevant laboratory screening equipment (5.2), add a portion of the prepared stock to the screen (3.3). Process the stock until the filtrate is clear.

It is recommended that initially a total mass of 100 g oven-dried pulp should be processed. It may be necessary to process more or less than 100 g of pulp depending on the content of Stickies and Plastics.

### 7.4 Removal of material retained on the screen

Stand the screen vertically in a suitable container and wash the slits first from the underside and then from the top side of the slits, with a fine jet of high pressure cold water. Use an amount of washing water that is just sufficient, as far as possible, to remove all the material retained on the screen. Retain the screen for a subsequent visual re-examination.

Filter the suspension through the filter paper (5.3) ensuring a uniform distribution of Stickies and Plastics on the filter paper. The number of filter papers used is determined by the amount of material retained on the screen.

NOTE Some commercial laboratory screening equipment transfers the material from the screen to the filter paper automatically.

When all the suspension has been filtered, re-examine the screen. Any remaining particles which might be Stickies or Plastics should be removed from the screen with the aid of a pair of tweezers (5.4) and placed on one of the filter papers.

Place all the filter papers on separate blotters (5.11) and dry at 105 °C for 1 h in an oven (5.12).

## 7.5 Examination of the material retained on the screen

Examine the filter paper(s) in reflected light by eye to identify the types of particles present. Record the number of particles of Stickies and Plastics and estimate the area of each particle. Calculate the total area of each particle type.

A magnifying glass or stereo-microscope (5.7) may be used as an aid to identify the Stickies and Plastics, but must not be used to count the number of these particles present or to estimate their areas.

### 7.5.1 Identification and size estimates of the Stickies at ambient temperature

Stickies tend to be opaque and rounded in shape and may bind with toner, ink or dye particles, giving the aggregate a coloured appearance. Starting with the largest particle, probe with a dissecting needle (5.8). If the particle is adhering or embedded in the filter paper then estimate the particle size using the comparison chart (5.10). Circle each Sticky identified; repeat the estimate of size for each particle present. Record the total number of particles present and calculate the total area, in square millimetres, of the Stickies.

### 7.5.2 Identification and size estimates of the Plastics

<https://standards.iteh.ai/catalog/standards/sist/92feb782-09a4-4f58-ba4a-135805ea8f59/iso-15360-1-2000>

Plastics are usually present in flakes or strands, often associated with fibre bundles. They may be clear or coloured, but rarely black. Starting with the largest particle not identified as a Sticky, examine each non-Sticky particle under a magnifying glass or microscope (5.7) and with tweezers. If the particle stretches and it fulfils the appearance criteria, estimate the particle size using the comparison chart (5.10). Circle and estimate the area for each Plastics particle identified. Record the total number of particles and calculate the total area, in square millimetres, of the Plastics.

### 7.5.3 Identification and size estimates of the Stickies at elevated temperature and pressures

Some Stickies, such as those derived from hot-melt adhesives, only become evident when subjected to elevated temperatures and pressures and become non-Stickies again when the temperature returns to ambient. Since there is a range of softening temperatures and pressures over which it occurs, estimation of these Stickies is optional. This part of the procedure may be used if it is suspected that the recycled pulp feedstock contains any bookbinding adhesives.

Place the filter paper(s) in the heated press (5.9) for 10 min ± 2 min at 690 kPa ± 20 kPa and 150 °C ± 10 °C.

These Stickies will be revealed as translucent spots in the filter paper. Place the filter paper on the light table (5.6). Circle and estimate the translucent areas using the comparison chart. Record the total number of translucent spots and calculate the total area, in square millimetres, of these Stickies. Report these values separately to the values for Stickies at ambient temperature. Record in clause 10 the temperature and pressure used to activate these Stickies.



## 8 Calculations

### 8.1 Number of Stickies and Plastics

Record separately the number of Stickies and, if tested, Plastics at ambient temperature, and Stickies at elevated temperature and pressure.

Calculate separately the total number of Stickies and Plastics per kilogram of pulp using the formula:

$$Y = \frac{a}{m} \quad (1)$$

where

$Y$  is the total number of Stickies or Plastics, as relevant, expressed in number per kilogram of oven-dried pulp;

$a$  is the observed total number of Stickies or Plastics, as relevant;

$m$  is the oven-dried mass of the pulp selected for the test, in kilograms.

### 8.2 Area of Stickies and Plastics

Calculate separately the total area of Stickies and Plastics per unit mass of pulp using the formula:

$$X = \frac{A}{m} \quad (2)$$

where

$X$  is the total area of the Stickies or the Plastics per unit mass of pulp, expressed in square millimetres per kilogram;

$A$  is the total area of the Stickies or the Plastics, in square millimetres;

$m$  is as defined in 8.1.

## 9 Precision

Five laboratories using either a Somerville Fractionator<sup>1)</sup> or a Pulmac Master Screen<sup>1)</sup> evaluated one batch of deinked pulp for Stickies (including hot melts) and Plastics. Based on a count of the particles present, the results were as shown in Table 1.

---

1) The Somerville Fractionator and the Pulmac Master Screen are examples of suitable models of screening equipment available commercially. This information is given for the convenience of users of this part of ISO 15360 and does not constitute an endorsement by ISO of these models.