
**Solid mineral fuels — Determination
of chlorine using Eschka mixture**

*Combustibles minéraux solides — Dosage du chlore au moyen
du mélange Eschka*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 587:1997

<https://standards.iteh.ai/catalog/standards/sist/f17965ab-056e-4727-a864-6ba0292f857e/iso-587-1997>



Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 587 was prepared by Technical Committee ISO/TC 27, *Solid mineral fuels*, Subcommittee SC 5, *Methods of analysis*.

This third edition cancels and replaces the second edition (ISO 587:1981), which has been technically revised.

Annex A of this International Standard is for information only.

© ISO 1997

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from the publisher.

International Organization for Standardization
Case postale 56 • CH-1211 Genève 20 • Switzerland
Internet central@iso.ch
X.400 c=ch; a=400net; p=iso; o=isocs; s=central

Printed in Switzerland

Solid mineral fuels — Determination of chlorine using Eschka mixture

1 Scope

This International Standard specifies a method of determining the chlorine content of hard coal, brown coals and lignite, and coke using Eschka mixture.

2 Normative references

The following standards contain provisions which, through reference in this text, constitute provisions of this International Standard. At the time of publication, the editions indicated were valid. All standards are subject to revision, and parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the standards indicated below. Members of IEC and ISO maintain registers of currently valid International Standards.

ISO 331:1983, *Coal — Determination of moisture in the analysis sample — Direct gravimetric method.*

ISO 687:1974, *Coke — Determination of moisture in the analysis sample.*

ISO 1015:1992, *Brown coals and lignites — Determination of moisture content — Direct volumetric method.*

ISO 1170:1977, *Coal and coke — Calculation of analyses to different bases.*

ISO 1988:1975, *Hard coal — Sampling.*

ISO 2309:1980, *Coke — Sampling.*

ISO 5068:1983, *Brown coals and lignites — Determination of moisture content — Indirect gravimetric method.*

ISO 5069-2:1983, *Brown coals and lignites — Principles of sampling — Part 2: Sample preparation for determination of moisture content and for general analysis.*

ISO 9411-1:1994, *Solid mineral fuels — Mechanical sampling from moving streams — Part 1: Coal.*

ISO 9411-2:1993, *Solid mineral fuels — Mechanical sampling from moving streams — Part 2: Coke.*

3 Principle

A known mass of sample is ignited in intimate contact with Eschka mixture in an oxidizing atmosphere to remove combustible matter and to convert the chlorine to alkaline chlorides. These are extracted with nitric acid or water and determined by either the Volhard or the Mohr method, or by potentiometric titration using an Ion Selective Electrode (ISE).

4 Reagents

WARNING — Care should be exercised when handling reagents, many of which are toxic and corrosive.

During analysis, unless otherwise stated, use only reagents of recognized analytical grade and only distilled water, or water of equivalent purity.

4.1 For all methods

4.1.1 Eschka mixture

Mix two parts by mass of light, calcined magnesium oxide with one part of anhydrous sodium or potassium carbonate. The mixture shall entirely pass a test sieve of 0,212 mm nominal aperture.

4.1.2 Nitric acid, concentrated, chlorine-free, approximately 70 % (m/m).

4.2 For the Volhard and ISE methods

4.2.1 Silver nitrate, standard volumetric solution, $c(\text{AgNO}_3) = 0,025 \text{ mol/l}$.

Heat crushed, crystalline silver nitrate at 125 °C for two to three hours. Dissolve 4,247 g in water and dilute to 1 l. Store in an amber glass bottle.

4.3 For the Volhard method only

4.3.1 3, 5, 5-trimethylhexan-1-ol.

4.3.2 *n*-Hexan-1-ol.

ISO 587:1997
<https://standards.iteh.ai/catalog/standards/sist/fl7965ab-056e-4727-a864-6ba0292f857e/iso-587-1997>

4.3.3 Potassium thiocyanate, standard volumetric solution, $c(\text{KSCN}) \approx 0,025 \text{ mol/l}$.

Dissolve 2,4 g of potassium thiocyanate in water and dilute to 1 l. Titrate against the silver nitrate solution (4.2.1) and calculate the exact equivalence.

4.3.4 Iron(III) alum (ammonium iron(III) sulfate) indicator, saturated solution.

Saturate 100 ml of water with approximately 125 g or iron(III) alum $[(\text{NH}_4)_2\text{SO}_4 \cdot \text{Fe}_2(\text{SO}_4)_3 \cdot 24\text{H}_2\text{O}]$ and add sufficient nitric acid (4.1.2) to remove the brown colour.

4.4 For the Mohr method only

4.4.1 Silver nitrate, standard volumetric solution, $c(\text{AgNO}_3) = 0,050 \text{ mol/l}$.

Weigh 8,494 g of silver nitrate, dried as in (4.2.1), dissolve in water and dilute to 1 l. Store in an amber glass bottle.

4.4.2 Potassium chromate, indicator solution.

Dissolve 5 g of potassium chromate in 100 ml of water.

5 Apparatus

5.1 Analytical balance, capable of weighing to the nearest 0,1 mg.

5.2 Graduated glassware, conforming to the requirements for Grade A in the International Standards prepared by ISO/TC 48, *Laboratory glassware and related apparatus*.

5.3 Electrically heated muffle furnace, capable of being maintained at a temperature of $675\text{ }^{\circ}\text{C} \pm 25\text{ }^{\circ}\text{C}$, with adequate ventilation.

5.4 Crucible, of platinum, silica or glazed porcelain, of approximately 25 ml capacity.

5.5 Flat plate, 6 mm thick, of silica or other suitable refractory material, which fits easily into the muffle furnace (5.3).

5.6 Potentiometric titration assembly, equipped with a chloride ion selective electrode and double junction reference electrode.

6 Preparation of the test sample

The test sample is the general analysis test sample prepared in accordance with ISO 1988, ISO 2309, ISO 5069-2, ISO 9411-1 or ISO 9411-2 as appropriate. Ensure that the moisture content of the sample is in equilibrium with the laboratory atmosphere, exposing it, if necessary, in a thin layer for the minimum time required to achieve equilibrium.

Before commencing the determination, thoroughly mix the equilibrated test sample for at least one minute, preferably by mechanical means.

If the results are to be calculated other than on an "air-dried" basis (see clause 8), then, after weighing the test portion (see 7.1), determine the moisture content using a further portion of the test sample by the method described in ISO 331, ISO 687, ISO 1015 or ISO 5068, as appropriate.

7 Procedure

7.1 Combustion

Weigh, to the nearest 0,1 mg, a test portion of approximately 1 g, for samples with an expected chlorine content greater than 0,1 % (*m/m*), or 2 g for samples with a lower expected chlorine content.

Cover the bottom of the crucible (5.4) uniformly with 0,5 g of the Eschka mixture (4.1.1). Thoroughly mix the test portion with 2,5 g of the Eschka mixture in a suitable container. Transfer the mixture to the crucible, level the contents by gently tapping the crucible on the bench and cover uniformly with a further 1 g of the Eschka mixture.

NOTE 1 It is convenient to weigh out initially 4 g of the Eschka mixture and to extract the portions required for the bottom and top layers using a small glass tube, calibrated for each batch of Eschka mixture, to deliver 0,5 g and 1 g portions without weighing. The bottom layer of Eschka mixture reduces attack on silica and porcelain surfaces so that extraction of chlorine with hot water is complete even when the surface deteriorates.

For coals, place the charged crucible in the cold muffle furnace (5.3) and raise the temperature to $675\text{ }^{\circ}\text{C} \pm 25\text{ }^{\circ}\text{C}$ in about one hour. Maintain this temperature for a further two hours. Withdraw the crucible and allow to cool.

For coke, place the charged crucible on the cold flat plate (5.5) and insert into the muffle furnace at a temperature of $675\text{ }^{\circ}\text{C} \pm 25\text{ }^{\circ}\text{C}$. Maintain this temperature for two hours. Withdraw the crucible and allow to cool.

NOTE 2 Cracking of the porcelain crucibles is prevented if they are cooled slowly by insertion into supports constructed from a light, porous refractory material after removal from the muffle furnace.

7.2 Completion

Complete the determination by either the Volhard (7.2.1), the Mohr (7.2.2) or the ISE method (7.2.3).

7.2.1 Volhard method

Transfer the incinerated mixture to a beaker, wash the crucible with about 125 ml of hot water and add the washings to the beaker. If unburnt particles are present, stop the test and repeat the determination, extending the combustion time. Cautiously add 20 ml of the nitric acid (4.1.2) and cover the beaker with a clock glass, swirling or stirring the contents, if necessary, to help dissolution.

If necessary, filter the solution through a rapid-filtering, hardened, acid-washed filter paper, collecting the filtrate in a conical flask.¹⁾ Wash the paper with a small quantity of hot water (for example four lots of 5 ml to 10 ml), cool to room temperature and add 20 ml of the silver nitrate solution (4.2.1) to the flask and mix thoroughly. Immediately add 5 ml of the 3, 5, 5-trimethylhexan-1-ol (4.3.1) or *n*-hexan-1-ol (4.3.2), shake the solution for one minute to coagulate the precipitate, add eight to ten drops of the iron(III) alum indicator solution (4.3.4) and titrate with the potassium thiocyanate solution (4.3.3). The end-point is reached when the solution becomes faintly orange-pink in colour.

7.2.2 Mohr method

Transfer the incinerated mixture to a beaker, wash the crucible with hot water, collect the washings in the beaker and crush the residue in the beaker with a flat-ended glass rod. If unburnt particles are present, stop the determination and repeat the test extending the combustion time.

Heat the solution to boiling point and filter, using a filter paper pad or rapid filtering paper, collecting the filtrate in a conical flask. Wash the residue with five portions (5 ml each) of hot water, collecting the washings in the flask. Neutralize the solution with the nitric acid (4.1.2), using a pH paper. Add ten drops of the potassium chromate indicator (4.4.2) and titrate with the silver nitrate solution (4.2.1). The end-point is indicated by the first appearance of a brown coloration.

<https://standards.iteh.ai/catalog/standards/sist/f17965ab-056e-4727-a864-6ba0292f857e/iso-587-1997>

7.2.3 ISE method

Transfer the incinerated mixture to a beaker, wash the crucible with 50 ml to 70 ml of hot water and add the washings to the beaker. If unburnt particles are present, stop the determination and repeat the test extending the combustion time. Cautiously add 20 ml of the nitric acid (4.1.2) and cover the beaker with a clock glass, swirling or stirring the contents, if necessary, to help dissolution.

If necessary, filter the solution through a rapid-filtering, hardened, acid-washed filter paper, collecting the filtrate in a conical flask.¹⁾ Wash the paper with a small quantity of hot water (the total volume of the filtrate should not exceed 100 ml) and cool to room temperature.

Titrate with 0,025 M silver nitrate solution (4.2.1), using the potentiometric titration assembly (5.6).

7.3 Blank test

Carry out a blank test, using the same procedure as described in 7.1 and 7.2 but omitting the test portion. This assesses both the chlorine in the reagents and any contamination in the laboratory atmosphere. This shall not be quantitatively significant.

1) Filtration is usually unnecessary when using 1 g test portions of low-ash fuels, but is required when dealing with larger test portions or with high-ash fuels.

8 Expression of results

8.1 Volhard method

The chlorine content (W_{Cl}) of the sample, as analyzed, expressed as a percentage by mass, is given by the formula

$$W_{\text{Cl}} = \frac{3,545 c_1 (V_2 - V_1)}{m}$$

where

- c_1 is the concentration, in moles per litre, of the potassium thiocyanate solution (4.3.3);
- V_1 is the volume, in millilitres, of the potassium thiocyanate solution (4.3.3) used in the determination (7.2.1);
- V_2 is the volume, in millilitres, of the potassium thiocyanate solution (4.3.3) used in the blank test (7.3);
- m is the mass, in grams, of the test portion.

8.2 Mohr titration

The chlorine content (W_{Cl}) of the sample, as analyzed, expressed as a percentage by mass, is given by the formula

$$W_{\text{Cl}} = \frac{3,545 c_2 (V_3 - V_4)}{m}$$

where

- c_2 is the concentration, in moles per litre, of the silver nitrate solution (4.4.1);
- V_3 is the volume, in millilitres, of the silver nitrate solution (4.4.1) used in the determination (7.2.2);
- V_4 is the volume, in millilitres, of the silver nitrate solution (4.4.1) used in the blank test (7.3);
- m is the mass, in grams, of the test portion.

8.3 ISE method

The chlorine content (W_{Cl}) of the sample, as analyzed, expressed as a percentage by mass, is given by the formula

$$W_{\text{Cl}} = \frac{3,545 c_3 (V_5 - V_6)}{m}$$

where

- c_3 is the concentration, in moles per litre, of the silver nitrate solution (4.2.1);
- V_5 is the volume, in millilitres, of the silver nitrate solution (4.2.1) used in the determination (7.2.3);
- V_6 is the volume, in millilitres, of the silver nitrate solution (4.2.1) used in the blank test (7.3);
- m is the mass, in grams, of the test portion.

8.4 All methods

Report the results as the mean of duplicate determinations, to the nearest 0,01 %.

The results of the determination described in this International Standard are reported on the "air-dried" basis. Calculation of results to other bases is dealt with in ISO 1170.

9 Precision

9.1 Repeatability limit

The results of duplicate determinations, carried out at different times within a short interval, in the same laboratory, by the same operator, with the same apparatus, on representative portions taken from the same analysis sample, should not differ by more than 0,03 % absolute.

9.2 Reproducibility critical difference

The means of the results of duplicate determinations, carried out in each of two laboratories, on representative portions taken from the same sample after the last stage of sample separation, should not differ by more than 0,06 % absolute.

10 Test report

The test report shall include the following information:

- a) reference to this International Standard;
- b) an identification of the sample tested;
- c) the results and the method of expression used;
- d) any unusual features noted during the determination;
- e) any operation not included in this International Standard, or regarded as optional;
- f) the date of the test.

ISO 587:1997
<https://standards.iteh.ai/catalog/standards/sist/fl7965ab-056e-4727-a864-6ba0292f857e/iso-587-1997>



Annex A (informative)

Derivation of factors used in calculations in this International Standard

A.1 General

In this annex, relative atomic masses and relative molecular masses are represented by the chemical formulae in square brackets.

The following equivalences occur in the determinations in this International Standard



A.2 Volhard method

The percentage by mass, W_{Cl} , of chlorine in the sample is given by the formula

$$W_{\text{Cl}} = \frac{[(cV - c_1V_1) - (cV - c_1V_2)] \times 35,45}{1\,000} \times \frac{100}{m}$$

$$\frac{3,545\,c_1(V_2 - V_1)}{m}$$

where

- V is the volume, in millilitres, of the silver nitrate solution (4.2.1) used in the determination (7.2.1) and the blank test (7.3);
- V_1 is the volume, in millilitres, of the potassium thiocyanate solution (4.3.3) used in the determination (7.2.1);
- V_2 is the volume, in millilitres, of the potassium thiocyanate solution (4.3.3) used in the blank test (7.3);
- c is the concentration, in moles per litre, of the silver nitrate solution (4.2.1);
- c_1 is the concentration, in moles per litre, of the potassium thiocyanate solution (4.3.3);
- m is the mass, in grams, of the test portion;
- 35,45 is the relative atomic mass of chlorine, $[\text{Cl}]$.

A.3 Mohr method

The percentage by mass, W_{Cl} , of chlorine in the sample is given by the formula

$$W_{\text{Cl}} = \frac{c_2(V_3 - V_4) \times 35,45}{1\,000} \times \frac{100}{m}$$

$$\frac{3,545\,c_2(V_3 - V_4)}{m}$$

where

- c_2 is the concentration, in moles per litre, of the silver nitrate solution (4.4.1);
- V_3 is the volume, in millilitres, of the silver nitrate solution (4.4.1) used in the determination (7.2.2);
- V_4 is the volume, in millilitres, of the silver nitrate solution (4.4.1) used in the blank test (7.3);
- m is the mass, in grams, of the test portion;
- 35,45 is the relative atomic mass of chlorine, $[\text{Cl}]$.