SLOVENSKI STANDARD
kSIST FprEN 12311-2:2009

01-september-2009

Hidroizolacijski trakovi - Določevanje nateznih lastnosti - 2. del: Polimerni in elastomerni trakovi za tesnjenje streh

Flexible sheets for waterproofing - Determination of tensile properties - Part 2: Plastic and rubber sheets for roof waterproofing

Abdichtungsbahnen - Bestimmung des Zug- Dehnungsverhaltens - Teil 2: Kunststoff- und Kautschukbahnen für Dachabdichtungen

Feuilles souples d'étanchéité - Détermination des propriétés en traction - Partie 2: Feuilles d'étanchéité de toiture plastiques et élastomères

Ta slovenski standard je istoveten z: **FprEN 12311-2**

ICS:

91.060.20	Strehe	Roofs
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

kSIST FprEN 12311-2:2009 **en,fr,de**

EUROPEAN STANDARD

NORME EUROPÉENNE

EUROPÄISCHE NORM

FINAL DRAFT
FprEN 12311-2

June 2009

ICS 91.100.50

Will supersede EN 12311-2:2000

English Version

Flexible sheets for waterproofing - Determination of tensile properties - Part 2: Plastic and rubber sheets for roof waterproofing

Feuilles souples d'étanchéité - Détermination des propriétés en traction - Partie 2: Feuilles d'étanchéité de toiture plastiques et élastomères

Abdichtungsbahnen - Bestimmung des Zug-Dehnungsverhaltens - Teil 2: Kunststoff- und Kautschukbahnen für Dachabdichtungen

This draft European Standard is submitted to CEN members for unique acceptance procedure. It has been drawn up by the Technical Committee CEN/TC 254.

If this draft becomes a European Standard, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration.

This draft European Standard was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.

EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword

This document (FprEN 12311-2:2009) has been prepared by Technical Committee CEN/TC 254 “Flexible sheets for waterproofing”, the secretariat of which is held by BSI.

This document is currently submitted to the Unique Acceptance Procedure.

This document will supersede EN 12311-2:2000.

Introduction

This European Standard is intended for characterisation of plastic and rubber sheets as manufactured or supplied before use. This test method relates exclusively to products, or to their components where appropriate, and not to waterproofing membrane systems composed of such products and installed in the works.

This test is intended to be used in conjunction with EN 13956, *Flexible sheet for waterproofing — Plastic and rubber sheets for roof waterproofing — Definitions and characteristics*.

The document contains two methods of test. Method A, based on EN ISO 1421, is the preferred method which should be used for all materials. If method A is not suited to the material, i.e. the material does not rupture; method B based on ISO 37 can then be used to determine tensile properties.

1 Scope

This European Standard specifies test methods for the determination of the tensile properties of plastic and rubber sheets for roof waterproofing:

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 1849-2, *Flexible sheets for waterproofing — Determination of thickness and mass per unit area — Part 2: Plastic and rubber sheets for roof waterproofing*

EN 13416, *Flexible sheets for waterproofing — Bitumen, plastic and rubber sheets for roof waterproofing — Rules for sampling*

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1:2004)*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1
top surface
the upper side of the sheet, as used in situ

NOTE This is usually the inside of the roll.

3.2
maximum tensile force
the largest value of tensile force recorded during testing

3.3
elongation at maximum tensile force
elongation of the test specimen at the maximum tensile force

3.4
elongation at break
elongation of the test specimen at rupture

4 Principle

A test specimen is stretched at a constant speed until it ruptures. The force and elongation is continuously recorded throughout the test, and preferably with a permanent record of the maximum tensile force.

5 Apparatus

Tensile testing machine equipped with a continuous recording of force and corresponding elongation and capable of maintaining a uniform speed of grip separation as specified below.

The tensile testing machine shall have a sufficient loading capacity of at least 2000 N and a grip separation speed of (100 ± 10 and 500 ± 50) mm/min. The width of grips shall not be less than 50 mm.

The tensile testing machine shall be equipped with grips of a type which maintain or increase the clamping pressure as a function of the increase of the force applied to the test specimen. The test specimen shall be held so that it does not slip in the grips more than 1 mm for products up to and including 3 mm thick, and 2 mm for thicker products. A mark or tape on the test specimen where it enters the grips will help reveal any slip.

The method of gripping shall not induce premature rupture close to the grips.

If the slippage from the grips exceeds the stated limits the actual elongation of the test specimen shall be measured with an extensometer.

The force measuring system shall meet at least Class 2 of EN ISO 7500-1 (i.e. ± 2 %).

6 Sampling

Samples shall be taken in accordance with EN 13416.

7 Preparation of test specimens

Unless otherwise specified, for a complete tensile test two sets of test specimens are to be prepared: a set of five for the longitudinal direction and a set of five for the transverse direction.

Test specimens are to be cut from a test piece not closer than (100 ± 10) mm from the edge of the sheet, with the aid of a template, or die cutter as follows:

- Method A; rectangular type (50 ± 0,5) mm x 200 mm according to Figure 1 and Table 1
- Method B; dumb-bell type (6 ± 0,4) mm x 115 mm according to Figure 2 and Table 1

Any non permanent surface layer should be removed.

Test specimens with a mesh or fabric internal layer, backing or laminated reinforcement shall have the same number of threads in their longitudinal and transversal direction. Cutting of threads should be avoided.

Condition the test specimens, prior to testing, for at least 20 h in a standard atmosphere of (23 ± 2) °C and (50 ± 5) % relative humidity.

8 Procedure

In the case of method B, the thickness is measured as the effective thickness of the sheet according to EN 1849-2.

The test specimen shall be tightly clamped in the tensile test machine grips (Clause 5) taking care that the longitudinal axis of the test specimens and the axis of the testing machine and grips are correctly