



SLOVENSKI STANDARD
SIST EN 15930:2010
01-december-2010

Vlakna - Elastičnost vlaken - Preskusne metode

Fibres - Elasticity of fibres - Test methods

Faser - Elastizität von Fasern - Prüfung

Fibres - Élasticité des fibres - Méthodes d'essai

Ta slovenski standard je istoveten z: EN 15930:2010

[SIST EN 15930:2010
https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010](https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

ICS:

59.060.01 Tekstilna vlakna na splošno Textile fibres in general

SIST EN 15930:2010

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15930:2010

<https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>

EUROPEAN STANDARD

EN 15930

NORME EUROPÉENNE

EUROPÄISCHE NORM

September 2010

ICS 59.060.01

English Version

Fibres - Elasticity of fibres - Test methods

Fibres - Elasticité des fibres - Méthodes d'essais

Fasern - Elastizität von Fasern - Prüfung

This European Standard was approved by CEN on 7 August 2010.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

(standards.iteh.ai)

[SIST EN 15930:2010](https://standards.iteh.ai/catalog/standards/sist/8aceabf6-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

<https://standards.iteh.ai/catalog/standards/sist/8aceabf6-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Principle.....	5
5 Apparatus	5
6 Atmosphere of conditioning and testing	6
7 Sampling.....	6
8 Preparation of the test specimens	6
9 Procedure	7
10 Calculation and expression of the results	11
11 Test report	12
Annex A (normative) "Elastic" qualification of fibres.....	14
Bibliography	15

iTech STANDARD PREVIEW
(standards.itech.ai)

SIST EN 15930:2010
<https://standards.itech.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>

Foreword

This document (EN 15930:2010) has been prepared by Technical Committee CEN/TC 248 "Textiles and textile products", the secretariat of which is held by BSI.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by March 2011, and conflicting national standards shall be withdrawn at the latest by March 2011.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 15930:2010](https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

<https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>

EN 15930:2010 (E)**1 Scope**

This test method covers the determination of the elasticity of fibres and may lead to classification of the fibre as elastic fibre (see Annex A).

It is applicable to single man-made crimped and uncrimped fibres.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 12751, *Textiles — Sampling of fibres, yarns and fabrics for testing*

EN ISO 139, *Textiles — Standard atmospheres for conditioning and testing (ISO 139:2005)*

EN ISO 1973, *Textile fibres — Determination of linear density — Gravimetric method and vibroscope method (ISO 1973:1995)*

EN ISO 7500-1, *Metallic materials — Verification of static uniaxial testing machines — Part 1: Tension/compression testing machines — Verification and calibration of the force-measuring system (ISO 7500-1:2004)*

STANDARD PREVIEW
(standards.iteh.ai)

3 Terms and definitions

SIST EN 15930:2010

<https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682->

[b313744202f5/sist-en-15930-2010](https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

For the purposes of this document, the following terms and definitions apply.

- 3.1 elasticity**
property of a fibre by virtue of which it tends to recover its original size and shape immediately after the removal of the force causing deformation
- 3.2 linear density**
mass per unit length of an essentially linear structure
- 3.3 constant-rate-of-extension (CRE) testing machine**
tensile testing machine provided with one clamp, which is virtually stationary, and another clamp, which moves with a constant speed throughout the test, the entire testing system being virtually free from deflection
- 3.4 gauge length**
distance between the two effective clamping or holding points of a testing device
- 3.5 initial length**
length of the test specimen between the two effective clamping or holding points at the required pretension, before testing

3.6**extension**

increase in length of a test specimen expressed in units of length e.g. millimetres

3.7**elongation**

ratio of the extension of the test specimen to its initial length, expressed as a percentage

3.8**maximum force**

force recorded in Newton at the position when a test specimen is taken to a fixed extension

3.9**cycle**

process whereby a fibre is taken from the gauge length to fixed extension or elongation and returned to gauge length

3.10**elastic recovery**

recovered elongation expressed as a percentage of the specified elongation

3.11**permanent deformation**

ratio of un-recovered extension of the test specimen after cycling to its initial length, expressed as a percentage

3.12**force decay**

loss of force measured over time when a test specimen is stretched to a specified elongation or extension and held at this position for a given time period

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 15930:2010](https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

<https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>

4 Principle

The measurements are performed on an individual fibre.

A fibre is cycled between the gauge length and a specified elongation at a constant rate for an agreed number of cycles. The fibre can be maintained at the specified elongation or at the gauge length – for a specific period of time. Its elasticity is determined by measuring certain physical characteristics.

5 Apparatus**5.1 Pretension device**

Pretension device able to apply $(0,010 \pm 0,005)$ cN/tex on the individual test specimen.

NOTE Pretension may be applied using masses with discontinuous values (e.g. adhesive paper or clips) or using a high-resolution load cells.

5.2 Tensile testing machine

The constant-rate-of-extension (CRE) testing machine shall conform to the following.

- a) The tensile testing machine shall be provided with the means for indicating or recording the force and elongation values when cycling between gauge length and either a fixed load or fixed extension. Under conditions of use, the accuracy of the apparatus shall be at least class 1 of EN ISO 7500-1. The error of

EN 15930:2010 (E)

the indicated or recorded maximum force at any point in the range in which the machine is used shall not exceed 1 %, and the error of the indicated or recorded jaw separation shall not exceed 1 mm.

- b) If recording of force or elongation is obtained by means of data acquisition boards and software, the frequency of data collection shall be at least eight per second.
- c) The machine shall be capable of constant rates of extension from $(20,0 \pm 0,5)$ mm/min to $(50,0 \pm 0,5)$ mm/min.
- d) The machine shall be capable of variable gauge length settings from $(20,0 \pm 0,5)$ mm to $(50,0 \pm 0,5)$ mm.
- e) The clamping or holding devices shall be positioned with the centre in line with the applied force.

The jaws shall be capable of holding the test specimen without allowing it to slip and designed so that they do not cut or otherwise weaken the test specimen.

6 Atmosphere of conditioning and testing

Samples shall be conditioned in a tension free state for at least 16 h in the standard atmosphere according to EN ISO 139.

Testing shall be performed in this standard atmosphere.

7 Sampling

iTeh STANDARD PREVIEW
(standards.iteh.ai)

The sampling of the fibres to be tested from staple fibres, from yarns or from fabrics shall be according to EN 12751.

[SIST EN 15930:2010](https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

<https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>

8 Preparation of the test specimens**8.1 Preparation from staples**

In order to isolate one fibre first open very carefully the sample in a direction perpendicular to the local fibre orientation, taking care to apply the force at two points sufficiently distant to allow free fibre movements necessary to disentangle the fibre mass.

In the middle of the small web thus created extract one fibre by using tweezers. There shall be no resistance.

If there is any entanglement, first open this entanglement by pulling the fibres sideways before extracting.

Avoid stretching a fibre, even lightly, by drawing it by one of its ends.

Once separated, the fibre can be pinched at one of its ends for handling.

8.2 Preparation from yarns

For all types of yarns (e.g. monofilament or fused multifilament alone, fused multifilament in core spun – e.g. elastane -, multifilament, etc.), take randomly at least five lengths (approx. 20 cm) from the yarn package.

8.3 Preparation from fabrics

For all types of fabric, remove at least five threads (approx. 20 cm) in the production direction (i.e. warp direction for woven fabric, wales' direction for knitted fabric) and/or in the perpendicular production direction (i.e. weft direction for woven fabric and courses' direction for knitted fabric).

9 Procedure

9.1 Determination of the linear density

Determine the linear density testing according to EN ISO 1973 using only the gravimetric method.

NOTE In the case of crimped fibres, the crimp should be removed in order to determine the length.

9.2 Number of results for determination of the elasticity properties

Determine at least five results.

9.3 Determination of the pretension

Based on the determination of the linear density, calculate the pretension force to be applied using a pretension of 0,01 cN/tex.

When applicable (in the case of the use of discontinuous values of pretension masses), choose the nearest pretension mass to fix onto the fibre in vertical position.

9.4 Determination of the elasticity

[SIST EN 15930:2010](https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010)

9.4.1 General

<https://standards.iteh.ai/catalog/standards/sist/8aceabfe-bc9e-4279-b682-b313744202f5/sist-en-15930-2010>

Set the gauge length to 50 mm. If it cannot be achieved, then set to 20 mm.

Set the testing speed at 100 % of the gauge length/minute (i.e. 50 mm/min for gauge length 50 mm).

Zero the load cell with the grips in position and the jaw faces closed, prior to testing.

NOTE See Figure 1 for illustration of the elongation-force curve and the position of the pretension point.