



SLOVENSKI STANDARD

SIST ISO 18928:2011

01-julij-2011

Upodobitveni materiali - Neprocesirani fotografski filmi in papirji - Shranjevanje

Imaging materials - Unprocessed photographic films and papers - Storage practices

Matériaux pour l'image - Films et papiers photographiques non traités - Pratiques de stockage

(standards.iteh.ai)

Ta slovenski standard je istoveten z: ISO 18928:2011

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

ICS:

37.040.20	Fotografski papir, filmi in fotografske plošče. Filmski zvitki	Photographic paper, films and cartridges
-----------	--	--

SIST ISO 18928:2011

en

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 18928:2011

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

INTERNATIONAL STANDARD

**ISO
18928**

Second edition
2002-02-01

Imaging materials — Unprocessed photographic films and papers — Storage practices

*Matériaux pour l'image — Films et papiers photographiques non traités —
Pratiques de stockage*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST ISO 18928:2011](https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011)

[https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-
9e1cea19f143/sist-iso-18928-2011](https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011)



Reference number
ISO 18928:2002(E)

© ISO 2002

ISO 18928:2002(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 18928:2011](https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011)

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Term and definition	1
3 Storage conditions	1
3.1 General	1
3.2 Relative humidity	1
3.3 Temperature	2
3.4 Gases	2
3.5 Extraneous radiations	2
4 Temperature acclimatization	3
5 Mechanical requirements	3
6 Handling conditions	3

Annexes

A Numbering system for related International Standards.....	5
B Background radiation	7
Bibliography.....	8

SIST ISO 18928:2011
<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

ISO 18928:2002(E)**Foreword**

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 18928 was prepared by Technical Committee ISO/TC 42, *Photography*.

This second edition cancels and replaces the first edition (ISO 10331:1991), which has been technically revised.

This International Standard is one of a series of standards dealing with the physical properties and stability of imaging materials. To facilitate identification of these International Standards, they are assigned a number within the block from 18900 to 18999 (see annex A).

Annexes A and B of this International Standard are for information only.

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

Introduction

International Standards have been written specifying the recommended practices for the storage of processed safety photographic film (ISO 18911), processed photographic reflection prints (ISO 18920), processed photographic plates (ISO 18918) and the specifications for safety film (ISO 18906).

This International Standard is concerned with the storage of unprocessed photographic materials. While many of the recommendations for unprocessed and processed storage are very similar, there are some important differences. These include the very beneficial effects of low temperature and the harmful effects of adverse storage and radiation.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST ISO 18928:2011](https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011)

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST ISO 18928:2011

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

Imaging materials — Unprocessed photographic films and papers — Storage practices

1 Scope

This International Standard specifies recommended storage conditions for unprocessed photographic materials. It is not applicable to processed films and prints.

This International Standard is applicable to black-and-white and colour photographic materials (negative films, positive films, reversal films, positive papers, and X-ray films) as well as to safety films.

2 Term and definition

For the purposes of this International Standard, the following term and definition apply.

2.1

raw photographic material iTeh STANDARD PREVIEW
photographic material that has not been exposed to actinic radiation and has not been processed
(standards.iteh.ai)

3 Storage conditions

[SIST ISO 18928:2011](https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011)

<https://standards.iteh.ai/catalog/standards/sist/038fb39d-36e9-4db4-aad1-9e1cea19f143/sist-iso-18928-2011>

3.1 General

The photographic properties of imaging materials change during ageing. These changes result from high temperatures and high relative humidities and may also be influenced by plastics, papers, solvents, lacquers, varnishes, gases (see 3.4) and extraneous radiation (see 3.5). Frequent temperature changes may also have adverse effects.

Changes caused by unfavourable storage conditions may be much greater than those due to variations in original manufacture. It is important to comply with the manufacturer's recommended storage conditions and, where given, to an expiration date.

Films and papers should be exposed and processed as soon as possible after the original package has been opened. Opened packages should be resealed under recommended conditions for further storage.

3.2 Relative humidity

Photographic material should generally be kept in equilibrium with 40 % to 60 % relative humidity (RH). Containers shall be kept sealed until the material is used.

Films and papers are not usually stored for long periods between exposing and processing. Production schedules, customer needs, latent image fading or growth, etc., are important factors here. Furthermore, vesicular, diazo, thermally processed silver and electrographic type materials are normally processed immediately.

If conventional sheet films or papers are not to be processed immediately, they may be stored in commercially available light-tight "paper safes" or in the manufacturer's original container.