
Lesene konstrukcije - Razvrščanje konstrukcijskega lesa pravokotnega prečnega prereza po trdnosti - 4. del: Strojno razvrščanje – Nastavitve strojev za razvrščanje pri strojno kontroliranih sistemih

Timber structures - Strength graded structural timber with rectangular cross section - Part 4: Machine grading - Grading machine settings for machine controlled systems

Holzbauwerke - Nach Festigkeit sortiertes Bauholz für tragende Zwecke mit rechteckigem Querschnitt - Teil 4: Maschinelle Sortierung - Einstellungen von Sortiermaschinen für maschinenkontrollierte Systeme

Structures en bois - Bois de structure de section rectangulaire classé selon la résistance - Partie 4: Classement par machine - Réglages pour les systèmes de contrôle par machine

Ta slovenski standard je istoveten z: EN 14081-4:2005+A1:2007

ICS:

79.040	Les, hlodovina in žagan les	Wood, sawlogs and sawn timber
91.080.20	Lesene konstrukcije	Timber structures

SIST EN 14081-4:2006+A1:2007 **en,fr,de**

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14081-4:2006+A1:2007](https://standards.iteh.ai/catalog/standards/sist/60c6d0c4-e5f8-48fb-9c09-bc8f9fb12f09/sist-en-14081-4-2006a1-2007)

<https://standards.iteh.ai/catalog/standards/sist/60c6d0c4-e5f8-48fb-9c09-bc8f9fb12f09/sist-en-14081-4-2006a1-2007>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN 14081-4:2005+A1

February 2007

ICS 91.080.20

Supersedes EN 14081-4:2005

English Version

**Timber structures - Strength graded structural timber with
rectangular cross section - Part 4: Machine grading - Grading
machine settings for machine controlled systems**

Structures en bois - Bois de structure de section
rectangulaire classé selon la résistance - Partie 4:
Classement par machine - Réglages pour les systèmes de
contrôle par machine

Holzbauwerke - Nach Festigkeit sortiertes Bauholz für
tragende Zwecke mit rechteckigem Querschnitt - Teil 4:
Maschinelle Sortierung - Einstellungen von
Sortiermaschinen für maschinenkontrollierte Systeme

This European Standard was approved by CEN on 26 August 2005 and includes Amendment 1 approved by CEN on 28 December 2006.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents		Page
	Foreword	3
1	Scope	4
2	Normative references	4
3	Terms and definitions	4
4	Symbols	4
5	Settings for timber strength grading machines	5

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[SIST EN 14081-4:2006+A1:2007](https://standards.iteh.ai/catalog/standards/sist/60c6d0c4-e5f8-48fb-9c09-bc8f9fb12f09/sist-en-14081-4-2006a1-2007)
<https://standards.iteh.ai/catalog/standards/sist/60c6d0c4-e5f8-48fb-9c09-bc8f9fb12f09/sist-en-14081-4-2006a1-2007>

Foreword

This European Standard (EN 14081-4:2005+A1:2007) has been prepared by Technical Committee CEN/TC 124 "Timber structures", the secretariat of which is held by SFS.

This document shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by August 2007 and conflicting national standards shall be withdrawn at the latest by August 2007.

This document includes Amendment 1, approved by CEN on 2006-12-28.

This document supersedes EN 14081-4:2005.

The start and finish of text introduced or altered by amendment is indicated in the text by tags $\boxed{A_1}$ $\boxed{A_1}$.

Other parts of this European Standard are

EN 14081-1, *Timber structures - Strength graded structural timber with rectangular cross section - Part 1: General requirements*

EN 14081-2, *Timber structures - Strength graded structural timber with rectangular cross section - Part 2: Machine Grading - Additional requirements for initial type testing*

EN 14081-3, *Timber structures - Strength graded structural timber with rectangular cross section - Part 3: Machine Grading - Additional requirements for factory production control*

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

EN 14081-4:2005+A1:2007 (E)**1 Scope**

This European Standard gives settings, derived according to the requirements given in EN 14081-2, for various combinations of strength classes or grades, grading machines and species from particular sources of growth. These settings are only applicable to timber from the sources indicated in the tables.

2 Normative references

The following referenced documents are indispensable for the application of this European Standard. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 336, *Structural timber – Sizes, permitted deviations*

EN 14081-1:2005, *Timber structures - Strength graded structural timber with rectangular cross section - Part 1: General requirements*

EN 14081-2:2005, *Timber structures - Strength graded structural timber with rectangular cross section - Part 2: Machine Grading - Additional requirements for initial type testing*

3 Terms and definitions

For the purpose of this European Standard the terms and definitions in EN 14081-1:2005 and EN 14081-2:2005 and the following apply

3.1 Speed range

maximum and minimum throughput speeds appropriate to the critical speed for the derived settings (see 6.2.2 of EN 14081-2:2005).

4 Symbols

a	deflection (in mm)
b	width of timber cross section (in mm)
F	force (units as stated)
I	indicating property (units as stated)
P	pressure (units as stated)
t	thickness of timber cross section (in mm)
$E_{t,mean}$	characteristic mean tensile modulus of elasticity parallel to grain (in N/mm ²)
$f_{t,k}$	characteristic tensile strength (in N/mm ²)
ρ_k	characteristic value of density (in kg/m ³)

subscripts

n for setting being calculated

a actual size measured as the average dimension of a batch

5 Settings for timber strength grading machines

Tables 1 to 6 give settings for certain grades, timber species and types of grading machine.

Settings for other grades, species or grading machines shall be added when the relevant information is sent to, and assessed by, CEN/TC 124.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 14081-4:2006+A1:2007

<https://standards.iteh.ai/catalog/standards/sist/60c6d0c4-e5f8-48fb-9c09-bc8f9fb12f09/sist-en-14081-4-2006a1-2007>

Table 1 — Settings for Cook Bolinder (Tecmach) machine types SG-AR, SG-AF and SG-TF

Source country or countries	Source mark ^{a)}	Species	Permitted timber sizes ^{b)} (mm)	Grade ^{c)} or grade Combination	Model value	Feed speed Range (m/min)	Comments and additional requirements
UK Ireland	GB IE	Spruce <i>Picea abies</i> <i>Picea sitchensis</i>	$35 \leq t_n \leq 75$	C24 C16	$F = 2,68$ $F = 2,27$	150 max	Minimum temperature of timber at time of grading shall be $-10\text{ }^\circ\text{C}$. The following equations shall be used to calculate settings for the target size $b_n \times t_n$. (Note. For timber with a thickness to tolerance class 1, i.e. sawn, t_n in the following equations is the target $t_n + 1$ mm). $a_n = 830,7 t_n^{-1,299}$ $P_n = 4,412 F_n / t_n^{0,61}$ $F_n = \frac{F b_n t_n^{1,701}}{(413,9 t_n + 572,73)}$ (kN)
			$60 \leq b_n \leq 300$	C16	$F = 1,24$	150 max	
		Pine <i>Pinus nigra</i> <i>Pinus sylvestris</i>	$35 \leq t_n \leq 75$	C24 C16	$F = 2,79$ $F = 1,90$	150 max	
			$60 \leq b_n \leq 300$	C16	$F = 1,34$	150 max	
Chile	CL	Radiata pine <i>Pinus radiata</i>	$44 \leq t_n \leq 50$	C27 C16	$F = 2,48$ $F = 1,64$	150 max	
			$60 \leq b_n \leq 300$	C24 C16	$F = 2,35$ $F = 1,92$	150 max	
^{a)} See 7.3 of EN 14081-1:2005. ^{b)} Timber sizes shall be to EN 336. ^{c)} Grades prefixed by C are strength classes given in EN 338.							

SISTEN 14081-4:2005+A1:2007
 (standards.iteh.ai)
 STANDARD PREVIEW

Table 1 — Settings for Cook Bolinder (Tecmach) machine types SG-AR, SG-AF and SG-TF (continued)

Source country or countries	Source mark ^{a)}	Species	Permitted timber sizes ^{b)} (mm)	Grade ^{c)} or grade Combination	Model value	Feed speed Range (m/min)	Comments and additional requirements
Estonia Finland Latvia Norway Russia ^{d)} Sweden A1) Poland A1)	EE FI LV NO RU SE A1) PL A1)	Spruce <i>Picea</i> <i>abies</i> Pine <i>Pinus</i> <i>Sylvestris</i>	$30 \leq t_n \leq 75$ $60 \leq b_n \leq 300$	C18 C24 C27 C30 C24 C35 C18 C30 C40	$f_{mod} = 20,8$ $f_{mod} = 20,8$ $f_{mod} = 21,8$ $f_{mod} = 28,5$ $f_{mod} = 20,0$ $f_{mod} = 46,5$ $f_{mod} = 23,8$ $f_{mod} = 30,6$ $f_{mod} = 54,5$	150 max	Air temperature to be +10 °C min. +35 °C max. Minimum timber temperature to be -10 °C. Maximum relative humidity to be 85 %. Timber mean moisture content to be > 10 %. The following equations shall be used to calculate settings for the target size $b_n \times t_n$. (Note. For timber with a thickness to tolerance class 1, i.e. sawn, t_n in the following equations is the target $t_n + 1$ mm). $F_n = (5,5 I_n a_n b_n t_n^3) 10^{-9} \quad (N)$ $a_n = 830,7 t_n^{-1,299}$ $I_n = \left[\frac{4228}{t_n^{0,22} b_n^{0,24}} \right] f_{mod}^{0,79}$

^{a)} See 7.3 of EN 14081-1:2005.

^{b)} Timber sizes shall be to EN 336.

^{c)} Grades prefixed by C are strength classes given in EN 338.

^{d)} Settings apply only to timber grown west of the Ural mountain range in Russia.

<https://standards.iteh.ai/catalog/standards/sist/6c66d0c4-c5f8-81b-9c09-bc8f9fb12f09/sist-en-14081-4-2006a1-2007>
 SIST EN 14081-4:2006+A1:2007
 (standards.iteh.ai)
 iTeh STANDARD PREVIEW

Table 1 — Settings for Cook Bolinder (Tecmach) machine types SG-AR, SG-AF and SG-TF (continued)

Source country or countries	Source mark ^{a)}	Species	Permitted timber sizes ^{b)} (mm)	Grade ^{c)} or grade combination	Model value	Feed speed Range (m/min)	Comments and additional requirements
Spain	ES	Scots pine <i>Pinus Sylvestris</i>	35 ≤ t _n ≤ 75 60 ≤ b _n ≤ 300	C27 C16	F = 2,84 F = 1,71	100 max	Minimum temperature of timber at time of grading shall be -10 °C. The following equations shall be used to calculate settings for the target size b _n x t _n . (Note. For timber with a thickness to tolerance class 1, i.e. sawn, t _n in the following equations is the target t _n + 1 mm). a _n = 830,7 t _n ^{-1,299} P _n = 4,412 F _n / t _n ^{0,61} $F_n = \frac{F b_n t_n^{1,701}}{(413,9 t_n + 572,73)} \text{ (kN)}$
Spain	ES	Corsican pine <i>Pinus nigra</i>	40 ≤ t _n ≤ 70 100 ≤ b _n ≤ 200	C30 C18	Not relevant as all settings shall be calculated using equations in comments column	100 max	Minimum temperature of timber at time of grading shall be -10 °C. The following equations shall be used to calculate settings for the target size b _n x t _n . (Note. For timber with a thickness to tolerance class 1, i.e. sawn, t _n in the following equations is the target t _n + 1 mm). a _n = 830,7 t _n ^{-1,299} P _n = 4,412 F _n / t _n ^{0,61} F _n C30 = (96,2979 - 0,489321t _n)a _n b _n t _n ³ / (1,3189433.10 ⁹) F _n C18 = (54,4979 - 0,489321t _n)a _n b _n t _n ³ / (1,3189433.10 ⁹)
^{a)} See 7.3 of EN 14081-1:2005. ^{b)} Timber sizes shall be to EN 336. ^{c)} Grades prefixed by C are strength classes given in EN 338.							

<https://standards.iteh.ai/catalog/standards/sist/60c6d0c4-c5f8-48fb-9c09-bc87db12d09/sist-en-14081-4-2006a1-2007>
(standards.iteh.ai)
ITeH STANDARD PREVIEW

Table 2 — Settings for Computermatic and Micromatic machines

Source country or countries	Source mark ^{a)}	Species	Permitted timber sizes ^{b)} (mm)	Grade ^{c)} or grade combination	Model Value	Feed speed Range (m/min)	Comments and additional requirements	
					Deflection a (mm)			
UK Ireland	GB IE	Spruce <i>Picea abies</i> <i>Picea sitchensis</i>	$35 \leq t_n \leq 75$ $60 \leq b_n \leq 300$	C24 C16	6,35 7,49	105 max	Minimum temperature of timber at time of grading shall be -10 °C. The following equations shall be used to calculate settings for the target size $b_n \times t_n$. (Note. For timber with a thickness to tolerance class 1, i.e. sawn, t_n in the following equations is the target $t_n + 1$ mm). Actual deflection settings are determined from $a_n/0,19$ rounded to the nearest whole number. Refer to calibration tables for machine to convert Force F_n to pressure setting $F_n = 0,0101 b_n t_n^2$ $a_n = \frac{36,71a(0,00567t_n + 0,7846)}{t_n(0,9851 \times 10^{-5} t_n b_n + 0,91)}$	
				C16	13,78	105 max		
		Pine <i>Pinus nigra</i> <i>Pinus sylvestris</i>	$35 \leq t_n \leq 75$ $60 \leq b_n \leq 300$	C24 C16	6,10 8,97	105 max		
				C16	12,74	105 max		
Chile	CL	Radiata pine <i>Pinus radiata</i>	$44 \leq t_n \leq 50$ $60 \leq b_n \leq 300$	C27 C16	6,89 10,37	105 max		
				C24 C16	7,25 8,88	105 max		
		^{a)} See 7.3 of EN 14081-1:2005. ^{b)} Timber sizes shall be to EN 336. ^{c)} Grades prefixed by C are strength classes given in EN 338.						