



Designation: B 333 – 03

Standard Specification for Nickel-Molybdenum Alloy Plate, Sheet, and Strip¹

This standard is issued under the fixed designation B 333; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

1. Scope

1.1 This specification² covers plate, sheet, and strip of nickel-molybdenum alloys (UNS N10001, N10665, N10675, N10629, and N10624)* as shown in Table 1, for use in general corrosive service.

1.2 The following products are covered under this specification:

1.2.1 *Sheet and Strip*—Hot or cold rolled, solution annealed, and descaled unless solution anneal is performed in an atmosphere yielding a bright finish.

1.2.2 *Plate*—Hot or cold rolled, solution annealed, and descaled.

1.3 The values stated in inch-pound units are to be regarded as the standard. The values given in parentheses are for information only.

1.4 *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to become familiar with all hazards including those identified in the appropriate Material Safety Data Sheet for this product/material as provided by the manufacturer, to establish appropriate safety and health practices, and determine the applicability of regulatory limitations prior to use.*

2. Referenced Documents

2.1 ASTM Standards:

- B 906 Specification for General Requirements for Flat-Rolled Nickel and Nickel Alloys Plate, Sheet, and Strip³
- E 112 Test Methods for Determining the Average Grain Size⁴

¹ This specification is under the jurisdiction of ASTM Committee B02 on Nonferrous Metals and Alloys and is the direct responsibility of Subcommittee B02.07 on Refined Nickel and Cobalt and Their Alloys.

Current edition approved June 10, 2003. Published July 2003. Originally approved in 1958. Last previous edition approved in 1998 as B 333 – 98.

* New designation established in accordance with ASTM E 527 and SAE J 1086, Practice for Numbering Metals and Alloys (UNS).

² For ASME Boiler and Pressure Vessel Code applications, see related Specification SB-333 in Section II of that Code.

³ *Annual Book of ASTM Standards*, Vol 02.04.

⁴ *Annual Book of ASTM Standards*, Vol 03.01.

TABLE 1 Chemical Requirements

Element	Composition Limits, %				
	Alloy N10001	Alloy N10665	Alloy N10675	Alloy N10629	Alloy N10624
Nickel	remainder ^A	remainder ^A	65.0 min	remainder ^A	Bal
Molybdenum	26.0–30.0	26.0–30.0	27.0–32.0	26.0–30.0	21.0–25.0
Iron	4.0–6.0	2.0 max	1.0–3.0	1.0–6.0	5.0–8.0
Chromium	1.0 max	1.0 max	1.0–3.0	0.5–1.5	6.0–10.0
Carbon, max	0.05	0.02	0.01	0.01	0.01
Silicon, max	1.0	0.10	0.10	0.05	0.10
Cobalt, max	2.5	1.00	3.0	2.5	1.0
Manganese, max	1.0	1.0	3.0	1.5	1.0
Phosphorus, max	0.04	0.04	0.030	0.04	0.025
Sulfur, max	0.03	0.03	0.010	0.01	0.01
Vanadium	0.2–0.4	...	0.20 max
Nickel plus Molybdenum	94.0–98.0
Aluminum	0.50 max	0.1–0.5	0.5
Columbium (Nb), max	0.20
Copper, max	0.20	0.5	0.5
Tantalum, max	0.20
Titanium, max	0.20
Tungsten, max	3.0
Zirconium, max	0.10
Magnesium, max

^ASee Specification B 906.

3. Terminology

3.1 Definitions of Terms Specific to This Standard:

3.1.1 *cold-rolled plate*—material $\frac{3}{16}$ to $\frac{3}{8}$ in. (4.76 to 9.52 mm), inclusive, in thickness.

3.1.2 *hot-rolled plate*—material $\frac{3}{16}$ in. (4.76 mm) and over in thickness.

3.1.3 *plate*—material $\frac{3}{16}$ in. (4.76 mm) and over in thickness.

3.1.4 *sheet and strip*—material under $\frac{3}{16}$ in. (4.76 mm) in thickness.