
**Petroleum and natural gas industries —
Aluminium alloy drill pipe**

*Industries du pétrole et du gaz naturel — Tige de forage en alliage
d'aluminium*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 15546:2002](https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002)

[https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-
9e113b7f24ed/iso-15546-2002](https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15546:2002

<https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002>

© ISO 2002

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword.....	iv
Introduction	v
1 Scope.....	1
2 Normative references	1
3 Terms, definitions and symbols	1
3.1 Terms and definitions.....	1
3.2 Symbols	2
4 Information to be supplied by purchaser	3
5 Process of manufacture and delivery condition.....	4
5.1 General	4
5.2 Heat treatment.....	4
5.3 Traceability	4
5.4 Delivery condition	5
6 Material requirements.....	5
6.1 Material groups.....	5
6.2 Metallographic examination.....	6
6.3 Chemical composition.....	6
6.4 Steel tool joints	6
7 Configuration and dimensions of pipes.....	6
7.1 Configuration.....	6
7.2 Length	6
7.3 Dimensions of pipes and tool joints	7
7.4 Design mass	7
7.5 Upset run-out.....	17
7.6 Straightness	17
7.7 Ovality and eccentricity of pipes.....	17
7.8 Drift requirements	17
7.9 Internal coating	18
7.10 Drill pipe–tool joint assembly	18
8 Test methods.....	18
9 Measuring methods	19
10 Inspection	19
11 Marking	20
12 Packaging, transport and storage.....	21
13 Documents.....	21
13.1 Certification	21
13.2 Retention of records	21
14 Delivery conditions	21
Annex A (normative) Purchaser inspection.....	22
Annex B (normative) Supplementary requirement — Full scale fatigue design verification test.....	23
Annex C (normative) Corrosion test.....	25
Bibliography	26

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15546 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15546:2002

<https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002>

Introduction

Users of this International Standard need to be aware that further or differing requirements could be needed for individual applications. This International Standard is not intended to inhibit a manufacturer from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application — particularly applicable where there is innovative or developing technology. Where an alternative is offered, the manufacturer will need to identify any variations from this International Standard and provide details.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 15546:2002](https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002)

<https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15546:2002

<https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002>

Petroleum and natural gas industries — Aluminium alloy drill pipe

1 Scope

This International Standard specifies the technical delivery condition, manufacturing process, material requirements, configuration and dimensions, and verification and inspection procedures for aluminium alloy drill pipes with or without attached steel tool joints for use in drilling and production operations in the petroleum and natural gas industries.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 2566-1, *Steel — Conversion of elongation values — Part 1: Carbon and low alloy steels*

ISO 6892, *Metallic materials — Tensile testing at ambient temperature*

ISO 9303, *Seamless and welded (except submerged arc-welded) steel tubes for pressure purposes — Full peripheral ultrasonic testing for the detection of longitudinal imperfections*

ISO 11484, *Steel tubes for pressure purposes — Qualification and certification of non-destructive testing (NDT) personnel*

ASTM¹⁾ A370, *Standard Test Methods and Definitions for Mechanical Testing of Steel Products*

ASTM G1, *Standard Practice for Preparing, Cleaning, and Evaluating Corrosion Test Specimens*

ASTM G44, *Standard for Exposure of Metals and Alloys by Alternate Immersion in Neutral 3,5 % Sodium Chloride Solution*

API²⁾ Spec 7, *Specification for Rotary Drill Stem Elements*

Manual on Statistical Planning and Analysis for Fatigue Experiments — STP-588, ASTM

3 Terms, definitions and symbols

3.1 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

1) American Society for Testing and Materials, 1916 Race Street, Philadelphia, Pennsylvania 19103-1187, USA.

2) American Petroleum Institute, 1220 L Street NW, Washington D.C. 20005, USA.

ISO 15546:2002(E)

3.1.1

defect

imperfection of sufficient magnitude to warrant rejection of the product

NOTE Rejection will be based on the provisions of this International Standard.

3.1.2

drill pipe

seamless pipe used to rotate the drill bit and circulate the drilling mud, pipes being coupled together by means of tool joints

3.1.3

heat

metal produced by a single cycle of a batch melting process

3.1.4

imperfection

discontinuity or irregularity in the product

NOTE Imperfections are detected by methods outlined in this International Standard.

3.1.5

lot

lengths of pipe with the same specified dimensions and grade, heat treated as part of a continuous operation (or batch), and which are of a single heat or from different heats grouped according to documented procedure

NOTE The documented procedure will ensure that the appropriate requirements of this International Standard are met.

3.1.6

manufacturer

firm, company or corporation responsible for marking the product

NOTE Marking by the manufacturer warrants that the product conforms to this International Standard, and it is the manufacturer who is responsible for compliance with all of its applicable provisions.

3.1.7

pipe mill

firm, company or corporation that operates pipe-making facilities

3.1.8

processor

firm, company or corporation that operates facilities capable of cutting the threads and assembly of the pipe with the tool joints

3.1.9

seamless pipe

wrought tubular product made without a welded seam, manufactured by hot working and, if necessary, by subsequent cold finishing of the tubular product to produce the desired shape, dimensions and properties

3.2 Symbols

The following symbols are used in this International Standard.

- D Pipe body outside diameter, expressed in millimetres
- D_1 Outside diameter of upset end, expressed in millimetres
- D_2 Diameter, thread end groove in the pipe end plane, expressed in millimetres
- D_3 Pipe end outside diameter, expressed in millimetres

D_4	Pipe thread outside diameter in the end plane, expressed in millimetres
D_5	Minor diameter of the pipe thread at the gauge point, expressed in millimetres
D_6	Diameter of the tapered seal at the gauge point of the pipe, expressed in millimetres
D_{pt}	Outside diameter of protector thickening, expressed in millimetres
D_s	Tool joint bevel diameter, expressed in millimetres
D_{se}	Tool joint elevator bevel diameter, expressed in millimetres
D_{tj}	Tool joint outside diameter, expressed in millimetres
d	Pipe body inside diameter, expressed in millimetres
d_3	Diameter of the tapered seal at the plane of the end of the tool joint, expressed in millimetres
d_4	Tool joint thread inside diameter in the end plane, expressed in millimetres
d_5	Minor diameter of the tool joint thread at the gauge point, expressed in millimetres
d_6	Diameter of the tapered seal at the gauge point of the tool joint, expressed in millimetres
d_{tp}	Tool joint pin inside diameter, expressed in millimetres
d_{tb}	Tool joint box inside diameter, expressed in millimetres
l	Distance from tool joint end plane to inside shoulder face, expressed in millimetres
l_1	Length of upset end, expressed in millimetres
l_2	Length of upset end transition zone, expressed in millimetres
l_3	Length of protector thickening, expressed in millimetres
l_4	Length of protector thickening transition zone, expressed in millimetres
l_5	Unfinished surface, expressed in millimetres
l_p	Pipe length without tool joint, expressed in metres (the distance between the pipe ends)
l_{pj}	Pipe length with tool joint, expressed in metres (the distance between the tool joint box face and pin shoulder)
l_{tb}	Tool joint box length, expressed in millimetres
l_{tp}	Tool joint pin length, expressed in millimetres
t	Wall thickness of pipe body, expressed in millimetres
t_1	Wall thickness of upset end, expressed in millimetres

4 Information to be supplied by purchaser

4.1 In placing orders for drill pipe without threads, with threads but without tool joints, or with tool joints attached, the purchaser shall specify the following on the purchase order:

- a) reference to this International Standard (i.e. "ISO 15546");

- b) quantity;
- c) internal upset, external upset, external or internal upset and protector thickening (see Tables 4 to 7);
- d) drill pipe delivery condition (see 5.4 and Clause 14);
- e) outside diameter (see Tables 4 to 7);
- f) wall thickness (see Tables 4 to 7);
- g) material group (see Table 1);
- h) length (see 7.2, Table 3);
- i) delivery date and shipping instruction;
- j) inspection by purchaser (see Annex A);
- k) alternatives of tool joints (see Figure 7).

4.2 The purchaser should also state on the purchase order any requirements concerning the following stipulations, which are at the option of the purchaser:

- a) pipe coatings (see 7.9);
- b) marking requirements (see Clause 11);
- c) non-destructive inspection (see 10.4);
- d) corrosion rate test for Group IV chemistry (see Table 1);
- e) test certificates (see 13.1);
- f) alloy system (see Table 1).

STANDARD PREVIEW

(standards.iteh.ai)

ISO 15546:2002

<https://standards.iteh.ai/catalog/standards/sist/49817651-6acc-41b5-b4b2-9e113b7f24ed/iso-15546-2002>

5 Process of manufacture and delivery condition

5.1 General

Drill pipe furnished to this International Standard shall be made by the seamless process.

5.2 Heat treatment

Drill pipes shall be heat-treated by solution heat treatment followed by artificial or natural ageing. The aluminium pipe shall not be subjected to cold working after the final heat-treatment process, except for that which is incidental to normal straightening or threading operations.

The temperature and time requirements for the solution and ageing heat-treatment cycles shall be determined in accordance with the manufacturer's documented practice. Actual furnace temperatures and transfer timing shall be documented in order to verify that each heat-treatment lot meets the manufacturer's documented requirements.

5.3 Traceability

The manufacturer shall establish and follow procedures for maintaining heat or lot identity or both until all required heat/lot tests have been performed and conformance with specification requirements has been verified.

5.4 Delivery condition

Aluminium alloy drill pipes are normally supplied as

- a) plain end pipe (with external or internal upsets but without threads),
- b) threaded pipe (with external or internal upsets but without tool joints), or
- c) with tool joints attached (with external or internal upsets).

6 Material requirements

6.1 Material groups

Materials for aluminium alloy drill pipes after heat treatment shall be in accordance with Table 1. They are divided into four material groups:

- **Group 1**, without additional requirements for high strength or corrosion resistance;
- **Group II**, with improved strength;
- **Group III**, with high temperature mechanical properties;
- **Group IV**, with improved corrosion resistance.

Table 1 — Material requirements for aluminium alloy drill pipes

Characteristic	Unit	Material group			
		I	II	III	IV
Alloy system		Al-Cu-Mg	Al-Zn-Mg	Al-Cu-Mg-Si-Fe	Al-Zn-Mg
Yield strength, min. (0,2 % offset method)	MPa	325	480	340	350
Tensile strength, min.	MPa	460	530	410	400
Elongation, min.	%	12	7	8	9
Operational temperature, max.	°C	160	120	220	160
Corrosion rate in 3,5 % sodium chloride solution, max.	g/(m ² h)	—	—	—	0,08
<p>It is permitted to use an alternative aluminium alloy system, provided there is purchaser agreement and that it conforms to the requirements of one of the four material group categories.</p> <p>The manufacturer shall have a documented procedure that demonstrates the minimum yield strength which can be achieved at the maximum operational temperature defined in Table 1.</p> <p>Mechanical testing shall be in accordance with ISO 6892.</p> <p>Users need to be aware that the yield strength at ambient temperature might be reduced by up to 30 % at the maximum operational temperature for exposure times greater than 500 h.</p>					
NOTE The mechanical properties of the alloys given in this table are for a test temperature of 21 °C ± 3 °C.					

6.2 Metallographic examination

Each heat treatment lot sample shall undergo metallographic examination. The macrostructure shall be homogeneous, without cracks, pits, laminations, shrinkage cavities, surface tears or sponginess. The microstructure shall not contain porosities or grain boundary eutectic melting resulting from solution heat treatment.

For terminology relating to microstructure examination, see ASTM B 579.

6.3 Chemical composition

Chemical analysis shall be undertaken on each heat. The residual lead content shall be limited to 0,005 % wt. for all material groups.

6.4 Steel tool joints

Material for steel tool joints shall be in accordance with Table 2.

Table 2 — Mechanical property requirements for steel tool joints

Characteristic	Unit	Requirement
Tensile strength, min.	MPa	880
Yield strength, min. (0,2 % offset method)	MPa	735
Elongation after fracture, min. (see Note 2)	%	13
Longitudinal Charpy V notch absorbed energy requirement, min. ^a	J	70 average of three tests (47 single value)
Brinell hardness, min.	HBW	285
<p>Determination of the mechanical properties of the pin shall be in accordance with ASTM A370.</p> <p>Other gauge lengths may be used with purchaser agreement. In such cases, the corresponding elongation values shall be obtained in accordance with ISO 2566-1. In cases of dispute, the gauge length, $l_o = 5,65\sqrt{S_o}$ shall be used.</p> <p>For location of test-pieces, see API Spec 7.</p> <p>NOTE The mechanical properties of the tool joint material given in Table 2 are for a test temperature of 21 °C ± 3 °C.</p> <p>^a By agreement between the purchaser and the manufacturer, and when specified on the purchase order, the Charpy impact testing shall be carried out at -10 °C ± 3 °C and shall meet these requirements.</p>		

7 Configuration and dimensions of pipes

7.1 Configuration

The configuration of the aluminium alloy drill pipe shall be in accordance with Figure 1 for pipes with internal upset ends, with Figure 2 for pipes with external upset ends, and with Figure 3 for pipes with protector thickening.

7.2 Length

Drill pipe length ranges shall be in accordance with Table 3 and Figure 1.