
**Textile glass — Mats (made from chopped
or continuous strands) — Designation and
basis for specifications**

*Verre textile — Mats (constitués de fils de base, coupés ou non) —
Désignation et base de spécifications*

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2559:2000](https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000)

[https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-
c94511e6c33d/iso-2559-2000](https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000)



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2559:2000](#)

<https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Technical requirements	2
5 Designation	5
6 Labelling	5
7 Sampling and conditioning	5
8 Presentation, packaging and storage conditions	5

Annex

A Determination of the width of an untrimmed mat	6
A.1 General	6
A.2 Mats untrimmed along one edge	6
A.3 Mats untrimmed along both edges	6

ITeH STANDARD PREVIEW
(standards.iteh.ai)

[ISO 2559:2000](https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000)

<https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 2559 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 13, *Composites and reinforcement fibres*.

This fourth edition cancels and replaces the third edition (ISO 2559:1991), which has been technically revised.

Annex A of this International Standard is for information only.

ISO 2559:2000
<https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000>

Textile glass — Mats (made from chopped or continuous strands) — Designation and basis for specifications

1 Scope

This International Standard provides a basis for specifications which is applicable only to textile glass mats that are made from chopped or continuous strands bonded together by chemical or mechanical means, and that are used for the reinforcement of plastics.

It is not applicable to surfacing mats, staple-fibre mats or glass mats (or bats) of the type used for thermal and acoustic insulation.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 291, *Plastics — Standard atmospheres for conditioning and testing.*

ISO 472, *Plastics — Vocabulary.* <https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000>

ISO 1886, *Reinforcement fibres — Sampling plans applicable to received batches.*

ISO 1887, *Textile glass — Determination of combustible-matter content.*

ISO 1888, *Textile glass — Staple fibres or filaments — Determination of average diameter.*

ISO 2078, *Textile glass — Yarns — Designation.*

ISO 2558, *Textile glass chopped-strand mats for reinforcement of plastics — Determination of time of dissolution of the binder in styrene.*

ISO 3342, *Textile glass — Mats — Determination of tensile breaking force.*

ISO 3374, *Reinforcement products — Mats and fabrics — Determination of mass per unit area.*

ISO 3616, *Textile glass — Chopped-strand and continuous-filament mats — Determination of average thickness, thickness under load and recovery after compression.*

ISO 5025, *Reinforcement products — Woven fabrics — Determination of width and length.*

3 Terms and definitions

For the purposes of this International Standard, the terms and definitions given in ISO 472, with the following additions, apply.

3.1

characteristic properties

properties not normally subject to routine quality control in the mat production process

3.2

controlled properties

quantitative properties subject to routine quality control in the mat production process

3.3

visual properties

qualitative properties not necessarily subject to routine quality control in the mat production process

4 Technical requirements

4.1 General

A given mat shall be designed so as to satisfy the requirements of one or several applications. Essentially, a specific mat is chosen so as to bring to the laminate its reinforcement properties under certain environmental conditions which may range from a dry inert to a wet corrosive atmosphere.

The expected product performance properties are generally not guaranteed as such due to the difficulty of standardizing the conditions under which the mat is used (resin mix, cure system, laminate structure, glass/resin/filler ratio, etc.). For this reason, the mat will be characterized in the specification by other guaranteed properties which can be correlated with the desired practical laminating properties. The latter can be divided into characteristic, controlled and visual properties, as defined in clause 3.

ISO 2559:2000

Where required, the controlled properties (measured parameters) may be stated on certificates of conformity or other quality control test reports.

c94511e6c33d/iso-2559-2000

The following is a proposed list of "characteristic" and "controlled" properties with, when applicable, the relevant test method. The distinction between characteristic and controlled properties is indicative only, and may vary for different mat products.

The specification for a given mat shall include the relevant properties among those listed hereafter, with tolerances where applicable.

4.2 Characteristic properties

4.2.1 Resin compatibility

The resin(s) recommended for use with the mat.

4.2.2 Glass type

The glass type as defined in ISO 2078.

4.2.3 Filament diameter

The average diameter of the filaments constituting the strands in the mat. If necessary, the average filament diameter may be determined in accordance with ISO 1888.

4.2.4 Strand linear density

It is not normally possible to determine the linear density of the strands in the mat since they might have been split and/or chopped during the production process. Therefore the figure quoted is usually that of the input strand, the linear density of which can only be determined by the mat manufacturer.

4.2.5 Strand length

The length of the strands, which may be either unchopped (continuous-filament mat) or chopped to a given length, with the possibility of a mix of different specified lengths (chopped-strand mat).

NOTE This International Standard covers only mats manufactured with strands made of continuous filaments and not mats made of discontinuous fibres.

4.2.6 Size type

The type of size (essentially the type of coupling agent) used to coat the filaments.

4.2.7 Bonding system

The system used to bond the strands, which may be

- either of a chemical type, which might be either a liquid binder (emulsion) or a solid binder (powder);
- or of a mechanical type, with or without carrier (if a carrier it is used, it shall be identified).

4.2.8 Width

The width of the mat, expressed in centimetres or millimetres. For mats with trimmed edges, the width may be determined by the method given for woven fabrics in ISO 5025. For mats with untrimmed edges, the method given in annex A may be used.

4.2.9 Edges

The nature of the edges of the mat, which may be

- either untrimmed (feathered) on one or both sides;
- or trimmed on both sides.

In the case of mats untrimmed along one or both edges, the width shall be measured between two points where the thickness of the mat does not visibly vary. For such mats, the tolerances on the width shall be agreed upon between the interested parties.

4.2.10 Length

The length of the material in a roll. The specification may allow the length to vary between rolls or to be fixed within agreed tolerances. Moreover, it is possible that a shipment incorporates incomplete rolls. The number, the mass, or the minimum length of the incomplete rolls shall be specified.

4.2.11 Degree of solubility of chopped-strand mat binder in styrene

The solubility of the mat binder in styrene shall be determined in accordance with ISO 2558. It is generally expressed as high (< 60 s), medium (60 s to 200 s) or low (> 200 s), depending on the result obtained using this method.

4.3 Controlled properties

4.3.1 Mass per unit area

The mass per unit area shall be determined in accordance with ISO 3374 and expressed in grams per square metre. This mass includes the glass strands, the size and the binder(s) plus any carrier present.

For each type of mat, the manufacturer shall give a nominal value of the mass per unit area and shall define the tolerances on the measured values, specifying if the tolerances apply for the average of the test specimens taken across the width of the mat or to each test specimen.

NOTE The most common nominal values are 300 g/m², 375 g/m², 450 g/m² and 600 g/m².

4.3.2 Percentage combustible matter

The percentage of combustible matter shall be determined in accordance with ISO 1887. The combustible matter corresponds to the sum of the size applied to the filaments and the binder(s) applied to the strands. In the case of mats bonded mechanically with an organic-fibre carrier, the mass of the carrier would be included in the combustible matter content.

The tolerances given in the specification shall be related to the average for test specimens taken across the width of the mat, unless otherwise agreed upon between purchaser and supplier.

4.3.3 Tensile strength

The dry tensile strength of the mat shall be determined in accordance with ISO 3342, which includes two types of specimen depending on the type of mat being tested. The type of test specimen to be used shall be stated in the specification.

iTeh STANDARD PREVIEW
(standards.iteh.ai)
<https://standards.iteh.ai/catalog/standards/sist/ef649c67-a7c4-4ea5-be10-c94511e6c33d/iso-2559-2000>

4.3.4 Thickness

The thickness of the mat shall be determined in accordance with ISO 3616.

4.4 Visual properties

The mat shall be uniform in appearance. The roll shall be wound with appropriate compaction and the edges aligned so that telescoping does not exceed a given tolerance, agreed between purchaser and supplier.

Listed below are a number of recognized visible non-conformities which may exist in a mat, and which can occur during manufacture or during subsequent handling:

- tears;
- holes;
- dirt marks;
- grease spots;
- foreign matter;
- clumps of strands;
- clumps or strips of binder;
- dark strands;
- locally thin areas;

- locally poorly bonded areas;
- irregular edges.

The permissible number and extent of these and/or other visible non-conformities shall be agreed between the interested parties.

5 Designation

The designation of the mat shall be up of the following elements:

Block 1: mat type (chopped strand or continuous filament).

Block 2: mass per unit area, width.

Block 3: binder type (powder or emulsion), strand length(s) and tex.

This designation is generally preceded by the commercial name given by the manufacturer, and followed by coded information concerning the trimmed edges or any other information specific to the relevant mat.

6 Labelling

Each roll of mat and each pallet shall bear a label indicating the manufacturer's name, the type of mat and any data needed to ensure material traceability (such as roll number, mass, length, production date, etc.).

7 Sampling and conditioning

Sampling procedures and sampling plans defined in ISO 1886 shall be used.

Unroll the outer layer of the rolls selected, ensuring that any damaged section is removed. Then take, over the whole width, a laboratory sample of sufficient length to enable all the required test specimens to be cut out, as specified in the applicable test methods.

Condition the laboratory sample for at least 1 h in one of the standard atmospheres specified in ISO 291, unless another atmosphere is required by the particular nature of the product.

8 Presentation, packaging and storage conditions

Requirements concerning the presentation, packaging and storage conditions shall be given.