

Designation: A 289/A 289M - 97 (Reapproved 2003)

Standard Specification for Alloy Steel Forgings for Nonmagnetic Retaining Rings for Generators¹

This standard is issued under the fixed designation A 289/A 289M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

1. Scope

- 1.1 This specification covers nonmagnetic alloy steel retaining ring forgings for generators.
- 1.2 The values stated in either inch-pound units or SI (metric) units are to be regarded separately as standards. Within the text and tables, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore each system must be used independent of the other. Combining values from the two systems may result in nonconformance with the specification.
- 1.3 Unless the order specifies the applicable "M" specification designation, the material shall be furnished to the inchpound units.

2. Referenced Documents

- 2.1 ASTM Standards:
- A 342/A 342M Test Methods for Permeability of Feebly Magnetic Materials²
- A 370 Test Methods and Definitions for Mechanical Testing of Steel Products³
- A 531/A 531M Practice for Ultrasonic Examination of Turbine-Generator Steel Retaining Rings⁴
- A 788 Standard Specification for Steel Forgings, General Requirements⁴
- E 45 Practice for Determining the Inclusion Content of Steel⁵
- E 112 Test Method for Determining Average Grain Size⁶
- E 165 Practice for Liquid Penetrant Examination⁷

3. Ordering Information and General Requirements

3.1 Material supplied to this specification shall conform to the requirements of Specification A 788, which outlines order-

¹ This specification is under the jurisdiction of ASTM Committee A01 on Steel, Stainless Steel and Related Alloys, and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved April 10, 2003. Published July 2003. Originally approved in 1946. Last previous edition approved in 1997 as A 289 – 97/A 289M.

- ² Annual Book of ASTM Standards, Vol 03.04.
- ³ Annual Book of ASTM Standards, Vol 01.13.
- ⁴ Annual Book of ASTM Standards, Vol 01.05.
- ⁵ Annual Book of ASTM Standards, Vol 04.09.
- ⁶ Annual Book of ASTM Standards, Vol 04.09.
- ⁷ Annual Book of ASTM Standards, Vol 04.08.

- ing information, manufacturing requirements, testing methods and retesting procedures, marking, certification, product analysis variation, and additional supplementary requirements.
- 3.2 If the requirements of this specification are in conflict with the requirements of Specification A 788, the requirements of this specification shall prevail.
- 3.3 Supplementary requirements of an optional nature are provided. They shall apply only when specified by the purchaser.

4. Manufacture

- 4.1 The steel shall be made by the electro-slag-remelt (ESR) process. The electrodes shall be made by either the basic electric furnace or ladle refining processes.
- 4.2 Sufficient discard shall be taken from each ingot to secure freedom from piping and undue segregation.
- 4.3 Forged rings shall be solution treated following hot working and prior to the cold expansion procedure.
- 4.4 Rings shall be rough machined prior to cold expansion or final heat treatment.
- 4.5 Rings shall be expanded by an appropriate method such as segmented dies, tapered plug, etc. in the temperature range of 60 to 390°F [15 to 200°C] in order to develop the required tensile properties.
- 4.6 After cold expansion, the rings shall be heated to between 575 and 750°F [300 to 400°C] at a rate not to exceed 75°F [40°C]/h, held at this temperature for 6 to 12 h, and then slow cooled to ambient temperature.

5. Chemical Requirements

- 5.1 *Heat Analysis*—The heat analysis obtained from sampling in accordance with Specification A 788 shall comply with Table 1 of this specification.
- 5.2 *Product Analysis*—When a product analysis is performed at the request of the purchaser, the provisions of Table 1 of Specification A 788 shall apply. The analysis shall be made from a forging representing each heat.

Note 1—The material shown in Table 1 of A $289/A\ 289M$ was formerly known as Class C.