

INTERNATIONAL STANDARD

ISO
9809-3

First edition
2000-12-15

Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing —

Part 3: Normalized steel cylinders

*Bouteilles à gaz — Bouteilles à gaz rechargeables en acier sans
soudure — Conception, construction et essais —
Partie 3: Bouteilles en acier normalisé*



Reference number
ISO 9809-3:2000(E)

© ISO 2000

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9809-3:2000

<https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df-283fad64b3bb/iso-9809-3-2000>

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.ch
Web www.iso.ch

Printed in Switzerland

Contents

	Page
Foreword.....	iv
Introduction	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Symbols	3
5 Inspection and testing.....	4
6 Materials	4
7 Design	6
8 Construction and workmanship.....	10
9 Type approval procedure.....	11
10 Batch tests.....	15
11 Tests on every cylinder.....	22
12 Certification.....	23
13 Marking	23
Annex A (informative) Description, evaluation of manufacturing defects and conditions for rejection of seamless steel gas cylinders at time of final visual inspection by the manufacturer.....	24
Annex B (normative) Ultrasonic inspection	30
Annex C (informative) Type approval certificate.....	34
Annex D (informative) Acceptance certificate.....	35
Bibliography	37

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this part of ISO 9809 may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 9809-3 was prepared by Technical Committee ISO/TC 58, *Gas cylinders*, Subcommittee SC 3, *Cylinder design*.

This first edition of ISO 9809-3, together with ISO 9809-1 and ISO 9809-2, cancels and replaces ISO 4705:1983.

ISO 9809 consists of the following parts, under the general title *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing*:

- *Part 1: Quenched and tempered steel cylinders with tensile strength less than 1 100 MPa*
- *Part 2: Quenched and tempered steel cylinders with tensile strength greater than or equal to 1 100 MPa*
- *Part 3: Normalized steel cylinders*

Annex B forms a normative part of this part of ISO 9809. Annexes A, C and D are for information only.

Introduction

The purpose of this part of ISO 9809 is to provide a specification for the design, manufacture, inspection and testing of a seamless steel cylinder for worldwide usage. The objective is to balance design and economic efficiency against international acceptance and universal utility.

This part of ISO 9809 aims to eliminate the concern about climate, duplicate inspections and restrictions currently existing because of lack of definitive International Standards and should not be construed as reflecting on the suitability of the practice of any nation or region.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 9809-3:2000](https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df-283fad64b3bb/iso-9809-3-2000)

<https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df-283fad64b3bb/iso-9809-3-2000>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 9809-3:2000

<https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df-283fad64b3bb/iso-9809-3-2000>

Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing —

Part 3: Normalized steel cylinders

1 Scope

This part of ISO 9809 specifies minimum requirements for the material, design, construction and workmanship, manufacturing processes and tests at manufacture of refillable normalized, or normalized and tempered seamless steel gas cylinders with water capacities from 0,5 l up to and including 150 l for compressed, liquefied and dissolved gases.

NOTE 1 If so desired, cylinders of water capacity less than 0,5 l may be manufactured and certified to this part of ISO 9809.

NOTE 2 For quenched and tempered cylinders with maximum tensile strength less than 1 100 MPa, refer to ISO 9809-1. For quenched and tempered cylinders with maximum tensile strength \geq 1 100 MPa, refer to ISO 9809-2.

(standards.iteh.ai)

2 Normative references

ISO 9809-3:2000

<https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df>

The following normative documents contain provisions which, through reference in this text, constitute provisions of this part of ISO 9809. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this part of ISO 9809 are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 148:1983, *Steel — Charpy impact test (V-notch)*.

ISO 2604-2:1975, *Steel products for pressure purposes — Quality requirements — Part 2: Wrought seamless tubes*.

ISO 6506-1:1999, *Metallic materials — Brinell hardness test — Part 1: Test method*.

ISO 6508-1:1999, *Metallic materials — Rockwell hardness test — Part 1: Test method (scales A, B, C, D, E, F, G, H, K, N, T)*.

ISO 6892:1998, *Metallic materials — Tensile testing at ambient temperature*.

ISO 7438:1985, *Metallic materials — Bend test*.

ISO 9712:1999, *Non-destructive testing — Qualification and certification of personnel*.

ISO 9809-1:1999, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 1: Quenched and tempered steel cylinders with tensile strength less than 1 100 MPa*.

ISO 9809-2:2000, *Gas cylinders — Refillable seamless steel gas cylinders — Design, construction and testing — Part 2: Quenched and tempered steel cylinders with tensile strength greater than or equal to 1 100 MPa*.

ISO 11114-1:1997, *Transportable gas cylinders — Compatibility of cylinder and valve materials with gas contents — Part 1: Metallic materials.*

ISO 13769:—¹⁾, *Gas cylinders — Stamp marking.*

3 Terms and definitions

For the purposes of this part of ISO 9809, the following terms and definitions apply.

3.1 yield stress

value corresponding to the lower yield stress R_{eL} or, for steels that do not exhibit a defined yield, the 0,2 % proof stress (non-proportional elongation) $R_{p0,2}$

cf. ISO 6892.

3.2 normalizing

heat treatment in which a cylinder is heated to a uniform temperature above the upper critical point (A_{c3}) of the steel and then cooled in still air

3.3 tempering

softening heat treatment which follows normalizing, in which the cylinder is heated to a uniform temperature below the lower critical point (A_{c1}) of the steel

3.4 batch

quantity of up to 200 cylinders plus cylinders for destructive testing of the same nominal diameter, thickness and design made successively from the same steel and subjected to the same heat treatment for the same duration of time

NOTE The lengths of the cylinders in a heat-treatment batch may vary by $\pm 12\%$.

3.5 test pressure

p_h
required pressure applied during a pressure test

NOTE It is used for cylinder wall thickness calculations.

3.6 burst pressure

p_b
highest pressure reached in a cylinder during a burst test

3.7 design stress factor (variable)

F
ratio of equivalent wall stress at test pressure (p_h) to guaranteed minimum yield stress (R_e)

1) To be published.

4 Symbols

a	Calculated minimum thickness, in millimetres, of the cylindrical shell
a'	Guaranteed minimum thickness, in millimetres, of the cylindrical shell
a_1	Guaranteed minimum thickness, in millimetres, of a concave base at the knuckle (see Figure 2)
a_2	Guaranteed minimum thickness, in millimetres, at the centre of a concave base (see Figure 2)
A	Percentage elongation
b	Guaranteed minimum thickness, in millimetres, at the centre of a convex base (see Figure 1)
c	Maximum permissible deviation of burst profile, in millimetres [see Figure 5b), c) and d)]
D	Nominal design outside diameter of the cylinder, in millimetres (see Figure 1)
D_f	Diameter, in millimetres, of former (see Figure 8)
F	Design stress factor (variable), see 7.2.
h	Outside depth (concave base end), in millimetres (see Figure 2)
H	Outside height, in millimetres, of domed part (convex head or base end) (see Figure 1)
L_0	Original gauge length, in millimetres, as defined in ISO 6892 (see Figure 7)
n	Ratio of diameter of bend test former to actual thickness of test piece (t)
p_b	Measured burst pressure, in bar ²⁾ , above atmospheric pressure
p_h	Hydraulic test pressure, in bar, above atmospheric pressure
p_w	Working pressure, in bar, above atmospheric pressure
p_y	Observed pressure when cylinder starts yielding during hydraulic bursting test, in bar, above atmospheric pressure
r	Inside knuckle radius, in millimetres (see Figures 1 and 2)
R_e	Minimum guaranteed value of yield stress, in megapascals (see 3.1)
R_{ea}	Actual value of the yield stress, in megapascals, as determined by the tensile test (see 10.2)
R_g	Minimum guaranteed value of tensile strength, in megapascals
R_m	Actual value of tensile strength, in megapascals, as determined by the tensile test (see 10.2)
S_0	Original cross-sectional area of tensile test piece, in square millimetres, in accordance with ISO 6892
t	Actual thickness of the test specimen, in millimetres
u	Ratio of distance between knife edges or platens in the flattening test to average cylinder wall thickness at the position of test

2) 1 bar = 10⁵ Pa = 10⁵ N/m².

- V Water capacity of cylinder, in litres
- w Width, in millimetres, of the tensile test piece (see Figure 7)

5 Inspection and testing

Evaluation of conformity is required to be performed in accordance with the relevant regulations of the country(ies) where the cylinders are used.

In order to ensure that the cylinders are in compliance with this part of ISO 9809 they shall be subject to inspection and testing in accordance with clauses 9, 10 and 11 by an authorized inspection body (hereafter referred to as “the inspector”) recognized in the countries of use. The inspector shall be competent for inspection of cylinders.

6 Materials

6.1 General requirements

6.1.1 Materials for the manufacture of normalized, or normalized and tempered, gas cylinders intended for international service shall be those generically classified as: carbon-steels, carbon-manganese or manganese-molybdenum steels. The maximum tensile strength for cylinders made from those steels shall not exceed 800 MPa.

Other steels permitted in ISO 9809-1 or ISO 9809-2 for quenched and tempered cylinders may be used and subjected to normalizing and tempering as specified in 6.3 provided they additionally pass the impact test requirements as stipulated in ISO 9809-1, and the maximum tensile strength R_m does not exceed 950 MPa.

The steel used shall fall within one of the following categories:

- a) internationally recognized cylinder steels; [ISO 9809-3:2000](https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df-283fad64b3bb/iso-9809-3-2000)
- b) nationally recognized cylinder steels; [283fad64b3bb/iso-9809-3-2000](https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df-283fad64b3bb/iso-9809-3-2000)
- c) new cylinder steels resulting from technical progress.

6.1.2 The material used for the fabrication of gas cylinders shall be steel, other than rimming quality, with non-ageing properties, and shall be aluminium and/or silicon killed. The aluminium content shall be at least 0,015 %.

In cases where examination of this non-ageing property is required by the customer, the criteria by which it is to be specified shall be agreed with the customer and inserted in the order.

6.1.3 The cylinder manufacturer shall establish means to identify the cylinders with the cast of steel from which they are made.

6.1.4 Grades of steel used for cylinder manufacture shall be compatible with the intended gas service, e.g. corrosive gases, embrittling gases (see ISO 11114-1).

6.2 Controls on chemical composition

6.2.1 The chemical composition of all steels shall be defined at least by:

- the carbon, manganese and silicon contents in all cases;
- the chromium, nickel and molybdenum contents or other alloying elements intentionally added to the steel;
- the maximum sulfur and phosphorus contents in all cases.

The carbon, manganese and silicon contents and, where appropriate, the chromium, nickel and molybdenum contents shall be given, with tolerances, such that the differences between the maximum and minimum values of the cast do not exceed the values shown in Table 1.

Table 1 — Chemical composition tolerances

Element	Maximum content mass fraction in %	Permissible range mass fraction in %
Carbon	< 0,30 ≥ 0,30	0,06 0,07
Manganese	All values	0,30
Silicon	All values	0,30
Molybdenum	All values	0,15

The actual content of any element deliberately added shall be reported and their maximum content shall be representative of good steelmaking practice.

6.2.2 Except for steels complying with the requirements of ISO 9809-1 or ISO 9809-2, the following limits on carbon, manganese, sulfur, phosphorus and other alloying elements shall not be exceeded in the cast analysis of material used:

carbon	0,45 %
manganese	1,70 %
chromium	0,20 %
nickel	0,20 %
copper	0,20 %
combined value of micro alloying elements: i.e. V, Nb, Ti, B, Zr, Sn	0,15 %
sulfur	0,020 %
phosphorus	0,020 %
sulfur + phosphorus	0,030 %

6.2.3 The cylinder manufacturer shall obtain and provide certificates of cast (heat) analyses of the steels supplied for the construction of gas cylinders.

Should check analyses be required, they shall be carried out either on specimens taken during manufacture from the material in the form as supplied by the steelmaker to the cylinder manufacturer, or from finished cylinders. In any check analysis, the maximum permissible deviation from the limits specified for the cast analyses shall conform to the values specified in ISO 2604-2.

6.3 Heat treatment

The heat treatment process applied to the finished cylinder shall be either normalizing or normalizing and tempering. The cylinder manufacturer shall certify the heat treatment process applied.

The heat treatment process shall achieve the required mechanical properties.

The actual temperature to which a type of steel is subjected for a given tensile strength shall not deviate by more than 30 °C from the temperature specified by the cylinder manufacturer.

6.4 Testing requirements

The material of the finished cylinders shall satisfy the requirements of clauses 9, 10 and 11.

6.5 Failure to meet test requirements

In the event of failure to meet test requirements, retesting or reheat treatment and retesting shall be carried out as follows to the satisfaction of the inspector.

- a) If there is evidence of a fault in carrying out a test, or an error of measurement, a further test shall be performed. If the result of this test is satisfactory, the first test shall be ignored.
- b) If the test has been carried out in a satisfactory manner, the cause of test failure shall be identified.
 - 1) If the failure is considered to be due to the heat treatment applied, the manufacturer may subject all the cylinders implicated by the failure to a further heat treatment, i.e. if the failure is in a test representing the prototype or batch cylinders, test failure shall require reheat treatment of all the represented cylinders prior to retesting; however, if the failure occurs sporadically in a test applied to every cylinder, then only those cylinders which fail the test shall require reheat treatment and retesting.

This heat treatment shall consist of renormalizing, or renormalizing and tempering, or retempering.

Whenever cylinders are reheat treated, the minimum guaranteed wall thickness shall be maintained.

Only the relevant prototype or batch tests needed to prove the acceptability of the batch shall be performed again. If one or more of these retests prove even partially unsatisfactory, all cylinders of the batch shall be rejected.

- 2) If the failure is due to a cause other than the heat treatment applied, all defective cylinders shall be either rejected or repaired by an approved method. Provided that the repaired cylinders pass the test(s) required for the repair, they shall be re-instated as part of the original batch.

7 Design

7.1 General requirements

7.1.1 The calculation of the wall thickness of the pressure-containing parts shall be related to the guaranteed minimum yield stress (R_e) of the material.

7.1.2 For calculation purposes, the value of R_e shall not exceed $0,75 R_g$.

7.1.3 The internal pressure upon which the calculation of wall thickness is based shall be the hydraulic test pressure p_h .

7.2 Calculation of cylindrical shell thickness

The guaranteed minimum thickness of the cylindrical shell (a') shall not be less than the thickness calculated using equations (1) and (2) and, in addition, condition (3) shall be satisfied:

$$a = \frac{D}{2} \left(1 - \sqrt{\frac{10FR_e - \sqrt{3} p_h}{10FR_e}} \right) \quad (1)$$

where $F \leq 0,85$.

The wall thickness shall also satisfy the formula:

$$a \geq \frac{D}{250} + 1 \quad (2)$$

with an absolute minimum of $a = 1,5$ mm.

The burst ratio

$$p_b / p_h \geq 1,22 / (R_e / R_g) \quad (3)$$

shall be satisfied by test.

NOTE It is generally assumed that $p_h = 1,5 \times p_w$ for permanent gases for cylinders designed and manufactured in accordance with this part of ISO 9809.

7.3 Calculation of convex ends (heads and bases)

7.3.1 The thickness, b , at the centre of a convex end shall be not less than that required by the following criteria.

Where the inside knuckle radius, r , is not less than $0,075D$, then

$$b \geq 1,5 a \quad \text{for } 0,20 \leq H/D < 0,40$$

$$b \geq a \quad \text{for } H/D \geq 0,40$$

In order to obtain a satisfactory stress distribution in the region where the end joins the shell, any thickening of the end that may be required shall be gradual from the point of juncture. For the application of this rule the point of juncture between the shell and the end is defined by the horizontal line indicating dimension H in Figure 1.

Shape B shall not be excluded from this requirement.

<https://standards.iteh.ai/catalog/standards/sist/666ab600-b2a3-4f53-a0df>

7.3.2 The cylinder manufacturer shall prove by the pressure cycling test detailed in 9.2.3 that the design is satisfactory.

The shapes shown in Figure 1 are typical of convex heads and base ends. Shapes A, B, D and E are base ends, and shapes C and F are heads.

7.4 Calculation of concave base ends

When concave base ends (see Figure 2) are used, the following design values are recommended:

$$a_1 \geq 2a$$

$$a_2 \geq 2a$$

$$h \geq 0,12D$$

$$r \geq 0,075D$$

The design drawing shall at least show values for a_1 , a_2 , h and r .

In order to obtain a satisfactory stress distribution, the thickness of the cylinder shall increase progressively in the transition region between the cylindrical part and the base.

The cylinder manufacturer shall in any case prove by the pressure cycling test detailed in 9.2.3 that the design is satisfactory.