



**Designation: D 602 – 81 (Reapproved 1999)**

## Standard Specification for Barium Sulfate Pigments<sup>1</sup>

This standard is issued under the fixed designation D 602; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ε) indicates an editorial change since the last revision or reapproval.

### 1. Scope

1.1 This specification covers the barium sulfate pigments commercially known as barytes and blanc fixe.

### 2. Referenced Documents

#### 2.1 ASTM Standards:

- D 185 Test Methods for Coarse Particles in Pigments, Pastes, and Paints<sup>2</sup>
- D 280 Test Methods for Hygroscopic Moisture (and Other Matter Volatile Under the Test Conditions) in Pigments<sup>2</sup>
- D 715 Test Methods for Analysis of Barium Sulfate Pigment<sup>2</sup>
- D 1208 Test Methods for Common Properties of Certain Pigments<sup>2</sup>

### 3. Composition and Properties

3.1 The pigment shall consist of barium sulfate (BaSO<sub>4</sub>) without any admixture of other materials in the case of blanc fixe, and without any admixture of other materials not naturally occurring in the barite ore in the case of barytes, and which conform to the following requirements:

	Barytes	Blanc Fixe
Barium sulfate, min, %	94	97
Ferric oxide, max, %	0.05	0.02
pH, min	3.5	3.5
Matter soluble in water, max, %	0.2	0.2

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee D-1 on Paint and Related Coatings, Materials, and Applications, and is the direct responsibility of Subcommittee D01.31 on Pigment Specifications.

Current edition approved Oct. 30, 1981. Published December 1981. Originally published as D 602 – 41 T. Last previous edition D 602 – 42 (1975).

<sup>2</sup> Annual Book of ASTM Standards, Vol 06.03.

**TABLE** Continued

	Barytes	Blanc Fixe
Moisture and other volatile matter, max, %	0.5	0.5
Coarse particles (total residue retained on No. 325 (45-μm sieve), max, %	0.5	0.5
Free silica (quartz, clays, or other foreign materials), max, %	2.0	2.0

3.2 In such physical properties as are specified by the purchaser, the pigment shall satisfactorily match a reference sample mutually agreed upon by the purchaser and the seller.

### 4. Sampling

4.1 Two samples shall be taken at random from different packages from each lot, batch, day's pack, or other unit of production in a shipment. When no markings distinguishing between units of production appear, samples shall be taken from different packages in the ratio of two samples of each 10 000 lb (5000 kg), except that for shipments of less than 10 000 lb two samples shall be taken. At the option of the purchaser, the samples may be tested separately or after blending in equal quantities the samples from the same production unit to form a composite sample.

### 5. Test Methods

5.1 Tests shall be conducted in accordance with the following ASTM test methods. Test procedures not covered by ASTM test methods shall be mutually agreed upon by the purchaser and the seller.

5.2 *Coarse Particles in Pigment*—Test Methods D 185.

5.3 *Moisture*—Test Methods D 280.

5.4 *Barium Sulfate, Ferric Oxide, and Free Silica*—Test Methods D 715.

5.5 *Hydrogen Ion Concentration and Matter Soluble in Water*—Test Methods D 1208.

### 6. Keywords

6.1 barium sulfate; barytes; blanc fixe; pigments