
**Specification and qualification of welding
procedures for metallic materials —
Welding procedure specification —**

**Part 1:
Arc welding**

iTeh STANDARD PREVIEW

(standards.iteh.ai)
*Descriptif et qualification d'un mode opératoire de soudage pour les
matériaux métalliques — Descriptif d'un mode opératoire de
soudage —*

Partie 1: Soudage à l'arc

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO 15609-1:2004](#)

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>

© ISO 2004

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 15609-1 was prepared by the European Committee for Standardization (CEN) in collaboration with Technical Committee ISO/TC 44, *Welding and allied processes*, Subcommittee SC 10, *Unification of requirements in the field of metal welding*, in accordance with the Agreement on technical cooperation between ISO and CEN (Vienna Agreement).

This first edition of ISO 15609-1 cancels and replaces ISO 9956-2:1995 which has been technically revised.

Throughout the text of this document, read “...this European Standard...” to mean “...this International Standard...”.

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>

ISO 15609 consists of the following parts, under the general title *Specification and qualification of welding procedures for metallic materials — Welding procedure specification*:

- *Part 1: Arc welding*
- *Part 2: Gas welding*
- *Part 3: Electron beam welding*
- *Part 4: Laser beam welding*
- *Part 5: Resistance welding*
- *Part 6: Laser beam cladding*

Annex ZA provides a list of corresponding International and European Standards for which equivalents are not given in the text.

Contents

Page

Foreword.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	1
4 Technical content of welding procedure specification (WPS).....	1
4.1 General.....	1
4.2 Related to the manufacturer	2
4.3 Related to the parent material	2
4.4 Common to all welding procedures.....	2
4.5 Specific to a group of welding processes.....	4
Annex A (informative) Welding Procedure Specification (WPS)	6
Annex ZA (normative) Normative references to International publications with their relevant European publications	7

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 15609-1:2004](https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>

Foreword

This document (EN ISO 15609-1:2004) has been prepared by Technical Committee CEN/TC 121 "Welding", the secretariat of which is held by DIN, in collaboration with Technical Committee ISO/TC 44 "Welding and allied processes".

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by April 2005, and conflicting national standards shall be withdrawn at the latest by April 2005.

This document supersedes EN 288-2:1992.

NOTE Normative references to International Standards are listed in annex ZA (normative).

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO 15609-1:2004](https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004)

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 15609-1:2004

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>

1 Scope

This standard specifies requirements for the content of welding procedure specifications for arc welding processes.

This standard is part of a series of standards, details of this series are given in EN ISO 15607:2003, Annex A.

The variables listed in this standard are those influencing the quality of the welded joint.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 439, *Welding consumables – Shielding gases for arc welding and cutting.*

EN 26848, *Tungsten electrodes for inert gas shielded arc welding and for plasma cutting and welding – Codification.*

EN ISO 4063, *Welding and allied processes – Nomenclature of processes and reference numbers. (ISO 4063:1998)*

EN ISO 6947, *Welds – Working positions - Definitions of angles of slope and rotation. (ISO 6947:1993)*

EN ISO 13916, *Welding – Guidance on the measurement of preheating temperature, interpass temperature and preheat maintenance temperature. (ISO 13916:1996)*

EN ISO 15607:2003, *Specification and qualification of welding procedures for metallic materials – General rules. (ISO 15607:2003)*

CR ISO 15608, *Welding – Guidelines for a metallic material grouping system (ISO/TR 15608:2000).*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN ISO 15607:2003 apply.

4 Technical content of welding procedure specification (WPS)

4.1 General

A preliminary Welding Procedure Specification/Welding Procedure Specification (pWPS/WPS) shall provide all the necessary information required to make a weld. The information required in a pWPS/WPS is given in 4.2 to 4.5.

NOTE For some applications it may be necessary to supplement or reduce the list.

Welding procedure specifications cover a certain range of material thickness and also cover a range of parent materials and even welding consumables. Some manufacturers prefer additionally to prepare work instructions for each specific job as part of detailed production planning.

Ranges and tolerances, according to the relevant standard of the series (see EN ISO 15607) and to the manufacturer's experience, shall be specified where appropriate.

An example of the WPS-format is shown in annex A.

4.2 Related to the manufacturer

- Identification of the manufacturer;
- Identification of the WPS;
- Reference to the Welding Procedure Qualification Record (WPQR) or other documents as required (see EN ISO 15607:2003, Annex C).

4.3 Related to the parent material

4.3.1 Parent material type

- Designation of the material(s), and reference standard(s);
- Number(s) of the group(s) as given in CR ISO 15608.

A WPS may cover a group of materials.

4.3.2 Material dimensions

- Thickness ranges of the joint;
- Outside diameter ranges for pipes.

iteh STANDARD PREVIEW
(standards.iteh.ai)

4.4 Common to all welding procedures

4.4.1 Welding process

<https://standards.iteh.ai/catalog/standards/sist/cc867c91-bb31-4823-beb3-e18ee062d634/iso-15609-1-2004>

Welding process(es) used in accordance with EN ISO 4063.

4.4.2 Joint design

- A sketch of the joint design/configuration and dimensions or reference to standards which provide such information.
- Weld run sequence given on the sketch if essential for the properties of the weld.

4.4.3 Welding position

Applicable welding positions in accordance with EN ISO 6947.

4.4.4 Joint preparation

- Joint preparation methods, cleaning, degreasing, including methods to be used;
- Jigging, fixtures and tack welding.

4.4.5 Welding technique

- Weaving if applicable
 - a) For manual welding maximum width of the run.

b) For mechanized and automatic welding maximum weaving or amplitude, frequency and dwell time of oscillation.

- Torch, electrode and/or wire angle.

4.4.6 Back gouging

— The method to be used.

— Depth and shape.

4.4.7 Backing

— The method and type of backing, backing material and dimensions.

— For gas backing, gas in accordance with EN 439.

4.4.8 Welding consumables

— Designation, make (manufacturer and trade name).

— Dimensions (size).

— Handling (baking, exposure to atmosphere, re-drying, etc.).

4.4.9 Electrical parameters

— Type of current (alternating current (AC) or direct current (DC)) and polarity.

— Pulse welding details (machine settings, programme selection) if applicable.

— Current range.

4.4.10 Mechanized and automatic welding

— Travel speed range.

— Wire/strip feed speed range.

If the equipment does not permit control of one of either variable, the machine settings shall be specified instead. The range of application for the WPS shall then be limited to equipment of that particular type. This applies to 4.4.9 and 4.4.10.

4.4.11 Preheat temperature

— The minimum temperature applied at the start of welding and during welding.

— If pre-heating is not required the lowest work piece temperature prior to welding.

4.4.12 Interpass temperature

Maximum and if necessary minimum interpass temperature.