



DRAFT INTERNATIONAL STANDARD ISO/DIS 3327

ISO/TC 119/SC 4

Secretariat: SIS

Voting begins on
2001-06-07

Voting terminates on
2001-11-07

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Hardmetals — Determination of transverse rupture strength

[Revision of second edition (ISO 3327:1982)]

Métaux-durs — Détermination de la résistance à la flexion

ICS 77.040.10; 77.160

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/DIS 3327](#)

<https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327>

ISO/CEN PARALLEL ENQUIRY

The CEN Secretary-General has advised the ISO Secretary-General that this ISO/DIS covers a subject of interest to European standardization. **In accordance with subclause 5.1 of the Vienna Agreement, consultation on this ISO/DIS has the same effect for CEN members as would a CEN enquiry on a draft European Standard.** Should this draft be accepted, a final draft, established on the basis of comments received, will be submitted to a parallel two-month FDIS vote in ISO and formal vote in CEN.

To expedite distribution, this document is circulated as received from the committee secretariat. ISO Central Secretariat work of editing and text composition will be undertaken at publication stage.

Pour accélérer la distribution, le présent document est distribué tel qu'il est parvenu du secrétariat du comité. Le travail de rédaction et de composition de texte sera effectué au Secrétariat central de l'ISO au stade de publication.

THIS DOCUMENT IS A DRAFT CIRCULATED FOR COMMENT AND APPROVAL. IT IS THEREFORE SUBJECT TO CHANGE AND MAY NOT BE REFERRED TO AS AN INTERNATIONAL STANDARD UNTIL PUBLISHED AS SUCH.

IN ADDITION TO THEIR EVALUATION AS BEING ACCEPTABLE FOR INDUSTRIAL, TECHNOLOGICAL, COMMERCIAL AND USER PURPOSES, DRAFT INTERNATIONAL STANDARDS MAY ON OCCASION HAVE TO BE CONSIDERED IN THE LIGHT OF THEIR POTENTIAL TO BECOME STANDARDS TO WHICH REFERENCE MAY BE MADE IN NATIONAL REGULATIONS.

Contents

| | | |
|----|-------------------------------|------------------------------|
| 1 | Scope..... | 1 |
| 2 | Symbols and designations..... | 1 |
| 3 | Field of application..... | 1 |
| 4 | Principle | 1 |
| 5 | Apparatus..... | 1 |
| 6 | Test pieces | 2 |
| 7 | Procedure..... | 3 |
| 8 | Expression of results..... | 3 |
| 9 | Test report..... | 4 |
| 10 | Bibliography..... | Error! Bookmark not defined. |

iTeh STANDARD PREVIEW
(standards.iteh.ai)

[ISO/DIS 3327](https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327)

<https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

International Standard ISO 3327 was prepared by Technical Committee ISO/TC 119, *Powder metallurgy*, Subcommittee SC 4, *Sampling and testing methods for hardmetals*.

This third edition cancels and replaces the second edition (ISO 3327:1982) which has been technically revised.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[ISO/DIS 3327](https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327)

<https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO/DIS 3327

<https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327>

Hardmetals — Determination of transverse rupture strength

1 Scope

This International Standard specifies a method for determination of the transverse rupture strength of hardmetals.

2 Symbols and designations

See table 1.

Table 1 — Symbols and designations

| Symbol | Designation | Unit |
|-----------------|---|-------------------|
| F | Force required to fracture the test piece | N |
| l | Distance between supports | mm |
| b | Width of test piece perpendicular to its height | mm |
| h | Height of test piece parallel to the direction of application of the test force | mm |
| k | Correction factor to compensate for the chamfer | |
| R_{bm} | Transverse rupture strength | N/mm ² |
| d | Diameter of test piece (if cylindrical test piece is used) | mm |

3 Field of application

The method is applicable to hardmetals of negligible ductility. If it is used for hardmetals showing significant plastic deformation before breaking, incorrect results may be obtained. In such instances, the method may be used for comparison purposes only.

4 Principle

Breaking a test piece lying freely on two supports by application of a force at the midpoint of the span under conditions of short-term static application of the force.

5 Apparatus

5.1 The test equipment shall comprise any device capable of applying a uniformly increasing force with an accuracy of 1 % or better.

5.2 The fixture for testing shall have two freely lying support cylinders (rollers) with a fixed distance between them and a freely lying force cylinder (roller). The three cylinders shall be of equal diameter between 3,2 and 6 mm.

Alternatively, the force may be applied by a ball having a diameter of 10 mm. Loading of the test piece can only be made via three cylinders if a cylindrical test piece is used. Consequently, a ball is only applicable for test pieces having plane surfaces.

The support cylinders and the force cylinder or ball shall be made of tungsten carbide hardmetal which will not be visibly deformed by the applied force. The surface roughness R_a of the cylinders and the ball shall not be greater than 0,63 μm .

5.3 The support cylinders shall be mounted parallel, with a span between them of $30 \pm 0,5$ mm for type A test pieces and $14,5 \pm 0,5$ mm for type B and type C test pieces. The measurement of the span used for the calculation shall be made to an accuracy of 0,1 mm for type B and type C test pieces and to an accuracy of 0,2 mm for type A test pieces.

5.4 The mounting of the cylinders shall be such as to minimise deviations from parallelism of the support cylinders.

5.5 For safety, the fixture shall be surrounded by a suitable protective guard.

6 Test pieces

6.1 The test pieces shall be of rectangular (type A and B) or cylindrical (type C) cross-section and shall have the dimensions shown in table 2.

Table 2 – Dimensions of test pieces
 iTech STANDARD PREVIEW
 (standards.itech.ai)

Dimensions in millimetres

| Type | Length | Width/Diameter | Height |
|------|------------|----------------|-----------------|
| A | 35 ± 1 | $5 \pm 0,25$ | $5 \pm 0,25$ |
| B | 20 ± 1 | $6,5 \pm 0,25$ | $5,25 \pm 0,25$ |
| C | 25 ± 5 | $3,3 \pm 0,5$ | |

NOTE – In general, type B test pieces give strength values which are about 10-20 % higher than those obtained using type A test pieces depending on the material tested and provided that they have the same surface conditions. The repeatability is similar for all types of test piece. Type C test pieces give strength values which are about 5–10 % higher than type B specimens with the increase material related.

6.2 The test pieces shall be ground on the four faces which are parallel to the length with a free cutting diamond wheel, preferably resin bonded, using copious quantities of coolant. No pass shall exceed 0,01 mm and all grinding marks shall be parallel to the length. The amount taken off each face shall be not less than 0,1 mm and the surface roughness shall be $R_a \leq 0,4 \mu\text{m}$. The four long edges shall be chamfered to 0,15 to 0,20 mm at an angle of 45° and all grinding marks shall be parallel to the length. Type C test pieces shall be centreless ground to a surface roughness $R_a \leq 0,4 \mu\text{m}$.

6.3 It is also permitted to use test pieces in the as-sintered condition. Such test pieces shall have a chamfer of 0,4 to 0,5 mm at an angle of 45° , made before sintering to avoid flash. Bend strength results from as-sintered test pieces are generally significantly lower than for ground test pieces.

NOTE – Surface preparation is an important variable and should be standardised to ensure consistent results are obtained.

6.4 The deviation from parallelism of opposite longitudinal sides, in both the longitudinal and transverse directions, shall not exceed 0,05 mm for each 10 mm length for as-sintered test pieces and 0,01 mm for each 10 mm length for ground test pieces. For round test pieces opposite sides shall be parallel within 0,015 mm.

6.5 Width and height measurements used for calculation of the results shall be carried out at the middle of the test pieces to the nearest 0,01 mm.

6.6 The test pieces shall be free from visual surface cracks and structural defects.

7 Procedure

7.1 Place a test piece flat and centrally on the support cylinders so that its length is perpendicular to the lengths of the support cylinders. In the case of a type B test piece, place its width on the support cylinders.

7.2 Bring the force cylinder or ball gradually into contact with the test piece.

The deviation of the line or the point of application of the force from the middle of the span shall not exceed 0,5 mm for type A test pieces and 0,2 mm for type B test pieces.

7.3 Increase the stress in the test piece at a uniform rate not exceeding 200 N/mm² per second.

NOTE – This corresponds to a force increasing at a maximum rate of 1600 N per second for type B and type C test pieces and 600 N per second for type A test pieces.

8 Expression of results

8.1 The transverse rupture strength R_{bm} , expressed in newtons per square millimetre, is given by the formula

$$R_{bm} = \frac{3 \times k \times F \times l}{2 \times b \times h^2}$$

for rectangular test pieces.

Values of k are given in table 3.

ISO/DIS 3327
<https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-6c74c54ad24/iso-dis-3327>
Table 3 — Values of chamfer correction factor, k

| Test piece type | Chamfer mm | Correction factor k |
|-----------------|-------------|-----------------------|
| A | 0,4 to 0,5 | 1,03 |
| A | 0,15 to 0,2 | 1,00 |
| B | 0,4 to 0,5 | 1,02 |
| B | 0,15 to 0,2 | 1,00 |

and

$$R_{bm} = \frac{8 \times F \times l}{\pi \times d^3}$$

for cylindrical test pieces.

NOTE – The formula for calculating the transverse rupture strength does not take into account the effect of any plastic deformation that may occur.

8.2 Report the arithmetical mean of at least five transverse rupture strength determinations, round to the nearest 10 N/mm².

9 Test report

Since the test piece geometry and surface preparation can significantly affect the values of transverse rupture strength it is important that the test report shall include the following information:

- a) a reference to this International Standard;
- b) all details necessary for identification of the test sample;
- c) the type of test piece and the method of preparation of its surface;
- d) the method of applying the force;
- e) the result obtained. The following additional subscripts shall be added to the symbol indicating transverse rupture strength, indicating surface condition, i.e. sintered (S) or ground (G):
 - for type A test pieces: A30S or A30G;
 - for type B test pieces: B15S or B15G;
 - for type C test pieces: C15S or C15G.Example: $R_{\text{bm}30}$ (A30S) or $R_{\text{bm}30}$ (A30G)
- f) all operations not specified in this International Standard, or regarded as optional;
- g) details of any occurrence which may have affected the result.

ISO/DIS 3327
<https://standards.iteh.ai/catalog/standards/sist/289b7d00-448a-40a9-bff6-dc74c34afa24/iso-dis-3327>