



SLOVENSKI STANDARD

SIST EN 15856:2011

01-februar-2011

Neporušitveno preskušanje - Akustična emisija - Osnove preskušanja z AE pri zaznavanju korozije v kovinskih posodah, napolnjenih s tekočino

Non-destructive testing - Acoustic emission - General principles of AE testing for the detection of corrosion within metallic surrounding filled with liquid

Zerstörungsfreie Prüfung - Schallemission - Allgemeine Grundsätze der Schallemissionsprüfung zum Nachweis von Korrosion innerhalb von mit Flüssigkeit gefüllten metallischen Umschließungen

Essais non destructifs - Emission acoustique - Principes généraux des contrôles par émission acoustique pour la détection de la corrosion dans une enceinte métallique remplie de liquide

Ta slovenski standard je istoveten z: EN 15856:2010

ICS:

19.100 Neporušitveno preskušanje Non-destructive testing

SIST EN 15856:2011

en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15856:2011

<https://standards.iteh.ai/catalog/standards/sist/5272183b-1bfa-4c8e-bbdb-8dd92551bac7/sist-en-15856-2011>

EUROPEAN STANDARD

EN 15856

NORME EUROPÉENNE

EUROPÄISCHE NORM

January 2010

ICS 19.100

English Version

Non-destructive testing - Acoustic emission - General principles of AE testing for the detection of corrosion within metallic surrounding filled with liquid

Essais non destructifs - Emission acoustique - Principes
généraux des contrôles par émission acoustique pour la
détection de la corrosion dans une enceinte métallique
remplie de liquide

Zerstörungsfreie Prüfung - Schallemissionsprüfung -
Allgemeine Grundsätze der Schallemissionsprüfung zum
Nachweis von Korrosion innerhalb von mit Flüssigkeit
gefüllten metallischen Umschließungen

This European Standard was approved by CEN on 28 November 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....	3
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Personnel qualifications.....	5
5 General	5
5.1 Introduction	5
5.2 Test preparation.....	5
5.3 Sensors	5
5.4 Source location.....	5
5.5 Preliminary information.....	6
5.6 Written instruction requirements.....	6
6 Instrumentation.....	7
7 Testing.....	7
7.1 Sensor positions.....	7
7.2 Test detection threshold	8
7.3 Background noise	9
7.4 In-situ verification	9
7.5 Apparent acoustic emission velocity	9
7.6 Performing the test.....	10
8 Interpretation of results.....	10
8.1 Data evaluation	10
8.2 Tank grading.....	10
9 Documentation	10
10 Safety regulations.....	11

ITeH STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15856:2011

<https://standards.iteh.ai/catalog/standards/sist/5272183b-1bfa-4c8e-bbdb-8dd92551bac7/sist-en-15856-2011>

Foreword

This document (EN 15856:2010) has been prepared by Technical Committee CEN/TC 138 “Non-destructive testing”, the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by July 2010, and conflicting national standards shall be withdrawn at the latest by July 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

[SIST EN 15856:2011](https://standards.iteh.ai/catalog/standards/sist/5272183b-1bfa-4c8e-bbdb-8dd92551bac7/sist-en-15856-2011)

<https://standards.iteh.ai/catalog/standards/sist/5272183b-1bfa-4c8e-bbdb-8dd92551bac7/sist-en-15856-2011>

EN 15856:2010 (E)**1 Scope**

This European Standard describes acoustic emission testing (AT) on metallic surroundings filled with liquids for the detection of corrosion processes that are active at the time of the test. It is applicable to metallic storage tanks, such as those used in the chemical and petrochemical industry.

The results provide a qualitative statement regarding the condition of the test object and a recommendation regarding the maximum allowable duration of the follow-on service period, based on the AT indications and additional information in order to characterize the AT indications.

In the case of flat bottomed storage tanks (FBST) the procedure described within this standard provides testing of the complete bottom, the tank shell up to the filling height and in case of a floating roof tank also the roof sheets in contact with the stored liquid.

As for every application of acoustic emission testing, the measured data contain information regarding active sources. An ongoing corrosion process, such as general corrosion and localized corrosion defined in EN ISO 8044, leading to progressive loss of wall thickness will be detected. A corrosion process which has stopped does not produce acoustic emission and will therefore not be detected at the time of test.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 473, *Non-destructive testing — Qualification and certification of NDT personnel — General principles*

EN 1330-1:1998, *Non-destructive testing — Terminology — Part 1: List of general terms*

<https://standards.iteh.ai/catalog/standards/sist/5272183b-1bfa-4c8e-bbdb-8d7575147c01/sist-en-15856-2010>

EN 1330-2:1998, *Non-destructive testing — Terminology — Part 2: Terms common to the non-destructive testing methods*

EN 1330-9:2009, *Non-destructive testing — Terminology — Part 9: Terms used in acoustic emission testing*

EN 13477-1, *Non-destructive testing — Acoustic emission — Equipment characterisation — Part 1: Equipment description*

EN 13477-2, *Non-destructive testing — Acoustic emission — Equipment characterisation — Part 2: verification of operating characteristics*

EN 13554, *Non-destructive testing — Acoustic emission — General principles*

EN ISO 8044:1999, *Corrosion of metals and alloys — Basic terms and definitions (ISO 8044:1999)*

EN ISO/IEC 17025, *General requirements for the competence of testing and calibration laboratories (ISO/IEC 17025:2005)*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 1330-1:1998, EN 1330-2:1998, EN 1330-9:2009 and EN ISO 8044:1999 apply.

4 Personnel qualifications

It is assumed that acoustic emission testing is performed by qualified and capable personnel. In order to prove this qualification, it is recommended to certify the personnel in accordance with EN 473.

5 General

5.1 Introduction

Evaluation of the AE data shall be done according to an established grading system, providing grades relating to the rate of degradation of the component under test as a result of corrosion.

The recommended duration of the service period following the test is with respect to the service condition prior to and at the time of the test. This recommendation is invalid, if the storage product or any other major service parameter has been altered.

The final test result shall not be affected by external or internal noise sources. The testing service provider has to communicate the demands regarding tank preparation to the tank operator. Proper support by the plant personnel for identification and elimination of noise sources shall be ensured.

5.2 Test preparation

AE originating from corrosion propagates through both the liquid and the structure. Where corrosion testing of tanks utilises wave propagation through the liquid stock product, the minimum filling level of the tank to be tested shall exceed the highest position of sensors mounted onto the tank shell at least by 1 m.

When testing flat bottomed storage tanks (FBST) the tank operation shall be static before the test in order to reduce internal noise to a minimum. No product shall be fed into or taken out of the tank, no internal circulation shall take place and, if operated, the heater shall be shut down. The necessary time period varies depending on the tank size and the stock product. Twenty-four hours is usually sufficient.

5.3 Sensors

When wave propagation through the liquid is used, the sensor frequency band is usually in the range from 20 kHz to 80 kHz. When wave propagation through the metal is used, the sensing frequency band is usually in the range from 100 kHz to 300 kHz.

The equipment surface below the sensors shall be prepared to ensure the maximum coupling efficiency. The sensor couplant shall be as specified in the written test instruction. The sensors may be directly attached to the structure using magnetic devices or suitable adhesive.

The effectiveness and reliability of the acoustic couplant shall be verified. The characteristics of the type of the acoustic couplant used shall not affect the structure adversely.

5.4 Source location

The location of AE sources is based on delta t measurement. In case of tank floor testing two rows of sensors and wave propagation through the liquid shall be used.

When evaluating the floor condition regarding active corrosion, the location error is normally within 10 % of the tank diameter. The location error is smaller near the centre area and increases as the AE source approaches the annular ring.

If the height of first row sensors (see 7.1) is changed as a result of the presence of sludge or internal structure, then the location error increases, especially near to the annular ring.

EN 15856:2010 (E)

The same principle applies to the evaluation regarding active corrosion of the floating roof. The location error of the roof testing is normally within 15 % of the tank diameter. The error increases when the distance of the second row of sensors from the floating roof increases.

Waves propagate through liquid and metal from the source to the sensors and perhaps also on different paths. Therefore the planar location error on the tank shell is normally within 15 % of the sensor spacing.

5.5 Preliminary information

The tank operator shall provide information necessary for performing the test. This shall include the following, as relevant and available:

- a) Customer nominated on-site test co-ordinator;
- b) Tank information: identification, manufacturer, year of manufacturing, serial number, capacity, shell height, diameter, thermal insulation, stock product, roof type, bottom type, foundation, internal coating, internal installation, cathodic protection, tank history including NDT and repairs, assembly drawings with sufficient details of the structure;
- c) AE test information: intended date and expected conditions such as stock product, temperature, filling height, sludge level, water bottom;
- d) Potential external and internal noise interference sources.

5.6 Written instruction requirements

The AE test organisation shall provide a written test instruction, which shall include but not necessarily be restricted to the following:

- a) explicit indication of the purpose of the test and limitations if any;
- b) sensor type, frequency and manufacturer;
- c) method of sensor attachment;
- d) type of acoustic couplant used;
- e) type of surface preparation;
- f) type of AE equipment used with the main characteristics;
- g) energy measurement method to be used;
- h) number of sensors required and the sensor arrangement;
- i) description of equipment verification procedure;
- j) description of in-situ verification;
- k) description of test performance;
- l) recorded data and recording method;
- m) available on-line presentation of data;
- n) cluster parameters (e.g. shape, size, minimum number of located events);
- o) post-test analysis procedure;

- p) final report requirements;
- q) qualification/certification of the personnel.

The test instruction shall be prepared in accordance with EN 473 and EN 13554.

6 Instrumentation

An AE system consists of sensors and equipment for signal conditioning and processing and for displaying and recording data according to EN 13477-1.

The AE instrument shall be capable of measuring at least the following parameters on every channel:

- a) AE burst count;
- b) appropriate parameter indicating the background noise;
- c) burst signal peak amplitude;
- d) burst signal duration;
- e) burst signal rise time;
- f) burst signal energy;
- g) arrival time.

ITeh STANDARD PREVIEW
(standards.iteh.ai)

In addition to the acquired burst signal parameters, waveform data of each detected hit on any available AE channel enables evaluation by signal frequency analysis.

<https://standards.iteh.ai/catalog/standards/sist/5272183b-1bfa-4c8e-bbdb-8dd92551bac7/sist-en-15856-2011>

The test instrumentation shall:

- h) store all the acquired data; and
- i) provide an on-line location display

for preliminary on-site reporting on the performed test.

The AE system performance check (including sensors) shall be performed according to EN 13477-2.

7 Testing

7.1 Sensor positions

For use of wave propagation through liquid, e.g. testing flat bottomed storage tanks (FBST), the following applies:

The number of sensors necessary for a certain tank diameter is derived from the requirement, that the distance between the sensors distributed equally around the circumference shall not exceed 15 m. Due to the fact that manholes, nozzles, welds and other structural details have to be taken into account when selecting the sensor positions, a reduced maximum distance of 13 m has proven to be applicable. With this value it is possible to shift positions as required by the structure and to stay within the limit of 15 m. The number of sensors applied shall not be less than six per row.

The distance of a sensor to a weld or a reinforcing plate shall not be less than 200 mm.