



SLOVENSKI STANDARD
SIST EN 12697-6:2004+A1:2007

01-november-2007

6]li a Ybg_Y'na Ygj!'DfYg_i gbY'a YlcXY'nUj fc Y'UgZU'fbY'na Ygj!'* "XY.
I [cHJj`Ub^Y[cglcH^V]li a Ybg_] `dfYg_i yUbWj

Bituminous mixtures - Test methods for hot mix asphalt - Part 6: Determination of bulk density of bituminous specimens

Asphalt - Prüfverfahren für Heißasphalt - Teil 6: Bestimmung der Raumdichte von Asphalt-Probekörpern

Mélanges bitumineux - Méthodes d'essai pour mélange hydrocarboné a chaud - Partie 6 : Détermination de la masse volumique apparente des éprouvettes bitumineuses

<https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfccc/sist-en-12697-6-2004a1-2007>

Ta slovenski standard je istoveten z: EN 12697-6:2003+A1:2007

ICS:

93.080.20 Materiali za gradnjo cest Road construction materials

SIST EN 12697-6:2004+A1:2007 en,fr,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 12697-6:2004+A1:2007

<https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfccc/sist-en-12697-6-2004a1-2007>

English Version

Bituminous mixtures - Test methods for hot mix asphalt - Part 6:
Determination of bulk density of bituminous specimens

Matériaux enrobés - Méthodes d'essai pour enrobés à
chaud - Partie 6: Détermination de la masse volumique
apparente des éprouvettes bitumineuses

Asphalt - Prüfverfahren für Heiasphalt - Teil 6:
Bestimmung der Raumdichte von Asphalt-Probekrpern

This European Standard was approved by CEN on 21 November 2002 and includes Amendment 1 approved by CEN on 16 May 2007.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 12697-6:2004+A1:2007](https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfcc/sist-en-12697-6-2004a1-2007)

<https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfcc/sist-en-12697-6-2004a1-2007>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents

	page
Foreword.....	3
1 Scope	6
2 Normative references	6
3 Terms and definitions	6
4 Principle.....	6
5 Materials	7
6 Apparatus	7
7 Sample sizes and sample handling	8
8 Preparation of sample	8
9 Procedure	8
10 Calculation.....	10
11 Precision.....	11
12 Test report	12
Annex A (informative) General guidance on selection of a test procedure to determine the bulk density of compacted bituminous materials	13
Bibliography	16

iTeh STANDARD PREVIEW
(standards.iteh.ai)

<https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfccc/sist-en-12697-6-2004a1-2007>

Foreword

This document (EN 12697-6:2003+A1:2007) has been prepared by Technical Committee CEN/TC 227 "Road materials", the secretariat of which is held by DIN.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by January 2008 and conflicting national standards shall be withdrawn at the latest by January 2008.

This document includes Amendment 1, approved by CEN on 2007-05-16.

This document supersedes EN 12697-6:2003.

The start and finish of text introduced or altered by amendment is indicated in the text by tags $\boxed{A1}$ $\boxed{A1}$.

This European Standard is one of a series of standards as listed below.

EN 12697-1, *Bituminous mixtures – Test methods for hot mix asphalt – Part 1: Soluble binder content*

EN 12697-2, *Bituminous mixtures – Test method for hot mix asphalt – Part 2: Determination of particle size distribution*

EN 12697-3, *Bituminous mixtures – Test methods for hot mix asphalt – Part 3: Binder recovery: Rotary evaporator*

EN 12697-4, *Bituminous mixtures – Test methods for hot mix asphalt – Part 4: Binder recovery: Fractionating column*

EN 12697-5, *Bituminous mixtures – Test methods for hot mix asphalt – Part 5: Determination of the maximum density*

EN 12697-6, *Bituminous mixtures – Test methods for hot mix asphalt – Part 6: Determination of bulk density of bituminous specimens*

EN 12697-7, *Bituminous mixtures – Test methods for hot mix asphalt – Part 7: Determination of bulk density of bituminous specimens by gamma rays*

EN 12697-8, *Bituminous mixtures – Test methods for hot mix asphalt – Part 8: Determination of void characteristics of bituminous specimens*

EN 12697-9, *Bituminous mixtures – Test methods for hot mix asphalt – Part 9: Determination of the reference density*

EN 12697-10, *Bituminous mixtures – Test methods for hot mix asphalt – Part 10: Compactibility*

EN 12697-11, *Bituminous mixtures – Test methods for hot mix asphalt – Part 11: Determination of the affinity between aggregate and bitumen*

EN 12697-12, *Bituminous mixtures – Test methods for hot mix asphalt – Part 12: Determination of the water sensitivity of bituminous specimens*

EN 12697-13, *Bituminous mixtures – Test methods for hot mix asphalt – Part 13: Temperature measurement*

EN 12697-14, *Bituminous mixtures – Test methods for hot mix asphalt – Part 14: Water content*

EN 12697-6:2003+A1:2007 (E)

- EN 12697-15, *Bituminous mixtures – Test methods for hot mix asphalt – Part 15: Determination of the segregation sensitivity*
- EN 12697-16, *Bituminous mixtures – Test methods for hot mix asphalt – Part 16: Abrasion by studded tyres*
- EN 12697-17, *Bituminous mixtures – Test methods for hot mix asphalt – Part 17: Particle loss of porous asphalt specimen*
- EN 12697-18, *Bituminous mixtures – Test methods for hot mix asphalt – Part 18: Binder drainage*
- EN 12697-19, *Bituminous mixtures – Test methods for hot mix asphalt – Part 19: Permeability of specimen*
- EN 12697-20, *Bituminous mixtures – Test methods for hot mix asphalt – Part 20: Indentation using cube or Marshall specimen*
- EN 12697-21, *Bituminous mixtures – Test methods for hot mix asphalt – Part 21: Indentation using plate specimens*
- EN 12697-22, *Bituminous mixtures – Test methods for hot mix asphalt – Part 22: Wheel tracking*
- EN 12697-23, *Bituminous mixtures – Test methods for hot mix asphalt – Part 23: Determination of the indirect tensile strength of bituminous specimens*
- EN 12697-24, *Bituminous mixtures – Test methods for hot mix asphalt – Part 24: Resistance to fatigue*
- EN 12697-25, *Bituminous mixtures – Test methods for hot mix asphalt – Part 25: Cyclic compression test*
- EN 12697-26, *Bituminous mixtures – Test methods for hot mix asphalt – Part 26: Stiffness*
- EN 12697-27, *Bituminous mixtures – Test methods for hot mix asphalt – Part 27: Sampling*
- EN 12697-28, *Bituminous mixtures – Test methods for hot mix asphalt – Part 28: Preparation of samples for determining binder content, water content and grading*
- EN 12697-29, *Bituminous mixtures – Test methods for hot mix asphalt – Part 29: Determination of the dimensions of a bituminous specimen*
- EN 12697-30, *Bituminous mixtures – Test methods for hot mix asphalt – Part 30: Specimen preparation by impact compactor*
- EN 12697-31, *Bituminous mixtures – Test methods for hot mix asphalt – Part 31: Specimen preparation by gyratory compactor*
- EN 12697-32, *Bituminous mixtures – Test methods for hot mix asphalt – Part 32: Laboratory compaction of bituminous mixtures by a vibratory compactor*
- EN 12697-33, *Bituminous mixtures – Test methods for hot mix asphalt – Part 33: Specimen preparation by roller compactor*
- EN 12697-34, *Bituminous mixtures – Test methods for hot mix asphalt – Part 34: Marshall test*
- EN 12697-35, *Bituminous mixtures – Test methods for hot mix asphalt – Part 35: Laboratory mixing*
- EN 12697-36, *Bituminous mixtures – Test methods for hot mix asphalt – Part 36: Determination of the thickness of a bituminous pavement*
- EN 12697-37, *Bituminous mixtures – Test methods for hot mix asphalt – Part 37: Hot sand test for the adhesivity of binder on precoated chippings for HRA*

EN 12697-38, *Bituminous mixtures – Test methods for hot mix asphalt – Part 38: Test equipment and calibration*

EN 12697-39, *Bituminous mixtures – Test methods for hot mix asphalt – Part 39: Binder content of by ignition*

EN 12697-40, *Bituminous mixtures – Test methods for hot mix asphalt – Part 40: In situ drainability*

EN 12697-41, *Bituminous mixtures – Test methods for hot mix asphalt – Part 41: Resistance to deicing fluids*

EN 12697-42, *Bituminous mixtures – Test methods for hot mix asphalt – Part 42: Amount of coarse foreign matters in reclaimed asphalt*

EN 12697-43, *Bituminous mixtures – Test methods for hot mix asphalt – Part 43: Resistance to fuel*

The applicability of this European Standard is described in the product standards for bituminous mixtures.

 deleted text 

Annex A is informative.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN 12697-6:2004+A1:2007

<https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfccc/sist-en-12697-6-2004a1-2007>

1 Scope

This European Standard describes test methods for determining the bulk density of a compacted bituminous specimen. The test methods are intended for use with laboratory compacted specimens or specimens from cores cut from the pavement after placement and compacting.

This European Standard describes the following four procedures, the choice of which is used being dependent on the estimated content and accessibility of voids in the specimen:

- a) bulk density — dry (for specimens with a very closed surface);
- b) bulk density — saturated surface dry (SSD) (for specimens with a closed surface);
- c) bulk density — sealed specimen (for specimens with an open or coarse surface);
- d) bulk density by dimensions (for specimens with a regular surface and with geometric shapes, i. e. squares, rectangles, cylinders etc.

NOTE Annex A (informative) gives general guidance on selecting the appropriate procedure.

2 Normative references

This European Standard incorporates by dated or undated reference, provisions from other publications. These normative references are cited at the appropriate places in the text, and the publications are listed hereafter. For dated references, subsequent amendments to or revisions of any of these publications apply to this European Standard only when incorporated in it by amendment or revision. For undated references the latest edition of the publication referred to applies (including amendments).

EN 12697-29, *Bituminous mixtures* — Test methods for hot mix asphalt — Part 29: Determination of the dimensions of a bituminous specimen.

3 Terms and definitions

For the purposes of this European Standard, the following terms and definitions apply.

3.1

maximum density

mass per unit volume, without air voids, of a bituminous mixture at known test temperature

3.2

bulk density

mass per unit volume, including the air voids, of a specimen at known test temperature

4 Principle

The bulk density of an intact compacted bituminous specimen is determined from the mass of the specimen and its volume. The mass of the specimen is obtained by weighing the dry specimen in air.

For the first three procedures the volume of the specimen is obtained from its mass in air and its mass in water. In the dry procedure the mass in water is determined without pre-treatment. In the SSD-procedure the specimen is first saturated with water, after which its surface is blotted dry with a damp Chamois. In the sealed specimen procedure, the specimen is sealed before immersion in water to prevent access of water to the voids in the specimen. In the fourth procedure by dimensions the volume of the specimen is obtained by measurement of the dimensions.

5 Materials

5.1 General

Water, with a known density at the test temperature. The water density at 25 °C shall be 997,1 kg/m³. For other temperatures the water density shall be $(977,1 \times K)$ kg/m³ (see Table 1).

Table 1 — Water density

Water temperature °C	Correction factor K	Water density kg/m ³	Water temperature °C	Correction factor K	Water density kg/m ³
10	1,0027	999,8	20	1,0012	998,3
11	1,0026	999,7	21	1,0010	998,1
12	1,0025	999,6	22	1,0007	997,8
13	1,0023	999,4	23	1,0005	997,6
14	1,0022	999,3	24	1,0003	997,4
15	1,0021	999,2	25	1,0000	997,1
16	1,0019	999,0	26	0,9997	996,8
17	1,0017	998,8	27	0,9995	996,6
18	1,0016	998,7	28	0,9992	996,3
19	1,0014	998,5	29	0,9989	996,0
20	1,0012	998,3	30	0,9986	995,7

<https://standards.iteh.ai/catalog/standards/sist/ca6d7726-073b-4d14-aaac-bbba677cfccc/sist-en-12697-6-2004a1-2007>

5.2 Additional materials for the sealed specimen procedure

Material to seal the specimen, in such a way, that inclusion of voids (being no part of the specimen) between seal and specimen is prevented. The density of the sealing material at test temperature shall be known to the nearest 0,010 g/cm³.

NOTE The material used can be paraffin wax, shrinkage foil, latex emulsion etc. The procedure to apply such materials should be such that the specimen is not damaged. It is very important that the seal exactly covers the specimen including the voids which technologically form part of its volume: when applying the seal penetration of the internal voids belonging to the material is prevented, as well as inclusion of extra voids between seal and specimen or in seal folds.

6 Apparatus

6.1 General

Balance, with sufficient capacity and an accuracy of at least $\pm 0,1$ g suitable for weighing, the specimen in air and under water (e. g. via a wire basket, the mass and water displacement of which are taken into account by tarring); the precision of the scale shall be limited to a maximum mass of the specimen.

6.2 Additional apparatus for the dry, SSD and sealed specimen procedures

6.2.1 Water-bath, maintained at a uniform temperature within $\pm 1,0$ °C in the vicinity of the test specimen(s). It shall be provided with a grid to ensure the water circulation around the test specimen. The bath shall have a capacity of at least three times that of the volume of the specimen.

6.2.2 Thermometer, accurate to at least $\pm 1,0$ °C;