
**Plastics — Poly(methyl methacrylate)
sheets — Types, dimensions and
characteristics —**

**Part 2:
Extruded sheets**

iTeh STANDARD PREVIEW

*Plastiques — Plaques en poly(méthacrylate de méthyle) — Types,
dimensions et caractéristiques —*

Partie 2: Plaques extrudées

ISO 7823-2:2003

<https://standards.itih.ai/catalog/standards/sist/1faa389a-6ef7-4b9f-8848-17a8acb3fbee/iso-7823-2-2003>



PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 7823-2:2003

<https://standards.iteh.ai/catalog/standards/sist/1faa389a-6ef7-4b9f-8848-17a8acb3fbee/iso-7823-2-2003>

© ISO 2003

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 General requirements	3
5 Test methods	6
6 Retest and rejection	8
Annex A (normative) Determination of light transmittance at 420 nm	9
Annex B (normative) Determination of dimensional change on heating (shrinkage)	10

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 7823-2:2003

<https://standards.iteh.ai/catalog/standards/sist/1faa389a-6ef7-4b9f-8848-17a8acb3fbee/iso-7823-2-2003>

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 7823-2 was prepared by Technical Committee ISO/TC 61, *Plastics*, Subcommittee SC 11, *Products*.

This third edition cancels and replaces the second edition (ISO 7823-2:1996), which has been technically revised.

ISO 7823 consists of the following parts, under the general title *Plastics — Poly(methyl methacrylate) sheets — Types, dimensions and characteristics*:

- ITC STANDARD PREVIEW
(standards.iteh.ai)
- ISO 7823-2:2003
<https://standards.iteh.ai/catalog/standards/sist/1faa389a-6ef7-4b9f-8848-17a8acb3fbee/iso-7823-2-2003>
- *Part 1: Cast sheets*
 - *Part 2: Extruded sheets*
 - *Part 3: Continuous cast sheets*

Plastics — Poly(methyl methacrylate) sheets — Types, dimensions and characteristics —

Part 2: Extruded sheets

1 Scope

This part of ISO 7823 specifies requirements for flat poly(methyl methacrylate) (PMMA) sheets extruded from colourless or coloured, transparent, translucent or opaque materials as defined in 3.1.

The thickness range of the sheets covered by this part of ISO 7823 is 1,5 mm to 20 mm.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

- ISO 62:1999, *Plastics — Determination of water absorption*
- ISO 75-1:—¹⁾, *Plastics — Determination of temperature of deflection under load — Part 1: General test method*
- ISO 75-2:—²⁾, *Plastics — Determination of temperature of deflection under load — Part 2: Plastics, ebonite and long-fibre-reinforced composites*
- ISO 178:2001, *Plastics — Determination of flexural properties*
- ISO 179-1:2000, *Plastics — Determination of Charpy impact properties — Part 1: Non-instrumented impact test*
- ISO 291:1997, *Plastics — Standard atmospheres for conditioning and testing*
- ISO 306:—³⁾, *Plastics — Thermoplastic materials — Determination of Vicat softening temperature (VST)*
- ISO 489:1999, *Plastics — Determination of refractive index*
- ISO 527-1:1993, *Plastics — Determination of tensile properties — Part 1: General principles*

1) To be published. (Revision of ISO 75-1:1993)

2) To be published. (Revision of ISO 75-2:1993)

3) To be published. (Revision of ISO 306:1994)

ISO 7823-2:2003(E)

ISO 527-2:1993, *Plastics — Determination of tensile properties — Part 2: Test conditions for moulding and extrusion plastics*

ISO 877:1994, *Plastics — Methods of exposure to direct weathering, to weathering using glass-filtered daylight, and to intensified weathering by daylight using Fresnel mirrors*

ISO 1133:—⁴⁾, *Plastics — Determination of the melt mass-flow rate (MFR) and the melt volume-flow rate (MVR) of thermoplastics*

ISO 1183-1:—⁵⁾, *Plastics — Methods for determining the density of non-cellular plastics — Part 1: Immersion method, liquid pycnometer method and titration method*

ISO 1183-2:—⁵⁾, *Plastics — Methods for determining the density of non-cellular plastics — Part 2: Density gradient column method*

ISO 1628-6:1990, *Plastics — Determination of viscosity number and limiting viscosity number — Part 6: Methyl methacrylate polymers*

ISO 2039-2:1987, *Plastics — Determination of hardness — Part 2: Rockwell hardness*

ISO 2818:1994, *Plastics — Preparation of test specimens by machining*

ISO 2859-1:1999, *Sampling procedures for inspection by attributes — Part 1: Sampling schemes indexed by acceptance quality limit (AQL) for lot-by-lot inspection*

ISO 4582:1998, *Plastics — Determination of changes in colour and variations in properties after exposure to daylight under glass, natural weathering or laboratory light sources*

ISO 4892-2:1994, *Plastics — Methods of exposure to laboratory light sources — Part 2: Xenon-arc sources*

ISO 4892-4:1994, *Plastics — Methods of exposure to laboratory light sources — Part 4: Open-flame carbon-arc lamps*

ISO 8257-1:1998, *Plastics — Poly(methyl methacrylate) (PMMA) moulding and extrusion materials — Part 1: Designation system and basis for specifications*

ISO 11359-2:1999, *Plastics — Thermomechanical analysis (TMA) — Part 2: Determination of coefficient of linear thermal expansion and glass transition temperature*

ISO 13468-1:1996, *Plastics — Determination of the total luminous transmittance of transparent materials — Part 1: Single-beam instrument*

ISO 14782:1999, *Plastics — Determination of haze for transparent materials*

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1 homopolymers and copolymers of methyl methacrylate (MMA)
PMMA homopolymers and copolymers of MMA containing at least a mass fraction of 80 % of MMA and not more than a mass fraction of 20 % of acrylic ester or other suitable monomers

4) To be published. (Revision of ISO 1133:1997)

5) To be published. (Revision in parts of ISO 1183:1987)

NOTE 1 They may include both unmodified materials and materials containing lubricants, processing aids, UV absorbers, pigments and colorants. They do not include PMMA modified with elastomers (see ISO 8257-1).

NOTE 2 The use of additives will be governed by national environmental legislation and regulations.

3.2

flat PMMA sheets

sheets with two plane, substantially parallel surfaces

4 General requirements

4.1 Protective coverings

Unless otherwise agreed upon by the interested parties, the surfaces of the sheet, as delivered, shall be protected by suitable materials, for example kraft paper secured with a water-soluble or pressure-sensitive adhesive, or a polyethylene film, which are readily removable without causing surface contamination or damage.

4.2 Appearance

4.2.1 Surface defects

The sheet shall have a smooth surface. There shall be no scratches, marks or other surface defects larger than 4 mm² each anywhere in the sheet.

4.2.2 Inclusion defects

There shall be no bubbles, foreign-matter inclusions, cracks or other defects that could adversely affect the performance of the sheet in its intended application. In the case of inclusions, there shall also be none which are larger than 2 mm² each anywhere in the sheet.

4.2.3 Classification of defects

The area of any defect found in the sheets shall be classified as specified in Table 1. Each defect shall be considered separately.

Table 1 — Classification of defects

Classification	Area of surface defect	Area of inclusion defect
Negligible	Less than 2 mm ²	Less than 1 mm ²
Acceptable	2 mm ² to 4 mm ²	1 mm ² to 2 mm ²

4.2.4 Distribution of defects

4.2.4.1 There shall not be a significant number (for the application) of small defects, each of which is defined as negligible in Table 1, within 1 m² anywhere in the sheet. What constitutes a significant number shall be agreed between the interested parties.

4.2.4.2 No defect defined as acceptable in Table 1 shall be within 500 mm of another acceptable defect anywhere in or on the sheet.

4.3 Colour

The colour distribution shall be homogeneous, unless otherwise specified. Variations in colour shall be agreed upon between the interested parties.

4.4 Dimensions

4.4.1 Length and width

The length and width of the sheet shall be agreed upon between the interested parties. For cut sheets, the tolerances for each sheet shall be as specified in Table 2.

Table 2 — Tolerances on length and width of cut sheets

Length or width mm	Tolerance mm
Up to 1 000	+3 0
From 1 001 to 2 000	+6 0
From 2 001 to 3 000	+9 0
3 001 and over	+0,3 % 0

4.4.2 Thickness

The thickness tolerance for sheets in the range from 1,5 mm to less than 3 mm shall be ± 10 %; for sheets from 3 mm to 20 mm thick, it shall be ± 5 %.

The tolerances apply within each sheet and from sheet to sheet.

4.4.3 Deviation of shape from rectangular

The difference Δl between the lengths of the two diagonals of the rectangular sheet, expressed in millimetres, shall be less than $3,5 \times 10^{-3} \times b$ (where b is the width, in millimetres, of the sheet, measured perpendicular to the direction of extrusion) down to a lower limit of 2 mm (i.e. with shorter widths, the difference Δl does not have to be less than 2 mm).

4.4.4 Conditions of measurement

Measurements of dimensions shall be made at room temperature, except that, in cases of dispute, measurements shall be made under standard conditions, as specified in ISO 291. For measurements made under ambient conditions, due allowance shall be made for dimensional changes due to the differences in temperature and relative humidity between test locations.

4.5 Basic and other properties

4.5.1 Basic properties

The basic mechanical, thermal and optical properties of sheets shall be as specified in Table 3.

4.5.2 Other properties

Other properties of sheets shall be agreed upon between the interested parties. Examples of, and test methods for, such properties are presented in Table 4.

Table 3 — Basic properties of PMMA extruded sheets — Required values

Property	Unit	Test method	Required value	Subclause
Tensile strength	MPa	ISO 527-2/1B/5	min. 60	5.5.2
Tensile strain	%	ISO 527-2/1B/5	min. 2	5.5.2
Modulus of elasticity in tension	MPa	ISO 527-2/1B/1	min. 2 900	5.5.2
Charpy impact strength (unnotched)	kJ/m ²	ISO 179-1/1fU	min. 8	5.5.3
Vicat softening temperature	°C	ISO 306:—, method B50	min. 88	5.6.1
Dimensional change on heating (shrinkage):				
Thickness, t (mm)				
$1,5 \leq t < 2$	%	Annex B	max. 15	5.6.3
$2 \leq t < 3$	%	Annex B	max. 12	5.6.3
$3 \leq t \leq 20$	%	Annex B	max. 7	5.6.3
Total luminous transmittance: ^a				
Thickness, t (mm)				
$t < 12$	%	ISO 13468-1	min. 91	5.8.1
$12 \leq t < 20$	%	ISO 13468-1	min. 90	5.8.1
Light transmittance at 420 nm (thickness 3 mm) ^a				
— before exposure to xenon lamp	%	Annex A	min. 90	5.8.3
— after exposure to xenon lamp for 1 000 h (ISO 4892-2:1994, method A)	%	Annex A	min. 88	5.8.3

^a For transparent, colourless material.

ISO 7823-2:2003

<https://standards.iteh.ai/catalog/standards/sist/1faa389a-6ef7-4b9f-8848-17aa6b51bce/iso-7823-2-2003>

Table 4 — Other properties of PMMA extruded sheets — Typical values

Property	Unit	Test method	Typical value	Subclause
Flexural strength	MPa	ISO 178	100 to 115	5.5.1
Rockwell hardness		ISO 2039-2	90 to 95	5.5.4
Linear expansion coefficient	K ⁻¹	ISO 11359-2	7×10^{-5}	5.6.4
Temperature of deflection under load	°C	ISO 75-2/A	80 to 101	5.6.2
Melt mass-flow rate	g/10 min	ISO 1133:— (230 °C/3,8 kg)	0,5 to 3,0	5.9.5
Viscosity number	ml/g	ISO 1628-6	55 to 88	5.9.4
Haze ^a	%	ISO 14782	0,5 to 2	5.8.2
Refractive index, n_D^{23}		ISO 489:1999, method A	1,49	5.8.4
Density ^{a, b}	g/cm ³	ISO 1183-1:—, method A or C, or ISO 1183-2	1,19	5.9.1
Water absorption	%	ISO 62:1999, method 1 (24 h, 23 °C)	0,5 ^c	5.9.2

^a For transparent, colourless material.
^b Coloured sheets may have a higher value.
^c Value reported refers to a square specimen of edge 50 mm and thickness 3 mm.