



SLOVENSKI STANDARD SIST EN ISO 10426-1:2010

01-februar-2010

Nadomešča:

SIST EN ISO 10426-1:2007

Industrija za predelavo nafte in zemeljskega plina - Cementi in materiali za cementiranje vrtin - 1. del: Specifikacija (ISO 10426-1:2009)

Petroleum and natural gas industries - Cements and materials for well cementing - Part 1: Specification (ISO 10426-1:2009)

Erdöl- und Erdgasindustrie - Zemente und Materialien für die Zementation von Tieflochbohrungen - Teil 1: Anforderungen (ISO 10426-1:2009)

Industries du pétrole et du gaz naturel - Ciments et matériaux pour la cimentation des puits - Partie 1: Spécifications (ISO 10426-1:2009)

Ta slovenski standard je istoveten z: EN ISO 10426-1:2009

ICS:

75.180.10	Oprema za raziskovanje in odkopavanje	Exploratory and extraction equipment
91.100.10	Cement. Mavec. Apno. Malta	Cement. Gypsum. Lime. Mortar

SIST EN ISO 10426-1:2010

en,fr

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 10426-1:2010

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010>

EUROPEAN STANDARD
NORME EUROPÉENNE
EUROPÄISCHE NORM

EN ISO 10426-1

December 2009

ICS 91.100.10; 75.020

Supersedes EN ISO 10426-1:2006

English Version

Petroleum and natural gas industries - Cements and materials for well cementing - Part 1: Specification (ISO 10426-1:2009)

Industries du pétrole et du gaz naturel - Ciments et
matériaux pour la cimentation des puits - Partie 1:
Spécification (ISO 10426-1:2009)

Erdöl- und Erdgasindustrie - Zemente und Materialien für
die Zementation von Tieflochbohrungen - Teil 1:
Anforderungen (ISO 10426-1:2009)

This European Standard was approved by CEN on 14 December 2009.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN ISO 10426-1:2010](https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ff8f99b80/sist-en-iso-10426-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ff8f99b80/sist-en-iso-10426-1-2010>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents

Page

Foreword.....3

**iTeh STANDARD PREVIEW
(standards.iteh.ai)**

SIST EN ISO 10426-1:2010

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010>

Foreword

This document (EN ISO 10426-1:2009) has been prepared by Technical Committee ISO/TC 67 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" in collaboration with Technical Committee CEN/TC 12 "Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries" the secretariat of which is held by AFNOR.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by June 2010, and conflicting national standards shall be withdrawn at the latest by June 2010.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document supersedes EN ISO 10426-1:2006.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and the United Kingdom.

ITEH STANDARD PREVIEW
(standards.iteh.ai)
Endorsement notice

The text of ISO 10426-1:2009 has been approved by CEN as a EN ISO 10426-1:2009 without any modification.

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ff8f99b80/sist-en-iso-10426-1-2010>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 10426-1:2010

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010>

INTERNATIONAL
STANDARD

ISO
10426-1

Third edition
2009-12-15

**Petroleum and natural gas industries —
Cements and materials for well
cementing —**

**Part 1:
Specification**

iTeh STANDARD PREVIEW
*Industries du pétrole et du gaz naturel — Ciments et matériaux pour la
cimentation des puits —
(standards.iteh.ai)
Partie 1. Spécification*

SIST EN ISO 10426-1:2010

[https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-
b12d-58ff8f99b80/sist-en-iso-10426-1-2010](https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ff8f99b80/sist-en-iso-10426-1-2010)



Reference number
ISO 10426-1:2009(E)

© ISO 2009

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

SIST EN ISO 10426-1:2010

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010>

**COPYRIGHT PROTECTED DOCUMENT**

© ISO 2009

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office
Case postale 56 • CH-1211 Geneva 20
Tel. + 41 22 749 01 11
Fax + 41 22 749 09 47
E-mail copyright@iso.org
Web www.iso.org

Published in Switzerland

Contents

Page

Foreword	iv
Introduction.....	v
1 Scope	1
2 Normative references	1
3 Terms and definitions	2
4 Requirements.....	3
4.1 Specification, chemical and physical requirements.....	3
4.2 Sampling frequency, timing of tests, and equipment.....	7
5 Sampling procedure	8
6 Fineness tests.....	8
6.1 Procedure	8
6.2 Requirements.....	8
7 Preparation of slurry for free fluid, compressive strength and thickening time tests	8
7.1 Apparatus	8
7.2 Procedure.....	11
8 Free-fluid test (formerly free water)	11
8.1 Apparatus	11
8.2 Calibration	16
8.3 Procedure	17
8.4 Calculation of percent free fluid	17
8.5 Acceptance requirements.....	18
9 Compressive strength tests	18
9.1 Apparatus	18
9.2 Procedure	19
9.3 Test procedure (after ASTM C109/C109M).....	21
9.4 Compressive strength acceptance criteria.....	21
10 Thickening-time tests.....	22
10.1 Apparatus	22
10.2 Calibration.....	28
10.3 Procedure	31
10.4 Thickening time and consistency.....	33
10.5 Specification acceptance requirements.....	33
11 Marking	33
12 Packing	34
13 Bentonite	34
Annex A (informative) Calibration procedures for thermocouples, temperature measuring systems, and controllers	35
Bibliography.....	38

ISO 10426-1:2009(E)

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 2.

The main task of technical committees is to prepare International Standards. Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

ISO 10426-1 was prepared by Technical Committee ISO/TC 67, *Materials, equipment and offshore structures for petroleum, petrochemical and natural gas industries*, Subcommittee SC 3, *Drilling and completion fluids, and well cements*.

This third edition cancels and replaces the second edition (ISO 10426-1:2005), which has been technically revised.

ISO 10426 consists of the following parts, under the general title *Petroleum and natural gas industries — Cements and materials for well cementing*:

- *Part 1: Specification*
- *Part 2: Testing of well cements*
- *Part 3: Testing of deepwater well cement formulations*
- *Part 4: Preparation and testing of foamed cement slurries at atmospheric pressure*
- *Part 5: Determination of shrinkage and expansion of well cement formulations at atmospheric pressure*
- *Part 6: Methods for determining the static gel strength of cement formulations*

Introduction

This part of ISO 10426 is based on ISO 10426-1:2005 with the intent that the 24th edition of API Spec 10A will be identical to this part of ISO 10426.

It is necessary that users of this part of ISO 10426 be aware that further or differing requirements can be required for individual applications. This part of ISO 10426 is not intended to inhibit a vendor from offering, or the purchaser from accepting, alternative equipment or engineering solutions for the individual application. This can be particularly applicable where there is innovative or developing technology. Where an alternative is offered, it is the responsibility of the vendor to identify any variations from this part of ISO 10426 and provide details.

In this part of ISO 10426, where practical, US Customary (USC) or other units are included in brackets for information. The units do not necessarily represent a direct conversion of SI to USC units, or USC to SI. Consideration has been given to the precision of the instrument making the measurement. For example, thermometers are typically marked in 1° increments, thus temperature values have been rounded to the nearest degree.

In this part of ISO 10426, calibrating an instrument refers to assuring the accuracy of the measurement. Accuracy is the degree of conformity of a measurement of a quantity to its actual or true value. Accuracy is related to precision, or reproducibility, of a measurement. Precision is the degree to which further measurements or calculations will show the same or similar results. Precision is characterized in terms of the standard deviation of the measurement. The results of calculations or a measurement can be accurate, but not precise, precise but not accurate, neither or both. A result is valid if it is both accurate and precise.

[SIST EN ISO 10426-1:2010](https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010)

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010>

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN ISO 10426-1:2010

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ffc8f99b80/sist-en-iso-10426-1-2010>

Petroleum and natural gas industries — Cements and materials for well cementing —

Part 1: Specification

1 Scope

This part of ISO 10426 specifies requirements and gives recommendations for six classes of well cements, including their chemical and physical requirements and procedures for physical testing.

This part of ISO 10426 is applicable to well cement classes A, B, C and D, which are the products obtained by grinding Portland cement clinker and, if needed, calcium sulfate as an interground additive. Processing additives can be used in the manufacture of cement of these classes. Suitable set-modifying agents can be interground or blended during manufacture of class D cement.

This part of ISO 10426 is also applicable to well cement classes G and H, which are the products obtained by grinding clinker with no additives other than one or more forms of calcium sulfate, water or chemical additives as required for chromium (VI) reduction.

SIST EN ISO 10426-1:2010

2 Normative references

<https://standards.iteh.ai/catalog/standards/sist/b4928d0b-bbd7-4737-b12d-58ff8f99b80/sist-en-iso-10426-1-2010>

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

ISO 3310-1, *Test sieves — Technical requirements and testing — Part 1: Test sieves of metal wire cloth*

ISO 13500, *Petroleum and natural gas industries — Drilling fluid materials — Specifications and tests*

ISO 24450, *Laboratory glassware — Wide-necked boiling flasks*

ASTM C109/C109M, *Standard Test Method for Compressive Strength of Hydraulic Cement Mortars (Using 2-in or [50-mm] Cube Specimens)*

ASTM C115, *Standard Test Method for Fineness of Portland Cement by the Turbidimeter*

ASTM C465, *Standard Specification for Processing Additions for Use in the Manufacture of Hydraulic Cements*

ASTM E1404-94(2008), *Standard Specification for Laboratory Glass Conical Flasks*

EN 196-1, *Methods of testing cement — Part 1: Determination of strength*

EN 196-2, *Methods of testing cement — Part 2: Chemical analysis of cement*

EN 196-6, *Methods of testing cement — Part 6: Determination of fineness*

EN 196-7, *Methods of testing cement — Part 7: Methods of taking and preparing samples of cement*

ISO 10426-1:2009(E)

3 Terms and definitions

For the purposes of this document, the following terms and definitions apply.

3.1

additive

material added to a cement slurry to modify or enhance some desired property

NOTE Properties that are commonly modified include setting time (by use of retarders or accelerators), fluid loss, viscosity, etc.

3.2

atmospheric pressure consistometer

device used for stirring and conditioning the cement slurry

NOTE The device is not intended to measure thickening time.

3.3

Bearden unit of consistency

B_c
measure of the consistency of a cement slurry when determined on a pressurized consistometer

3.4

cement

Portland cement

ground clinker generally consisting of hydraulic calcium silicates and aluminates and usually containing one or more forms of calcium sulfate as an interground additive

3.5

cement class

designation achieved under the ISO system for classification of well cement according to its intended use

3.6

cement grade

designation achieved under the ISO system for denoting the sulfate resistance of a particular cement

3.7

cement blend

mixture of dry cement and other dry materials

3.8

clinker

fused materials produced in the kiln during cement manufacturing that are interground with calcium sulfate to make cement

3.9

compressive strength

force per unit area required to cause a set cement sample to fail under compression

3.10

consistometer

device used to measure the thickening time of a cement slurry under temperature and under pressure

3.11

filtrate

liquid that is forced out of a cement slurry during a fluid loss test

3.12**free fluid**

coloured or colourless liquid that separates from a cement slurry under static conditions

3.13**slurry container****slurry cup**

container in an atmospheric or pressurized consistometer used to hold the slurry for conditioning purposes or for the thickening-time test

3.14**thickening time**

time after which the consistency of a cement slurry has become so high that the slurry is considered unpumpable

NOTE The results of a thickening-time test provide an indication of the length of time a cement slurry remains pumpable under the test conditions.

4 Requirements**4.1 Specification, chemical and physical requirements****4.1.1 Classes and grades****4.1.1.1 General**

Well cement shall be specified using classes A, B, C, D, G and H and the grades: ordinary (O), moderate sulfate-resistant (MSR) and high sulfate-resistant (HSR).

A well cement that has been manufactured and supplied in accordance with this part of ISO 10426 may be mixed and placed in the field using water ratios or additives at the user's discretion. It is not intended that manufacturing compliance with this part of ISO 10426 be based on such field conditions.

Processing additives, set modifying agents or chemical additives used to reduce chromium (VI) shall not prevent a well cement from performing its intended functions.

4.1.1.2 Class A

This product is obtained by grinding clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of class A cement, provided that such materials in the amounts used have been shown to meet the requirements of ASTM C465.

This product is intended for use when special properties are not required and is available only in O grade, similar to ASTM C150, type I.

4.1.1.3 Class B

This product is obtained by grinding clinker, consisting essentially of hydraulic calcium silicates, usually containing one or more forms of calcium sulfate as an interground additive. At the option of the manufacturer, processing additives may be used in the manufacture of class B cement, provided that such materials in the amounts used have been shown to meet the requirements of ASTM C465.

This product is intended for use when conditions require moderate or high sulfate resistance and is available in both MSR and HSR grades, similar to ASTM C150, type II.