



INTERNATIONAL STANDARD ISO 2505-2:1994
TECHNICAL CORRIGENDUM 1

Published 1997-05-15

INTERNATIONAL ORGANIZATION FOR STANDARDIZATION • МЕЖДУНАРОДНАЯ ОРГАНИЗАЦИЯ ПО СТАНДАРТИЗАЦИИ • ORGANISATION INTERNATIONALE DE NORMALISATION

Thermoplastics pipes — Longitudinal reversion —

Part 2: Determination parameters

TECHNICAL CORRIGENDUM 1

Tubes en matières thermoplastiques — Retrait longitudinal à chaud —

Partie 2: Paramètres de détermination

RECTIFICATIF TECHNIQUE 1

iTeh STANDARD PREVIEW
(standards.iteh.ai)

ISO 2505-2:1994/Cor 1:1997

Technical Corrigendum 1 to International Standard ISO 2505-2:1994 was prepared by Technical Committee ISO/TC 138, *Plastics pipes, fittings and valves for the transport of fluids*, Subcommittee SC 5, *General properties of pipes, fittings and valves of plastic materials and their accessories — Test methods and basic specifications*.

Page 3

Table 2

In the “Oven temperature” column, for PVC-C, replace “170 ± 2” by “150 ± 2”.

In the “Duration of exposure in oven” column, for PVC-C, replace “30” by:

“60 for $e \leq 8$

120 for $8 < e \leq 16$ ”.

ICS 23.040.20

Ref. No. ISO 2505-2:1994/Cor.1:1997(E)

Descriptors: pipes (tubes), thermoplastic resins, plastic tubes, tests, dimensional stability tests, high temperature tests, determination, shrinkage.

© ISO 1997

Printed in Switzerland

iTeh STANDARD PREVIEW
This page intentionally left blank
(standards.iteh.ai)

[ISO 2505-2:1994/Cor 1:1997](https://standards.iteh.ai/catalog/standards/sist/318c47b6-885f-481e-8d9e-9a3806bbc020/iso-2505-2-1994-cor-1-1997)

<https://standards.iteh.ai/catalog/standards/sist/318c47b6-885f-481e-8d9e-9a3806bbc020/iso-2505-2-1994-cor-1-1997>