



SLOVENSKI STANDARD

SIST EN 15407:2011

01-maj-2011

Nadomešča:

SIST-TS CEN/TS 15407:2007

Trdna alternativna goriva - Metode za določevanje ogljika (C), vodika (H) in dušika (N)

Solid recovered fuels - Methods for the determination of carbon (C), hydrogen (H) and nitrogen (N) content

Feste Sekundärbrennstoffe - Verfahren zur Bestimmung des Gehaltes an Kohlenstoff (C), Wasserstoff (H) und Stickstoff (N)

Combustibles solides de récupération - Méthodes pour la détermination de la teneur en carbone (C), en hydrogène (H) et en azote (N)

Ta slovenski standard je istoveten z: EN 15407:2011

ICS:

75.160.10 Trda goriva Solid fuels

SIST EN 15407:2011 en,de

iTeh STANDARD PREVIEW
(standards.iteh.ai)

SIST EN 15407:2011

<https://standards.iteh.ai/catalog/standards/sist/0b350642-64a9-4215-aa6b-3eb9e2e29dec/sist-en-15407-2011>

EUROPEAN STANDARD

EN 15407

NORME EUROPÉENNE

EUROPÄISCHE NORM

March 2011

ICS 75.160.10

Supersedes CEN/TS 15407:2006

English Version

Solid recovered fuels - Methods for the determination of carbon (C), hydrogen (H) and nitrogen (N) content

Combustibles solides de récupération - Méthodes pour la détermination de la teneur en carbone (C), en hydrogène (H) et en azote (N)

Feste Sekundärbrennstoffe - Verfahren zur Bestimmung des Gehaltes an Kohlenstoff (C), Wasserstoff (H) und Stickstoff (N)

This European Standard was approved by CEN on 22 January 2011.

CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for giving this European Standard the status of a national standard without any alteration. Up-to-date lists and bibliographical references concerning such national standards may be obtained on application to the CEN-CENELEC Management Centre or to any CEN member.

This European Standard exists in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN-CENELEC Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 15407:2011](https://standards.iteh.ai/catalog/standards/sist/0350642-64a9-4215-aa6b-3eb9e2e29dec/sist-en-15407-2011)

<https://standards.iteh.ai/catalog/standards/sist/0350642-64a9-4215-aa6b-3eb9e2e29dec/sist-en-15407-2011>



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: Avenue Marnix 17, B-1000 Brussels

Contents	Page
Foreword.....	3
Introduction	4
1 Scope	4
2 Normative references	4
3 Terms and definitions	4
4 Safety remarks	4
5 Principle	5
6 Reagents and calibration standards	5
7 Apparatus	5
8 Procedure	6
9 Expression of results	7
10 Performance characteristics	7
11 Test report	7
Annex A (normative) Guidelines - Characteristics of the laboratory sample for chemical analysis of SRF	9
Annex B (informative) Data on performance characteristics	11
Annex C (informative) Major results of ruggedness testing	13
Bibliography	14

Foreword

This document (EN 15407:2011) has been prepared by Technical Committee CEN/TC 343 “Solid recovered fuels”, the secretariat of which is held by SFS.

This European Standard shall be given the status of a national standard, either by publication of an identical text or by endorsement, at the latest by September 2011, and conflicting national standards shall be withdrawn at the latest by September 2011.

This document supersedes CEN/TS 15407:2006.

Attention is drawn to the possibility that some of the elements of this document may be the subject of patent rights. CEN [and/or CENELEC] shall not be held responsible for identifying any or all such patent rights.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association.

This document differs from CEN/TS 15407:2006 only editorially.

According to the CEN/CENELEC Internal Regulations, the national standards organizations of the following countries are bound to implement this European Standard: Austria, Belgium, Bulgaria, Croatia, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

[SIST EN 15407:2011](https://standards.iteh.ai/catalog/standards/sist/0B50642-64a9-4215-aa6b-3eb9e2e29dec/sist-en-15407-2011)

<https://standards.iteh.ai/catalog/standards/sist/0B50642-64a9-4215-aa6b-3eb9e2e29dec/sist-en-15407-2011>

Introduction

The determination of carbon, hydrogen and nitrogen is usually performed using instrumental methods. The latter can be divided in two groups depending on the amount of test portion used. Micro instrumental methods require few mg of sample; macro methods use grams of sample. If micro methods are used for SRF analysis, a very homogeneous test sample needs to be prepared in order to obtain the required precision.

1 Scope

This European Standard specifies a method for the determination of total carbon, hydrogen and nitrogen contents in solid recovered fuels by instrumental techniques.

This method is applicable for concentrations on dry matter basis of C over 0,1 %, N over 0,01 % and H over 0,1 %.

2 Normative references

The following referenced documents are indispensable for the application of this document. For dated references, only the edition cited applies. For undated references, the latest edition of the referenced document (including any amendments) applies.

EN 15357:2011, *Solid recovered fuels — Terminology, definitions and descriptions*

[SIST EN 15407:2011](#)

EN 15413¹⁾, *Solid recovered fuels — Methods for the preparation of the test sample from the laboratory sample*

[3eb9e2e29dec/sist-en-15407-2011](#)

EN 15414-3, *Solid recovered fuels — Determination of moisture content using the oven dry method — Part 3: Moisture in general analysis sample*

3 Terms and definitions

For the purposes of this document, the terms and definitions given in EN 15357:2011 apply.

4 Safety remarks

The safety in handling of potentially hazardous materials is dealt with relevant national and European regulations, which every laboratory should refer to.

In addition the following information is given:

- only experienced personnel, following the safety instructions of the manufacturer, shall use instruments for carbon, hydrogen and nitrogen determination.

¹⁾ To be published.

5 Principle

The method is based on the complete oxidation of the sample ("flash combustion" instruments can also be used) which converts all organic substances into combustion products. The resulting combustion gases pass through a reduction furnace and are swept into the chromatographic column by the carrier gas (helium) where they are separated and detected quantitatively by appropriate instrumental gas analysis procedures (for example by a thermal conductivity detector (TCD)). The samples are held in a suitable container (tin or other crucible) and then dropped inside the quartz tube furnace at about 1 000 °C in an oxygen stream for complete oxidation in the presence of a catalyst layer. Excess oxygen is removed by contact with copper, while nitrogen oxides are reduced to elemental nitrogen.

6 Reagents and calibration standards

All reagents shall be at least of analytical grade and suitable for their specific purposes.

- 6.1 Carrier gas:** Helium, 99,99 % or other gases as specified by the instrument manufacturer.
- 6.2 Oxygen,** free of combustion material, purity 99,95 %, or as specified by the instrument manufacturer.
- 6.3 Additional reagents:** as specified by the instrument manufacturer.
- 6.4 Calibration standards**

Examples are given in Table 1.

Table 1 — Calibration standards
(standards.iten.ai)

Name	Formula	C %	H %	N %
Acetanilide	C ₈ H ₉ NO	71,1	6,7	10,4
Atropine	C ₁₇ H ₂₃ NO ₃	70,6	8,0	4,8
Benzoic acid	C ₇ H ₆ O ₂	68,8	5,0	0,0
Cystine	C ₆ H ₁₂ N ₂ O ₄ S ₂	30,0	5,0	11,7
Diphenylamine	C ₁₂ H ₁₁ N	85,2	6,5	8,3
EDTA	C ₁₀ H ₁₆ N ₂ O ₈	41,1	5,5	9,6
Phenylalanine	C ₉ H ₁₁ NO ₂	65,4	6,7	8,5
Sulfanil amide	C ₆ H ₈ N ₂ O ₂ S	41,8	4,7	16,3
Sulfanilic acid	C ₆ H ₇ NO ₃ S	41,6	4,1	8,1
TRIS	C ₄ H ₁₁ NO ₃	39,7	9,1	11,6

7 Apparatus

Various instrumental configurations are available. The general requirements for a suitable apparatus are:

- the combustion conditions shall be such that all carbon, hydrogen and nitrogen are converted to carbon dioxide, water vapour and nitrogen oxide or elemental nitrogen;
- a separation step is included to reduce or eliminate any possible interference during the subsequent determination;

EN 15407:2011 (E)

- c) nitrogen shall be reduced to the elemental form before the detection;
- d) analytical balance, resolution of at least 1 part per thousand of the weighted amount.

8 Procedure**8.1 Sample conservation and pre-treatment**

The laboratory samples shall be stored according to guidelines defined in Annex A.

8.2 Sample preparation

The test portion shall be prepared from the laboratory sample according to EN 15413.

The amount of test portion depends on the particular instrument used. The particle size of the test sample should be related to the amount of sample to be used, according to EN 15413.

For some types of instruments it is necessary to carry out the determination of hydrogen on dried analysis samples. For some other types of instruments it is necessary to carry out the determination of carbon on analysis samples that are not completely dried. Working with samples that has been dried at 105 °C and then equilibrated with the moisture in the air on the lab where the CHN analysis are handled, is a good compromise for the C and H moisture artefact, but then extra moisture determinations on the air-dry sample will have to be done.

The nominal top size of the test sample shall be 1 mm or less. For some instruments it may be necessary to prepare a test sample with a lower nominal top size than 1 mm, e.g. 0,25 mm, in order to keep the desired precision. For "new products" an adequate particle size shall be determined by validation experiments.

Whereas the determination is carried out on dry basis, the moisture content shall be determined according to EN 15414-3.

<https://standards.itech.ai/catalog/standards/sist/0b350642-64a9-4215-aa6b-3eb9e2e29dec/sist-en-15407-2011>

8.3 Preparation of the test portion

Weigh the appropriate amount of material as recommended by the instrument manufacturer as appropriate for the type of instrument and the expected content of carbon, hydrogen and nitrogen.

The test portion shall be weighed directly into the sample capsule in the case of a micro- or semi-micro analyser. Otherwise it may be weighed directly or transferred from a suitable weighing container.

8.4 Calibration

Set up the instrument following the manufacturer instructions.

Stabilize the furnace and analyzer.

Select 3 to 5 reference materials with increasing concentration of nitrogen, hydrogen and carbon. Calibrate the instruments for nitrogen, hydrogen and carbon determination following the manufacturer instructions. Use the same procedure as for sample analysis (see below). Alternatively different amounts of the same substance may be used to prepare the calibration.

Verify the calibration by analysing as a test sample a portion of a suitable standard, preferably with a different material than that used for the calibration.

The calibration is acceptable if the measured value differs from the standard value by no more than the repeatability limit for the test method. Otherwise repeat the calibration procedure.

8.5 Analysis of samples

Weight the test portion and transfer it into the instrumental apparatus. Start the cycle following then operating instruction for the specific instruments. At least 3 replicates are necessary.

9 Expression of results

The total carbon, hydrogen and nitrogen contents of the solid recovered fuels shall be expressed as a percentage by mass on the dry basis. Most commercially available instruments give the results directly.

The following equations shall be used:

for the carbon content:

$$C_d = C_{ad} \times \frac{100}{100 - M_{ad}} \quad (1)$$

for the nitrogen content:

$$N_d = N_{ad} \times \frac{100}{100 - M_{ad}} \quad (2)$$

for the hydrogen content:

$$H_d = H_{ad} - \frac{M_{ad}}{8,937} \times \frac{100}{100 - M_{ad}} \quad (3)$$

where

d is dry basis;

ad is as determined;

M_{ad} is the moisture content of the general analysis sample when analysed.

10 Performance characteristics

Data on performance characteristics of the present method are given in Annex B which presents the results of the QUOVADIS validation project (Quality Management, Organisation, Validation of standards, Developments and Inquiries for SRF) [9].

11 Test report

The test report shall contain at least the following information:

- a) name, address and location of any laboratory involved in the analysis;
- b) description and identification of the laboratory sample;