



Designation: D 6100 – 03

Standard Specification for Extruded, Compression Molded and Injection Molded Acetal Shapes (POM)¹

This standard is issued under the fixed designation D 6100; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon (ϵ) indicates an editorial change since the last revision or reapproval.

INTRODUCTION

This specification is intended to be a means of calling out plastic product used in the fabrication of end items or parts.

1. Scope*

1.1 This specification covers requirements and test methods for the material, dimensions, and workmanship, and the properties of extruded, compression molded and injection molded acetal sheet, plate, rod, and tubular bar manufactured from acetal.

1.2 The properties included in this specification are those required for the compositions covered. Requirements necessary to identify particular characteristics important to specialized applications may be described by using the classification system given in Section 4.

1.3 This specification allows for the use of recycled plastics as defined in Guide D 5033.²

1.4 The values stated in inch-pound units are to be regarded as the standard in all property and dimensional tables. For reference purposes, SI units are included in Table S-POM and Table 1 only.

1.5 The following precautionary caveat pertains only to the test method portions, Section 11, of this specification: *This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.*

NOTE 1—There is no similar or equivalent ISO Standard.

2. Referenced Documents

2.1 ASTM Standards:

D 256 Test Methods for Determining the Izod Pendulum Impact Resistance of Plastics³

D 618 Practice for Conditioning Plastics for Testing³
D 638 Test Method for Tensile Properties of Plastics³
D 790 Test Methods for Flexural Properties of Unreinforced and Reinforced Plastics and Electrical Insulating Materials³
D 883 Terminology Relating to Plastics³
D 3892 Practice for Packaging/Packing of Plastics⁴
D 4000 Classification System for Specifying Plastic Materials⁴
D 5033 Guide for the Development of ASTM Standards Relating to Recycling and Use of Recycled Plastics⁵
D 6778 Classification System for Polyoxymethylene (POM), Acetal Molding and Extrusion Materials⁵
2.2 ANSI Standard:
Z1.4-1993 Sampling Procedures and Tables for Inspection by Attributes⁶

3. Terminology

3.1 Definitions:

3.1.1 *regrind (plastic), n*—a product or scrap such as sprues, runners and edge trim that have been reclaimed by shredding and granulating for use in-house.

3.1.2 For definitions of other technical terms pertaining to plastics used in this specification, see Terminology D 883 or Guide D 5033.

3.2 Definitions of Terms Specific to This Standard:

3.2.1 *centerline porosity, n*—microvoids which are visibly detectable with the unaided eye using the dye penetration procedure detailed in 7.4.1.

3.2.2 *low porosity, n*—product which either exhibits no white centerline or a white centerline but no dye remains when tested in accordance with section 7.4.1.

3.2.3 *plate, n*—flat stock greater than ¼ in.

¹ This specification is under the jurisdiction of ASTM Committee D20 on Plastics and is the direct responsibility of Subcommittee D20.20 on Plastic Products (Section D20.20.02).

Current edition approved July 10, 2003. Published September 2003. Originally approved in 1997. Last previous edition approved in 1997 as D 6100 - 97.

² As defined in Guide D 5033.

³ Annual Book of ASTM Standards, Vol 08.01.

⁴ Annual Book of ASTM Standards, Vol 08.02.

⁵ Annual Book of ASTM Standards, Vol 08.03.

⁶ Available from American National Standards Institute (ANSI), 25 W. 43rd St., 4th Floor, New York, NY 10036.

*A Summary of Changes section appears at the end of this standard.

3.2.4 *Porosity Level 1, n*—products containing microvoids with a pore size greater than 50 μm [0.002 in.] in which dye remains either in a broken or continuous line which does not exceed 4 % centerline porosity when tested in accordance with 7.4.1.

3.2.5 *recycled plastic shape, n*—a product made from up to 100 % recycled plastic.

3.2.6 *rod, n*—solid cylindrical shape with a minimum diameter of 1/8 in.

3.2.7 *sheet, n*—flat stock less than and including 1/4 in. [mm] thickness.

3.2.8 *tubular bar, n*—annular shapes with minimum inside diameter of 3/8 in. and minimum wall thickness of 1/16 in.

3.2.9 *virgin plastic shape, n*—product that is produced from 100 % plastic resin that has not been subjected to subsequent melt processing.

TABLE S-POM Requirements for Acetal (Polyoxymethylene) Shapes

Type	Description	Class	Description	Grade	Classification System D 6778 Resin Callout ^A	Description	Ultimate Tensile Strength min, psi [MPa]	Tensile Elongation % at break, mm	Tensile Modulus min, psi	Dimensional Stability %, max
01	Homopolymer	1	Unfilled	1	POM0111 ^B	General Purpose	9000 [62]	25	350 000	0.4
				2	POM0110B56540 ^B	General Purpose	9000 [62]	15	350 000	0.4
				0	As Specified	Recycle Grade	8000 [55]	25	275 000	0.4
		2	Lubricated	1	POM0110L20A21730 ^B	General purpose	6100 [42]	10	345 000	0.4
			Lubricated (PTFE filled)	2	POM0110L13 ^B	General Purpose	6800 [47]	10	340 000	0.4
02	Copolymer	1	Unfilled	1	POM0211 ^B	General Purpose	8000 [55]	25	350 000	0.4
				2	As Specified	Recycle Grade	7000 [48]	25	275 000	0.4
				0	As Specified	As Specified
00	Other Acetals	0	As Specified	1	As Specified	General Purpose
				2	As Specified	Recycle Grade
				3	As Specified	As Specified
				4	As Specified	As Specified
				5	As Specified	As Specified

^A Applicable Classification System D 6778 resin type to be specified on purchase order.

^B In accordance with Classification System D 6778.

4. Classification and Material

4.1 Product shape and size as defined in the applicable purchase order.

4.2 This specification covers product as listed in Table S-POM. Products included in the designations reference Classification System D 6778 callouts where applicable.

4.2.1 The type of acetal extruded, compression molded or injection molded product may be categorized by type, grade and class depending on resin and filler compositions as defined in Table S-POM.

4.3 Every type of acetal shape may be categorized into one of several grades as follows:

4.3.1 *Grade 1—General Purpose:*

4.3.1.1 Extruded, compression molded and injection molded product made using only 100 % virgin acetal resin.

4.3.1.2 Up to 20 % acetal regrind plastic developed during the internal processing steps, may be reused for sheet product.

4.3.2 *Grade 2—Recycle Grade:*

4.3.2.1 Extruded, compression molded or injection molded product made using any amount up to 100 % of recycled acetal plastic.

4.4 The type class and grade is further differentiated based on dimensional stability (elevated temperature excursion test), Table S-POM and dimensional requirements, Tables A and B.

4.4.1 When the level of centerline porosity needs to be documented it will be designated as either low porosity (LP) or P1 (Porosity Level 1) that is determined using the procedure detailed in 7.4 and will be added to the callout as a suffix (see Example 2 in 4.6.1.2).

4.5 *Property Tables:*

4.5.1 Table S-POM may be used to describe extruded, compression molded and injection molded products.

4.5.2 Table 1 may also be used to describe extruded, compression molded and injection molded products not included in Table S-POM via a cell callout which includes the applicable Table S-POM acetal type and specific properties (Designations 1 through 7).

4.5.3 To facilitate the incorporation of future or special materials not covered by Table S-POM, the “as specified” category (OO) for type, class and grade is shown on the table with the basic properties to be obtained from Table 1, as they apply.

4.5.4 *Reinforcements and Additive Materials*—A symbol (single-letter) will be used for the major reinforcement or combination, or both, along with two numbers that indicate the

TABLE A-1 Dimensional Requirements for Acetal Rod (Grade 1)

Size, in.	Diameter Tolerance, in.	Roundness TIR, in.	Camber, in./ft
1/8 to 7/8	+0.002/−0.001	0.002	2 1/2 /8
1	+0.005/−0	0.002	1 1/4 /8
1 1/8 to 1 1/4	+0.005/−0	0.004	1 1/4 /8
1 3/8 to 1 7/8	+0.005/−0	0.005	1 1/4 /8
2	+0.005/−0	0.010	1 1/4 /8
2 1/8 to 2 1/2	+0.030/−0	0.025	1 1/4 /8
2 5/8 to 6	+0.250/−0	0.050	1/8
Over 6	+0.250/−0	0.060	1/4 /4

percentage of addition by mass with the tolerances as tabulated below. This must be included in all Table 1 callouts (see Example 3 in 4.6.1.3).

Symbol	Material	Tolerance (Based on the Total Mass)
C	Carbon and graphite fiber	±2 %
G	Glass	±2 %
L	Lubricants (for example, PTFE, graphite, silicone and molybdenum disulfide)	by agreement between the supplier and the user
M	Mineral	±2 %
R	Combinations of reinforcements or fillers, or both	±3 % for the total reinforcement

4.6 Callout Designation—A one-line system shall be used to specify acetal materials covered by this specification. The system uses pre-defined cells to refer to specific aspects of this specification as illustrated below:

4.6.1 Description:

4.6.1.1 Example 1—Product made from general purpose acetal homopolymer:

CELL CALLOUT: S-POM0111

- S-POM01 = Product made from POM homopolymer in accordance with Table S-POM
- 1 = Unfilled class
- 1 = General purpose grade product

4.6.1.2 Example 2—Product made from general purpose acetal copolymer, low porosity:

CELL CALLOUT: S-POM0211,LP

- S-POM02 = Product made from POM copolymer in accordance with Table S-POM
- 1 = Unfilled class
- 1 = General purpose grade product
- LP = Low porosity material

4.6.1.3 Example 3—Product made from 20 % PTFE reinforced general purpose acetal homopolymer resin:

CELL CALLOUT: S-POM0121

- S-POM01 = Product made from POM homopolymer in accordance with Table S-POM
- 2 = Lubricated
- 1 = PTFE filled

4.6.2 The three examples illustrate how a one-line, alpha-numeric sequence can identify the product composition, commercial parameters and physical characteristics of extruded, compression molded and injection molded product. A space must be used as a separator between the specification number and the type designation. No separators are needed between type, class and grade. When special notes are to be included, such information should be preceded by a comma. Special tolerances must be noted at time of order and are inserted after the grade in parenthesis and preceded by a comma.

TABLE B-1 Dimensional Requirements for Acetal Sheets and Plates (Grades 1 and 2)^A

NOTE 1—*Squareness*—All sizes 1/8 in. max, gap when measured in accordance with 11.4.

Size, in.	Thickness Tolerances	Length Camber, in./ft	Width Bow, in./ft
1/16 to 3/16	±10 %	3/4 /4	3/16 /2
1/4 to 1	+0.025/-0	3/4 /4	3/16 /2

1 1/8 to 3	+0.050/-0	1/4 /4	1/16 /2
3 1/8 and over	+0.125/-0	1/4 /4	1/8 /2

^ACompression molded plate is supplied sufficiently oversize to finish to nominal dimension listed.

TABLE B-2 Dimensional Requirements for Acetal Compression Molded Plates (Grade 1)

Size in.	Thickness Tolerances	Length Camber, in./ft	Width Bow, in./ft
1/4	+0.090/-0	3/8 /4	0.090/2
5/16	+0.090/-0	3/8 /4	0.090/2
3/8	+0.090/-0	3/8 /4	0.090/2
7/16	+0.090/-0	3/8 /4	0.090/2
1/2	+0.090/-0	3/8 /4	0.090/2
5/8	+0.090/-0	3/8 /4	0.090/2
3/4	+0.090/-0	3/8 /4	0.090/2
7/8	+0.090/-0	3/8 /4	0.090/2
1	+0.090/-0	1/8 /4	0.050/2
1 1/8	+0.090/-0	1/8 /4	0.050/2
1 1/4	+0.090/-0	1/8 /4	0.050/2
1 3/8	+0.090/-0	1/8 /4	0.050/2
1 1/2	+0.090/-0	1/8 /4	0.050/2
1 5/8	+0.090/-0	1/8 /4	0.050/2
1 3/4	+0.090/-0	1/8 /4	0.050/2
1 7/8	+0.090/-0	1/8 /4	0.050/2
2	+0.090/-0	1/8 /4	0.050/2

5. Physical Property Requirements

5.1 The physical property values listed within this specification's tables are to be considered minimum specification values. Any requirement for specific test data for a given production lot should be specified at the time of order. Physical properties for products not yet included in Table S-POM may be specified using Table 1 for extruded, compression molded and injection molded products.

6. Dimensional Requirements

6.1 The type, class and grade is further differentiated based on dimensional stability (elevated temperature excursion test), Table S-POM, and dimensional requirements, Tables A and B. Products shall be produced within commercial tolerances and with the lowest stress levels for machined parts as delineated in Tables A and B for extruded, compression molded or injection molded products. The manner in which the tolerances are obtained is not relevant.

6.2 Tubular bar dimensions shall be supplied in the unfinished condition, unless otherwise specified at time of order, sufficient to finish to the nominal dimension ordered.

6.3 The maximum allowable camber and/or bow shall be within the limits referenced in Tables A-1 and B-1.

7. Workmanship, Finish, and Appearance

7.1 *Appearance*—The color of products shall be as published by the shapes manufacturer. They shall be uniform in color throughout the thickness. Specific colors and color matching only as agreed to by order. Physical properties may be affected by colors.

7.2 *Finish*—All products shall be free of blisters, wrinkles, cracks, gouges and defects that restrict commercial use of the product. Special surface finish shall be supplied only when specified in the purchase order or contract.

7.3 *Defects*—All products shall be free of dirt, foreign material and embedded particles exceeding 1/32 in. maximum diameter as defined in 7.3.1.