

Designation: D 449 – 03

# Standard Specification for Asphalt Used in Dampproofing and Waterproofing<sup>1</sup>

This standard is issued under the fixed designation D 449; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

This standard has been approved for use by agencies of the Department of Defense.

## 1. Scope

1.1 This specification covers three types of asphalt suitable for use as a mopping coat in dampproofing; or as a plying or mopping cement in the construction of membrane waterproofing systems with felts in accordance with Specification D 226; fabrics in accordance with Specifications D 173 or D 1668 (asphalt types); asphalt-impregnated glass mat in accordance with Specifications D 2178; and with primer in accordance with Specification D 41.

1.2 The values stated in SI units are to be regarded as the standard. The values given in parentheses are for information only.

1.3 This standard does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this standard to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

#### 2. Referenced Documents

- 2.1 ASTM Standards:
- D 5 Test Method for Penetration of Bituminous Materials<sup>2</sup>
- D 36 Test Method for Softening Point of Bitumen (Ringand-Ball Apparatus)<sup>3</sup>
- D 41 Specification for Asphalt Primer Used in Roofing, Dampproofing, and Waterproofing<sup>3</sup>
- D 92 Test Method for Flash and Fire Points by Cleveland Open Cup Tester<sup>4</sup>
- D 113 Test Method for Ductility of Bituminous Materials<sup>2</sup>
- D 140 Practice for Sampling Bituminous Materials<sup>2</sup>
- D 173 Specification for Bitumen-Saturated Cotton Fabrics Used in Roofing and Waterproofing<sup>3</sup>

D 226 Specification for Asphalt-Saturated Organic Felt

Used in Roofing and Waterproofing<sup>3</sup>

- D 1668 Specification for Glass Fabrics (Woven and Treated) for Roofing and Waterproofing<sup>3</sup>
- D 2042 Test Method for Solubility of Asphalt Materials in Trichlorethylene<sup>2</sup>
- D 2178 Specification for Asphalt Glass Felt Used in Roofing and Waterproofing<sup>3</sup>
- D 3461 Test Method for Softening Point of Asphalt and Pitch (Mettler Cup-and-Ball Method)<sup>5</sup>

#### 3. Classification

3.1 Asphalts covered by this specification include three types:

3.1.1 *Type I*—A soft, adhesive, "self-healing" asphalt that flows easily under the mop and is suitable for use below grade under uniformly moderate temperature conditions both during the process of installation and during service.

Note 1—Type I asphalt is suitable for foundations, tunnels, subways, and so forth.

3.1.2 *Type II*—A somewhat less susceptible asphalt than Type I, with good adhesive and "self-healing" properties, suitable for use above grade where it will not be exposed to temperatures exceeding  $50^{\circ}$ C (122°F).

Note 2-Type II asphalt is suitable for railroad bridges, culverts, retaining walls, tanks, dams, conduits, spray decks, and so forth.

3.1.3 *Type III*—An asphalt less susceptible to temperature than Type II, with good adhesive properties, and suitable for use above grade on vertical surfaces exposed to direct sunlight or temperatures above 50°C (122°F).

#### 4. Materials and Manufacture

4.1 The asphalt shall be prepared from crude petroleum by suitable refining processes to conform to the applicable physical requirements for each type.

### 5. Physical Requirements

5.1 The asphalt shall be homogeneous and free of water.

Copyright © ASTM International, 100 Barr Harbor Drive, PO Box C700, West Conshohocken, PA 19428-2959, United States.

<sup>&</sup>lt;sup>1</sup> This specification is under the jurisdiction of ASTM Committee D08 on Roofing and Waterproofing and is the direct responsibility of Subcommittee D08.03 on Surfacing and Bituminous Materials for Membrane Waterproofing and Built-up Roofing.

Current edition approved July 10, 2003. Published August 2003. Originally approved in 1937. Last previous edition approved in 1999 as D 449 –  $89(1999)^{\epsilon_1}$ .

<sup>&</sup>lt;sup>2</sup> Annual Book of ASTM Standards, Vol 04.03.

<sup>&</sup>lt;sup>3</sup> Annual Book of ASTM Standards, Vol 04.04.

<sup>&</sup>lt;sup>4</sup> Annual Book of ASTM Standards, Vol 05.01.

<sup>&</sup>lt;sup>5</sup> Annual Book of ASTM Standards, Vol 05.02.