

SLOVENSKI STANDARD
SIST EN 14909:2006/oprA1:2008
01-julij-2008

Hidroizolacijski trakovi - Polimerni in elastomerni trakovi za tesnjenje - Definicije in lastnosti

Flexible sheets for waterproofing - Plastic and rubber damp proof courses - Definitions and characteristics

Abdichtungsbahnen - Kunststoff- und Elastomer-Mauersperrbahnen - Definitionen und Eigenschaften

Feuilles souples d'étanchéité - Feuilles plastiques et élastomères utilisées dans les murs contre les remontées d'humidité - Définitions et caractéristiques

Ta slovenski standard je istoveten z: EN 14909:2006/prA1

ICS:

01.040.91	Gradbeni materiali in gradnja (Slovarji)	Construction materials and building (Vocabularies)
91.100.50	Veziva. Tesnilni materiali	Binders. Sealing materials

SIST EN 14909:2006/oprA1:2008 **en,fr,de**

ICS 91.100.50

English Version

Flexible sheets for waterproofing - Plastic and rubber damp proof courses - Definitions and characteristics

Feuilles souples d'étanchéité - Feuilles plastiques et élastomères utilisées dans les murs contre les remontées d'humidité - Définitions et caractéristiques

Abdichtungsbahnen - Kunststoff- und Elastomer-Mauersperrbahnen - Definitionen und Eigenschaften

This draft amendment is submitted to CEN members for enquiry. It has been drawn up by the Technical Committee CEN/TC 254.

This draft amendment A1, if approved, will modify the European Standard EN 14909:2006. If this draft becomes an amendment, CEN members are bound to comply with the CEN/CENELEC Internal Regulations which stipulate the conditions for inclusion of this amendment into the relevant national standard without any alteration.

This draft amendment was established by CEN in three official versions (English, French, German). A version in any other language made by translation under the responsibility of a CEN member into its own language and notified to the CEN Management Centre has the same status as the official versions.

CEN members are the national standards bodies of Austria, Belgium, Bulgaria, Cyprus, Czech Republic, Denmark, Estonia, Finland, France, Germany, Greece, Hungary, Iceland, Ireland, Italy, Latvia, Lithuania, Luxembourg, Malta, Netherlands, Norway, Poland, Portugal, Romania, Slovakia, Slovenia, Spain, Sweden, Switzerland and United Kingdom.

Recipients of this draft are invited to submit, with their comments, notification of any relevant patent rights of which they are aware and to provide supporting documentation.

Warning : This document is not a European Standard. It is distributed for review and comments. It is subject to change without notice and shall not be referred to as a European Standard.



EUROPEAN COMMITTEE FOR STANDARDIZATION
COMITÉ EUROPÉEN DE NORMALISATION
EUROPÄISCHES KOMITEE FÜR NORMUNG

Management Centre: rue de Stassart, 36 B-1050 Brussels

Contents	Page
Foreword.....	3
Introduction	4
5.8.2 Against chemicals	5
C.1 Principle.....	5

Foreword

This document (EN 14909:2006/prA1:2008) has been prepared by Technical Committee CEN/TC 254 "Flexible sheets for waterproofing", the secretariat of which is held by BSI.

This document is currently submitted to the CEN Enquiry.

This document has been prepared under a mandate given to CEN by the European Commission and the European Free Trade Association, and supports essential requirements of EC Directive(s).

Introduction

This amendment to Clauses 5.8.2 and C.1 of EN 149096 is seen as necessary to clarify that the accelerated ageing in an alkaline environment test was originally intended for polyolefin sheets only.

5.8.2 Against chemicals

Amend 5.8.2 as follows:

The durability of polyolefin sheets against alkali shall be evaluated when subject to regulatory requirements, and may be evaluated when not subject to such requirements. It shall be determined in accordance with Annex C. The elongation shall be determined in accordance with EN 12311-2 and the value after ageing shall be not less than 50 % of the initial elongation.

C.1 Principle

Amend paragraph 1 of C.1 as follows:

This method is intended for use with polyolefin sheets, films and foils which may come into contact with moist concrete, for example when used as damp-proof sheets and courses and vapour control layers in concrete foundation slab construction.