



Designation: A 372/A 372M – 99

# Standard Specification for Carbon and Alloy Steel Forgings for Thin-Walled Pressure Vessels<sup>1</sup>

This standard is issued under the fixed designation A 372/A 372M; the number immediately following the designation indicates the year of original adoption or, in the case of revision, the year of last revision. A number in parentheses indicates the year of last reapproval. A superscript epsilon ( $\epsilon$ ) indicates an editorial change since the last revision or reapproval.

## 1. Scope

1.1 This specification<sup>2</sup> covers relatively thin-walled forgings (including gas bottles) for pressure vessel use. Three types of carbon steel and six types of alloy steel are included. Provision is made for integrally forging the ends of vessel bodies made from seamless pipe or tubing.

NOTE 1—When working to the chemical and tensile requirements of this specification, the influence of wall thickness and cooling rate will necessarily eliminate certain forging sizes in each class.

NOTE 2—Designations have been changed as follows:

Current	Formerly
Grade A	Type I
Grade B	Type II
Grade C	Type III
Grade D	Type IV
Grade E Class 55	Type V Grade 1 Class 55
Grade E Class 65	Type V Grade 1 Class 65
Grade E Class 70	Type V Grade 1 Class 70
Grade F Class 55	Type V Grade 2 Class 55
Grade F Class 65	Type V Grade 2 Class 65
Grade F Class 70	Type V Grade 2 Class 70
Grade G Class 55	Type V Grade 3 Class 55
Grade G Class 65	Type V Grade 3 Class 65
Grade G Class 70	Type V Grade 3 Class 70
Grade H Class 55	Type V Grade 4 Class 55
Grade H Class 65	Type V Grade 4 Class 65
Grade H Class 70	Type V Grade 4 Class 70
Grade J Class 55	Type V Grade 5 Class 55
Grade J Class 65	Type V Grade 5 Class 65
Grade J Class 70	Type V Grade 5 Class 70
Grade K	Type VI
Grade L	Type VII
Grade J Class 110	Type VIII
Grade M Class 85	Type IX Class A
Grade M Class 100	Type IX Class B

1.2 The values stated in either inch-pound or SI [metric] units are to be regarded separately as the standard. Within the text and the tables, the SI units are shown in brackets. The values stated in each system are not exact equivalents; therefore, each system must be used independently of the other.

Combining values from the two systems may result in nonconformance with the specification.

1.3 Unless the order specifies the applicable “M” specification designation (SI units), the material shall be furnished to inch-pound units.

## 2. Referenced Documents

### 2.1 ASTM Standards:

A 275/A 275M Test Method for Magnetic Particle Examination of Steel Forgings<sup>3</sup>

A 370 Test Methods and Definitions for Mechanical Testing of Steel Products<sup>4</sup>

A 388/A 388M Practice for Ultrasonic Examination of Heavy Steel Forgings<sup>3</sup>

A 530/A 530M Specification for General Requirements for Specialized Carbon and Alloy Steel Pipe<sup>5</sup>

A 788 Specification for Steel Forgings, General Requirements<sup>3</sup>

E 112 Test Methods for Determining the Average Grain Size<sup>6</sup>

E 165 Practice for Liquid Penetrant Examination<sup>7</sup>

E 290 Test Method for Semi-Guided Bend Test for Ductility of Metallic Materials<sup>6</sup>

E 433 Reference Photographs for Liquid Penetrant Inspection<sup>7</sup>

## 3. Ordering Information and General Requirements

3.1 In addition to the ordering information required by Specification A 788, the purchaser shall include with the inquiry and order a detailed drawing, sketch, or written description of the forging and the areas of significant loading in the forging when required (see 6.4.2.2).

<sup>1</sup> This specification is under the jurisdiction of ASTM Committee A-1 on Steel, Stainless Steel and Related Alloys and is the direct responsibility of Subcommittee A01.06 on Steel Forgings and Billets.

Current edition approved March 10, 1999. Published June 1999. Originally published as A 372 – 53T. Last previous edition A 372/A 372M – 95.

<sup>2</sup> For ASME Boiler and Pressure Vessel Code applications, see related Specification SA-372/SA-372M in Section II of that code.

<sup>3</sup> *Annual Book of ASTM Standards*, Vol 01.05.

<sup>4</sup> *Annual Book of ASTM Standards*, Vol 01.03.

<sup>5</sup> *Annual Book of ASTM Standards*, Vol 01.01.

<sup>6</sup> *Annual Book of ASTM Standards*, Vol 03.01.

<sup>7</sup> *Annual Book of ASTM Standards*, Vol 03.03.

 **A 372/A 372M – 99**

3.2 Material supplied to this specification shall conform to the requirements of Specification A 788, which outlines additional ordering information, manufacturing requirements, testing and retesting methods and procedures, marking, certification, product analysis variations, and additional supplementary requirements.

3.3 If the requirements of this specification are in conflict with the requirements of Specification A 788, the requirements of this specification shall prevail.

**4. Materials and Manufacture**

*4.1 Melting Practice:*

4.1.1 The steel melting procedures of Specification A 788 shall apply except that for Grade M forgings, only steel that has been vacuum treated prior to or during the pouring of the ingot, in order to remove objectionable gases, particularly hydrogen, shall be used.

*4.2 Production Methods:*

4.2.1 Methods for the production of gas bottles and similar vessels may include the cupping of slabs or plates, the piercing of billets or plates, and the subsequent drawing of cups so produced. Such semifinished forgings or seamless steel pipe or tubing may be closed by spinning, swedging, or pressing. In all cases there shall be sufficient discard to ensure soundness in the completed forging.

*4.3 Heat Treatment:*

4.3.1 At the option of the manufacturer, Grades A, B, C, D and Classes 55, 65, 70 of Grades E, F, G, H, and J forgings shall be normalized, normalized and tempered, or liquid-quenched and tempered.

4.3.2 Grades K, L, M, and Class 110 of Grade J forgings shall be liquid-quenched and tempered.

4.3.3 When normalized forgings are to be tempered, or when forgings have been quenched, they shall be reheated to a subcritical temperature and held for at least ½ h/in. [25 mm] of maximum cross section.

4.3.3.1 Minimum tempering temperatures shall be as follows:

Grades E, F, G, H, J in Classes 55, 65, 70	1100°F [595°C]
Grade K	1100°F [595°C]
Grade L	1000°F [540°C]
Grade J Class 110	1000°F [540°C]
Grade M	1100°F [595°C]

4.3.4 All quenched and tempered forgings shall be subject to magnetic particle examination in accordance with Section 7.

**5. Chemical Composition**

5.1 *Heat Analysis*—The heat analysis obtained from sampling in accordance with Specification A 788 shall comply with Table 1.

5.2 *Product Analysis*—The purchaser may use the product analysis provision of Specification A 788 to obtain a product analysis from a forging representing each heat or multiple heat.

5.3 Starting material produced to a specification that specifically requires the addition of any element beyond those listed in Table 1 for the applicable grade of material is not permitted. This does not preclude use of deoxidation or inclusion control additions. Supplementary Requirements S1 and S2 of Specification A 788 shall apply.

**TABLE 1 Chemical Requirements**

Elements	Composition, %				
	Grade A	Grade B	Grade C	Grade D	
Carbon	0.30 max	0.35 max	0.48 max	0.40–0.50	
Manganese	1.00 max	1.35 max	1.65 max	1.40–1.80	
Phosphorus, max	0.025	0.025	0.025	0.025	
Sulfur, max	0.025	0.025	0.025	0.025	
Silicon	0.15–0.35	0.15–0.35	0.15–0.35	0.15–0.35	
Nickel	—	—	—	—	
Chromium	—	—	—	—	
Molybdenum	—	—	—	0.17–0.27	
	Grade E Classes 55, 65, 70	Grade F Classes 55, 65, 70	Grade G Classes 55, 65, 70	Grade H Classes 55, 65, 70	Grade J Classes 55, 65, 70, 110
Carbon	0.25–0.35	0.30–0.40	0.25–0.35	0.30–0.40	0.35–0.50
Manganese	0.40–0.90	0.70–1.00	0.70–1.00	0.75–1.05	0.75–1.05
Phosphorus, max	0.025	0.025	0.025	0.025	0.025
Sulfur, max	0.025	0.025	0.025	0.025	0.025
Silicon	0.15–0.35	0.15–0.35	0.15–0.35	0.15–0.35	0.15–0.35
Nickel	—	—	—	—	—
Chromium	0.80–1.15	0.80–1.15	0.40–0.65	0.40–0.65	0.80–1.15
Molybdenum	0.15–0.25	0.15–0.25	0.15–0.25	0.15–0.25	0.15–0.25
	Grade K	Grade L	Grade M Classes 85 and 100		
Carbon	0.18 max	0.38–0.43	0.23 max		
Manganese	0.10–0.40	0.60–0.80	0.20–0.40		
Phosphorus, max	0.025 max	0.025	0.020		
Sulfur, max	0.025 max	0.025	0.020		
Silicon	0.15–0.35	0.15–0.35	0.30 max		
Nickel	2.0–3.3	1.65–2.00	2.8–3.9		
Chromium	1.00–1.80	0.70–0.90	1.50–2.00		
Molybdenum	0.20–0.60	0.20–0.30	0.40–0.60		
Vanadium			0.08 max		

**6. Mechanical Properties**

6.1 Mechanical tests for acceptance shall be made after the final heat treatment of the forgings.

6.2 *Tension Test*—When tested in accordance with Test Methods and Definitions A 370, the material shall conform to

**TABLE 2 Mechanical Requirements**

Type	Tensile Strength, ksi [MPa]	Yield Strength (0.2 % Offset), ksi [MPa], min	Elongation in 2 in. [50 mm], min, %	Hardness, HB, min <sup>A</sup>
Grade A	60–85 [415–585]	35 [240]	20	121
Grade B	75–100 [515–690]	45 [310]	18	156
Grade C	90–115 [620–795]	55 [380]	15	187
Grade D	105–130 [725–895]	65 [450]	15	217
Grades E, F, G, H, J (Class 55)	85–110 [545–760]	55 [380]	20	179
Grades E, F, G, H, J (Class 65)	105–130 [725–895]	65 [450]	19	217
Grades E, F, G, H, J (Class 70)	120–145 [825–1000]	70 [485]	18	248
Grade J (Class 110)	135–160 [930–1100]	110 [760]	15	277
Grade K	100–125 [690–860]	80 [550]	20	207
Grade L	155–180 [1070–1240]	135 [930]	12	311
Grade M (Class 85)	105–130 [725–895]	85 [585]	18	217
Grade M (Class 100)	120–145 [825–1000]	100 [690]	16	248

<sup>A</sup> When required by 6.6.