

SLOVENSKI STANDARD SIST ISO 4383:2002

01-marec-2002

8 fgb]``YÿU'J`!`JY g`c'b]`a UhYf]U']`nU'HUb_cghYbY`XfgbY``YÿU'Y

Plain bearings -- Multilayer materials for thin-walled plain bearings

Paliers lisses -- Matériaux multicouches pour paliers lisses minces

(standards.iteh.ai) Ta slovenski standard je istoveten z: ISO 4383:2000

SIST ISO 4383:2002https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-
59f918046399/sist-iso-4383-2002ICS:21.100.10Drsni ležajiPlain bearings

SIST ISO 4383:2002

en



iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 4383:2002</u> https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-59f918046399/sist-iso-4383-2002



INTERNATIONAL STANDARD

ISO 4383

Third edition 2000-04-15

Plain bearings — Multilayer materials for thin-walled plain bearings

Paliers lisses — Matériaux multicouches pour paliers lisses minces

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 4383:2002</u> https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-59f918046399/sist-iso-4383-2002



Reference number ISO 4383:2000(E)

PDF disclaimer

This PDF file may contain embedded typefaces. In accordance with Adobe's licensing policy, this file may be printed or viewed but shall not be edited unless the typefaces which are embedded are licensed to and installed on the computer performing the editing. In downloading this file, parties accept therein the responsibility of not infringing Adobe's licensing policy. The ISO Central Secretariat accepts no liability in this area.

Adobe is a trademark of Adobe Systems Incorporated.

Details of the software products used to create this PDF file can be found in the General Info relative to the file; the PDF-creation parameters were optimized for printing. Every care has been taken to ensure that the file is suitable for use by ISO member bodies. In the unlikely event that a problem relating to it is found, please inform the Central Secretariat at the address given below.

iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 4383:2002</u> https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-59f918046399/sist-iso-4383-2002

© ISO 2000

All rights reserved. Unless otherwise specified, no part of this publication may be reproduced or utilized in any form or by any means, electronic or mechanical, including photocopying and microfilm, without permission in writing from either ISO at the address below or ISO's member body in the country of the requester.

ISO copyright office Case postale 56 • CH-1211 Geneva 20 Tel. + 41 22 749 01 11 Fax + 41 22 734 10 79 E-mail copyright@iso.ch Web www.iso.ch

Foreword

ISO (the International Organization for Standardization) is a worldwide federation of national standards bodies (ISO member bodies). The work of preparing International Standards is normally carried out through ISO technical committees. Each member body interested in a subject for which a technical committee has been established has the right to be represented on that committee. International organizations, governmental and non-governmental, in liaison with ISO, also take part in the work. ISO collaborates closely with the International Electrotechnical Commission (IEC) on all matters of electrotechnical standardization.

International Standards are drafted in accordance with the rules given in the ISO/IEC Directives, Part 3.

Draft International Standards adopted by the technical committees are circulated to the member bodies for voting. Publication as an International Standard requires approval by at least 75 % of the member bodies casting a vote.

Attention is drawn to the possibility that some of the elements of this International Standard may be the subject of patent rights. ISO shall not be held responsible for identifying any or all such patent rights.

International Standard ISO 4383 was prepared by Technical Committee ISO/TC 123, *Plain bearings*, Subcommittee SC 2, *Materials and lubricants, their properties, characteristics, test methods and testing conditions*.

This third edition cancels and replaces the second edition (ISO 4383:1991), which has been technically revised.

Annex A of this International Standard is for information only teh.ai)

<u>SIST ISO 4383:2002</u> https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-59f918046399/sist-iso-4383-2002



iTeh STANDARD PREVIEW (standards.iteh.ai)

<u>SIST ISO 4383:2002</u> https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-59f918046399/sist-iso-4383-2002

Plain bearings — Multilayer materials for thin-walled plain bearings

1 Scope

This International Standard specifies requirements for multilayer materials for the manufacture of thin-walled plain bearings (half bearings, bushes, thrust washers). The multilayer material consists of a steel backing, the bearing layer (cast, sintered, roll bonded) and possibly an electrodeposited overlay.

NOTE Environmental concerns will, in the future, restrict the use of some materials such as lead.

2 Normative references

The following normative documents contain provisions which, through reference in this text, constitute provisions of this International Standard. For dated references, subsequent amendments to, or revisions of, any of these publications do not apply. However, parties to agreements based on this International Standard are encouraged to investigate the possibility of applying the most recent editions of the normative documents indicated below. For undated references, the latest edition of the normative document, referred to applies. Members of ISO and IEC maintain registers of currently valid International Standards.

ISO 4381, Plain bearings - Lead and tin casting alloys for multilayer plain bearings.

ISO 4382-1, Plain bearings — Copper alloys — Part 1: Cast copper alloys for solid and multilayer thick-walled plain bearings.

ISO 6691, Thermoplastic polymers for plain bearings — Classification and designation.

3 Requirements

3.1 Chemical composition

The chemical composition shall be within the limits specified in Tables 1 to 5, where single figures denote maximum values.

3.2 Steel backings

The chemical composition of the steel for backings shall be the subject of agreement between manufacturer and purchaser. In general, low carbon steel will be used.

For the bronze/polymer composite materials listed in Table 4, copper-coated steel may be used.

3.3 Bearing layers

Bearing metals based on lead and tin shall be in accordance with Table 1.

Bearing metals based on copper shall be in accordance with Table 2.

Bearing metals based on aluminium shall be in accordance with Table 3.

Bearing layers based on sintered porous bronze and polymers shall be in accordance with Table 4.

NOTE There is now a new class of aluminium-based materials containing both aluminium and silicon or manganese as well as a "soft" material such as lead or tin. Detailed information is available from individual manufacturers.

3.4 Overlays

Overlays in accordance with Table 5 may be applied for bearing metal layers as indicated in Table A.2. The thickness of the overlay and any additional layers between the bearing metal layer and the overlay shall be the subject of agreement between the manufacturer and purchaser.

3.5 Properties and selection of materials

Guidance on bearing metal hardness in strip form and uses of bearing metals is given in annex A.

4 Designation

iTeh STANDARD PREVIEW (standards.iteh.ai)

EXAMPLE

A multilayer material consisting of a steel backing, the bearing metal CuPb24Sn as cast (G) and the overlay PbSn10Cu2 is designated as follows: https://standards.iteh.ai/catalog/standards/sist/ba9c93e4-e938-4908-884f-

59f918046399/sist-iso-4383-2002

Bearing metal ISO 4383 - G - CuPb24Sn - PbSn10Cu2

	Chemical composition, % (m/m)					
Chemical element	PbSb10Sn6	PbSb15SnAs	PbSb15Sn10	SnSb8Cu4		
Pb	Remainder	Remainder	Remainder	0,35		
Sb	9 to 11	13,5 to 15,5	14 to 16	7 to 8		
Sn	5 to 7	0,9 to 1,7	9 to 11	Remainder		
Cu	0,7	0,7	0,7	3 to 4		
As	0,25	0,8 to 1,2	0,6	0,1		
Ві	0,1	0,1	0,1	0,08		
Zn	0,01	0,01	0,01	0,01		
AI	0,01	0,01	0,01	0,01		
Fe	0,1	0,1	0,1	0,1		
Total others	0,2	0,2	0,2	0,2		

Table 1 — Lead and tin alloys (see ISO 4381)

Chemical element	Chemical composition, % (m/m)							
	CuPb10Sn10 ^a	CuPb17Sn5	CuPb24Sn4	CuPb24Sn	CuPb30 P - sintered			
	G - cast	G - cast	G - cast	G - cast				
	P - sintered		P - sintered	P - sintered				
Cu	Remainder	Remainder	Remainder	Remainder	Remainder			
Pb	9 to 11	14 to 20	19 to 27	19 to 27	26 to 33			
Sn	9 to 11	4 to 6	3 to 4,5	0,6 to 2	0,5			
Zn	0,5	0,5	0,5	0,5	0,5			
Р	0,1	0,1	0,1	0,1	0,1			
Fe	0,7	0,7	0,7	0,7	0,7			
Ni	0,5	0,5	0,5	0,5	0,5			
Sb	0,5	0,5	0,5	0,5	0,5			
Total others	0,5	0,5	0,5	0,5	0,5			

Table 2 — Copper alloys

^a The chemical composition of this alloy differs from that of solid and multilayer thick-walled plain bearings (see ISO 4382-1).

iTeh STrable 3D Aluminium alloysVIEW

Chemical element	(standar chemical composition, % (m/m)					
	AlSn20Cu	AlSn6Cu SIST ISO 4383:2002	AlSi11Cu	AlZn5Si1,5Cu1Pb1Mg		
AI	https://standards.iteh.ai/c	atalog/standards/sist/ba9c 8046399/sist-iso-4383-	93e4-6938-4908-884f- Remainder	Remainder		
Cu	0,7 to 1,3	0,7 to 1,3	0,7 to 1,3	0,8 to 1,2		
Sn	16,5 to 22,5	5,5 to 7	0,2	0,2		
Ni	0,1	1,3	0,1	0,2		
Si	0,7 ^a	0,7 ^a	10 to 12	1 to 2		
Fe	0,7 ^a	0,7 ^a	0,3	0,6		
Mn	0,7 ^a	0,7 ^a	0,1	0,3		
Ti	0,2	0,2	0,1	0,2		
Pb	-	_	_	0,7 to 1,3		
Zn	-	_	-	4,4 to 5,5		
Mg	-	_	_	0,6		
Total others	0,5	0,5	0,3	0,4		